

Refractive Index	$n_d$	<b>1.67003</b> 1.670029	Abbe Number	$V_d$	<b>47.23</b> 46.94	Dispersion	$n_F - n_C$	<b>0.01418</b> 0.014186
		$n_e$		1.673402			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.63546
$n_{1970}$	1.97009	1.64108
$n_{1530}$	1.52958	1.64722
$n_{1129}$	1.12864	1.65293
$n_t$	1.01398	1.65492
$n_s$	0.85211	1.65852
$n_{A'}$	0.76819	1.66105
$n_r$	0.70652	1.66341
$n_c$	0.65627	<b>1.66579</b>
$n_{c'}$	0.64385	1.66646
$n_{\text{He-Ne}}$	0.6328	1.66709
$n_D$	0.58929	1.66990
$n_d$	0.58756	<b>1.67003</b>
$n_e$	0.54607	1.67340
$n_F$	0.48613	<b>1.67997</b>
$n_{F'}$	0.47999	1.68080
$n_{\text{He-Cd}}$	0.44157	1.68689
$n_g$	0.435835	<b>1.68796</b>
$n_h$	0.404656	1.69473
$n_i$	0.365015	1.70663
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point. ( $^{\circ}\text{C}$ )	<b>StP</b>	584
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	612
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	623
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	669
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	734
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		68
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	80
Thermal Conductivity (W/m·K)	<b>k</b>	0.902

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	962
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	378
Poisson's Ratio	$\sigma$	0.273
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	127
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.12

Partial Dispersions	
$n_c - n_t$	0.010866
$n_c - n_{A'}$	0.004735
$n_d - n_c$	0.004241
$n_e - n_c$	0.007614
$n_g - n_d$	0.017928
$n_g - n_F$	0.007983
$n_h - n_g$	0.006774
$n_i - n_g$	0.018670
$n_{c'} - n_t$	0.011535
$n_e - n_{c'}$	0.006945
$n_{F'} - n_e$	0.007400
$n_i - n_{F'}$	0.025825

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0023
$\Delta\theta_{c,A'}$	0.0007
$\Delta\theta_{g,d}$	-0.0028
$\Delta\theta_{g,F}$	-0.0024
$\Delta\theta_{i,g}$	-0.0134

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.59034337	
A 2	1.38464579	E-1
A 3	1.21988043	
B 1	9.32734340	E-3
B 2	4.27498654	E-2
B 3	1.19251777	E2
1129 ~ 2325 nm		
A 1	1.59034337	
A 2	1.38464579	E-1
A 3	1.21988043	
B 1	9.32734340	E-3
B 2	4.27498654	E-2
B 3	1.19251777	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7660
$\theta_{c,A'}$	0.3338
$\theta_{d,c}$	0.2990
$\theta_{e,c}$	0.5367
$\theta_{g,d}$	1.2638
$\theta_{g,F}$	0.5627
$\theta_{h,g}$	0.4775
$\theta_{i,g}$	1.3161
$\theta'_{c,t}$	0.8041
$\theta'_{e,c'}$	0.4841
$\theta'_{F',e}$	0.5159
$\theta'_{i,F'}$	1.8003

Internal Transmittance			
$\lambda_{80}$	378	$\lambda_5$	342

CCI		
B	G	R
0.00	1.25	1.25

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.010	
350	0.190	
360	0.480	
365		
370	0.700	
380	0.830	
390	0.902	
400	0.939	
420	0.969	
440	0.979	
460	0.984	
480	0.989	
500	0.993	
550	0.997	
600	0.996	
650	0.996	
700	0.997	
800	0.998	
900	0.997	
1000	0.997	
1200	0.998	
1400	0.996	
1600	0.996	
1800	0.991	
2000	0.981	
2200	0.949	
2400	0.850	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	<b>d</b>	3.48		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.4	3.9	3.9	4.1	4.3	4.8	5.3		
-20 ~ 0	3.5	3.9	4.0	4.1	4.4	4.9	5.5		
0 ~ 20	3.5	4.0	4.1	4.2	4.5	5.0	5.6		
20 ~ 40	3.6	4.1	4.1	4.3	4.6	5.2	5.7		
40 ~ 60	3.6	4.2	4.2	4.4	4.7	5.3	5.9		
60 ~ 80	3.7	4.2	4.3	4.5	4.8	5.4	6.0		

Refractive Index	$n_d$	<b>1.66672</b>	Abbe Number	$V_d$	<b>48.32</b>	Dispersion	$n_F - n_C$	<b>0.01380</b>
	$n_e$	1.666718		$V_e$	48.04		$n_{F'} - n_{C'}$	0.013797
		1.670000						0.013948

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.63328
$n_{1970}$	1.97009	1.63866
$n_{1530}$	1.52958	1.64456
$n_{1129}$	1.12864	1.65008
$n_t$	1.01398	1.65201
$n_s$	0.85211	1.65551
$n_{A'}$	0.76819	1.65798
$n_r$	0.70652	1.66027
$n_c$	0.65627	<b>1.66259</b>
$n_{c'}$	0.64385	1.66324
$n_{\text{He-Ne}}$	0.6328	1.66385
$n_D$	0.58929	1.66660
$n_d$	0.58756	<b>1.66672</b>
$n_e$	0.54607	1.67000
$n_F$	0.48613	<b>1.67639</b>
$n_{F'}$	0.47999	1.67719
$n_{\text{He-Cd}}$	0.44157	1.68309
$n_g$	0.435835	<b>1.68412</b>
$n_h$	0.404656	1.69067
$n_i$	0.365015	1.70213
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010576
$n_c - n_{A'}$	0.004611
$n_d - n_c$	0.004129
$n_e - n_c$	0.007411
$n_g - n_d$	0.017407
$n_g - n_F$	0.007739
$n_h - n_g$	0.006549
$n_i - n_g$	0.018002
$n_{c'} - n_t$	0.011228
$n_e - n_{c'}$	0.006759
$n_{F'} - n_e$	0.007189
$n_i - n_{F'}$	0.024938

Relative Partial Dispersions	
$\theta_{c,t}$	0.7665
$\theta_{c,A'}$	0.3342
$\theta_{d,c}$	0.2993
$\theta_{e,c}$	0.5371
$\theta_{g,d}$	1.2617
$\theta_{g,F}$	0.5609
$\theta_{h,g}$	0.4747
$\theta_{i,g}$	1.3048
$\theta'_{c,t}$	0.8050
$\theta'_{e,c'}$	0.4846
$\theta'_{F',e}$	0.5154
$\theta'_{i,F'}$	1.7879

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0069
$\Delta\theta_{c,A'}$	-0.0002
$\Delta\theta_{g,d}$	-0.0027
$\Delta\theta_{g,F}$	-0.0024
$\Delta\theta_{i,g}$	-0.0156

Internal Transmittance			
$\lambda_{80}$	375	$\lambda_5$	340

CCI		
B	G	R
0.00	0.98	0.94

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.57138860	
A 2	1.47869313	E-1
A 3	1.28092846	
B 1	9.10807936	E-3
B 2	4.02401684	E-2
B 3	1.30399367	E2
1129 ~ 2325 nm		
A 1	1.57138860	
A 2	1.47869313	E-1
A 3	1.28092846	
B 1	9.10807936	E-3
B 2	4.02401684	E-2
B 3	1.30399367	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.040	
350	0.270	
360	0.560	
365		
370	0.750	
380	0.860	
390	0.922	
400	0.952	
420	0.975	
440	0.982	
460	0.987	
480	0.991	
500	0.994	
550	0.997	
600	0.995	
650	0.995	
700	0.996	
800	0.997	
900	0.997	
1000	0.997	
1200	0.998	
1400	0.994	
1600	0.995	
1800	0.988	
2000	0.976	
2200	0.936	
2400	0.840	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	593
Annealing Point (°C)	<b>AP</b>	617
Transformation Temperature (°C)	<b>Tg</b>	629
Yield Point (°C)	<b>At</b>	675
Softening Point (°C)	<b>SP</b>	738
Expansion Coefficient $\alpha$ (-30~+70°C)		69
(10-7 /°C) (+100~+300°C)		82
Thermal Conductivity (W/m·K)	<b>k</b>	0.858

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	929
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	365
Poisson's Ratio	$\sigma$	0.274
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	154
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.06

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	3.59		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.3	3.7	3.7	3.9	4.1	4.6	5.1		
-20 ~ 0	3.3	3.8	3.8	4.0	4.2	4.7	5.2		
0 ~ 20	3.3	3.8	3.9	4.1	4.3	4.8	5.4		
20 ~ 40	3.3	3.9	3.9	4.1	4.4	4.9	5.5		
40 ~ 60	3.4	4.0	4.0	4.2	4.5	5.0	5.6		
60 ~ 80	3.4	4.0	4.1	4.3	4.6	5.1	5.8		

Refractive Index	$n_d$	<b>1.70154</b>	Abbe Number	$V_d$	<b>41.24</b>	Dispersion	$n_F - n_C$	<b>0.01701</b>
		1.701536			$V_e$		40.95	
	$n_e$	1.705571					$n_{F'} - n_{C'}$	0.017228

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.66253
$n_{1970}$	1.97009	1.66858
$n_{1530}$	1.52958	1.67526
$n_{1129}$	1.12864	1.68160
$n_t$	1.01398	1.68386
$n_s$	0.85211	1.68800
$n_{A'}$	0.76819	1.69094
$n_r$	0.70652	1.69370
$n_c$	0.65627	<b>1.69650</b>
$n_{c'}$	0.64385	1.69729
$n_{\text{He-Ne}}$	0.6328	1.69804
$n_D$	0.58929	1.70139
$n_d$	0.58756	<b>1.70154</b>
$n_e$	0.54607	1.70557
$n_F$	0.48613	<b>1.71351</b>
$n_{F'}$	0.47999	1.71452
$n_{\text{He-Cd}}$	0.44157	1.72200
$n_g$	0.435835	<b>1.72332</b>
$n_h$	0.404656	1.73180
$n_i$	0.365015	1.74712
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.012641
$n_c - n_{A'}$	0.005561
$n_d - n_c$	0.005033
$n_e - n_c$	0.009068
$n_g - n_d$	0.021787
$n_g - n_F$	0.009808
$n_h - n_g$	0.008480
$n_i - n_g$	0.023797
$n_{c'} - n_t$	0.013433
$n_e - n_{c'}$	0.008276
$n_{F'} - n_e$	0.008952
$n_i - n_{F'}$	0.032597

Relative Partial Dispersions	
$\theta_{c,t}$	0.7431
$\theta_{c,A'}$	0.3269
$\theta_{d,c}$	0.2958
$\theta_{e,c}$	0.5330
$\theta_{g,d}$	1.2807
$\theta_{g,F}$	0.5765
$\theta_{h,g}$	0.4985
$\theta_{i,g}$	1.3988
$\theta'_{c,t}$	0.7797
$\theta'_{e,c'}$	0.4804
$\theta'_{F',e}$	0.5196
$\theta'_{i,F'}$	1.8921

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0029
$\Delta\theta_{c,A'}$	0.0011
$\Delta\theta_{g,d}$	0.0016
$\Delta\theta_{g,F}$	0.0018
$\Delta\theta_{i,g}$	0.0191

Internal Transmittance			
$\lambda_{80}$	388	$\lambda_5$	356

CCI		
B	G	R
0.00	1.99	2.01

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.68939052	
A 2	1.33081013	E-1
A 3	1.41165515	
B 1	1.03598193	E-2
B 2	5.33982239	E-2
B 3	1.26515503	E2
1129 ~ 2325 nm		
A 1	1.68939052	
A 2	1.33081013	E-1
A 3	1.41165515	
B 1	1.03598193	E-2
B 2	5.33982239	E-2
B 3	1.26515503	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.160	
365		
370	0.470	
380	0.700	
390	0.830	
400	0.890	
420	0.955	
440	0.971	
460	0.979	
480	0.985	
500	0.989	
550	0.995	
600	0.994	
650	0.994	
700	0.996	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.993	
1600	0.994	
1800	0.987	
2000	0.974	
2200	0.921	
2400	0.810	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	611
Annealing Point (°C)	<b>AP</b>	636
Transformation Temperature (°C)	<b>Tg</b>	647
Yield Point (°C)	<b>At</b>	682
Softening Point (°C)	<b>SP</b>	749
Expansion Coefficient $\alpha$ (-30~+70°C)		64
(10-7 / °C) (+100~+300°C)		75
Thermal Conductivity (W/m·K)	<b>k</b>	0.869

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	936
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	368
Poisson's Ratio	$\sigma$	0.272
Knoop Hardness	<b>Hk</b>	580 [6]
Abrasion	<b>Aa</b>	129
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.18

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	3.67		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.2	3.7	3.7	4.0	4.2	4.8	5.5		
-20 ~ 0	3.3	3.8	3.9	4.1	4.4	5.0	5.7		
0 ~ 20	3.4	4.0	4.0	4.2	4.5	5.2	5.9		
20 ~ 40	3.5	4.1	4.1	4.4	4.7	5.4	6.2		
40 ~ 60	3.5	4.2	4.3	4.5	4.8	5.6	6.4		
60 ~ 80	3.7	4.4	4.4	4.6	5.0	5.8	6.6		

Refractive Index	$n_d$	<b>1.72342</b>	Abbe Number	$V_d$	<b>37.95</b>	Dispersion	$n_F - n_C$	<b>0.01906</b>
	$n_e$	1.723420		$V_e$	37.68		$n_{F'} - n_{C'}$	0.019060
		1.727935						0.019320

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68198
$n_{1970}$	1.97009	1.68808
$n_{1530}$	1.52958	1.69490
$n_{1129}$	1.12864	1.70154
$n_t$	1.01398	1.70396
$n_s$	0.85211	1.70844
$n_{A'}$	0.76819	1.71167
$n_r$	0.70652	1.71471
$n_c$	0.65627	<b>1.71782</b>
$n_{c'}$	0.64385	1.71870
$n_{\text{He-Ne}}$	0.6328	1.71952
$n_D$	0.58929	1.72325
$n_d$	0.58756	<b>1.72342</b>
$n_e$	0.54607	1.72794
$n_F$	0.48613	<b>1.73688</b>
$n_{F'}$	0.47999	1.73802
$n_{\text{He-Cd}}$	0.44157	1.74649
$n_g$	0.435835	<b>1.74800</b>
$n_h$	0.404656	1.75769
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	599
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	626
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	643
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	676
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	739
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	66
	(+100~+300 $^{\circ}\text{C}$ )	73
Thermal Conductivity (W/m·K)	<b>k</b>	0.889

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	911
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	375
Poisson's Ratio	$\sigma$	0.213
Knoop Hardness	<b>Hk</b>	600 [6]
Abrasion	<b>Aa</b>	138
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.31

Partial Dispersions	
$n_c - n_t$	0.013857
$n_c - n_{A'}$	0.006146
$n_d - n_c$	0.005604
$n_e - n_c$	0.010119
$n_g - n_d$	0.024580
$n_g - n_F$	0.011124
$n_h - n_g$	0.009689
$n_i - n_g$	
$n_{c'} - n_t$	0.014736
$n_e - n_{c'}$	0.009240
$n_{F'} - n_e$	0.010080
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0023
$\Delta\theta_{c,A'}$	0.0006
$\Delta\theta_{g,d}$	0.0037
$\Delta\theta_{g,F}$	0.0035
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.69493484	
A 2	1.92890298	E-1
A 3	1.56385948	
B 1	1.02723190	E-2
B 2	5.21187640	E-2
B 3	1.37818035	E2
1129 ~ 2325 nm		
A 1	1.69493484	
A 2	1.92890298	E-1
A 3	1.56385948	
B 1	1.02723190	E-2
B 2	5.21187640	E-2
B 3	1.37818035	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7270
$\theta_{c,A'}$	0.3225
$\theta_{d,c}$	0.2940
$\theta_{e,c}$	0.5309
$\theta_{g,d}$	1.2896
$\theta_{g,F}$	0.5836
$\theta_{h,g}$	0.5083
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7627
$\theta'_{e,c'}$	0.4783
$\theta'_{F',e}$	0.5217
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	395	$\lambda_5$	360

CCI		
B	G	R
0.00	2.78	2.88

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.060	
365		
370	0.320	
380	0.580	
390	0.750	
400	0.850	
420	0.934	
440	0.963	
460	0.975	
480	0.982	
500	0.987	
550	0.994	
600	0.995	
650	0.995	
700	0.996	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.994	
1600	0.995	
1800	0.990	
2000	0.979	
2200	0.938	
2400	0.840	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	415				
Specific Gravity	<b>d</b>	3.67		$\lambda_5$	355				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.8	4.5	4.5	4.8	5.1	5.8	6.6		
-20 ~ 0	3.9	4.6	4.7	4.9	5.3	6.0	6.9		
0 ~ 20	4.0	4.8	4.8	5.1	5.4	6.2	7.1		
20 ~ 40	4.1	4.9	5.0	5.2	5.6	6.5	7.4		
40 ~ 60	4.2	5.1	5.1	5.4	5.8	6.7	7.7		
60 ~ 80	4.3	5.2	5.3	5.6	6.0	6.9	7.9		

Refractive Index	$n_d$	<b>1.66998</b>	Abbe Number	$V_d$	<b>39.27</b>	Dispersion	$n_F - n_C$	<b>0.01706</b>
	$n_e$	1.669979		$V_e$	38.99		$n_{F'} - n_{C'}$	0.017061
		1.674022						0.017287

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.63134
$n_{1970}$	1.97009	1.63728
$n_{1530}$	1.52958	1.64386
$n_{1129}$	1.12864	1.65013
$n_t$	1.01398	1.65237
$n_s$	0.85211	1.65648
$n_{A'}$	0.76819	1.65941
$n_r$	0.70652	1.66216
$n_c$	0.65627	<b>1.66495</b>
$n_{c'}$	0.64385	1.66574
$n_{\text{He-Ne}}$	0.6328	1.66648
$n_D$	0.58929	1.66983
$n_d$	0.58756	<b>1.66998</b>
$n_e$	0.54607	1.67402
$n_F$	0.48613	<b>1.68201</b>
$n_{F'}$	0.47999	1.68303
$n_{\text{He-Cd}}$	0.44157	1.69059
$n_g$	0.435835	<b>1.69193</b>
$n_h$	0.404656	1.70056
$n_i$	0.365015	1.71630
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	546
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	563
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	608
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	657
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	726
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		69
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	78
Thermal Conductivity (W/m·K)	<b>k</b>	0.921

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	904
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	359
Poisson's Ratio	$\sigma$	0.260
Knoop Hardness	<b>Hk</b>	580 [6]
Abrasion	<b>Aa</b>	138
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.74

Partial Dispersions	
$n_c - n_t$	0.012577
$n_c - n_{A'}$	0.005542
$n_d - n_c$	0.005030
$n_e - n_c$	0.009073
$n_g - n_d$	0.021950
$n_g - n_F$	0.009919
$n_h - n_g$	0.008632
$n_i - n_g$	0.024370
$n_{c'} - n_t$	0.013368
$n_e - n_{c'}$	0.008282
$n_{F'} - n_e$	0.009005
$n_i - n_{F'}$	0.033272

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0063
$\Delta\theta_{c,A'}$	0.0013
$\Delta\theta_{g,d}$	0.0034
$\Delta\theta_{g,F}$	0.0035
$\Delta\theta_{i,g}$	0.0322

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.58023630	
A 2	1.37504632	E-1
A 3	1.60603298	
B 1	1.03578062	E-2
B 2	5.48393088	E-2
B 3	1.47982885	E2
1129 ~ 2325 nm		
A 1	1.58023630	
A 2	1.37504632	E-1
A 3	1.60603298	
B 1	1.03578062	E-2
B 2	5.48393088	E-2
B 3	1.47982885	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7372
$\theta_{c,A'}$	0.3248
$\theta_{d,c}$	0.2948
$\theta_{e,c}$	0.5318
$\theta_{g,d}$	1.2866
$\theta_{g,F}$	0.5814
$\theta_{h,g}$	0.5059
$\theta_{i,g}$	1.4284
$\theta'_{c,t}$	0.7733
$\theta'_{e,c'}$	0.4791
$\theta'_{F',e}$	0.5209
$\theta'_{i,F'}$	1.9247

Internal Transmittance			
$\lambda_{80}$	385	$\lambda_5$	357

CCI		
B	G	R
0.00	1.79	1.85

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.160	
365		
370	0.510	
380	0.740	
390	0.850	
400	0.910	
420	0.955	
440	0.971	
460	0.978	
480	0.984	
500	0.988	
550	0.994	
600	0.994	
650	0.994	
700	0.996	
800	0.998	
900	0.997	
1000	0.997	
1200	0.996	
1400	0.992	
1600	0.993	
1800	0.988	
2000	0.980	
2200	0.948	
2400	0.880	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	3.26		$\lambda_5$	355				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.7	4.3	4.3	4.6	4.8	5.4	6.2		
-20 ~ 0	3.7	4.4	4.4	4.7	4.9	5.6	6.4		
0 ~ 20	3.7	4.4	4.5	4.7	5.0	5.7	6.5		
20 ~ 40	3.8	4.5	4.6	4.8	5.1	5.9	6.7		
40 ~ 60	3.8	4.6	4.7	4.9	5.3	6.0	6.9		
60 ~ 80	3.8	4.7	4.8	5.0	5.4	6.2	7.1		

Refractive Index	$n_d$	<b>1.57099</b>	Abbe Number	$V_d$	<b>50.80</b>	Dispersion	$n_F - n_C$	<b>0.01124</b>
		1.570989			$V_e$		50.50	
	$n_e$	1.573663					$n_{F'} - n_{C'}$	0.011359

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.54240
$n_{1970}$	1.97009	1.54721
$n_{1530}$	1.52958	1.55244
$n_{1129}$	1.12864	1.55722
$n_t$	1.01398	1.55886
$n_s$	0.85211	1.56179
$n_{A'}$	0.76819	1.56383
$n_r$	0.70652	1.56572
$n_c$	0.65627	<b>1.56762</b>
$n_{c'}$	0.64385	1.56815
$n_{\text{He-Ne}}$	0.6328	1.56865
$n_D$	0.58929	1.57089
$n_d$	0.58756	<b>1.57099</b>
$n_e$	0.54607	1.57366
$n_F$	0.48613	<b>1.57886</b>
$n_{F'}$	0.47999	1.57951
$n_{\text{He-Cd}}$	0.44157	1.58430
$n_g$	0.435835	<b>1.58514</b>
$n_h$	0.404656	1.59045
$n_i$	0.365015	1.59972
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008753
$n_c - n_{A'}$	0.003787
$n_d - n_c$	0.003373
$n_e - n_c$	0.006047
$n_g - n_d$	0.014148
$n_g - n_F$	0.006281
$n_h - n_g$	0.005308
$n_i - n_g$	0.014580
$n_{c'} - n_t$	0.009286
$n_e - n_{c'}$	0.005514
$n_{F'} - n_e$	0.005845
$n_i - n_{F'}$	0.020209

Relative Partial Dispersions	
$\theta_{c,t}$	0.7787
$\theta_{c,A'}$	0.3369
$\theta_{d,c}$	0.3001
$\theta_{e,c}$	0.5380
$\theta_{g,d}$	1.2587
$\theta_{g,F}$	0.5588
$\theta_{h,g}$	0.4722
$\theta_{i,g}$	1.2972
$\theta'_{c,t}$	0.8175
$\theta'_{e,c'}$	0.4854
$\theta'_{F',e}$	0.5146
$\theta'_{i,F'}$	1.7791

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0063
$\Delta\theta_{c,A'}$	-0.0005
$\Delta\theta_{g,d}$	-0.0005
$\Delta\theta_{g,F}$	-0.0005
$\Delta\theta_{i,g}$	-0.0024

Internal Transmittance			
$\lambda_{80}$	363	$\lambda_5$	339

CCI		
B	G	R
0.00	0.33	0.34

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.30923813	
A 2	1.14137353	E-1
A 3	1.17882259	
B 1	8.38873953	E-3
B 2	3.99436485	E-2
B 3	1.40257892	E2
1129 ~ 2325 nm		
A 1	1.30923813	
A 2	1.14137353	E-1
A 3	1.17882259	
B 1	8.38873953	E-3
B 2	3.99436485	E-2
B 3	1.40257892	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.100	
350	0.470	
360	0.760	
365		
370	0.890	
380	0.947	
390	0.971	
400	0.983	
420	0.992	
440	0.993	
460	0.995	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.992	
1600	0.992	
1800	0.976	
2000	0.951	
2200	0.890	
2400	0.840	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	492
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	525
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	540
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	582
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	663
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		91
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	109
Thermal Conductivity (W/m·K)	<b>k</b>	0.901

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	727
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	292
Poisson's Ratio	$\sigma$	0.245
Knoop Hardness	<b>Hk</b>	510 [5]
Abrasion	<b>Aa</b>	163
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.32

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	2.89		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.7	-0.3	-0.3	-0.2		0.4	0.7		
-20 ~ 0	-0.7	-0.3	-0.3	-0.1		0.4	0.8		
0 ~ 20	-0.6	-0.2	-0.2	-0.1	0.1	0.5	0.9		
20 ~ 40	-0.6	-0.2	-0.2		0.2	0.6	1.1		
40 ~ 60	-0.6	-0.1	-0.1	0.1	0.2	0.7	1.2		
60 ~ 80	-0.5	-0.1	-0.1	0.1	0.3	0.8	1.3		



Refractive Index	$n_d$	<b>1.57135</b>	Abbe Number	$V_d$	<b>52.95</b>	Dispersion	$n_F - n_C$	<b>0.01079</b>
	$n_e$	1.571351		$V_e$	52.65		$n_{F'} - n_{C'}$	0.010790
		1.573920						0.010900

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.54361
$n_{1970}$	1.97009	1.54831
$n_{1530}$	1.52958	1.55341
$n_{1129}$	1.12864	1.55806
$n_t$	1.01398	1.55965
$n_s$	0.85211	1.56248
$n_{A'}$	0.76819	1.56445
$n_r$	0.70652	1.56627
$n_c$	0.65627	<b>1.56810</b>
$n_{c'}$	0.64385	1.56862
$n_{\text{He-Ne}}$	0.6328	1.56910
$n_D$	0.58929	1.57126
$n_d$	0.58756	<b>1.57135</b>
$n_e$	0.54607	1.57392
$n_F$	0.48613	<b>1.57889</b>
$n_{F'}$	0.47999	1.57952
$n_{\text{He-Cd}}$	0.44157	1.58409
$n_g$	0.435835	<b>1.58489</b>
$n_h$	0.404656	1.58993
$n_i$	0.365015	1.59867
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008456
$n_c - n_{A'}$	0.003653
$n_d - n_c$	0.003246
$n_e - n_c$	0.005815
$n_g - n_d$	0.013536
$n_g - n_F$	0.005992
$n_h - n_g$	0.005041
$n_i - n_g$	0.013784
$n_{c'} - n_t$	0.008970
$n_e - n_{c'}$	0.005301
$n_{F'} - n_e$	0.005599
$n_i - n_{F'}$	0.019152

Relative Partial Dispersions	
$\theta_{c,t}$	0.7837
$\theta_{c,A'}$	0.3386
$\theta_{d,c}$	0.3008
$\theta_{e,c}$	0.5389
$\theta_{g,d}$	1.2545
$\theta_{g,F}$	0.5553
$\theta_{h,g}$	0.4672
$\theta_{i,g}$	1.2775
$\theta'_{c,t}$	0.8229
$\theta'_{e,c'}$	0.4863
$\theta'_{F',e}$	0.5137
$\theta'_{i,F'}$	1.7571

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0114
$\Delta\theta_{c,A'}$	-0.0015
$\Delta\theta_{g,d}$	-0.0003
$\Delta\theta_{g,F}$	-0.0005
$\Delta\theta_{i,g}$	-0.0041

Internal Transmittance			
$\lambda_{80}$	358	$\lambda_5$	332

CCI		
B	G	R
0.00	0.24	0.25

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.29366890	
A 2	1.32440252	E-1
A 3	1.10197293	
B 1	8.00367962	E-3
B 2	3.54711196	E-2
B 3	1.34517431	E2
1129 ~ 2325 nm		
A 1	1.29366890	
A 2	1.32440252	E-1
A 3	1.10197293	
B 1	8.00367962	E-3
B 2	3.54711196	E-2
B 3	1.34517431	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310		
320		
330	0.010	
340	0.260	
350	0.630	
360	0.840	
365		
370	0.928	
380	0.963	
390	0.979	
400	0.988	
420	0.994	
440	0.994	
460	0.995	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.996	
1400	0.991	
1600	0.990	
1800	0.972	
2000	0.945	
2200	0.880	
2400	0.830	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	483
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	516
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	531
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	573
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	652
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		95
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	111
Thermal Conductivity (W/m·K)	<b>k</b>	0.864

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	719
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	288
Poisson's Ratio	$\sigma$	0.249
Knoop Hardness	<b>Hk</b>	510 [5]
Abrasion	<b>Aa</b>	172
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.18

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	2.98		$\lambda_5$	330				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.0	-0.8	-0.7	-0.6	-0.5	-0.1	0.2		
-20 ~ 0	-1.0	-0.7	-0.7	-0.6	-0.4	-0.1	0.3		
0 ~ 20	-1.0	-0.7	-0.7	-0.6	-0.4		0.4		
20 ~ 40	-1.0	-0.7	-0.6	-0.5	-0.3	0.1	0.5		
40 ~ 60	-1.0	-0.7	-0.6	-0.5	-0.3	0.1	0.5		
60 ~ 80	-1.0	-0.6	-0.6	-0.4	-0.2	0.2	0.6		

Refractive Index	$n_d$	<b>1.53996</b>	Abbe Number	$V_d$	<b>59.46</b>	Dispersion	$n_F - n_C$	<b>0.00908</b>
	$n_e$	1.539956		$V_e$	59.20		$n_{F'} - n_{C'}$	0.009081
		1.542121						0.009158

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.51358
$n_{1970}$	1.97009	1.51848
$n_{1530}$	1.52958	1.52370
$n_{1129}$	1.12864	1.52825
$n_t$	1.01398	1.52974
$n_s$	0.85211	1.53230
$n_{A'}$	0.76819	1.53404
$n_r$	0.70652	1.53562
$n_c$	0.65627	<b>1.53719</b>
$n_{c'}$	0.64385	1.53763
$n_{\text{He-Ne}}$	0.6328	1.53804
$n_D$	0.58929	1.53988
$n_d$	0.58756	<b>1.53996</b>
$n_e$	0.54607	1.54212
$n_F$	0.48613	<b>1.54627</b>
$n_{F'}$	0.47999	1.54679
$n_{\text{He-Cd}}$	0.44157	1.55056
$n_g$	0.435835	<b>1.55122</b>
$n_h$	0.404656	1.55532
$n_i$	0.365015	1.56232
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.007456
$n_C - n_{A'}$	0.003156
$n_d - n_C$	0.002762
$n_e - n_C$	0.004927
$n_g - n_d$	0.011260
$n_g - n_F$	0.004941
$n_h - n_g$	0.004105
$n_i - n_g$	0.011107
$n_{C'} - n_t$	0.007896
$n_e - n_{C'}$	0.004487
$n_{F'} - n_e$	0.004671
$n_i - n_{F'}$	0.015531

Relative Partial Dispersions	
$\theta_{C,t}$	0.8211
$\theta_{C,A'}$	0.3475
$\theta_{d,C}$	0.3042
$\theta_{e,C}$	0.5426
$\theta_{g,d}$	1.2400
$\theta_{g,F}$	0.5441
$\theta_{h,g}$	0.4520
$\theta_{i,g}$	1.2231
$\theta'_{C,t}$	0.8622
$\theta'_{e,C'}$	0.4900
$\theta'_{F',e}$	0.5100
$\theta'_{i,F'}$	1.6959

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.0046
$\Delta\theta_{C,A'}$	-0.0005
$\Delta\theta_{g,d}$	-0.0012
$\Delta\theta_{g,F}$	-0.0012
$\Delta\theta_{i,g}$	-0.0040

Internal Transmittance			
$\lambda_{80}$	330	$\lambda_5$	301

CCI		
B	G	R
0.00	0.09	0.06

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	7.14605258	E-1
A 2	6.21993289	E-1
A 3	1.22537681	
B 1	3.01763913	E-3
B 2	1.66505450	E-2
B 3	1.43506314	E2
1129 ~ 2325 nm		
A 1	7.14605258	E-1
A 2	6.21993289	E-1
A 3	1.22537681	
B 1	3.01763913	E-3
B 2	1.66505450	E-2
B 3	1.43506314	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.020	
310	0.230	
320	0.570	
330	0.800	
340	0.914	
350	0.959	
360	0.979	
365		
370	0.989	
380	0.992	
390	0.995	
400	0.997	
420	0.997	
440	0.997	
460	0.997	
480	0.998	
500	0.999	
550	0.999	
600	0.999	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.993	
1600	0.995	
1800	0.983	
2000	0.966	
2200	0.920	
2400	0.890	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	432
Annealing Point (°C)	<b>AP</b>	468
Transformation Temperature (°C)	<b>Tg</b>	478
Yield Point (°C)	<b>At</b>	527
Softening Point (°C)	<b>SP</b>	624
Expansion Coefficient $\alpha$ (-30~+70°C)		86
Expansion Coefficient $\alpha$ (+100~+300°C)		102
Thermal Conductivity (W/m·K)	<b>k</b>	0.982

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	710
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	306
Poisson's Ratio	$\sigma$	0.161
Knoop Hardness	<b>Hk</b>	520 [5]
Abrasion	<b>Aa</b>	105
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.6

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	330				
Specific Gravity	<b>d</b>	2.75		$\lambda_5$	300				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.4	1.7	1.8	1.8	2.0	2.3	2.6		
-20 ~ 0	1.4	1.7	1.8	1.9	2.0	2.3	2.6		
0 ~ 20	1.4	1.7	1.8	1.9	2.0	2.3	2.7		
20 ~ 40	1.4	1.7	1.8	1.9	2.0	2.4	2.7		
40 ~ 60	1.4	1.7	1.8	1.9	2.1	2.4	2.8		
60 ~ 80	1.4	1.8	1.8	1.9	2.1	2.4	2.8		



Refractive Index	$n_d$	<b>1.56883</b>	Abbe Number	$V_d$	<b>56.36</b>	Dispersion	$n_F - n_C$	<b>0.01010</b>
	$n_e$	1.568832		$V_e$	56.09		$n_{F'} - n_{C'}$	0.010092
		1.571237					$n_{F'} - n_{C'}$	0.010185

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.54050
$n_{1970}$	1.97009	1.54565
$n_{1530}$	1.52958	1.55116
$n_{1129}$	1.12864	1.55601
$n_t$	1.01398	1.55761
$n_s$	0.85211	1.56040
$n_{A'}$	0.76819	1.56230
$n_r$	0.70652	1.56404
$n_c$	0.65627	<b>1.56577</b>
$n_{c'}$	0.64385	1.56626
$n_{\text{He-Ne}}$	0.6328	1.56671
$n_D$	0.58929	1.56874
$n_d$	0.58756	<b>1.56883</b>
$n_e$	0.54607	1.57124
$n_F$	0.48613	<b>1.57587</b>
$n_{F'}$	0.47999	1.57645
$n_{\text{He-Cd}}$	0.44157	1.58067
$n_g$	0.435835	<b>1.58141</b>
$n_h$	0.404656	1.58604
$n_i$	0.365015	1.59400
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	533
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	562
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	580
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	622
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	700
Expansion Coefficient $\alpha$ ( $-30 \sim +70^{\circ}\text{C}$ )		80
( $10^{-7}/^{\circ}\text{C}$ )	( $+100 \sim +300^{\circ}\text{C}$ )	93
Thermal Conductivity (W/m·K)	<b>k</b>	0.967

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	811
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	327
Poisson's Ratio	$\sigma$	0.240
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	134
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.32

Partial Dispersions	
$n_c - n_t$	0.008164
$n_c - n_{A'}$	0.003476
$n_d - n_c$	0.003057
$n_e - n_c$	0.005462
$n_g - n_d$	0.012574
$n_g - n_F$	0.005539
$n_h - n_g$	0.004629
$n_i - n_g$	0.012595
$n_{c'} - n_t$	0.008650
$n_e - n_{c'}$	0.004976
$n_{F'} - n_e$	0.005209
$n_i - n_{F'}$	0.017555

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0021
$\Delta\theta_{c,A'}$	0.0002
$\Delta\theta_{g,d}$	-0.0018
$\Delta\theta_{g,F}$	-0.0014
$\Delta\theta_{i,g}$	-0.0051

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.27553696	
A 2	1.46083393	E-1
A 3	1.16754699	
B 1	7.49692359	E-3
B 2	3.10421530	E-2
B 3	1.28947092	E2
1129 ~ 2325 nm		
A 1	1.27553696	
A 2	1.46083393	E-1
A 3	1.16754699	
B 1	7.49692359	E-3
B 2	3.10421530	E-2
B 3	1.28947092	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8090
$\theta_{c,A'}$	0.3444
$\theta_{d,c}$	0.3029
$\theta_{e,c}$	0.5412
$\theta_{g,d}$	1.2459
$\theta_{g,F}$	0.5489
$\theta_{h,g}$	0.4587
$\theta_{i,g}$	1.2480
$\theta'_{c,t}$	0.8493
$\theta'_{e,c'}$	0.4886
$\theta'_{F',e}$	0.5114
$\theta'_{i,F'}$	1.7236

Internal Transmittance			
$\lambda_{80}$	354	$\lambda_5$	329

CCI		
B	G	R
0.00	0.26	0.24

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.090	
340	0.440	
350	0.740	
360	0.880	
365		
370	0.946	
380	0.970	
390	0.983	
400	0.989	
420	0.992	
440	0.993	
460	0.994	
480	0.995	
500	0.997	
550	0.998	
600	0.998	
650	0.997	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.989	
1600	0.993	
1800	0.983	
2000	0.967	
2200	0.914	
2400	0.860	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	2.89		$\lambda_5$	325				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn/dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.2	1.5	1.5	1.6	1.8	2.1	2.4		
-20 ~ 0	1.2	1.5	1.6	1.7	1.8	2.2	2.5		
0 ~ 20	1.3	1.6	1.6	1.7	1.9	2.2	2.6		
20 ~ 40	1.3	1.7	1.7	1.8	2.0	2.3	2.7		
40 ~ 60	1.4	1.7	1.8	1.8	2.0	2.4	2.8		
60 ~ 80	1.4	1.8	1.8	1.9	2.1	2.5	2.9		

Refractive Index	$n_d$	<b>1.58913</b>	Abbe Number	$V_d$	<b>61.14</b>	Dispersion	$n_F - n_C$	<b>0.00963</b>
	$n_e$	1.589130		$V_e$	60.88		$n_{F'} - n_{C'}$	0.009636
		1.591429						0.009714

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55959
$n_{1970}$	1.97009	1.56531
$n_{1530}$	1.52958	1.57134
$n_{1129}$	1.12864	1.57648
$n_t$	1.01398	1.57813
$n_s$	0.85211	1.58093
$n_{A'}$	0.76819	1.58280
$n_r$	0.70652	1.58450
$n_c$	0.65627	<b>1.58619</b>
$n_{c'}$	0.64385	1.58666
$n_{\text{He-Ne}}$	0.6328	1.58710
$n_D$	0.58929	1.58904
$n_d$	0.58756	<b>1.58913</b>
$n_e$	0.54607	1.59143
$n_F$	0.48613	<b>1.59582</b>
$n_{F'}$	0.47999	1.59637
$n_{\text{He-Cd}}$	0.44157	1.60034
$n_g$	0.435835	<b>1.60103</b>
$n_h$	0.404656	1.60535
$n_i$	0.365015	1.61268
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008061
$n_c - n_{A'}$	0.003384
$n_d - n_c$	0.002942
$n_e - n_c$	0.005241
$n_g - n_d$	0.011904
$n_g - n_F$	0.005210
$n_h - n_g$	0.004314
$n_i - n_g$	0.011647
$n_{c'} - n_t$	0.008530
$n_e - n_{c'}$	0.004772
$n_{F'} - n_e$	0.004942
$n_i - n_{F'}$	0.016310

Relative Partial Dispersions	
$\theta_{c,t}$	0.8366
$\theta_{c,A'}$	0.3512
$\theta_{d,c}$	0.3053
$\theta_{e,c}$	0.5439
$\theta_{g,d}$	1.2354
$\theta_{g,F}$	0.5407
$\theta_{h,g}$	0.4477
$\theta_{i,g}$	1.2087
$\theta'_{c,t}$	0.8781
$\theta'_{e,c'}$	0.4912
$\theta'_{F',e}$	0.5088
$\theta'_{i,F'}$	1.6790

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0030
$\Delta\theta_{c,A'}$	0.0012
$\Delta\theta_{g,d}$	-0.0024
$\Delta\theta_{g,F}$	-0.0018
$\Delta\theta_{i,g}$	-0.0044

Internal Transmittance			
$\lambda_{80}$	339	$\lambda_5$	303

CCI		
B	G	R
0.00	0.17	0.15

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.41357273	E-1
A 2	5.46174895	E-1
A 3	1.16168917	
B 1	1.40333996	E-2
B 2	9.06635683	E-4
B 3	1.14163758	E2
1129 ~ 2325 nm		
A 1	9.41357273	E-1
A 2	5.46174895	E-1
A 3	1.16168917	
B 1	1.40333996	E-2
B 2	9.06635683	E-4
B 3	1.14163758	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.010	
310	0.160	
320	0.430	
330	0.670	
340	0.820	
350	0.904	
360	0.949	
365		
370	0.972	
380	0.983	
390	0.989	
400	0.993	
420	0.995	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.984	
1600	0.994	
1800	0.987	
2000	0.972	
2200	0.890	
2400	0.800	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	619
Annealing Point (°C)	<b>AP</b>	646
Transformation Temperature (°C)	<b>Tg</b>	669
Yield Point (°C)	<b>At</b>	709
Softening Point (°C)	<b>SP</b>	768
Expansion Coefficient $\alpha$ (-30~+70°C)		57
(10-7 / °C) (+100~+300°C)		67
Thermal Conductivity (W/m·K)	<b>k</b>	0.915

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	4.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	832
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	333
Poisson's Ratio	$\sigma$	0.250
Knoop Hardness	<b>Hk</b>	590 [6]
Abrasion	<b>Aa</b>	115
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.15

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	3.31		$\lambda_5$	300				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.9	3.1	3.1	3.3	3.4	3.6	3.9		
-20 ~ 0	3.0	3.3	3.3	3.4	3.5	3.8	4.1		
0 ~ 20	3.2	3.5	3.5	3.6	3.7	4.0	4.3		
20 ~ 40	3.3	3.6	3.6	3.8	3.9	4.2	4.5		
40 ~ 60	3.5	3.8	3.8	3.9	4.1	4.4	4.7		
60 ~ 80	3.6	3.9	4.0	4.1	4.2	4.5	4.9		

Refractive Index	$n_d$	<b>1.56384</b>	Abbe Number	$V_d$	<b>60.67</b>	Dispersion	$n_F - n_C$	<b>0.00929</b>
		1.563839			$V_e$		60.42	
	$n_e$	1.566056					$n_{F'} - n_{C'}$	0.009369

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.53530
$n_{1970}$	1.97009	1.54083
$n_{1530}$	1.52958	1.54667
$n_{1129}$	1.12864	1.55164
$n_t$	1.01398	1.55322
$n_s$	0.85211	1.55593
$n_{A'}$	0.76819	1.55774
$n_r$	0.70652	1.55938
$n_c$	0.65627	<b>1.56100</b>
$n_{c'}$	0.64385	1.56145
$n_{\text{He-Ne}}$	0.6328	1.56188
$n_D$	0.58929	1.56376
$n_d$	0.58756	<b>1.56384</b>
$n_e$	0.54607	1.56606
$n_F$	0.48613	<b>1.57029</b>
$n_{F'}$	0.47999	1.57082
$n_{\text{He-Cd}}$	0.44157	1.57465
$n_g$	0.435835	<b>1.57532</b>
$n_h$	0.404656	1.57947
$n_i$	0.365015	1.58652
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	486
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	521
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	541
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	577
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	644
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		75
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	91
Thermal Conductivity (W/m·K)	<b>k</b>	1.043

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	890
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	358
Poisson's Ratio	$\sigma$	0.242
Knoop Hardness	<b>Hk</b>	600 [6]
Abrasion	<b>Aa</b>	122
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.32

Partial Dispersions	
$n_c - n_t$	0.007779
$n_c - n_{A'}$	0.003265
$n_d - n_c$	0.002838
$n_e - n_c$	0.005055
$n_g - n_d$	0.011477
$n_g - n_F$	0.005021
$n_h - n_g$	0.004155
$n_i - n_g$	0.011208
$n_{c'} - n_t$	0.008231
$n_e - n_{c'}$	0.004603
$n_{F'} - n_e$	0.004766
$n_i - n_{F'}$	0.015702

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0057
$\Delta\theta_{c,A'}$	0.0019
$\Delta\theta_{g,d}$	-0.0038
$\Delta\theta_{g,F}$	-0.0031
$\Delta\theta_{i,g}$	-0.0111

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.24344200	
A 2	1.66301104	E-1
A 3	1.10586114	
B 1	1.16396708	E-2
B 2	-8.90464938	E-3
B 3	1.14111220	E2
1129 ~ 2325 nm		
A 1	1.24344200	
A 2	1.66301104	E-1
A 3	1.10586114	
B 1	1.16396708	E-2
B 2	-8.90464938	E-3
B 3	1.14111220	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	3.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8370
$\theta_{c,A'}$	0.3513
$\theta_{d,c}$	0.3054
$\theta_{e,c}$	0.5439
$\theta_{g,d}$	1.2349
$\theta_{g,F}$	0.5402
$\theta_{h,g}$	0.4471
$\theta_{i,g}$	1.2059
$\theta'_{c,t}$	0.8785
$\theta'_{e,c'}$	0.4913
$\theta'_{F',e}$	0.5087
$\theta'_{i,F'}$	1.6760

Internal Transmittance			
$\lambda_{80}$	336	$\lambda_5$	300

CCI		
B	G	R
0.00	0.20	0.14

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.050	
310	0.250	
320	0.510	
330	0.720	
340	0.850	
350	0.925	
360	0.960	
365		
370	0.978	
380	0.985	
390	0.990	
400	0.993	
420	0.994	
440	0.994	
460	0.995	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.997	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.987	
1600	0.993	
1800	0.984	
2000	0.971	
2200	0.908	
2400	0.830	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	340				
Specific Gravity	<b>d</b>	2.78		$\lambda_5$	295				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.1	2.3	2.3	2.4	2.5	2.8	3.0		
-20 ~ 0	2.1	2.3	2.3	2.4	2.6	2.9	3.2		
0 ~ 20	2.1	2.4	2.4	2.5	2.7	3.0	3.3		
20 ~ 40	2.1	2.5	2.5	2.6	2.7	3.1	3.4		
40 ~ 60	2.2	2.5	2.5	2.7	2.8	3.2	3.5		
60 ~ 80	2.2	2.6	2.6	2.7	2.9	3.2	3.6		

Refractive Index	$n_d$	<b>1.58313</b> 1.583126	Abbe Number	$V_d$	<b>59.38</b> 59.11	Dispersion	$n_F - n_C$	<b>0.00982</b> 0.009821
		$n_e$		1.585468			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55463
$n_{1970}$	1.97009	1.55992
$n_{1530}$	1.52958	1.56557
$n_{1129}$	1.12864	1.57048
$n_t$	1.01398	1.57208
$n_s$	0.85211	1.57485
$n_{A'}$	0.76819	1.57673
$n_r$	0.70652	1.57844
$n_c$	0.65627	<b>1.58014</b>
$n_{c'}$	0.64385	1.58061
$n_{\text{He-Ne}}$	0.6328	1.58106
$n_D$	0.58929	1.58304
$n_d$	0.58756	<b>1.58313</b>
$n_e$	0.54607	1.58547
$n_F$	0.48613	<b>1.58996</b>
$n_{F'}$	0.47999	1.59052
$n_{\text{He-Cd}}$	0.44157	1.59459
$n_g$	0.435835	<b>1.59530</b>
$n_h$	0.404656	1.59972
$n_i$	0.365015	1.60724
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008056
$n_c - n_{A'}$	0.003413
$n_d - n_c$	0.002987
$n_e - n_c$	0.005329
$n_g - n_d$	0.012171
$n_g - n_F$	0.005337
$n_h - n_g$	0.004424
$n_i - n_g$	0.011946
$n_{c'} - n_t$	0.008531
$n_{e'} - n_{c'}$	0.004854
$n_{F'} - n_e$	0.005051
$n_i - n_{F'}$	0.016724

Relative Partial Dispersions	
$\theta_{c,t}$	0.8203
$\theta_{c,A'}$	0.3475
$\theta_{d,c}$	0.3041
$\theta_{e,c}$	0.5426
$\theta_{g,d}$	1.2393
$\theta_{g,F}$	0.5434
$\theta_{h,g}$	0.4505
$\theta_{i,g}$	1.2164
$\theta'_{c,t}$	0.8613
$\theta'_{e,c'}$	0.4901
$\theta'_{F',e}$	0.5099
$\theta'_{i,F'}$	1.6884

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0050
$\Delta\theta_{c,A'}$	-0.0004
$\Delta\theta_{g,d}$	-0.0021
$\Delta\theta_{g,F}$	-0.0020
$\Delta\theta_{i,g}$	-0.0114

Internal Transmittance			
$\lambda_{80}$	335	$\lambda_5$	292

CCI		
B	G	R
0.00	0.16	0.14

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.39570615	
A 2	7.18505070	E-2
A 3	1.27129267	
B 1	1.12218843	E-2
B 2	-2.52117422	E-2
B 3	1.34497860	E2
1129 ~ 2325 nm		
A 1	1.39570615	
A 2	7.18505070	E-2
A 3	1.27129267	
B 1	1.12218843	E-2
B 2	-2.52117422	E-2
B 3	1.34497860	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290	0.030	
300	0.150	
310	0.360	
320	0.580	
330	0.750	
340	0.860	
350	0.932	
360	0.964	
365		
370	0.979	
380	0.986	
390	0.991	
400	0.993	
420	0.995	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.997	
1000	0.997	
1200	0.997	
1400	0.987	
1600	0.994	
1800	0.985	
2000	0.973	
2200	0.917	
2400	0.860	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	503
Annealing Point (°C)	<b>AP</b>	534
Transformation Temperature (°C)	<b>Tg</b>	550
Yield Point (°C)	<b>At</b>	588
Softening Point (°C)	<b>SP</b>	672
Expansion Coefficient $\alpha$ (-30~+70°C)		66
(10-7 /°C) (+100~+300°C)		76
Thermal Conductivity (W/m·K)	<b>k</b>	0.974

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	2
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	847
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	340
Poisson's Ratio	$\sigma$	0.246
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	117
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.2

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	340				
Specific Gravity	<b>d</b>	3.19		$\lambda_5$	290				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.9	3.2	3.2	3.3	3.5	3.8	4.0		
-20 ~ 0	2.9	3.3	3.3	3.4	3.5	3.8	4.1		
0 ~ 20	3.0	3.3	3.3	3.4	3.6	3.9	4.2		
20 ~ 40	3.0	3.4	3.4	3.5	3.7	4.0	4.3		
40 ~ 60	3.0	3.4	3.4	3.6	3.7	4.1	4.4		
60 ~ 80	3.1	3.5	3.5	3.7	3.8	4.2	4.5		

Refractive Index	$n_d$	<b>1.60562</b>	Abbe Number	$V_d$	<b>43.70</b>	Dispersion	$n_F - n_C$	<b>0.01385</b>
	$n_e$	1.605620		$V_e$	43.41		$n_{F'} - n_{C'}$	0.013857
		1.608909						0.014026

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.57351
$n_{1970}$	1.97009	1.57850
$n_{1530}$	1.52958	1.58402
$n_{1129}$	1.12864	1.58926
$n_t$	1.01398	1.59113
$n_s$	0.85211	1.59453
$n_{A'}$	0.76819	1.59695
$n_r$	0.70652	1.59921
$n_c$	0.65627	<b>1.60151</b>
$n_{c'}$	0.64385	1.60215
$n_{\text{He-Ne}}$	0.6328	1.60276
$n_D$	0.58929	1.60550
$n_d$	0.58756	<b>1.60562</b>
$n_e$	0.54607	1.60891
$n_F$	0.48613	<b>1.61536</b>
$n_{F'}$	0.47999	1.61618
$n_{\text{He-Cd}}$	0.44157	1.62222
$n_g$	0.435835	<b>1.62329</b>
$n_h$	0.404656	1.63010
$n_i$	0.365015	1.64228
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010380
$n_c - n_{A'}$	0.004557
$n_d - n_c$	0.004113
$n_e - n_c$	0.007402
$n_g - n_d$	0.017671
$n_g - n_F$	0.007927
$n_h - n_g$	0.006811
$n_i - n_g$	0.018992
$n_{c'} - n_t$	0.011028
$n_e - n_{c'}$	0.006754
$n_{F'} - n_e$	0.007272
$n_i - n_{F'}$	0.026102

Relative Partial Dispersions	
$\theta_{c,t}$	0.7491
$\theta_{c,A'}$	0.3289
$\theta_{d,c}$	0.2968
$\theta_{e,c}$	0.5342
$\theta_{g,d}$	1.2752
$\theta_{g,F}$	0.5721
$\theta_{h,g}$	0.4915
$\theta_{i,g}$	1.3706
$\theta'_{c,t}$	0.7863
$\theta'_{e,c'}$	0.4815
$\theta'_{F',e}$	0.5185
$\theta'_{i,F'}$	1.8610

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0026
$\Delta\theta_{c,A'}$	0.0001
$\Delta\theta_{g,d}$	0.0012
$\Delta\theta_{g,F}$	0.0013
$\Delta\theta_{i,g}$	0.0115

Internal Transmittance			
$\lambda_{80}$	375	$\lambda_5$	350

CCI		
B	G	R
0.00	0.69	0.65

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.41059317	
A 2	1.11201306	E-1
A 3	1.34148939	
B 1	9.63312192	E-3
B 2	4.98778210	E-2
B 3	1.52237696	E2
1129 ~ 2325 nm		
A 1	1.41059317	
A 2	1.11201306	E-1
A 3	1.34148939	
B 1	9.63312192	E-3
B 2	4.98778210	E-2
B 3	1.52237696	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.060	
360	0.410	
365		
370	0.720	
380	0.870	
390	0.938	
400	0.965	
420	0.986	
440	0.991	
460	0.991	
480	0.993	
500	0.995	
550	0.998	
600	0.997	
650	0.996	
700	0.997	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.995	
1600	0.994	
1800	0.980	
2000	0.962	
2200	0.919	
2400	0.890	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	548
Annealing Point (°C)	<b>AP</b>	577
Transformation Temperature (°C)	<b>Tg</b>	599
Yield Point (°C)	<b>At</b>	641
Softening Point (°C)	<b>SP</b>	722
Expansion Coefficient $\alpha$ (-30~+70°C)		84
Expansion Coefficient $\alpha$ (+100~+300°C)		97
Thermal Conductivity (W/m·K)	<b>k</b>	0.931

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	762
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	306
Poisson's Ratio	$\sigma$	0.244
Knoop Hardness	<b>Hk</b>	520 [5]
Abrasion	<b>Aa</b>	151
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.41

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	2.91		$\lambda_5$		345			
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.6	1.0	1.0	1.2	1.4	1.9	2.4		
-20 ~ 0	0.7	1.1	1.1	1.3	1.5	2.0	2.6		
0 ~ 20	0.7	1.1	1.2	1.3	1.6	2.1	2.7		
20 ~ 40	0.8	1.2	1.2	1.4	1.7	2.2	2.9		
40 ~ 60	0.8	1.3	1.3	1.5	1.8	2.4	3.0		
60 ~ 80	0.9	1.4	1.4	1.6	1.9	2.5	3.2		

Refractive Index	$n_d$	<b>1.63930</b>	Abbe Number	$V_d$	<b>44.87</b>	Dispersion	$n_F - n_C$	<b>0.01424</b>
		1.639300			$V_e$		44.59	
	$n_e$	1.642684					$n_{F'} - n_{C'}$	0.014414

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.60480
$n_{1970}$	1.97009	1.61040
$n_{1530}$	1.52958	1.61653
$n_{1129}$	1.12864	1.62223
$n_t$	1.01398	1.62422
$n_s$	0.85211	1.62781
$n_{A'}$	0.76819	1.63033
$n_r$	0.70652	1.63268
$n_c$	0.65627	<b>1.63506</b>
$n_{c'}$	0.64385	1.63573
$n_{\text{He-Ne}}$	0.6328	1.63635
$n_D$	0.58929	1.63917
$n_d$	0.58756	<b>1.63930</b>
$n_e$	0.54607	1.64268
$n_F$	0.48613	<b>1.64930</b>
$n_{F'}$	0.47999	1.65014
$n_{\text{He-Cd}}$	0.44157	1.65631
$n_g$	0.435835	<b>1.65740</b>
$n_h$	0.404656	1.66433
$n_i$	0.365015	1.67665
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	565
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	592
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	608
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	645
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	717
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		76
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	91
Thermal Conductivity (W/m·K)	<b>k</b>	0.954

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	904
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	361
Poisson's Ratio	$\sigma$	0.253
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	144
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.3

Partial Dispersions	
$n_c - n_t$	0.010836
$n_c - n_{A'}$	0.004725
$n_d - n_c$	0.004243
$n_e - n_c$	0.007627
$n_g - n_d$	0.018101
$n_g - n_F$	0.008097
$n_h - n_g$	0.006929
$n_i - n_g$	0.019244
$n_{c'} - n_t$	0.011505
$n_e - n_{c'}$	0.006958
$n_{F'} - n_e$	0.007456
$n_i - n_{F'}$	0.026505

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0034
$\Delta\theta_{c,A'}$	0.0014
$\Delta\theta_{g,d}$	-0.0010
$\Delta\theta_{g,F}$	-0.0006
$\Delta\theta_{i,g}$	0.0014

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.50161605	
A 2	1.26987445	E-1
A 3	1.43544052	
B 1	9.40761826	E-3
B 2	4.72602195	E-2
B 3	1.41666499	E2
1129 ~ 2325 nm		
A 1	1.50161605	
A 2	1.26987445	E-1
A 3	1.43544052	
B 1	9.40761826	E-3
B 2	4.72602195	E-2
B 3	1.41666499	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	3.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7606
$\theta_{c,A'}$	0.3316
$\theta_{d,c}$	0.2978
$\theta_{e,c}$	0.5353
$\theta_{g,d}$	1.2705
$\theta_{g,F}$	0.5683
$\theta_{h,g}$	0.4863
$\theta_{i,g}$	1.3507
$\theta'_{c,t}$	0.7982
$\theta'_{e,c'}$	0.4827
$\theta'_{F',e}$	0.5173
$\theta'_{i,F'}$	1.8388

Internal Transmittance			
$\lambda_{80}$	374	$\lambda_5$	348

CCI		
B	G	R
0.00	0.93	0.93

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.130	
360	0.490	
365		
370	0.750	
380	0.870	
390	0.928	
400	0.955	
420	0.977	
440	0.983	
460	0.987	
480	0.990	
500	0.993	
550	0.997	
600	0.996	
650	0.996	
700	0.997	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.992	
1600	0.995	
1800	0.987	
2000	0.976	
2200	0.932	
2400	0.860	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	3.18		$\lambda_5$	345				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.3	2.6	2.7	2.8	3.0	3.5	4.1		
-20 ~ 0	2.3	2.7	2.7	2.9	3.1	3.6	4.2		
0 ~ 20	2.3	2.7	2.8	3.0	3.2	3.7	4.3		
20 ~ 40	2.4	2.8	2.8	3.0	3.3	3.8	4.5		
40 ~ 60	2.4	2.8	2.9	3.1	3.3	3.9	4.6		
60 ~ 80	2.4	2.9	2.9	3.1	3.4	4.0	4.7		



Refractive Index	$n_d$	<b>1.51633</b>	Abbe Number	$V_d$	<b>64.14</b>	Dispersion	$n_F - n_C$	<b>0.00805</b>
		1.516330			$V_e$		63.93	
	$n_e$	1.518251					$n_{F'} - n_{C'}$	0.008107

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.48899
$n_{1970}$	1.97009	1.49462
$n_{1530}$	1.52958	1.50050
$n_{1129}$	1.12864	1.50536
$n_t$	1.01398	1.50686
$n_s$	0.85211	1.50935
$n_{A'}$	0.76819	1.51097
$n_r$	0.70652	1.51243
$n_C$	0.65627	<b>1.51386</b>
$n_{C'}$	0.64385	1.51425
$n_{\text{He-Ne}}$	0.6328	1.51462
$n_D$	0.58929	1.51626
$n_d$	0.58756	<b>1.51633</b>
$n_e$	0.54607	1.51825
$n_F$	0.48613	<b>1.52191</b>
$n_{F'}$	0.47999	1.52236
$n_{\text{He-Cd}}$	0.44157	1.52564
$n_g$	0.435835	<b>1.52621</b>
$n_h$	0.404656	1.52977
$n_i$	0.365015	1.53578
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	532
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	563
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	576
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	625
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	718
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		72
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	86
Thermal Conductivity (W/m·K)	<b>k</b>	1.130

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	800
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	332
Poisson's Ratio	$\sigma$	0.205
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	94
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.79

Partial Dispersions	
$n_C - n_t$	0.006993
$n_C - n_{A'}$	0.002882
$n_d - n_C$	0.002475
$n_e - n_C$	0.004396
$n_g - n_d$	0.009884
$n_g - n_F$	0.004309
$n_h - n_g$	0.003554
$n_i - n_g$	0.009571
$n_{C'} - n_t$	0.007389
$n_e - n_{C'}$	0.004000
$n_{F'} - n_e$	0.004107
$n_i - n_{F'}$	0.013427

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0211
$\Delta\theta_{C,A'}$	0.0044
$\Delta\theta_{g,d}$	-0.0037
$\Delta\theta_{g,F}$	-0.0024
$\Delta\theta_{i,g}$	0.0010

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.15150190	
A 2	1.18583612	E-1
A 3	1.26301359	
B 1	1.05984130	E-2
B 2	-1.18225190	E-2
B 3	1.29617662	E2
1129 ~ 2325 nm		
A 1	1.15150190	
A 2	1.18583612	E-1
A 3	1.26301359	
B 1	1.05984130	E-2
B 2	-1.18225190	E-2
B 3	1.29617662	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.8687
$\theta_{C,A'}$	0.3580
$\theta_{d,C}$	0.3075
$\theta_{e,C}$	0.5461
$\theta_{g,d}$	1.2278
$\theta_{g,F}$	0.5353
$\theta_{h,g}$	0.4415
$\theta_{i,g}$	1.1889
$\theta'_{C,t}$	0.9114
$\theta'_{e,C'}$	0.4934
$\theta'_{F',e}$	0.5066
$\theta'_{i,F'}$	1.6562

Internal Transmittance			
$\lambda_{80}$	323	$\lambda_5$	289

CCI		
B	G	R
0.00	0.08	0.07

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290	0.080	
300	0.310	
310	0.580	
320	0.770	
330	0.880	
340	0.940	
350	0.968	
360	0.984	
365		
370	0.991	
380	0.991	
390	0.996	
400	0.997	
420	0.996	
440	0.995	
460	0.995	
480	0.996	
500	0.996	
550	0.998	
600	0.997	
650	0.997	
700	0.998	
800	0.998	
900	0.997	
1000	0.996	
1200	0.995	
1400	0.982	
1600	0.991	
1800	0.980	
2000	0.961	
2200	0.890	
2400	0.850	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	330				
Specific Gravity	<b>d</b>	2.52		$\lambda_5$	285				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.1	2.3	2.3	2.4	2.5	2.7	3.0		
-20 ~ 0	2.1	2.4	2.4	2.5	2.6	2.8	3.1		
0 ~ 20	2.2	2.5	2.5	2.6	2.7	3.0	3.2		
20 ~ 40	2.2	2.6	2.6	2.7	2.8	3.1	3.3		
40 ~ 60	2.3	2.6	2.7	2.8	2.9	3.2	3.5		
60 ~ 80	2.4	2.7	2.7	2.9	3.0	3.3	3.6		

Refractive Index	$n_d$	<b>1.60738</b>	Abbe Number	$V_d$	<b>56.81</b>	Dispersion	$n_F - n_C$	<b>0.01069</b>
		1.607379			$V_e$		56.53	
	$n_e$	1.609927					$n_{F'} - n_{C'}$	0.010790

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.57874
$n_{1970}$	1.97009	1.58374
$n_{1530}$	1.52958	1.58913
$n_{1129}$	1.12864	1.59398
$n_t$	1.01398	1.59561
$n_s$	0.85211	1.59849
$n_{A'}$	0.76819	1.60048
$n_r$	0.70652	1.60231
$n_c$	0.65627	<b>1.60414</b>
$n_{c'}$	0.64385	1.60466
$n_{\text{He-Ne}}$	0.6328	1.60514
$n_D$	0.58929	1.60728
$n_d$	0.58756	<b>1.60738</b>
$n_e$	0.54607	1.60993
$n_F$	0.48613	<b>1.61483</b>
$n_{F'}$	0.47999	1.61545
$n_{\text{He-Cd}}$	0.44157	1.61992
$n_g$	0.435835	<b>1.62070</b>
$n_h$	0.404656	1.62558
$n_i$	0.365015	1.63394
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008534
$n_c - n_{A'}$	0.003662
$n_d - n_c$	0.003235
$n_e - n_c$	0.005783
$n_g - n_d$	0.013318
$n_g - n_F$	0.005862
$n_h - n_g$	0.004885
$n_i - n_g$	0.013244
$n_{c'} - n_t$	0.009048
$n_e - n_{c'}$	0.005269
$n_{F'} - n_e$	0.005521
$n_i - n_{F'}$	0.018493

Relative Partial Dispersions	
$\theta_{c,t}$	0.7982
$\theta_{c,A'}$	0.3425
$\theta_{d,c}$	0.3026
$\theta_{e,c}$	0.5409
$\theta_{g,d}$	1.2457
$\theta_{g,F}$	0.5483
$\theta_{h,g}$	0.4569
$\theta_{i,g}$	1.2388
$\theta'_{c,t}$	0.8386
$\theta'_{e,c'}$	0.4883
$\theta'_{F',e}$	0.5117
$\theta'_{i,F'}$	1.7139

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0150
$\Delta\theta_{c,A'}$	-0.0022
$\Delta\theta_{g,d}$	-0.0010
$\Delta\theta_{g,F}$	-0.0013
$\Delta\theta_{i,g}$	-0.0105

Internal Transmittance			
$\lambda_{80}$	343	$\lambda_5$	310

CCI		
B	G	R
0.00	0.26	0.25

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	8.67168676	E-1
A 2	6.72848343	E-1
A 3	1.18456107	
B 1	3.69311003	E-3
B 2	1.81652804	E-2
B 3	1.32376147	E2
1129 ~ 2325 nm		
A 1	8.67168676	E-1
A 2	6.72848343	E-1
A 3	1.18456107	
B 1	3.69311003	E-3
B 2	1.81652804	E-2
B 3	1.32376147	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310	0.040	
320	0.270	
330	0.570	
340	0.770	
350	0.880	
360	0.941	
365		
370	0.967	
380	0.981	
390	0.987	
400	0.991	
420	0.991	
440	0.990	
460	0.991	
480	0.993	
500	0.995	
550	0.997	
600	0.997	
650	0.996	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.994	
1600	0.997	
1800	0.992	
2000	0.984	
2200	0.951	
2400	0.890	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	612
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	643
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	654
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	690
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	778
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	65
	(+10~+300 $^{\circ}\text{C}$ )	74
Thermal Conductivity (W/m·K)	<b>k</b>	0.802

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	5.2
Phosphate Resistance	<b>PR</b>	2.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	780
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	309
Poisson's Ratio	$\sigma$	0.264
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	133
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.26

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	350				
Specific Gravity	<b>d</b>	3.53		$\lambda_5$	300				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.1	3.5	3.6	3.7	3.8	4.2	4.5		
-20 ~ 0	3.2	3.6	3.7	3.8	3.9	4.3	4.7		
0 ~ 20	3.3	3.7	3.7	3.9	4.0	4.4	4.8		
20 ~ 40	3.4	3.8	3.8	4.0	4.1	4.5	4.9		
40 ~ 60	3.4	3.9	3.9	4.1	4.3	4.7	5.1		
60 ~ 80	3.5	4.0	4.0	4.2	4.4	4.8	5.2		

Refractive Index	$n_d$	<b>1.61272</b> 1.612716	Abbe Number	$V_d$	<b>58.72</b> 58.45	Dispersion	$n_F - n_C$	<b>0.01043</b> 0.010435
		$n_e$		1.615204			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.58338
$n_{1970}$	1.97009	1.58871
$n_{1530}$	1.52958	1.59440
$n_{1129}$	1.12864	1.59941
$n_t$	1.01398	1.60107
$n_s$	0.85211	1.60396
$n_{A'}$	0.76819	1.60594
$n_r$	0.70652	1.60775
$n_c$	0.65627	<b>1.60955</b>
$n_{c'}$	0.64385	1.61005
$n_{\text{He-Ne}}$	0.6328	1.61052
$n_D$	0.58929	1.61262
$n_d$	0.58756	<b>1.61272</b>
$n_e$	0.54607	1.61520
$n_F$	0.48613	<b>1.61998</b>
$n_{F'}$	0.47999	1.62058
$n_{\text{He-Cd}}$	0.44157	1.62491
$n_g$	0.435835	<b>1.62567</b>
$n_h$	0.404656	1.63039
$n_i$	0.365015	1.63845
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008474
$n_c - n_{A'}$	0.003609
$n_d - n_c$	0.003169
$n_e - n_c$	0.005657
$n_g - n_d$	0.012952
$n_g - n_F$	0.005686
$n_h - n_g$	0.004723
$n_i - n_g$	0.012778
$n_{c'} - n_t$	0.008978
$n_e - n_{c'}$	0.005153
$n_{F'} - n_e$	0.005373
$n_i - n_{F'}$	0.017869

Relative Partial Dispersions	
$\theta_{c,t}$	0.8121
$\theta_{c,A'}$	0.3459
$\theta_{d,c}$	0.3037
$\theta_{e,c}$	0.5421
$\theta_{g,d}$	1.2412
$\theta_{g,F}$	0.5449
$\theta_{h,g}$	0.4526
$\theta_{i,g}$	1.2245
$\theta'_{c,t}$	0.8529
$\theta'_{e,c'}$	0.4895
$\theta'_{F',e}$	0.5105
$\theta'_{i,F'}$	1.6976

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0101
$\Delta\theta_{c,A'}$	-0.0012
$\Delta\theta_{g,d}$	-0.0016
$\Delta\theta_{g,F}$	-0.0016
$\Delta\theta_{i,g}$	-0.0088

Internal Transmittance			
$\lambda_{80}$	346	$\lambda_5$	311

CCI		
B	G	R
0.00	0.18	0.18

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.62443080	E-1
A 2	5.95939234	E-1
A 3	1.10558352	
B 1	4.68062141	E-3
B 2	1.78772082	E-2
B 3	1.15896432	E2
1129 ~ 2325 nm		
A 1	9.62443080	E-1
A 2	5.95939234	E-1
A 3	1.10558352	
B 1	4.68062141	E-3
B 2	1.78772082	E-2
B 3	1.15896432	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.040	
320	0.240	
330	0.520	
340	0.730	
350	0.850	
360	0.924	
365		
370	0.960	
380	0.977	
390	0.985	
400	0.991	
420	0.994	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.997	
1000	0.997	
1200	0.997	
1400	0.990	
1600	0.994	
1800	0.985	
2000	0.971	
2200	0.911	
2400	0.820	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	613
Annealing Point (°C)	<b>AP</b>	643
Transformation Temperature (°C)	<b>Tg</b>	660
Yield Point (°C)	<b>At</b>	694
Softening Point (°C)	<b>SP</b>	757
Expansion Coefficient $\alpha$ (-30~+70°C)		67
(10-7 /°C) (+100~+300°C)		76
Thermal Conductivity (W/m·K)	<b>k</b>	0.836

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	816
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	322
Poisson's Ratio	$\sigma$	0.265
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	142
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.77

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	350				
Specific Gravity	<b>d</b>	3.57		$\lambda_5$	310				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.8	2.0	2.0	2.1	2.2	2.5	2.8		
-20 ~ 0	1.9	2.1	2.1	2.2	2.3	2.6	2.9		
0 ~ 20	1.9	2.2	2.2	2.3	2.4	2.8	3.1		
20 ~ 40	2.0	2.3	2.3	2.4	2.6	2.9	3.2		
40 ~ 60	2.0	2.3	2.4	2.5	2.7	3.0	3.3		
60 ~ 80	2.1	2.4	2.5	2.6	2.8	3.1	3.5		

Refractive Index	$n_d$	<b>1.62280</b>	Abbe Number	$V_d$	<b>57.05</b>	Dispersion	$n_F - n_C$	<b>0.01092</b>
		1.622799			$V_e$		56.78	
	$n_e$	1.625401					$n_{F'} - n_{C'}$	0.011014

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.59271
$n_{1970}$	1.97009	1.59809
$n_{1530}$	1.52958	1.60386
$n_{1129}$	1.12864	1.60898
$n_t$	1.01398	1.61069
$n_s$	0.85211	1.61368
$n_{A'}$	0.76819	1.61573
$n_r$	0.70652	1.61761
$n_c$	0.65627	<b>1.61949</b>
$n_{c'}$	0.64385	1.62001
$n_{\text{He-Ne}}$	0.6328	1.62051
$n_D$	0.58929	1.62270
$n_d$	0.58756	<b>1.62280</b>
$n_e$	0.54607	1.62540
$n_F$	0.48613	<b>1.63041</b>
$n_{F'}$	0.47999	1.63103
$n_{\text{He-Cd}}$	0.44157	1.63558
$n_g$	0.435835	<b>1.63637</b>
$n_h$	0.404656	1.64133
$n_i$	0.365015	1.64980
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008800
$n_c - n_{A'}$	0.003759
$n_d - n_c$	0.003310
$n_e - n_c$	0.005912
$n_g - n_d$	0.013570
$n_g - n_F$	0.005964
$n_h - n_g$	0.004960
$n_i - n_g$	0.013428
$n_{c'} - n_t$	0.009326
$n_e - n_{c'}$	0.005386
$n_{F'} - n_e$	0.005628
$n_i - n_{F'}$	0.018768

Relative Partial Dispersions	
$\theta_{c,t}$	0.8062
$\theta_{c,A'}$	0.3444
$\theta_{d,c}$	0.3032
$\theta_{e,c}$	0.5416
$\theta_{g,d}$	1.2431
$\theta_{g,F}$	0.5464
$\theta_{h,g}$	0.4544
$\theta_{i,g}$	1.2301
$\theta'_{c,t}$	0.8467
$\theta'_{e,c'}$	0.4890
$\theta'_{F',e}$	0.5110
$\theta'_{i,F'}$	1.7040

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0082
$\Delta\theta_{c,A'}$	-0.0006
$\Delta\theta_{g,d}$	-0.0031
$\Delta\theta_{g,F}$	-0.0028
$\Delta\theta_{i,g}$	-0.0172

Internal Transmittance			
$\lambda_{80}$	345	$\lambda_5$	309

CCI		
B	G	R
0.00	0.17	0.15

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.45443081	E-1
A 2	6.43237376	E-1
A 3	1.17752968	
B 1	1.57263798	E-2
B 2	1.61924066	E-3
B 3	1.21361748	E2
1129 ~ 2325 nm		
A 1	9.45443081	E-1
A 2	6.43237376	E-1
A 3	1.17752968	
B 1	1.57263798	E-2
B 2	1.61924066	E-3
B 3	1.21361748	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.080	
320	0.310	
330	0.570	
340	0.750	
350	0.860	
360	0.929	
365		
370	0.962	
380	0.977	
390	0.986	
400	0.991	
420	0.994	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.998	
600	0.998	
650	0.997	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.990	
1600	0.993	
1800	0.985	
2000	0.971	
2200	0.913	
2400	0.820	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	622
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	650
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	668
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	709
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	773
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	65
	(+10-7~+300 $^{\circ}\text{C}$ )	76
Thermal Conductivity (W/m·K)	<b>k</b>	0.822

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	835
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	330
Poisson's Ratio	$\sigma$	0.266
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	142
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.88

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	350				
Specific Gravity	<b>d</b>	3.60		$\lambda_5$	305				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.0	2.4	2.4	2.5	2.6	3.0	3.3		
-20 ~ 0	2.1	2.5	2.5	2.6	2.7	3.1	3.4		
0 ~ 20	2.2	2.6	2.6	2.7	2.8	3.2	3.5		
20 ~ 40	2.2	2.6	2.7	2.8	2.9	3.3	3.6		
40 ~ 60	2.3	2.7	2.8	2.9	3.0	3.4	3.8		
60 ~ 80	2.4	2.8	2.8	3.0	3.1	3.5	3.9		

Refractive Index	$n_d$	<b>1.60311</b> 1.603112	Abbe Number	$V_d$	<b>60.64</b> 60.39	Dispersion	$n_F - n_C$	<b>0.00994</b> 0.009945
		$n_e$		1.605484			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.57300
$n_{1970}$	1.97009	1.57880
$n_{1530}$	1.52958	1.58491
$n_{1129}$	1.12864	1.59013
$n_t$	1.01398	1.59180
$n_s$	0.85211	1.59467
$n_{A'}$	0.76819	1.59660
$n_r$	0.70652	1.59835
$n_c$	0.65627	<b>1.60008</b>
$n_{c'}$	0.64385	1.60056
$n_{\text{He-Ne}}$	0.6328	1.60101
$n_D$	0.58929	1.60302
$n_d$	0.58756	<b>1.60311</b>
$n_e$	0.54607	1.60548
$n_F$	0.48613	<b>1.61002</b>
$n_{F'}$	0.47999	1.61059
$n_{\text{He-Cd}}$	0.44157	1.61470
$n_g$	0.435835	<b>1.61541</b>
$n_h$	0.404656	1.61987
$n_i$	0.365015	1.62745
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.008275
$n_C - n_{A'}$	0.003482
$n_d - n_C$	0.003033
$n_e - n_C$	0.005405
$n_g - n_d$	0.012297
$n_g - n_F$	0.005385
$n_h - n_g$	0.004461
$n_i - n_g$	0.012043
$n_{C'} - n_t$	0.008758
$n_e - n_{C'}$	0.004922
$n_{F'} - n_e$	0.005105
$n_i - n_{F'}$	0.016863

Relative Partial Dispersions	
$\theta_{C,t}$	0.8321
$\theta_{C,A'}$	0.3501
$\theta_{d,C}$	0.3050
$\theta_{e,C}$	0.5435
$\theta_{g,d}$	1.2365
$\theta_{g,F}$	0.5415
$\theta_{h,g}$	0.4486
$\theta_{i,g}$	1.2110
$\theta'_{C,t}$	0.8734
$\theta'_{e,C'}$	0.4909
$\theta'_{F',e}$	0.5091
$\theta'_{i,F'}$	1.6818

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0009
$\Delta\theta_{C,A'}$	0.0007
$\Delta\theta_{g,d}$	-0.0023
$\Delta\theta_{g,F}$	-0.0019
$\Delta\theta_{i,g}$	-0.0062

Internal Transmittance			
$\lambda_{80}$	339	$\lambda_5$	306

CCI		
B	G	R
0.00	0.19	0.20

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.28286270	
A 2	2.47647429	E-1
A 3	1.10383999	
B 1	1.22902399	E-2
B 2	-6.13142361	E-3
B 3	1.06883378	E2
1129 ~ 2325 nm		
A 1	1.28286270	
A 2	2.47647429	E-1
A 3	1.10383999	
B 1	1.22902399	E-2
B 2	-6.13142361	E-3
B 3	1.06883378	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.170	
320	0.450	
330	0.680	
340	0.820	
350	0.906	
360	0.948	
365		
370	0.968	
380	0.980	
390	0.987	
400	0.991	
420	0.994	
440	0.994	
460	0.995	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.990	
1600	0.995	
1800	0.988	
2000	0.976	
2200	0.919	
2400	0.810	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	614
Annealing Point (°C)	<b>AP</b>	641
Transformation Temperature (°C)	<b>Tg</b>	663
Yield Point (°C)	<b>At</b>	698
Softening Point (°C)	<b>SP</b>	757
Expansion Coefficient $\alpha$ (-30~+70°C)		62
(10-7 /°C) (+100~+300°C)		73
Thermal Conductivity (W/m·K)	<b>k</b>	0.891

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	849
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	338
Poisson's Ratio	$\sigma$	0.257
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	131
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.01

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	350				
Specific Gravity	<b>d</b>	3.43		$\lambda_5$	295				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.5	2.7	2.7	2.8	2.9	3.1	3.4		
-20 ~ 0	2.5	2.8	2.8	2.9	3.0	3.3	3.5		
0 ~ 20	2.6	2.9	2.9	3.0	3.1	3.4	3.7		
20 ~ 40	2.6	2.9	3.0	3.1	3.2	3.5	3.8		
40 ~ 60	2.7	3.0	3.1	3.2	3.3	3.6	4.0		
60 ~ 80	2.7	3.1	3.1	3.3	3.4	3.8	4.1		

Refractive Index	$n_d$	<b>1.62299</b>	Abbe Number	$V_d$	<b>58.16</b>	Dispersion	$n_F - n_C$	<b>0.01071</b>
		1.622992			$V_e$		57.89	
	$n_e$	1.625545					$n_{F'} - n_{C'}$	0.010805

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.59236
$n_{1970}$	1.97009	1.59797
$n_{1530}$	1.52958	1.60399
$n_{1129}$	1.12864	1.60927
$n_t$	1.01398	1.61100
$n_s$	0.85211	1.61399
$n_{A'}$	0.76819	1.61603
$n_r$	0.70652	1.61789
$n_c$	0.65627	<b>1.61974</b>
$n_{c'}$	0.64385	1.62026
$n_{\text{He-Ne}}$	0.6328	1.62074
$n_D$	0.58929	1.62290
$n_d$	0.58756	<b>1.62299</b>
$n_e$	0.54607	1.62555
$n_F$	0.48613	<b>1.63045</b>
$n_{F'}$	0.47999	1.63106
$n_{\text{He-Cd}}$	0.44157	1.63552
$n_g$	0.435835	<b>1.63630</b>
$n_h$	0.404656	1.64116
$n_i$	0.365015	1.64948
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008741
$n_c - n_{A'}$	0.003709
$n_d - n_c$	0.003253
$n_e - n_c$	0.005806
$n_g - n_d$	0.013304
$n_g - n_F$	0.005846
$n_h - n_g$	0.004866
$n_i - n_g$	0.013186
$n_{c'} - n_t$	0.009259
$n_e - n_{c'}$	0.005288
$n_{F'} - n_e$	0.005517
$n_i - n_{F'}$	0.018420

Relative Partial Dispersions	
$\theta_{c,t}$	0.8161
$\theta_{c,A'}$	0.3463
$\theta_{d,c}$	0.3037
$\theta_{e,c}$	0.5421
$\theta_{g,d}$	1.2421
$\theta_{g,F}$	0.5458
$\theta_{h,g}$	0.4543
$\theta_{i,g}$	1.2311
$\theta'_{c,t}$	0.8569
$\theta'_{e,c'}$	0.4894
$\theta'_{F',e}$	0.5106
$\theta'_{i,F'}$	1.7048

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0035
$\Delta\theta_{c,A'}$	-0.0001
$\Delta\theta_{g,d}$	-0.0018
$\Delta\theta_{g,F}$	-0.0016
$\Delta\theta_{i,g}$	-0.0069

Internal Transmittance			
$\lambda_{80}$	357	$\lambda_5$	327

CCI		
B	G	R
0.00	0.32	0.30

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.53128328	E-1
A 2	6.37613977	E-1
A 3	1.65245647	
B 1	3.87638985	E-3
B 2	1.85094632	E-2
B 3	1.59442367	E2
1129 ~ 2325 nm		
A 1	9.53128328	E-1
A 2	6.37613977	E-1
A 3	1.65245647	
B 1	3.87638985	E-3
B 2	1.85094632	E-2
B 3	1.59442367	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.130	
340	0.440	
350	0.700	
360	0.850	
365		
370	0.926	
380	0.959	
390	0.976	
400	0.985	
420	0.991	
440	0.992	
460	0.994	
480	0.995	
500	0.997	
550	0.998	
600	0.997	
650	0.997	
700	0.998	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.991	
1600	0.994	
1800	0.987	
2000	0.973	
2200	0.918	
2400	0.810	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	615
Annealing Point (°C)	<b>AP</b>	639
Transformation Temperature (°C)	<b>Tg</b>	658
Yield Point (°C)	<b>At</b>	685
Softening Point (°C)	<b>SP</b>	746
Expansion Coefficient $\alpha$ (-30~+70°C)		65
(10-7 /°C) (+100~+300°C)		78
Thermal Conductivity (W/m·K)	<b>k</b>	0.845

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	3.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	854
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	338
Poisson's Ratio	$\sigma$	0.265
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	133
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.8

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	3.60		$\lambda_5$	320				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.3	1.6	1.6	1.7	1.8	2.1	2.4		
-20 ~ 0	1.4	1.7	1.7	1.8	1.9	2.2	2.5		
0 ~ 20	1.4	1.8	1.8	1.9	2.0	2.4	2.7		
20 ~ 40	1.5	1.9	1.9	2.0	2.2	2.5	2.8		
40 ~ 60	1.6	2.0	2.0	2.1	2.3	2.6	3.0		
60 ~ 80	1.6	2.1	2.1	2.2	2.4	2.8	3.1		



Refractive Index	$n_d$	<b>1.62041</b> 1.620411	Abbe Number	$V_d$	<b>60.29</b> 60.03	Dispersion	$n_F - n_C$	<b>0.01029</b> 0.010290
		$n_e$		1.622865			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.58957
$n_{1970}$	1.97009	1.59545
$n_{1530}$	1.52958	1.60168
$n_{1129}$	1.12864	1.60702
$n_t$	1.01398	1.60874
$n_s$	0.85211	1.61170
$n_{A'}$	0.76819	1.61368
$n_r$	0.70652	1.61549
$n_c$	0.65627	<b>1.61728</b>
$n_{c'}$	0.64385	1.61778
$n_{\text{He-Ne}}$	0.6328	1.61824
$n_D$	0.58929	1.62032
$n_d$	0.58756	<b>1.62041</b>
$n_e$	0.54607	1.62287
$n_F$	0.48613	<b>1.62757</b>
$n_{F'}$	0.47999	1.62815
$n_{\text{He-Cd}}$	0.44157	1.63241
$n_g$	0.435835	<b>1.63315</b>
$n_h$	0.404656	1.63778
$n_i$	0.365015	1.64567
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008531
$n_c - n_{A'}$	0.003595
$n_d - n_c$	0.003135
$n_e - n_c$	0.005589
$n_g - n_d$	0.012739
$n_g - n_F$	0.005584
$n_h - n_g$	0.004632
$n_i - n_g$	0.012520
$n_{c'} - n_t$	0.009030
$n_e - n_{c'}$	0.005090
$n_{F'} - n_e$	0.005286
$n_i - n_{F'}$	0.017519

Relative Partial Dispersions	
$\theta_{c,t}$	0.8291
$\theta_{c,A'}$	0.3494
$\theta_{d,c}$	0.3047
$\theta_{e,c}$	0.5431
$\theta_{g,d}$	1.2380
$\theta_{g,F}$	0.5427
$\theta_{h,g}$	0.4501
$\theta_{i,g}$	1.2167
$\theta'_{c,t}$	0.8703
$\theta'_{e,c'}$	0.4906
$\theta'_{F',e}$	0.5094
$\theta'_{i,F'}$	1.6884

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0005
$\Delta\theta_{c,A'}$	0.0004
$\Delta\theta_{g,d}$	-0.0015
$\Delta\theta_{g,F}$	-0.0012
$\Delta\theta_{i,g}$	-0.0035

Internal Transmittance			
$\lambda_{80}$	346	$\lambda_5$	312

CCI		
B	G	R
0.00	0.28	0.23

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.14490383	
A 2	4.39563911	E-1
A 3	1.27688079	
B 1	1.37034916	E-2
B 2	-1.86514205	E-3
B 3	1.19535585	E2
1129 ~ 2325 nm		
A 1	1.14490383	
A 2	4.39563911	E-1
A 3	1.27688079	
B 1	1.37034916	E-2
B 2	-1.86514205	E-3
B 3	1.19535585	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.010	
320	0.180	
330	0.490	
340	0.720	
350	0.850	
360	0.924	
365		
370	0.959	
380	0.976	
390	0.984	
400	0.989	
420	0.992	
440	0.993	
460	0.994	
480	0.996	
500	0.997	
550	0.999	
600	0.998	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.992	
1600	0.995	
1800	0.987	
2000	0.972	
2200	0.911	
2400	0.790	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	606
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	634
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	657
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	689
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	738
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	67
	(+100~+300 $^{\circ}\text{C}$ )	76
Thermal Conductivity (W/m·K)	<b>k</b>	0.835

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	53.2
Phosphate Resistance	<b>PR</b>	4.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	878
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	348
Poisson's Ratio	$\sigma$	0.262
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	146
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.81

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	350				
Specific Gravity	<b>d</b>	3.59		$\lambda_5$	305				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.2	1.4	1.5	1.6	1.7	1.9	2.2	2.2	
-20 ~ 0	1.2	1.5	1.6	1.7	1.8	2.1	2.3	2.3	
0 ~ 20	1.3	1.6	1.6	1.8	1.9	2.2	2.5	2.5	
20 ~ 40	1.4	1.7	1.7	1.9	2.0	2.3	2.6	2.6	
40 ~ 60	1.4	1.8	1.8	2.0	2.1	2.4	2.7	2.7	
60 ~ 80	1.6	1.9	1.9	2.1	2.2	2.5	2.9	2.9	

Refractive Index	$n_d$	<b>1.63854</b>	Abbe Number	$V_d$	<b>55.38</b>	Dispersion	$n_F - n_C$	<b>0.01153</b>
		1.638539			$V_e$		55.10	
	$n_e$	1.641287					$n_{F'} - n_{C'}$	0.011638

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.60779
$n_{1970}$	1.97009	1.61314
$n_{1530}$	1.52958	1.61892
$n_{1129}$	1.12864	1.62411
$n_t$	1.01398	1.62586
$n_s$	0.85211	1.62896
$n_{A'}$	0.76819	1.63111
$n_r$	0.70652	1.63308
$n_c$	0.65627	<b>1.63505</b>
$n_{c'}$	0.64385	1.63560
$n_{\text{He-Ne}}$	0.6328	1.63612
$n_D$	0.58929	1.63844
$n_d$	0.58756	<b>1.63854</b>
$n_e$	0.54607	1.64129
$n_F$	0.48613	<b>1.64658</b>
$n_{F'}$	0.47999	1.64724
$n_{\text{He-Cd}}$	0.44157	1.65207
$n_g$	0.435835	<b>1.65291</b>
$n_h$	0.404656	1.65818
$n_i$	0.365015	1.66720
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009188
$n_c - n_{A'}$	0.003946
$n_d - n_c$	0.003488
$n_e - n_c$	0.006236
$n_g - n_d$	0.014367
$n_g - n_F$	0.006324
$n_h - n_g$	0.005271
$n_i - n_g$	0.014291
$n_{c'} - n_t$	0.009742
$n_e - n_{c'}$	0.005682
$n_{F'} - n_e$	0.005956
$n_i - n_{F'}$	0.019954

Relative Partial Dispersions	
$\theta_{c,t}$	0.7968
$\theta_{c,A'}$	0.3422
$\theta_{d,c}$	0.3025
$\theta_{e,c}$	0.5408
$\theta_{g,d}$	1.2459
$\theta_{g,F}$	0.5484
$\theta_{h,g}$	0.4571
$\theta_{i,g}$	1.2394
$\theta'_{c,t}$	0.8371
$\theta'_{e,c'}$	0.4882
$\theta'_{F',e}$	0.5118
$\theta'_{i,F'}$	1.7146

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0097
$\Delta\theta_{c,A'}$	-0.0008
$\Delta\theta_{g,d}$	-0.0038
$\Delta\theta_{g,F}$	-0.0035
$\Delta\theta_{i,g}$	-0.0219

Internal Transmittance			
$\lambda_{80}$	345	$\lambda_5$	309

CCI		
B	G	R
0.00	0.21	0.22

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.27886025	E-1
A 2	7.08858526	E-1
A 3	1.18610897	
B 1	4.17549199	E-3
B 2	1.84691838	E-2
B 3	1.22210416	E2
1129 ~ 2325 nm		
A 1	9.27886025	E-1
A 2	7.08858526	E-1
A 3	1.18610897	
B 1	4.17549199	E-3
B 2	1.84691838	E-2
B 3	1.22210416	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.080	
320	0.310	
330	0.570	
340	0.750	
350	0.860	
360	0.929	
365		
370	0.961	
380	0.977	
390	0.985	
400	0.990	
420	0.993	
440	0.994	
460	0.995	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.993	
1600	0.994	
1800	0.986	
2000	0.973	
2200	0.924	
2400	0.840	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	567
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	600
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	613
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	655
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	717
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	70
	(+10~+300 $^{\circ}\text{C}$ )	84
Thermal Conductivity (W/m·K)	<b>k</b>	0.815

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	885
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	349
Poisson's Ratio	$\sigma$	0.268
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	159
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.79

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	350				
Specific Gravity	<b>d</b>	3.69		$\lambda_5$		305			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.8	2.2	2.3	2.4	2.5	2.9	3.2		
-20 ~ 0	1.8	2.3	2.3	2.4	2.6	3.0	3.3		
0 ~ 20	1.9	2.4	2.4	2.5	2.7	3.1	3.4		
20 ~ 40	1.9	2.4	2.5	2.6	2.8	3.2	3.5		
40 ~ 60	2.0	2.5	2.5	2.7	2.9	3.3	3.7		
60 ~ 80	2.1	2.6	2.6	2.8	2.9	3.4	3.8		

Refractive Index	$n_d$	<b>1.62230</b> 1.622296	Abbe Number	$V_d$	<b>53.17</b> 52.88	Dispersion	$n_F - n_C$	<b>0.01170</b> 0.011704
		$n_e$		1.625083			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.59157
$n_{1970}$	1.97009	1.59687
$n_{1530}$	1.52958	1.60260
$n_{1129}$	1.12864	1.60778
$n_t$	1.01398	1.60953
$n_s$	0.85211	1.61264
$n_{A'}$	0.76819	1.61479
$n_r$	0.70652	1.61678
$n_c$	0.65627	<b>1.61877</b>
$n_{c'}$	0.64385	1.61933
$n_{\text{He-Ne}}$	0.6328	1.61985
$n_D$	0.58929	1.62219
$n_d$	0.58756	<b>1.62230</b>
$n_e$	0.54607	1.62508
$n_F$	0.48613	<b>1.63047</b>
$n_{F'}$	0.47999	1.63115
$n_{\text{He-Cd}}$	0.44157	1.63610
$n_g$	0.435835	<b>1.63696</b>
$n_h$	0.404656	1.64241
$n_i$	0.365015	1.65185
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009237
$n_c - n_{A'}$	0.003977
$n_d - n_c$	0.003526
$n_e - n_c$	0.006313
$n_g - n_d$	0.014664
$n_g - n_F$	0.006486
$n_h - n_g$	0.005451
$n_i - n_g$	0.014894
$n_{c'} - n_t$	0.009796
$n_e - n_{c'}$	0.005754
$n_{F'} - n_e$	0.006067
$n_i - n_{F'}$	0.020704

Relative Partial Dispersions	
$\theta_{c,t}$	0.7892
$\theta_{c,A'}$	0.3398
$\theta_{d,c}$	0.3013
$\theta_{e,c}$	0.5394
$\theta_{g,d}$	1.2529
$\theta_{g,F}$	0.5542
$\theta_{h,g}$	0.4657
$\theta_{i,g}$	1.2726
$\theta'_{c,t}$	0.8287
$\theta'_{e,c'}$	0.4868
$\theta'_{F',e}$	0.5132
$\theta'_{i,F'}$	1.7515

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0070
$\Delta\theta_{c,A'}$	-0.0005
$\Delta\theta_{g,d}$	-0.0014
$\Delta\theta_{g,F}$	-0.0012
$\Delta\theta_{i,g}$	-0.0072

Internal Transmittance			
$\lambda_{80}$	369	$\lambda_5$	339

CCI		
B	G	R
0.00	0.74	0.67

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.44305741	
A 2	1.40786358	E-1
A 3	1.26093951	
B 1	8.19208910	E-3
B 2	3.56911455	E-2
B 3	1.31959337	E2
1129 ~ 2325 nm		
A 1	1.44305741	
A 2	1.40786358	E-1
A 3	1.26093951	
B 1	8.19208910	E-3
B 2	3.56911455	E-2
B 3	1.31959337	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.080	
350	0.370	
360	0.650	
365		
370	0.810	
380	0.901	
390	0.942	
400	0.964	
420	0.981	
440	0.985	
460	0.988	
480	0.991	
500	0.994	
550	0.997	
600	0.995	
650	0.994	
700	0.996	
800	0.998	
900	0.998	
1000	0.997	
1200	0.998	
1400	0.993	
1600	0.995	
1800	0.990	
2000	0.980	
2200	0.938	
2400	0.870	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	637
Annealing Point (°C)	<b>AP</b>	663
Transformation Temperature (°C)	<b>Tg</b>	685
Yield Point (°C)	<b>At</b>	726
Softening Point (°C)	<b>SP</b>	822
Expansion Coefficient $\alpha$ (-30~+70°C)		66
(10-7 /°C) (+100~+300°C)		76
Thermal Conductivity (W/m·K)	<b>k</b>	0.916

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	2
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	3.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	874
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	345
Poisson's Ratio	$\sigma$	0.265
Knoop Hardness	<b>Hk</b>	580 [6]
Abrasion	<b>Aa</b>	120
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.97

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	3.24		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.0	3.4	3.4	3.6	3.7	4.1	4.4		
-20 ~ 0	3.0	3.4	3.4	3.6	3.8	4.1	4.5		
0 ~ 20	3.1	3.5	3.5	3.6	3.8	4.2	4.6		
20 ~ 40	3.1	3.5	3.6	3.7	3.9	4.3	4.8		
40 ~ 60	3.1	3.6	3.6	3.7	4.0	4.4	4.9		
60 ~ 80	3.1	3.7	3.7	3.8	4.0	4.5	5.0		

Refractive Index	$n_d$	<b>1.65844</b>	Abbe Number	$V_d$	<b>50.88</b>	Dispersion	$n_F - n_C$	<b>0.01294</b>
		1.658441			$V_e$		50.59	
	$n_e$	1.661522					$n_{F'} - n_{C'}$	0.013076

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.62613
$n_{1970}$	1.97009	1.63145
$n_{1530}$	1.52958	1.63727
$n_{1129}$	1.12864	1.64264
$n_t$	1.01398	1.64450
$n_s$	0.85211	1.64785
$n_{A'}$	0.76819	1.65019
$n_r$	0.70652	1.65237
$n_c$	0.65627	<b>1.65455</b>
$n_{c'}$	0.64385	1.65517
$n_{\text{He-Ne}}$	0.6328	1.65574
$n_D$	0.58929	1.65833
$n_d$	0.58756	<b>1.65844</b>
$n_e$	0.54607	1.66152
$n_F$	0.48613	<b>1.66749</b>
$n_{F'}$	0.47999	1.66824
$n_{\text{He-Cd}}$	0.44157	1.67373
$n_g$	0.435835	<b>1.67469</b>
$n_h$	0.404656	1.68074
$n_i$	0.365015	1.69121
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010049
$n_c - n_{A'}$	0.004361
$n_d - n_c$	0.003888
$n_e - n_c$	0.006969
$n_g - n_d$	0.016250
$n_g - n_F$	0.007196
$n_h - n_g$	0.006049
$n_i - n_g$	0.016516
$n_{c'} - n_t$	0.010664
$n_e - n_{c'}$	0.006354
$n_{F'} - n_e$	0.006722
$n_i - n_{F'}$	0.022963

Relative Partial Dispersions	
$\theta_{c,t}$	0.7765
$\theta_{c,A'}$	0.3370
$\theta_{d,c}$	0.3004
$\theta_{e,c}$	0.5385
$\theta_{g,d}$	1.2556
$\theta_{g,F}$	0.5560
$\theta_{h,g}$	0.4674
$\theta_{i,g}$	1.2762
$\theta'_{c,t}$	0.8155
$\theta'_{e,c'}$	0.4859
$\theta'_{F',e}$	0.5141
$\theta'_{i,F'}$	1.7561

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0089
$\Delta\theta_{c,A'}$	-0.0005
$\Delta\theta_{g,d}$	-0.0034
$\Delta\theta_{g,F}$	-0.0031
$\Delta\theta_{i,g}$	-0.0228

Internal Transmittance			
$\lambda_{80}$	367	$\lambda_5$	331

CCI		
B	G	R
0.00	0.71	0.70

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.34814257	
A 2	3.47530319	E-1
A 3	1.38798368	
B 1	6.95364366	E-3
B 2	2.77863478	E-2
B 3	1.42138122	E2
1129 ~ 2325 nm		
A 1	1.34814257	
A 2	3.47530319	E-1
A 3	1.38798368	
B 1	6.95364366	E-3
B 2	2.77863478	E-2
B 3	1.42138122	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310		
320		
330	0.030	
340	0.190	
350	0.480	
360	0.710	
365		
370	0.840	
380	0.910	
390	0.945	
400	0.964	
420	0.980	
440	0.984	
460	0.988	
480	0.991	
500	0.994	
550	0.996	
600	0.995	
650	0.995	
700	0.996	
800	0.997	
900	0.997	
1000	0.996	
1200	0.997	
1400	0.995	
1600	0.995	
1800	0.989	
2000	0.980	
2200	0.947	
2400	0.870	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	605
Annealing Point (°C)	<b>AP</b>	630
Transformation Temperature (°C)	<b>Tg</b>	638
Yield Point (°C)	<b>At</b>	686
Softening Point (°C)	<b>SP</b>	760
Expansion Coefficient $\alpha$ (-30~+70°C)		68
(10-7 /°C) (+100~+300°C)		82
Thermal Conductivity (W/m·K)	<b>k</b>	0.891

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	5.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	951
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	374
Poisson's Ratio	$\sigma$	0.272
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	123
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.08

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	375				
Specific Gravity	<b>d</b>	3.50		$\lambda_5$	330				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.4	3.8	3.9	4.0	4.2	4.7	5.1		
-20 ~ 0	3.5	3.9	3.9	4.1	4.3	4.8	5.3		
0 ~ 20	3.6	4.0	4.0	4.2	4.4	4.9	5.4		
20 ~ 40	3.6	4.1	4.1	4.3	4.5	5.0	5.5		
40 ~ 60	3.7	4.2	4.2	4.4	4.6	5.1	5.7		
60 ~ 80	3.8	4.2	4.3	4.5	4.7	5.2	5.8		

Refractive Index	$n_d$	<b>1.61772</b>	Abbe Number	$V_d$	<b>49.81</b>	Dispersion	$n_F - n_C$	<b>0.01240</b>
		1.617722			$V_e$		49.52	
	$n_e$	1.620671					$n_{F'} - n_{C'}$	0.012534

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.58652
$n_{1970}$	1.97009	1.59173
$n_{1530}$	1.52958	1.59740
$n_{1129}$	1.12864	1.60260
$n_t$	1.01398	1.60439
$n_s$	0.85211	1.60760
$n_{A'}$	0.76819	1.60984
$n_r$	0.70652	1.61192
$n_c$	0.65627	<b>1.61401</b>
$n_{c'}$	0.64385	1.61459
$n_{\text{He-Ne}}$	0.6328	1.61514
$n_D$	0.58929	1.61761
$n_d$	0.58756	<b>1.61772</b>
$n_e$	0.54607	1.62067
$n_F$	0.48613	<b>1.62641</b>
$n_{F'}$	0.47999	1.62713
$n_{\text{He-Cd}}$	0.44157	1.63242
$n_g$	0.435835	<b>1.63335</b>
$n_h$	0.404656	1.63924
$n_i$	0.365015	1.64953
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009612
$n_c - n_{A'}$	0.004166
$n_d - n_c$	0.003717
$n_e - n_c$	0.006666
$n_g - n_d$	0.015632
$n_g - n_F$	0.006948
$n_h - n_g$	0.005882
$n_i - n_g$	0.016179
$n_{c'} - n_t$	0.010200
$n_e - n_{c'}$	0.006078
$n_{F'} - n_e$	0.006456
$n_i - n_{F'}$	0.022406

Relative Partial Dispersions	
$\theta_{c,t}$	0.7751
$\theta_{c,A'}$	0.3359
$\theta_{d,c}$	0.2997
$\theta_{e,c}$	0.5375
$\theta_{g,d}$	1.2605
$\theta_{g,F}$	0.5603
$\theta_{h,g}$	0.4743
$\theta_{i,g}$	1.3047
$\theta'_{c,t}$	0.8138
$\theta'_{e,c'}$	0.4849
$\theta'_{F',e}$	0.5151
$\theta'_{i,F'}$	1.7876

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0053
$\Delta\theta_{c,A'}$	-0.0003
$\Delta\theta_{g,d}$	-0.0008
$\Delta\theta_{g,F}$	-0.0006
$\Delta\theta_{i,g}$	-0.0032

Internal Transmittance			
$\lambda_{80}$	375	$\lambda_5$	341

CCI		
B	G	R
0.00	1.01	1.02

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.43822841	
A 2	1.28100017	E-1
A 3	1.34355530	
B 1	8.59779750	E-3
B 2	4.08617854	E-2
B 3	1.43709890	E2
1129 ~ 2325 nm		
A 1	1.43822841	
A 2	1.28100017	E-1
A 3	1.34355530	
B 1	8.59779750	E-3
B 2	4.08617854	E-2
B 3	1.43709890	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.020	
350	0.240	
360	0.540	
365		
370	0.740	
380	0.850	
390	0.918	
400	0.950	
420	0.975	
440	0.982	
460	0.987	
480	0.990	
500	0.993	
550	0.997	
600	0.996	
650	0.996	
700	0.997	
800	0.997	
900	0.997	
1000	0.996	
1200	0.996	
1400	0.994	
1600	0.995	
1800	0.988	
2000	0.978	
2200	0.944	
2400	0.880	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	530
Annealing Point (°C)	<b>AP</b>	559
Transformation Temperature (°C)	<b>Tg</b>	578
Yield Point (°C)	<b>At</b>	618
Softening Point (°C)	<b>SP</b>	680
Expansion Coefficient $\alpha$ (-30~+70°C)		84
(10-7 / °C)	(+100~+300°C)	96
Thermal Conductivity (W/m·K)	<b>k</b>	0.878

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	3.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	853
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	339
Poisson's Ratio	$\sigma$	0.258
Knoop Hardness	<b>Hk</b>	540 [5]
Abrasion	<b>Aa</b>	168
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.05

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	3.23		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.5	0.9	1.0	1.1	1.3	1.7	2.1		
-20 ~ 0	0.6	1.0	1.0	1.2	1.4	1.8	2.3		
0 ~ 20	0.7	1.1	1.1	1.2	1.5	1.9	2.4		
20 ~ 40	0.7	1.1	1.2	1.3	1.5	2.0	2.5		
40 ~ 60	0.8	1.2	1.2	1.4	1.6	2.1	2.6		
60 ~ 80	0.8	1.3	1.3	1.5	1.7	2.2	2.8		

Refractive Index	$n_d$	<b>1.64850</b>	Abbe Number	$V_d$	<b>53.02</b>	Dispersion	$n_F - n_C$	<b>0.01223</b>
		1.648498			$V_e$		52.73	
	$n_e$	1.651410					$n_{F'} - n_{C'}$	0.012353

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.61657
$n_{1970}$	1.97009	1.62205
$n_{1530}$	1.52958	1.62799
$n_{1129}$	1.12864	1.63336
$n_t$	1.01398	1.63518
$n_s$	0.85211	1.63842
$n_{A'}$	0.76819	1.64067
$n_r$	0.70652	1.64274
$n_c$	0.65627	<b>1.64482</b>
$n_{c'}$	0.64385	1.64540
$n_{\text{He-Ne}}$	0.6328	1.64595
$n_D$	0.58929	1.64839
$n_d$	0.58756	<b>1.64850</b>
$n_e$	0.54607	1.65141
$n_F$	0.48613	<b>1.65705</b>
$n_{F'}$	0.47999	1.65775
$n_{\text{He-Cd}}$	0.44157	1.66293
$n_g$	0.435835	<b>1.66383</b>
$n_h$	0.404656	1.66954
$n_i$	0.365015	1.67943
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009631
$n_c - n_{A'}$	0.004150
$n_d - n_c$	0.003683
$n_e - n_c$	0.006595
$n_g - n_d$	0.015333
$n_g - n_F$	0.006785
$n_h - n_g$	0.005706
$n_i - n_g$	0.015599
$n_{c'} - n_t$	0.010215
$n_e - n_{c'}$	0.006011
$n_{F'} - n_e$	0.006342
$n_i - n_{F'}$	0.021678

Relative Partial Dispersions	
$\theta_{c,t}$	0.7874
$\theta_{c,A'}$	0.3393
$\theta_{d,c}$	0.3011
$\theta_{e,c}$	0.5392
$\theta_{g,d}$	1.2536
$\theta_{g,F}$	0.5547
$\theta_{h,g}$	0.4665
$\theta_{i,g}$	1.2754
$\theta'_{c,t}$	0.8269
$\theta'_{e,c'}$	0.4866
$\theta'_{F',e}$	0.5134
$\theta'_{i,F'}$	1.7549

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0080
$\Delta\theta_{c,A'}$	-0.0008
$\Delta\theta_{g,d}$	-0.0010
$\Delta\theta_{g,F}$	-0.0010
$\Delta\theta_{i,g}$	-0.0057

Internal Transmittance			
$\lambda_{80}$	366	$\lambda_5$	337

CCI		
B	G	R
0.00	0.59	0.55

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.50847885	
A 2	1.58099826	E-1
A 3	1.36815368	
B 1	8.12769076	E-3
B 2	3.54200898	E-2
B 3	1.36110038	E2
1129 ~ 2325 nm		
A 1	1.50847885	
A 2	1.58099826	E-1
A 3	1.36815368	
B 1	8.12769076	E-3
B 2	3.54200898	E-2
B 3	1.36110038	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.150	
350	0.470	
360	0.720	
365		
370	0.860	
380	0.926	
390	0.958	
400	0.973	
420	0.985	
440	0.988	
460	0.990	
480	0.993	
500	0.995	
550	0.998	
600	0.997	
650	0.996	
700	0.997	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.993	
1600	0.993	
1800	0.985	
2000	0.972	
2200	0.925	
2400	0.820	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	607
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	635
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	651
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	687
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	737
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	71
	(+10-7 / $^{\circ}\text{C}$ )	83
Thermal Conductivity (W/m·K)	<b>k</b>	0.773

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	53.2
Phosphate Resistance	<b>PR</b>	4.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	862
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	339
Poisson's Ratio	$\sigma$	0.273
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	173
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.81

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	375				
Specific Gravity	<b>d</b>	3.74		$\lambda_5$		335			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.3	1.5	1.6	1.7	1.8	2.1	2.6		
-20 ~ 0	1.2	1.6	1.6	1.8	1.9	2.3	2.7		
0 ~ 20	1.3	1.8	1.8	1.9	2.1	2.5	3.0		
20 ~ 40	1.4	2.0	2.0	2.1	2.3	2.8	3.2		
40 ~ 60	1.5	2.2	2.2	2.4	2.6	3.1	3.5		
60 ~ 80	1.6	2.5	2.5	2.7	2.9	3.5	3.9		



Refractive Index	$n_d$	<b>1.64000</b> 1.639999	Abbe Number	$V_d$	<b>60.08</b> 59.88	Dispersion	$n_F - n_C$	<b>0.01065</b> 0.010653
		$n_e$		1.642540			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.60385
$n_{1970}$	1.97009	1.61138
$n_{1530}$	1.52958	1.61917
$n_{1129}$	1.12864	1.62555
$n_t$	1.01398	1.62752
$n_s$	0.85211	1.63078
$n_{A'}$	0.76819	1.63293
$n_r$	0.70652	1.63484
$n_c$	0.65627	<b>1.63673</b>
$n_{c'}$	0.64385	1.63725
$n_{\text{He-Ne}}$	0.6328	1.63774
$n_D$	0.58929	1.63990
$n_d$	0.58756	<b>1.64000</b>
$n_e$	0.54607	1.64254
$n_F$	0.48613	<b>1.64738</b>
$n_{F'}$	0.47999	1.64798
$n_{\text{He-Cd}}$	0.44157	1.65235
$n_g$	0.435835	<b>1.65310</b>
$n_h$	0.404656	1.65783
$n_i$	0.365015	1.66586
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009210
$n_c - n_{A'}$	0.003802
$n_d - n_c$	0.003271
$n_e - n_c$	0.005812
$n_g - n_d$	0.013103
$n_g - n_F$	0.005721
$n_h - n_g$	0.004730
$n_i - n_g$	0.012761
$n_{c'} - n_t$	0.009734
$n_e - n_{c'}$	0.005288
$n_{F'} - n_e$	0.005442
$n_i - n_{F'}$	0.017881

Relative Partial Dispersions	
$\theta_{c,t}$	0.8645
$\theta_{c,A'}$	0.3569
$\theta_{d,c}$	0.3070
$\theta_{e,c}$	0.5456
$\theta_{g,d}$	1.2300
$\theta_{g,F}$	0.5370
$\theta_{h,g}$	0.4440
$\theta_{i,g}$	1.1979
$\theta'_{c,t}$	0.9072
$\theta'_{e,c'}$	0.4928
$\theta'_{F',e}$	0.5072
$\theta'_{i,F'}$	1.6664

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0359
$\Delta\theta_{c,A'}$	0.0082
$\Delta\theta_{g,d}$	-0.0100
$\Delta\theta_{g,F}$	-0.0073
$\Delta\theta_{i,g}$	-0.0240

Internal Transmittance			
$\lambda_{80}$	358	$\lambda_5$	303

CCI		
B	G	R
0.00	0.55	0.49

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.96356844	E-1
A 2	6.51392837	E-1
A 3	1.22432622	
B 1	1.44821587	E-2
B 2	1.54826389	E-3
B 3	8.99818604	E1
1129 ~ 2325 nm		
A 1	9.96356844	E-1
A 2	6.51392837	E-1
A 3	1.22432622	
B 1	1.44821587	E-2
B 2	1.54826389	E-3
B 3	8.99818604	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290	0.010	
300	0.030	
310	0.100	
320	0.210	
330	0.380	
340	0.560	
350	0.710	
360	0.820	
365		
370	0.890	
380	0.934	
390	0.957	
400	0.970	
420	0.981	
440	0.985	
460	0.989	
480	0.992	
500	0.995	
550	0.995	
600	0.992	
650	0.993	
700	0.995	
800	0.997	
900	0.997	
1000	0.996	
1200	0.996	
1400	0.993	
1600	0.994	
1800	0.985	
2000	0.961	
2200	0.870	
2400	0.610	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	604
Annealing Point (°C)	<b>AP</b>	624
Transformation Temperature (°C)	<b>Tg</b>	653
Yield Point (°C)	<b>At</b>	679
Softening Point (°C)	<b>SP</b>	721
Expansion Coefficient $\alpha$ (-30~+70°C)		58
(10-7 /°C) (+100~+300°C)		72
Thermal Conductivity (W/m·K)	<b>k</b>	1.001

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	4
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	53.0
Phosphate Resistance	<b>PR</b>	4.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1057
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	416
Poisson's Ratio	$\sigma$	0.271
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	84
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	3.06		$\lambda_5$	305				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.8	3.1	3.1	3.3	3.3	3.6	3.8		
-20 ~ 0	2.9	3.2	3.2	3.4	3.5	3.7	4.0		
0 ~ 20	3.0	3.3	3.4	3.5	3.6	3.9	4.2		
20 ~ 40	3.2	3.5	3.5	3.6	3.7	4.0	4.3		
40 ~ 60	3.2	3.6	3.6	3.7	3.9	4.2	4.5		
60 ~ 80	3.2	3.7	3.7	3.8	4.0	4.4	4.7		

Refractive Index	$n_d$	<b>1.49700</b> 1.496999	Abbe Number	$V_d$	<b>81.54</b> 81.14	Dispersion	$n_F - n_C$	<b>0.00609</b> 0.006095
		$n_e$		1.498455			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.47952
$n_{1970}$	1.97009	1.48269
$n_{1530}$	1.52958	1.48610
$n_{1129}$	1.12864	1.48911
$n_t$	1.01398	1.49010
$n_s$	0.85211	1.49183
$n_{A'}$	0.76819	1.49300
$n_r$	0.70652	1.49407
$n_c$	0.65627	<b>1.49514</b>
$n_{c'}$	0.64385	1.49543
$n_{\text{He-Ne}}$	0.6328	1.49571
$n_D$	0.58929	1.49694
$n_d$	0.58756	<b>1.49700</b>
$n_e$	0.54607	1.49845
$n_F$	0.48613	<b>1.50123</b>
$n_{F'}$	0.47999	1.50158
$n_{\text{He-Cd}}$	0.44157	1.50407
$n_g$	0.435835	<b>1.50451</b>
$n_h$	0.404656	1.50720
$n_i$	0.365015	1.51176
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.005033
$n_C - n_{A'}$	0.002134
$n_d - n_C$	0.001863
$n_e - n_C$	0.003319
$n_g - n_d$	0.007508
$n_g - n_F$	0.003276
$n_h - n_g$	0.002698
$n_i - n_g$	0.007253
$n_{C'} - n_t$	0.005330
$n_e - n_{C'}$	0.003022
$n_{F'} - n_e$	0.003121
$n_i - n_{F'}$	0.010184

Relative Partial Dispersions	
$\theta_{C,t}$	0.8258
$\theta_{C,A'}$	0.3501
$\theta_{d,C}$	0.3057
$\theta_{e,C}$	0.5445
$\theta_{g,d}$	1.2318
$\theta_{g,F}$	0.5375
$\theta_{h,g}$	0.4427
$\theta_{i,g}$	1.1900
$\theta'_{C,t}$	0.8677
$\theta'_{e,C'}$	0.4919
$\theta'_{F',e}$	0.5081
$\theta'_{i,F'}$	1.6578

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.1035
$\Delta\theta_{C,A'}$	-0.0246
$\Delta\theta_{g,d}$	0.0364
$\Delta\theta_{g,F}$	0.0280
$\Delta\theta_{i,g}$	0.1478

Internal Transmittance			
$\lambda_{80}$	333	$\lambda_5$	290

CCI		
B	G	R
0.00	0.16	0.13

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.17010505	
A 2	4.75710783	E-2
A 3	7.63832445	E-1
B 1	6.16203924	E-3
B 2	2.63372876	E-2
B 3	1.41882642	E2
1129 ~ 2325 nm		
A 1	1.17010505	
A 2	4.75710783	E-2
A 3	7.63832445	E-1
B 1	6.16203924	E-3
B 2	2.63372876	E-2
B 3	1.41882642	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280	0.010	
290	0.050	
300	0.170	
310	0.370	
320	0.600	
330	0.770	
340	0.880	
350	0.947	
360	0.975	
365		
370	0.988	
380	0.994	
390	0.996	
400	0.995	
420	0.994	
440	0.994	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.999	
1800	0.999	
2000	0.999	
2200	0.997	
2400	0.996	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	458
Yield Point (°C)	<b>At</b>	489
Softening Point (°C)	<b>SP</b>	
Expansion Coefficient $\alpha$ (-30~+70°C)		131
(10-7 / °C) (+100~+300°C)		155
Thermal Conductivity (W/m·K)	<b>k</b>	0.780

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	52.1
Phosphate Resistance	<b>PR</b>	4.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	727
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	280
Poisson's Ratio	$\sigma$	0.299
Knoop Hardness	<b>Hk</b>	350 [4]
Abrasion	<b>Aa</b>	449
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	0.74

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	340				
Specific Gravity	<b>d</b>	3.62		$\lambda_5$	290				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-5.7	-5.5	-5.5	-5.4	-5.4	-5.3	-5.1		
-20 ~ 0	-5.9	-5.8	-5.7	-5.7	-5.6	-5.5	-5.3		
0 ~ 20	-6.2	-6.0	-6.0	-5.9	-5.8	-5.7	-5.5		
20 ~ 40	-6.4	-6.2	-6.2	-6.2	-6.1	-5.9	-5.8		
40 ~ 60	-6.7	-6.5	-6.5	-6.4	-6.3	-6.1	-6.0		
60 ~ 80	-6.9	-6.7	-6.7	-6.7	-6.6	-6.4	-6.2		

Refractive Index	$n_d$	<b>1.43875</b> 1.438750	Abbe Number	$V_d$	<b>94.93</b> 94.49	Dispersion	$n_F - n_C$	<b>0.00462</b> 0.004622
		$n_e$		1.439854			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.42512
$n_{1970}$	1.97009	1.42762
$n_{1530}$	1.52958	1.43032
$n_{1129}$	1.12864	1.43269
$n_t$	1.01398	1.43346
$n_s$	0.85211	1.43480
$n_{A'}$	0.76819	1.43570
$n_r$	0.70652	1.43652
$n_c$	0.65627	<b>1.43733</b>
$n_{c'}$	0.64385	1.43756
$n_{\text{He-Ne}}$	0.6328	1.43777
$n_D$	0.58929	1.43871
$n_d$	0.58756	<b>1.43875</b>
$n_e$	0.54607	1.43985
$n_F$	0.48613	<b>1.44195</b>
$n_{F'}$	0.47999	1.44221
$n_{\text{He-Cd}}$	0.44157	1.44410
$n_g$	0.435835	<b>1.44442</b>
$n_h$	0.404656	1.44645
$n_i$	0.365015	1.44986
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.003870
$n_c - n_{A'}$	0.001631
$n_d - n_c$	0.001417
$n_e - n_c$	0.002521
$n_g - n_d$	0.005673
$n_g - n_F$	0.002468
$n_h - n_g$	0.002028
$n_i - n_g$	0.005437
$n_{c'} - n_t$	0.004097
$n_e - n_{c'}$	0.002294
$n_{F'} - n_e$	0.002361
$n_i - n_{F'}$	0.007645

Relative Partial Dispersions	
$\theta_{c,t}$	0.8373
$\theta_{c,A'}$	0.3529
$\theta_{d,c}$	0.3066
$\theta_{e,c}$	0.5454
$\theta_{g,d}$	1.2274
$\theta_{g,F}$	0.5340
$\theta_{h,g}$	0.4388
$\theta_{i,g}$	1.1763
$\theta'_{c,t}$	0.8801
$\theta'_{e,c'}$	0.4928
$\theta'_{F',e}$	0.5072
$\theta'_{i,F'}$	1.6423

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.1548
$\Delta\theta_{c,A'}$	-0.0381
$\Delta\theta_{g,d}$	0.0598
$\Delta\theta_{g,F}$	0.0461
$\Delta\theta_{i,g}$	0.2462

Internal Transmittance			
$\lambda_{80}$	326	$\lambda_5$	283

CCI		
B	G	R
0.00	0.13	0.08

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.83532327	E-1
A 2	6.95688140	E-2
A 3	1.11409238	
B 1	4.92234955	E-3
B 2	1.93581091	E-2
B 3	2.64275294	E2
1129 ~ 2325 nm		
A 1	9.83532327	E-1
A 2	6.95688140	E-2
A 3	1.11409238	
B 1	4.92234955	E-3
B 2	1.93581091	E-2
B 3	2.64275294	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280	0.040	
290	0.120	
300	0.280	
310	0.510	
320	0.710	
330	0.850	
340	0.928	
350	0.967	
360	0.985	
365		
370	0.992	
380	0.996	
390	0.997	
400	0.996	
420	0.995	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.997	
700	0.998	
800	0.998	
900	0.997	
1000	0.997	
1200	0.998	
1400	0.998	
1600	0.998	
1800	0.998	
2000	0.998	
2200	0.997	
2400	0.998	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	426
Yield Point (°C)	<b>At</b>	456
Softening Point (°C)	<b>SP</b>	
Expansion Coefficient $\alpha$ (-30~+70°C)		145
(10 <sup>-7</sup> /°C)	(+100~+300°C)	169
Thermal Conductivity (W/m·K)	<b>k</b>	0.857

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	691
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	265
Poisson's Ratio	$\sigma$	0.303
Knoop Hardness	<b>Hk</b>	320 [3]
Abrasion	<b>Aa</b>	451
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	0.57

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.3
Phosphate Resistance	<b>PR</b>	4.3

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	330				
Specific Gravity	<b>d</b>	3.62		$\lambda_5$	280				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-5.9	-5.8	-5.8	-5.7	-5.7	-5.6	-5.5		
-20 ~ 0	-6.2	-6.1	-6.1	-6.1	-6.0	-5.9	-5.8		
0 ~ 20	-6.5	-6.4	-6.4	-6.4	-6.3	-6.2	-6.1		
20 ~ 40	-6.9	-6.8	-6.7	-6.7	-6.6	-6.5	-6.4		
40 ~ 60	-7.2	-7.1	-7.1	-7.0	-7.0	-6.8	-6.7		
60 ~ 80	-7.5	-7.4	-7.4	-7.3	-7.3	-7.2	-7.0		

Refractive Index	$n_d$	<b>1.43875</b>	Abbe Number	$V_d$	<b>94.66</b>	Dispersion	$n_F - n_C$	<b>0.00463</b>
		1.438750			$V_e$		94.23	
	$n_e$	1.439857					$n_{F'} - n_{C'}$	0.004668

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.42492
$n_{1970}$	1.97009	1.42747
$n_{1530}$	1.52958	1.43023
$n_{1129}$	1.12864	1.43264
$n_t$	1.01398	1.43343
$n_s$	0.85211	1.43478
$n_{A'}$	0.76819	1.43569
$n_r$	0.70652	1.43651
$n_c$	0.65627	<b>1.43733</b>
$n_{c'}$	0.64385	1.43755
$n_{\text{He-Ne}}$	0.6328	1.43777
$n_D$	0.58929	1.43871
$n_d$	0.58756	<b>1.43875</b>
$n_e$	0.54607	1.43986
$n_F$	0.48613	<b>1.44196</b>
$n_{F'}$	0.47999	1.44222
$n_{\text{He-Cd}}$	0.44157	1.44411
$n_g$	0.435835	<b>1.44444</b>
$n_h$	0.404656	1.44647
$n_i$	0.365015	1.44988
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.003898
$n_c - n_{A'}$	0.001639
$n_d - n_c$	0.001422
$n_e - n_c$	0.002529
$n_g - n_d$	0.005688
$n_g - n_F$	0.002475
$n_h - n_g$	0.002031
$n_i - n_g$	0.005445
$n_{c'} - n_t$	0.004125
$n_e - n_{c'}$	0.002302
$n_{F'} - n_e$	0.002366
$n_i - n_{F'}$	0.007660

Relative Partial Dispersions	
$\theta_{c,t}$	0.8410
$\theta_{c,A'}$	0.3536
$\theta_{d,c}$	0.3068
$\theta_{e,c}$	0.5456
$\theta_{g,d}$	1.2272
$\theta_{g,F}$	0.5340
$\theta_{h,g}$	0.4382
$\theta_{i,g}$	1.1748
$\theta'_{c,t}$	0.8837
$\theta'_{e,c'}$	0.4931
$\theta'_{F',e}$	0.5069
$\theta'_{i,F'}$	1.6410

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.1498
$\Delta\theta_{c,A'}$	-0.0371
$\Delta\theta_{g,d}$	0.0590
$\Delta\theta_{g,F}$	0.0457
$\Delta\theta_{i,g}$	0.2424

Internal Transmittance			
$\lambda_{80}$	329	$\lambda_5$	285

CCI		
B	G	R
0.00	0.13	0.08

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	8.39067682	E-1
A 2	2.14083503	E-1
A 3	1.47914677	
B 1	7.95286639	E-3
B 2	-2.32581717	E-3
B 3	3.40043700	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.020	
290	0.080	
300	0.220	
310	0.430	
320	0.650	
330	0.810	
340	0.910	
350	0.960	
360	0.979	
365		
370	0.989	
380	0.995	
390	0.996	
400	0.996	
420	0.995	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.997	
700	0.997	
800	0.997	
900	0.996	
1000	0.995	
1200	0.996	
1400	0.997	
1600	0.997	
1800	0.997	
2000	0.997	
2200	0.996	
2400	0.997	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	435
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	460
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		136
(+100~+300 $^{\circ}\text{C}$ )		166
Thermal Conductivity (W/m·K)	<b>k</b>	0.876

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.1
Phosphate Resistance	<b>PR</b>	4.1

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	698
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	268
Poisson's Ratio	$\sigma$	0.302
Knoop Hardness	<b>Hk</b>	340 [3]
Abrasion	<b>Aa</b>	387
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	0.59

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	335				
Specific Gravity	<b>d</b>	3.59		$\lambda_5$	290				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-5.4	-5.2	-5.2	-5.2	-5.1	-5.0	-4.9		
-20 ~ 0	-5.8	-5.7	-5.7	-5.6	-5.6	-5.4	-5.3		
0 ~ 20	-6.1	-6.0	-6.0	-6.0	-5.9	-5.8	-5.6		
20 ~ 40	-6.4	-6.3	-6.3	-6.3	-6.2	-6.0	-5.9		
40 ~ 60	-6.7	-6.5	-6.5	-6.5	-6.4	-6.3	-6.1		
60 ~ 80	-6.9	-6.8	-6.8	-6.7	-6.6	-6.5	-6.4		

Refractive Index	$n_d$	<b>1.59522</b> 1.595220	Abbe Number	$V_d$	<b>67.74</b> 67.37	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	<b>0.00879</b> 0.008787 0.008866
		$n_e$		1.597316			$V_e$	

Refractive Indices		
	$\lambda$ (μm)	
$n_{2325}$	2.32542	1.57252
$n_{1970}$	1.97009	1.57631
$n_{1530}$	1.52958	1.58045
$n_{1129}$	1.12864	1.58426
$n_t$	1.01398	1.58557
$n_s$	0.85211	1.58791
$n_{A'}$	0.76819	1.58954
$n_r$	0.70652	1.59105
$n_c$	0.65627	<b>1.59256</b>
$n_{c'}$	0.64385	1.59298
$n_{He-Ne}$	0.6328	1.59337
$n_D$	0.58929	1.59514
$n_d$	0.58756	<b>1.59522</b>
$n_e$	0.54607	1.59732
$n_F$	0.48613	<b>1.60134</b>
$n_{F'}$	0.47999	1.60184
$n_{He-Cd}$	0.44157	1.60549
$n_g$	0.435835	<b>1.60612</b>
$n_h$	0.404656	1.61008
$n_i$	0.365015	1.61681
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.006988
$n_C - n_{A'}$	0.003015
$n_d - n_C$	0.002665
$n_e - n_C$	0.004761
$n_g - n_d$	0.010904
$n_g - n_F$	0.004782
$n_h - n_g$	0.003960
$n_i - n_g$	0.010681
$n_{C'} - n_t$	0.007411
$n_e - n_{C'}$	0.004338
$n_{F'} - n_e$	0.004528
$n_i - n_{F'}$	0.014961

Relative Partial Dispersions	
$\theta_{C,t}$	0.7953
$\theta_{C,A'}$	0.3431
$\theta_{d,C}$	0.3033
$\theta_{e,C}$	0.5418
$\theta_{g,d}$	1.2409
$\theta_{g,F}$	0.5442
$\theta_{h,g}$	0.4507
$\theta_{i,g}$	1.2155
$\theta'_{C,t}$	0.8359
$\theta'_{e,C'}$	0.4893
$\theta'_{F',e}$	0.5107
$\theta'_{i,F'}$	1.6875

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.0692
$\Delta\theta_{C,A'}$	-0.0149
$\Delta\theta_{g,d}$	0.0169
$\Delta\theta_{g,F}$	0.0123
$\Delta\theta_{i,g}$	0.0577

Internal Transmittance			
$\lambda_{80}$	347	$\lambda_5$	302

CCI		
B	G	R
0.00	0.32	0.27

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	7.61242785	E-1
A 2	7.47033375	E-1
A 3	9.38928947	E-1
B 1	3.21174095	E-3
B 2	1.40234423	E-2
B 3	1.39523530	E2
1129 ~ 2325 nm		
A 1	7.61242785	E-1
A 2	7.47033375	E-1
A 3	9.38928947	E-1
B 1	3.21174095	E-3
B 2	1.40234423	E-2
B 3	1.39523530	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 mm}$	$\tau_{i 25 mm}$
280		
290		
300		
310	0.180	
320	0.350	
330	0.540	
340	0.720	
350	0.840	
360	0.917	
365		
370	0.958	
380	0.980	
390	0.988	
400	0.991	
420	0.989	
440	0.989	
460	0.992	
480	0.994	
500	0.996	
550	0.998	
600	0.997	
650	0.996	
700	0.996	
800	0.995	
900	0.995	
1000	0.996	
1200	0.997	
1400	0.997	
1600	0.997	
1800	0.995	
2000	0.992	
2200	0.989	
2400	0.983	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	571
Yield Point (°C)	<b>At</b>	596
Softening Point (°C)	<b>SP</b>	
Expansion Coefficient $\alpha$ (-30~+70°C)		117
(10-7 /°C)	(+100~+300°C)	135
Thermal Conductivity (W/m·K)	<b>k</b>	0.624

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	757
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	294
Poisson's Ratio	$\sigma$	0.287
Knoop Hardness	<b>Hk</b>	390 [4]
Abrasion	<b>Aa</b>	488
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	0.51

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	2
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.3
Phosphate Resistance	<b>PR</b>	4.1

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	355				
Specific Gravity	<b>d</b>	4.17		$\lambda_5$	295				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-5.8	-5.5	-5.5	-5.4	-5.3	-5.1	-4.9		
-20 ~ 0	-6.0	-5.7	-5.7	-5.6	-5.5	-5.3	-5.1		
0 ~ 20	-6.1	-5.9	-5.9	-5.8	-5.7	-5.5	-5.2		
20 ~ 40	-6.3	-6.1	-6.1	-6.0	-5.9	-5.6	-5.4		
40 ~ 60	-6.4	-6.2	-6.1	-6.1	-5.9	-5.7	-5.4		
60 ~ 80	-6.5	-6.2	-6.2	-6.1	-6.0	-5.7	-5.5		

Refractive Index	$n_d$	<b>1.53775</b>	Abbe Number	$V_d$	<b>74.70</b>	Dispersion	$n_F - n_C$	<b>0.00720</b>
	$n_e$	1.537750		$V_e$	74.34		$n_{F'} - n_{C'}$	0.007199
		1.539469						0.007257

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.51738
$n_{1970}$	1.97009	1.52105
$n_{1530}$	1.52958	1.52500
$n_{1129}$	1.12864	1.52849
$n_t$	1.01398	1.52965
$n_s$	0.85211	1.53167
$n_{A'}$	0.76819	1.53304
$n_r$	0.70652	1.53430
$n_c$	0.65627	<b>1.53555</b>
$n_{c'}$	0.64385	1.53590
$n_{\text{He-Ne}}$	0.6328	1.53623
$n_D$	0.58929	1.53769
$n_d$	0.58756	<b>1.53775</b>
$n_e$	0.54607	1.53947
$n_F$	0.48613	<b>1.54275</b>
$n_{F'}$	0.47999	1.54316
$n_{\text{He-Cd}}$	0.44157	1.54612
$n_g$	0.435835	<b>1.54664</b>
$n_h$	0.404656	1.54984
$n_i$	0.365015	1.55525
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.005905
$n_C - n_{A'}$	0.002510
$n_d - n_C$	0.002196
$n_e - n_C$	0.003915
$n_g - n_d$	0.008885
$n_g - n_F$	0.003882
$n_h - n_g$	0.003203
$n_i - n_g$	0.008618
$n_{C'} - n_t$	0.006255
$n_{e'} - n_{C'}$	0.003565
$n_{F'} - n_e$	0.003692
$n_i - n_{F'}$	0.012092

Relative Partial Dispersions	
$\theta_{C,t}$	0.8203
$\theta_{C,A'}$	0.3487
$\theta_{d,C}$	0.3050
$\theta_{e,C}$	0.5438
$\theta_{g,d}$	1.2342
$\theta_{g,F}$	0.5392
$\theta_{h,g}$	0.4449
$\theta_{i,g}$	1.1971
$\theta'_{C',t}$	0.8619
$\theta'_{e,C'}$	0.4912
$\theta'_{F',e}$	0.5088
$\theta'_{i,F'}$	1.6663

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.0769
$\Delta\theta_{C,A'}$	-0.0177
$\Delta\theta_{g,d}$	0.0246
$\Delta\theta_{g,F}$	0.0186
$\Delta\theta_{i,g}$	0.0976

Internal Transmittance			
$\lambda_{80}$	336	$\lambda_5$	284

CCI		
B	G	R
0.00	0.28	0.23

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	8.09407286	E-1
A 2	5.27007033	E-1
A 3	9.09127704	E-1
B 1	3.76072389	E-3
B 2	1.35654895	E-2
B 3	1.42503612	E2
1129 ~ 2325 nm		
A 1	8.09407286	E-1
A 2	5.27007033	E-1
A 3	9.09127704	E-1
B 1	3.76072389	E-3
B 2	1.35654895	E-2
B 3	1.42503612	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.030	
290	0.080	
300	0.190	
310	0.360	
320	0.550	
330	0.720	
340	0.850	
350	0.924	
360	0.962	
365		
370	0.981	
380	0.990	
390	0.992	
400	0.992	
420	0.989	
440	0.990	
460	0.992	
480	0.995	
500	0.996	
550	0.998	
600	0.997	
650	0.996	
700	0.996	
800	0.994	
900	0.995	
1000	0.996	
1200	0.997	
1400	0.997	
1600	0.996	
1800	0.995	
2000	0.993	
2200	0.987	
2400	0.984	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	496
Yield Point (°C)	<b>At</b>	524
Softening Point (°C)	<b>SP</b>	
Expansion Coefficient $\alpha$ (-30~+70°C)		115
(10-7 /°C)	(+100~+300°C)	138
Thermal Conductivity (W/m·K)	<b>k</b>	0.805

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	4
Acid Resistance (Surface Group)	<b>SR</b>	5.1
Phosphate Resistance	<b>PR</b>	4.1

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	806
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	312
Poisson's Ratio	$\sigma$	0.291
Knoop Hardness	<b>Hk</b>	390 [4]
Abrasion	<b>Aa</b>	373
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	0.85

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	3.64		$\lambda_5$					
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-3.9	-3.7	-3.7	-3.6	-3.5	-3.3	-3.2		
-20 ~ 0	-4.2	-4.0	-4.0	-3.9	-3.8	-3.6	-3.4		
0 ~ 20	-4.4	-4.2	-4.2	-4.2	-4.1	-3.8	-3.6		
20 ~ 40	-4.6	-4.4	-4.4	-4.3	-4.2	-4.0	-3.8		
40 ~ 60	-4.7	-4.5	-4.5	-4.4	-4.3	-4.1	-3.9		
60 ~ 80	-4.8	-4.6	-4.6	-4.5	-4.4	-4.2	-4.0		



Refractive Index	$n_d$	<b>1.48749</b>	Abbe Number	$V_d$	<b>70.23</b>	Dispersion	$n_F - n_C$	<b>0.00694</b>
	$n_e$	1.487490		$V_e$	70.04		$n_{F'} - n_{C'}$	0.006941
		1.489147						0.006984

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.46227
$n_{1970}$	1.97009	1.46765
$n_{1530}$	1.52958	1.47324
$n_{1129}$	1.12864	1.47778
$n_t$	1.01398	1.47915
$n_s$	0.85211	1.48138
$n_{A'}$	0.76819	1.48282
$n_r$	0.70652	1.48410
$n_C$	0.65627	<b>1.48534</b>
$n_{C'}$	0.64385	1.48569
$n_{\text{He-Ne}}$	0.6328	1.48601
$n_D$	0.58929	1.48743
$n_d$	0.58756	<b>1.48749</b>
$n_e$	0.54607	1.48915
$n_F$	0.48613	<b>1.49228</b>
$n_{F'}$	0.47999	1.49267
$n_{\text{He-Cd}}$	0.44157	1.49548
$n_g$	0.435835	<b>1.49596</b>
$n_h$	0.404656	1.49898
$n_i$	0.365015	1.50406
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	457
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	491
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	500
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	568
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	679
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	90
	(+100~+300 $^{\circ}\text{C}$ )	95
Thermal Conductivity (W/m·K)	<b>k</b>	1.007

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	623
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	254
Poisson's Ratio	$\sigma$	0.227
Knoop Hardness	<b>Hk</b>	520 [5]
Abrasion	<b>Aa</b>	111
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.87

Partial Dispersions	
$n_C - n_t$	0.006194
$n_C - n_{A'}$	0.002522
$n_d - n_C$	0.002146
$n_e - n_C$	0.003803
$n_g - n_d$	0.008474
$n_g - n_F$	0.003679
$n_h - n_g$	0.003019
$n_i - n_g$	0.008099
$n_{C'} - n_t$	0.006539
$n_{F'} - n_e$	0.003458
$n_i - n_{F'}$	0.011390

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0162
$\Delta\theta_{C,A'}$	0.0023
$\Delta\theta_{g,d}$	0.0020
$\Delta\theta_{g,F}$	0.0022
$\Delta\theta_{i,g}$	0.0299

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.17447043	
A 2	1.40056154	E-2
A 3	1.19272435	
B 1	8.41855181	E-3
B 2	-5.81790767	E-2
B 3	1.29599726	E2
1129 ~ 2325 nm		
A 1	1.17447043	
A 2	1.40056154	E-2
A 3	1.19272435	
B 1	8.41855181	E-3
B 2	-5.81790767	E-2
B 3	1.29599726	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	3.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.8924
$\theta_{C,A'}$	0.3633
$\theta_{d,C}$	0.3092
$\theta_{e,C}$	0.5479
$\theta_{g,d}$	1.2209
$\theta_{g,F}$	0.5300
$\theta_{h,g}$	0.4350
$\theta_{i,g}$	1.1668
$\theta'_{C,t}$	0.9363
$\theta'_{e,C'}$	0.4951
$\theta'_{F',e}$	0.5049
$\theta'_{i,F'}$	1.6309

Internal Transmittance			
$\lambda_{80}$	304	$\lambda_5$	277

CCI		
B	G	R
0.00	0.00	0.00

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.130	
290	0.430	
300	0.730	
310	0.890	
320	0.961	
330	0.984	
340	0.992	
350	0.995	
360	0.995	
365		
370	0.998	
380	0.998	
390	0.999	
400	0.999	
420	0.999	
440	0.999	
460	0.999	
480	0.999	
500	0.999	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.998	
1200	0.998	
1400	0.982	
1600	0.992	
1800	0.985	
2000	0.971	
2200	0.880	
2400	0.870	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	300				
Specific Gravity	<b>d</b>	2.46		$\lambda_5$	265				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.3	-1.2	-1.2	-1.1	-1.1	-0.9	-0.7		
-20 ~ 0	-1.3	-1.1	-1.1	-1.0	-1.0	-0.8	-0.6		
0 ~ 20	-1.3	-1.1	-1.0	-0.9	-0.8	-0.6	-0.4		
20 ~ 40	-1.1	-0.8	-0.8	-0.7	-0.6	-0.4	-0.3		
40 ~ 60	-1.0	-0.6	-0.6	-0.5	-0.4	-0.2			
60 ~ 80	-0.9	-0.4	-0.4	-0.3	-0.2	-0.1	0.2		

Refractive Index	$n_d$	<b>1.59270</b>	Abbe Number	$V_d$	<b>35.31</b>	Dispersion	$n_F - n_C$	<b>0.01679</b>
		1.592701			$V_e$		35.03	
	$n_e$	1.596670					$n_{F'} - n_{C'}$	0.017031

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55603
$n_{1970}$	1.97009	1.56154
$n_{1530}$	1.52958	1.56767
$n_{1129}$	1.12864	1.57357
$n_t$	1.01398	1.57569
$n_s$	0.85211	1.57962
$n_{A'}$	0.76819	1.58243
$n_r$	0.70652	1.58508
$n_c$	0.65627	<b>1.58779</b>
$n_{c'}$	0.64385	1.58856
$n_{\text{He-Ne}}$	0.6328	1.58929
$n_D$	0.58929	1.59255
$n_d$	0.58756	<b>1.59270</b>
$n_e$	0.54607	1.59667
$n_F$	0.48613	<b>1.60458</b>
$n_{F'}$	0.47999	1.60559
$n_{\text{He-Cd}}$	0.44157	1.61318
$n_g$	0.435835	<b>1.61454</b>
$n_h$	0.404656	1.62334
$n_i$	0.365015	1.63974
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	501
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	542
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient $\alpha$ ( $-30 \sim +70^{\circ}\text{C}$ )		90
		( $+100 \sim +300^{\circ}\text{C}$ )
Thermal Conductivity (W/m·K)	<b>k</b>	0.947

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	653
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	264
Poisson's Ratio	$\sigma$	0.238
Knoop Hardness	<b>Hk</b>	490 [5]
Abrasion	<b>Aa</b>	172
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.33

Partial Dispersions	
$n_c - n_t$	0.012104
$n_c - n_{A'}$	0.005365
$n_d - n_c$	0.004906
$n_e - n_c$	0.008875
$n_g - n_d$	0.021838
$n_g - n_F$	0.009959
$n_h - n_g$	0.008800
$n_i - n_g$	0.025202
$n_{c'} - n_t$	0.012872
$n_e - n_{c'}$	0.008107
$n_{F'} - n_e$	0.008924
$n_i - n_{F'}$	0.034147

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0088
$\Delta\theta_{c,A'}$	0.0010
$\Delta\theta_{g,d}$	0.0096
$\Delta\theta_{g,F}$	0.0090
$\Delta\theta_{i,g}$	0.0721

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.32940907	
A 2	1.41512125	E-1
A 3	1.44299068	
B 1	1.02377287	E-2
B 2	5.78081956	E-2
B 3	1.50597139	E2
1129 ~ 2325 nm		
A 1	1.32940907	
A 2	1.41512125	E-1
A 3	1.44299068	
B 1	1.02377287	E-2
B 2	5.78081956	E-2
B 3	1.50597139	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7211
$\theta_{c,A'}$	0.3196
$\theta_{d,c}$	0.2923
$\theta_{e,c}$	0.5287
$\theta_{g,d}$	1.3010
$\theta_{g,F}$	0.5933
$\theta_{h,g}$	0.5243
$\theta_{i,g}$	1.5015
$\theta'_{c,t}$	0.7558
$\theta'_{e,c'}$	0.4760
$\theta'_{F',e}$	0.5240
$\theta'_{i,F'}$	2.0050

Internal Transmittance			
$\lambda_{80}$	370	$\lambda_5$	350

CCI		
B	G	R
0.00	0.43	0.42

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.040	
360	0.430	
365		
370	0.810	
380	0.934	
390	0.973	
400	0.984	
420	0.989	
440	0.990	
460	0.991	
480	0.992	
500	0.994	
550	0.997	
600	0.997	
650	0.996	
700	0.996	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.994	
1800	0.989	
2000	0.987	
2200	0.959	
2400	0.953	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	2.64		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.0	-0.5	-0.4	-0.2		0.7	1.4		
-20 ~ 0	-0.9	-0.4	-0.3		0.2	0.8	1.6		
0 ~ 20	-0.8	-0.2	-0.2	0.1	0.3	1.0	1.8		
20 ~ 40	-0.7	-0.1	-0.1	0.2	0.5	1.2	2.1		
40 ~ 60	-0.6			0.3	0.6	1.4	2.3		
60 ~ 80	-0.5	0.1	0.1	0.4	0.7	1.6	2.5		

Refractive Index	$n_d$	<b>1.78590</b>	Abbe Number	$V_d$	<b>44.20</b>	Dispersion	$n_F - n_C$	<b>0.01778</b>
	$n_e$	1.785896		$V_e$	43.95		$n_{F'} - n_{C'}$	0.017780
		1.790123						0.017979

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.74265
$n_{1970}$	1.97009	1.74972
$n_{1530}$	1.52958	1.75740
$n_{1129}$	1.12864	1.76452
$n_t$	1.01398	1.76700
$n_s$	0.85211	1.77150
$n_{A'}$	0.76819	1.77466
$n_r$	0.70652	1.77761
$n_c$	0.65627	<b>1.78058</b>
$n_{c'}$	0.64385	1.78142
$n_{\text{He-Ne}}$	0.6328	1.78221
$n_D$	0.58929	1.78574
$n_d$	0.58756	<b>1.78590</b>
$n_e$	0.54607	1.79012
$n_F$	0.48613	<b>1.79836</b>
$n_{F'}$	0.47999	1.79940
$n_{\text{He-Cd}}$	0.44157	1.80704
$n_g$	0.435835	<b>1.80838</b>
$n_h$	0.404656	1.81687
$n_i$	0.365015	1.83175
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	568
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	598
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	617
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	641
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	677
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	59
	(+10~+300 $^{\circ}\text{C}$ )	72
Thermal Conductivity (W/m·K)	<b>k</b>	0.826

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1129
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	435
Poisson's Ratio	$\sigma$	0.297
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	79
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.88

Partial Dispersions	
$n_c - n_t$	0.013580
$n_c - n_{A'}$	0.005923
$n_d - n_c$	0.005312
$n_e - n_c$	0.009539
$n_g - n_d$	0.022480
$n_g - n_F$	0.010012
$n_h - n_g$	0.008492
$n_i - n_g$	0.023375
$n_{c'} - n_t$	0.014419
$n_e - n_{c'}$	0.008700
$n_{F'} - n_e$	0.009279
$n_i - n_{F'}$	0.032349

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0097
$\Delta\theta_{c,A'}$	0.0037
$\Delta\theta_{g,d}$	-0.0086
$\Delta\theta_{g,F}$	-0.0069
$\Delta\theta_{i,g}$	-0.0402

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.82586991	
A 2	2.83023349	E-1
A 3	1.35964319	
B 1	9.35297152	E-3
B 2	3.73803057	E-2
B 3	1.00655798	E2
1129 ~ 2325 nm		
A 1	1.82586991	
A 2	2.83023349	E-1
A 3	1.35964319	
B 1	9.35297152	E-3
B 2	3.73803057	E-2
B 3	1.00655798	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7638
$\theta_{c,A'}$	0.3331
$\theta_{d,c}$	0.2988
$\theta_{e,c}$	0.5365
$\theta_{g,d}$	1.2643
$\theta_{g,F}$	0.5631
$\theta_{h,g}$	0.4776
$\theta_{i,g}$	1.3147
$\theta'_{c,t}$	0.8020
$\theta'_{e,c'}$	0.4839
$\theta'_{F',e}$	0.5161
$\theta'_{i,F'}$	1.7993

Internal Transmittance			
$\lambda_{80}$	366	$\lambda_5$	333

CCI		
B	G	R
0.00	0.83	0.82

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.010	
340	0.170	
350	0.510	
360	0.730	
365		
370	0.840	
380	0.910	
390	0.942	
400	0.961	
420	0.977	
440	0.984	
460	0.989	
480	0.993	
500	0.995	
550	0.998	
600	0.997	
650	0.997	
700	0.998	
800	0.998	
900	0.997	
1000	0.996	
1200	0.996	
1400	0.991	
1600	0.989	
1800	0.981	
2000	0.957	
2200	0.890	
2400	0.680	

Other Properties								
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390			
Specific Gravity	<b>d</b>	4.40		$\lambda_5$	335			
Temperature Coefficients of Refractive Index								
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20		6.0		6.3	6.6	7.3	7.8	
-20 ~ 0		6.0		6.3	6.6	7.3	7.9	
0 ~ 20		6.1		6.4	6.7	7.4	8.1	
20 ~ 40		6.2		6.5	6.8	7.6	8.3	
40 ~ 60		6.4		6.7	7.0	7.8	8.6	
60 ~ 80		6.6		6.9	7.2	8.1	8.9	

Refractive Index	$n_d$	<b>1.79952</b> 1.799516	Abbe Number	$V_d$	<b>42.22</b> 41.97	Dispersion	$n_F - n_C$	<b>0.01893</b> 0.018935
		$n_e$		1.804015			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.75495
$n_{1970}$	1.97009	1.76202
$n_{1530}$	1.52958	1.76976
$n_{1129}$	1.12864	1.77703
$n_t$	1.01398	1.77961
$n_s$	0.85211	1.78430
$n_{A'}$	0.76819	1.78762
$n_r$	0.70652	1.79073
$n_c$	0.65627	<b>1.79388</b>
$n_{c'}$	0.64385	1.79477
$n_{\text{He-Ne}}$	0.6328	1.79560
$n_D$	0.58929	1.79935
$n_d$	0.58756	<b>1.79952</b>
$n_e$	0.54607	1.80401
$n_F$	0.48613	<b>1.81281</b>
$n_{F'}$	0.47999	1.81393
$n_{\text{He-Cd}}$	0.44157	1.82211
$n_g$	0.435835	<b>1.82355</b>
$n_h$	0.404656	1.83271
$n_i$	0.365015	1.84885
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.014274
$n_c - n_{A'}$	0.006258
$n_d - n_c$	0.005637
$n_e - n_c$	0.010136
$n_g - n_d$	0.024038
$n_g - n_F$	0.010740
$n_h - n_g$	0.009152
$n_i - n_g$	0.025292
$n_{c'} - n_t$	0.015163
$n_e - n_{c'}$	0.009247
$n_{F'} - n_e$	0.009910
$n_i - n_{F'}$	0.034921

Relative Partial Dispersions	
$\theta_{c,t}$	0.7538
$\theta_{c,A'}$	0.3305
$\theta_{d,c}$	0.2977
$\theta_{e,c}$	0.5353
$\theta_{g,d}$	1.2695
$\theta_{g,F}$	0.5672
$\theta_{h,g}$	0.4833
$\theta_{i,g}$	1.3357
$\theta'_{c,t}$	0.7915
$\theta'_{e,c'}$	0.4827
$\theta'_{F',e}$	0.5173
$\theta'_{i,F'}$	1.8229

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0090
$\Delta\theta_{c,A'}$	0.0035
$\Delta\theta_{g,d}$	-0.0075
$\Delta\theta_{g,F}$	-0.0060
$\Delta\theta_{i,g}$	-0.0358

Internal Transmittance			
$\lambda_{80}$	367	$\lambda_5$	331

CCI		
B	G	R
0.00	1.03	1.10

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.85390925	
A 2	2.97925555	E-1
A 3	1.39382086	
B 1	9.55320687	E-3
B 2	3.93816850	E-2
B 3	1.02706848	E2
1129 ~ 2325 nm		
A 1	1.85390925	
A 2	2.97925555	E-1
A 3	1.39382086	
B 1	9.55320687	E-3
B 2	3.93816850	E-2
B 3	1.02706848	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.020	
340	0.230	
350	0.520	
360	0.720	
365		
370	0.830	
380	0.890	
390	0.931	
400	0.951	
420	0.971	
440	0.979	
460	0.985	
480	0.990	
500	0.993	
550	0.997	
600	0.997	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.998	
1200	0.997	
1400	0.994	
1600	0.993	
1800	0.986	
2000	0.965	
2200	0.910	
2400	0.710	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	565
Annealing Point (°C)	<b>AP</b>	596
Transformation Temperature (°C)	<b>Tg</b>	618
Yield Point (°C)	<b>At</b>	636
Softening Point (°C)	<b>SP</b>	679
Expansion Coefficient $\alpha$ (-30~+70°C)		60
(10-7 /°C) (+100~+300°C)		73
Thermal Conductivity (W/m·K)	<b>k</b>	0.828

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1119
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	431
Poisson's Ratio	$\sigma$	0.297
Knoop Hardness	<b>Hk</b>	640 [6]
Abrasion	<b>Aa</b>	82
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.92

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	395				
Specific Gravity	<b>d</b>	4.41		$\lambda_5$	330				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.1	6.1	6.2	6.4	6.6	7.3	8.0		
-20 ~ 0	5.2	6.1	6.2	6.4	6.6	7.3	8.1		
0 ~ 20	5.2	6.1	6.1	6.4	6.7	7.5	8.3		
20 ~ 40	5.3	6.2	6.2	6.5	6.9	7.7	8.5		
40 ~ 60	5.5	6.4	6.5	6.7	7.1	7.9	8.8		
60 ~ 80	5.8	6.6	6.6	6.9	7.3	8.2	9.1		

Refractive Index	$n_d$	<b>1.79952</b>	Abbe Number	$V_d$	<b>42.24</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.018928
		1.799520			$V_e$		41.98	
	$n_e$	1.804018						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.75708
$n_{1970}$	1.97009	1.76345
$n_{1530}$	1.52958	1.77050
$n_{1129}$	1.12864	1.77732
$n_t$	1.01398	1.77980
$n_s$	0.85211	1.78438
$n_{A'}$	0.76819	1.78767
$n_r$	0.70652	1.79076
$n_c$	0.65627	<b>1.79389</b>
$n_{c'}$	0.64385	1.79478
$n_{\text{He-Ne}}$	0.6328	1.79561
$n_D$	0.58929	1.79935
$n_d$	0.58756	<b>1.79952</b>
$n_e$	0.54607	1.80402
$n_F$	0.48613	<b>1.81282</b>
$n_{F'}$	0.47999	1.81393
$n_{\text{He-Cd}}$	0.44157	1.82212
$n_g$	0.435835	<b>1.82356</b>
$n_h$	0.404656	1.83271
$n_i$	0.365015	1.84883
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.014094
$n_c - n_{A'}$	0.006224
$n_d - n_c$	0.005627
$n_e - n_c$	0.010125
$n_g - n_d$	0.024043
$n_g - n_F$	0.010742
$n_h - n_g$	0.009149
$n_i - n_g$	0.025268
$n_{c'} - n_t$	0.014980
$n_e - n_{c'}$	0.009239
$n_{F'} - n_e$	0.009915
$n_i - n_{F'}$	0.034898

Relative Partial Dispersions	
$\theta_{c,t}$	0.7446
$\theta_{c,A'}$	0.3288
$\theta_{d,c}$	0.2973
$\theta_{e,c}$	0.5349
$\theta_{g,d}$	1.2702
$\theta_{g,F}$	0.5675
$\theta_{h,g}$	0.4834
$\theta_{i,g}$	1.3350
$\theta'_{c,t}$	0.7821
$\theta'_{e,c'}$	0.4824
$\theta'_{F',e}$	0.5176
$\theta'_{i,F'}$	1.8220

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0003
$\Delta\theta_{c,A'}$	0.0017
$\Delta\theta_{g,d}$	-0.0068
$\Delta\theta_{g,F}$	-0.0056
$\Delta\theta_{i,g}$	-0.0363

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.91082318	
A 2	2.39854589	E-1
A 3	1.16159733	
B 1	1.03565352	E-2
B 2	4.13805081	E-2
B 3	9.66037300	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.130	
350	0.460	
360	0.730	
365		
370	0.860	
380	0.926	
390	0.954	
400	0.969	
420	0.982	
440	0.988	
460	0.992	
480	0.995	
500	0.997	
550	0.999	
600	0.998	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.989	
2000	0.967	
2200	0.924	
2400	0.750	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	553
Annealing Point (°C)	<b>AP</b>	576
Transformation Temperature (°C)	<b>Tg</b>	598
Yield Point (°C)	<b>At</b>	622
Softening Point (°C)	<b>SP</b>	651
Expansion Coefficient $\alpha$ (-30~+70°C)		60
(10 <sup>-7</sup> /°C) (+100~+300°C)		73
Thermal Conductivity (W/m·K)	<b>k</b>	0.852

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1098
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	418
Poisson's Ratio	$\sigma$	0.313
Knoop Hardness	<b>Hk</b>	620 [6]
Abrasion	<b>Aa</b>	54
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.31

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	<b>d</b>	4.47		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	8.5	9.5	9.5	9.8	10.2	11.0	11.9		
-20 ~ 0	8.6	9.6	9.6	9.9	10.3	11.2	12.1		
0 ~ 20	8.7	9.7	9.7	10.1	10.5	11.4	12.3		
20 ~ 40	8.7	9.8	9.8	10.2	10.6	11.5	12.5		
40 ~ 60	8.8	9.9	10.0	10.3	10.7	11.7	12.7		
60 ~ 80	9.0	10.1	10.2	10.5	11.0	12.0	13.1		

Refractive Index	$n_d$	<b>1.80610</b> 1.806098	Abbe Number	$V_d$	<b>40.92</b> 40.67	Dispersion	$n_F - n_C$	<b>0.01969</b> 0.019697
		$n_e$		1.810775			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.76051
$n_{1970}$	1.97009	1.76764
$n_{1530}$	1.52958	1.77546
$n_{1129}$	1.12864	1.78287
$n_t$	1.01398	1.78551
$n_s$	0.85211	1.79034
$n_{A'}$	0.76819	1.79377
$n_r$	0.70652	1.79699
$n_c$	0.65627	<b>1.80025</b>
$n_{c'}$	0.64385	1.80117
$n_{\text{He-Ne}}$	0.6328	1.80203
$n_D$	0.58929	1.80592
$n_d$	0.58756	<b>1.80610</b>
$n_e$	0.54607	1.81078
$n_F$	0.48613	<b>1.81994</b>
$n_{F'}$	0.47999	1.82110
$n_{\text{He-Cd}}$	0.44157	1.82967
$n_g$	0.435835	<b>1.83117</b>
$n_h$	0.404656	1.84078
$n_i$	0.365015	1.85782
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	610
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	637
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	687
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		59
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	70
Thermal Conductivity (W/m·K)	<b>k</b>	0.860

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1127
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	434
Poisson's Ratio	$\sigma$	0.299
Knoop Hardness	<b>Hk</b>	640 [6]
Abrasion	<b>Aa</b>	78
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.96

Partial Dispersions	
$n_c - n_t$	0.014740
$n_c - n_{A'}$	0.006479
$n_d - n_c$	0.005850
$n_e - n_c$	0.010527
$n_g - n_d$	0.025076
$n_g - n_F$	0.011229
$n_h - n_g$	0.009607
$n_i - n_g$	0.026650
$n_{c'} - n_t$	0.015661
$n_e - n_{c'}$	0.009606
$n_{F'} - n_e$	0.010329
$n_i - n_{F'}$	0.036720

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0096
$\Delta\theta_{c,A'}$	0.0034
$\Delta\theta_{g,d}$	-0.0066
$\Delta\theta_{g,F}$	-0.0052
$\Delta\theta_{i,g}$	-0.0294

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.91811619	
A 2	2.53724399	E-1
A 3	1.39473885	
B 1	1.02147684	E-2
B 2	4.33176011	E-2
B 3	1.01938021	E2
1129 ~ 2325 nm		
A 1	1.91811619	
A 2	2.53724399	E-1
A 3	1.39473885	
B 1	1.02147684	E-2
B 2	4.33176011	E-2
B 3	1.01938021	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	4.2
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7483
$\theta_{c,A'}$	0.3289
$\theta_{d,c}$	0.2970
$\theta_{e,c}$	0.5344
$\theta_{g,d}$	1.2731
$\theta_{g,F}$	0.5701
$\theta_{h,g}$	0.4877
$\theta_{i,g}$	1.3530
$\theta'_{c,t}$	0.7856
$\theta'_{e,c'}$	0.4819
$\theta'_{F',e}$	0.5181
$\theta'_{i,F'}$	1.8420

Internal Transmittance			
$\lambda_{80}$	370	$\lambda_5$	340

CCI		
B	G	R
0.00	1.07	1.13

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.060	
350	0.380	
360	0.650	
365		
370	0.800	
380	0.880	
390	0.925	
400	0.947	
420	0.969	
440	0.979	
460	0.985	
480	0.989	
500	0.993	
550	0.996	
600	0.996	
650	0.997	
700	0.998	
800	0.998	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.989	
2000	0.969	
2200	0.915	
2400	0.720	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	405				
Specific Gravity	<b>d</b>	4.43		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.1	6.2	6.2	6.5	6.8	7.6	8.3		
-20 ~ 0	5.2	6.3	6.3	6.6	6.9	7.7	8.5		
0 ~ 20	5.3	6.4	6.4	6.7	7.1	7.9	8.7		
20 ~ 40	5.6	6.6	6.7	6.9	7.3	8.1	9.0		
40 ~ 60	5.8	6.8	6.9	7.2	7.6	8.4	9.4		
60 ~ 80	6.2	7.1	7.2	7.5	7.8	8.7	9.8		



Refractive Index	$n_d$	<b>1.80610</b>	Abbe Number	$V_d$	<b>40.93</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.019695
		1.806100			$V_e$		40.67	
	$n_e$	1.810776						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.76201
$n_{1970}$	1.97009	1.76866
$n_{1530}$	1.52958	1.77600
$n_{1129}$	1.12864	1.78309
$n_t$	1.01398	1.78566
$n_s$	0.85211	1.79041
$n_{A'}$	0.76819	1.79381
$n_r$	0.70652	1.79701
$n_c$	0.65627	<b>1.80026</b>
$n_{c'}$	0.64385	1.80118
$n_{\text{He-Ne}}$	0.6328	1.80204
$n_D$	0.58929	1.80593
$n_d$	0.58756	<b>1.80610</b>
$n_e$	0.54607	1.81078
$n_F$	0.48613	<b>1.81995</b>
$n_{F'}$	0.47999	1.82112
$n_{\text{He-Cd}}$	0.44157	1.82969
$n_g$	0.435835	<b>1.83121</b>
$n_h$	0.404656	1.84085
$n_i$	0.365015	1.85798
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.014601
$n_c - n_{A'}$	0.006450
$n_d - n_c$	0.005841
$n_e - n_c$	0.010517
$n_g - n_d$	0.025106
$n_g - n_F$	0.011252
$n_h - n_g$	0.009639
$n_i - n_g$	0.026774
$n_{c'} - n_t$	0.015520
$n_e - n_{c'}$	0.009598
$n_{F'} - n_e$	0.010339
$n_i - n_{F'}$	0.036865

Relative Partial Dispersions	
$\theta_{c,t}$	0.7414
$\theta_{c,A'}$	0.3275
$\theta_{d,c}$	0.2966
$\theta_{e,c}$	0.5340
$\theta_{g,d}$	1.2747
$\theta_{g,F}$	0.5713
$\theta_{h,g}$	0.4894
$\theta_{i,g}$	1.3594
$\theta'_{c,t}$	0.7785
$\theta'_{e,c'}$	0.4814
$\theta'_{F',e}$	0.5186
$\theta'_{i,F'}$	1.8491

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0027
$\Delta\theta_{c,A'}$	0.0020
$\Delta\theta_{g,d}$	-0.0050
$\Delta\theta_{g,F}$	-0.0039
$\Delta\theta_{i,g}$	-0.0229

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.96600955	
A 2	2.05143305	E-1
A 3	1.23200934	
B 1	1.07817785	E-2
B 2	4.63727869	E-2
B 3	9.76940600	E1
1129 ~ 2325 nm		
A 1	1.96600955	
A 2	2.05143305	E-1
A 3	1.23200934	
B 1	1.07817785	E-2
B 2	4.63727869	E-2
B 3	9.76940600	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.020	
350	0.230	
360	0.560	
365		
370	0.780	
380	0.880	
390	0.931	
400	0.954	
420	0.975	
440	0.984	
460	0.989	
480	0.992	
500	0.995	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.995	
1800	0.987	
2000	0.966	
2200	0.916	
2400	0.730	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	569
Annealing Point (°C)	<b>AP</b>	589
Transformation Temperature (°C)	<b>Tg</b>	603
Yield Point (°C)	<b>At</b>	638
Softening Point (°C)	<b>SP</b>	670
Expansion Coefficient $\alpha$ (-30~+70°C)		58
(10-7 /°C) (+100~+300°C)		71
Thermal Conductivity (W/m·K)	<b>k</b>	0.859

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1135
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	434
Poisson's Ratio	$\sigma$	0.309
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	61
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.13

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	4.41		$\lambda_5$		345			
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	7.7	8.6	8.7	9.0	9.3	10.1	11.0		
-20 ~ 0	7.8	8.7	8.8	9.1	9.5	10.3	11.3		
0 ~ 20	7.8	8.8	8.9	9.2	9.6	10.5	11.4		
20 ~ 40	7.8	8.8	8.9	9.2	9.6	10.6	11.6		
40 ~ 60	7.9	9.0	9.0	9.4	9.8	10.8	11.8		
60 ~ 80	8.1	9.2	9.3	9.6	10.0	11.0	12.1		

Refractive Index	$n_d$	<b>1.83481</b> 1.834807	Abbe Number	$V_d$	<b>42.73</b> 42.47	Dispersion	$n_F - n_C$	<b>0.01954</b> 0.019539
		$n_e$		1.839452			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78870
$n_{1970}$	1.97009	1.79602
$n_{1530}$	1.52958	1.80402
$n_{1129}$	1.12864	1.81154
$n_t$	1.01398	1.81420
$n_s$	0.85211	1.81906
$n_{A'}$	0.76819	1.82251
$n_r$	0.70652	1.82572
$n_c$	0.65627	<b>1.82898</b>
$n_{c'}$	0.64385	1.82990
$n_{\text{He-Ne}}$	0.6328	1.83076
$n_D$	0.58929	1.83464
$n_d$	0.58756	<b>1.83481</b>
$n_e$	0.54607	1.83945
$n_F$	0.48613	<b>1.84852</b>
$n_{F'}$	0.47999	1.84966
$n_{\text{He-Cd}}$	0.44157	1.85808
$n_g$	0.435835	<b>1.85956</b>
$n_h$	0.404656	1.86893
$n_i$	0.365015	1.88539
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.014778
$n_c - n_{A'}$	0.006476
$n_d - n_c$	0.005826
$n_e - n_c$	0.010471
$n_g - n_d$	0.024749
$n_g - n_F$	0.011036
$n_h - n_g$	0.009373
$n_i - n_g$	0.025830
$n_{c'} - n_t$	0.015697
$n_e - n_{c'}$	0.009552
$n_{F'} - n_e$	0.010212
$n_i - n_{F'}$	0.035722

Relative Partial Dispersions	
$\theta_{c,t}$	0.7563
$\theta_{c,A'}$	0.3314
$\theta_{d,c}$	0.2982
$\theta_{e,c}$	0.5359
$\theta_{g,d}$	1.2666
$\theta_{g,F}$	0.5648
$\theta_{h,g}$	0.4797
$\theta_{i,g}$	1.3220
$\theta'_{c,t}$	0.7942
$\theta'_{e,c'}$	0.4833
$\theta'_{F',e}$	0.5167
$\theta'_{i,F'}$	1.8074

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0091
$\Delta\theta_{c,A'}$	0.0037
$\Delta\theta_{g,d}$	-0.0094
$\Delta\theta_{g,F}$	-0.0075
$\Delta\theta_{i,g}$	-0.0452

Internal Transmittance			
$\lambda_{80}$	363	$\lambda_5$	327

CCI		
B	G	R
0.00	0.93	0.96

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.97025325	E0
A 2	3.04894140	E-1
A 3	1.39214665	E0
B 1	9.91088134	E-3
B 2	3.83202295	E-2
B 3	9.77785249	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.140	
340	0.420	
350	0.640	
360	0.780	
365		
370	0.860	
380	0.910	
390	0.939	
400	0.956	
420	0.974	
440	0.982	
460	0.987	
480	0.992	
500	0.995	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.995	
1800	0.987	
2000	0.966	
2200	0.909	
2400	0.710	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	645
Annealing Point (°C)	<b>AP</b>	672
Transformation Temperature (°C)	<b>Tg</b>	695
Yield Point (°C)	<b>At</b>	718
Softening Point (°C)	<b>SP</b>	749
Expansion Coefficient $\alpha$ (-30~+70°C)		62
(10 <sup>-7</sup> /°C)	(+100~+300°C)	77
Thermal Conductivity (W/m·K)	<b>k</b>	0.853

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	4
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1178
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	470
Poisson's Ratio	$\sigma$	0.253
Knoop Hardness	<b>Hk</b>	740 [7]
Abrasion	<b>Aa</b>	59
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.3

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	4.73		$\lambda_5$	325				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.5	4.2	4.3	4.5	4.8	5.4	6.1		
-20 ~ 0	3.5	4.2	4.3	4.5	4.8	5.5	6.2		
0 ~ 20	3.5	4.2	4.3	4.5	4.8	5.5	6.3		
20 ~ 40	3.5	4.3	4.3	4.5	4.9	5.6	6.4		
40 ~ 60	3.5	4.4	4.4	4.7	5.0	5.8	6.6		
60 ~ 80	3.7	4.5	4.6	4.9	5.2	6.0	6.8		

Refractive Index	$n_d$	<b>1.83481</b>	Abbe Number	$V_d$	<b>42.74</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.019531
		1.834810			$V_e$		42.49	
	$n_e$	1.839452						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78946
$n_{1970}$	1.97009	1.79652
$n_{1530}$	1.52958	1.80427
$n_{1129}$	1.12864	1.81165
$n_t$	1.01398	1.81428
$n_s$	0.85211	1.81910
$n_{A'}$	0.76819	1.82253
$n_r$	0.70652	1.82574
$n_C$	0.65627	<b>1.82899</b>
$n_{C'}$	0.64385	1.82991
$n_{\text{He-Ne}}$	0.6328	1.83077
$n_D$	0.58929	1.83464
$n_d$	0.58756	<b>1.83481</b>
$n_e$	0.54607	1.83945
$n_F$	0.48613	<b>1.84852</b>
$n_{F'}$	0.47999	1.84966
$n_{\text{He-Cd}}$	0.44157	1.85807
$n_g$	0.435835	<b>1.85955</b>
$n_h$	0.404656	1.86892
$n_i$	0.365015	1.88534
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.014712
$n_C - n_{A'}$	0.006462
$n_d - n_C$	0.005822
$n_e - n_C$	0.010464
$n_g - n_d$	0.024741
$n_g - n_F$	0.011032
$n_h - n_g$	0.009365
$n_i - n_g$	0.025786
$n_{C'} - n_t$	0.015630
$n_e - n_{C'}$	0.009546
$n_{F'} - n_e$	0.010210
$n_i - n_{F'}$	0.035675

Relative Partial Dispersions	
$\theta_{C,t}$	0.7533
$\theta_{C,A'}$	0.3309
$\theta_{d,C}$	0.2981
$\theta_{e,C}$	0.5358
$\theta_{g,d}$	1.2668
$\theta_{g,F}$	0.5648
$\theta_{h,g}$	0.4795
$\theta_{i,g}$	1.3203
$\theta'_{C,t}$	0.7912
$\theta'_{e,C'}$	0.4832
$\theta'_{F',e}$	0.5168
$\theta'_{i,F'}$	1.8058

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0061
$\Delta\theta_{C,A'}$	0.0032
$\Delta\theta_{g,d}$	-0.0091
$\Delta\theta_{g,F}$	-0.0075
$\Delta\theta_{i,g}$	-0.0468

Internal Transmittance			
$\lambda_{80}$	356	$\lambda_5$	319

CCI		
B	G	R
0.00	0.65	0.68

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.92591095	
A 2	3.48953460	E-1
A 3	1.42230744	
B 1	9.61152490	E-3
B 2	3.65132980	E-2
B 3	1.03364090	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310		
320	0.060	
330	0.280	
340	0.550	
350	0.730	
360	0.840	
365		
370	0.900	
380	0.936	
390	0.957	
400	0.970	
420	0.982	
440	0.988	
460	0.991	
480	0.994	
500	0.996	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.988	
2000	0.968	
2200	0.920	
2400	0.740	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	639
Annealing Point (°C)	<b>AP</b>	667
Transformation Temperature (°C)	<b>Tg</b>	677
Yield Point (°C)	<b>At</b>	709
Softening Point (°C)	<b>SP</b>	738
Expansion Coefficient $\alpha$ (-30~+70°C)		63
Expansion Coefficient $\alpha$ (+100~+300°C)		77
Thermal Conductivity (W/m·K)	<b>k</b>	0.864

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1223
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	472
Poisson's Ratio	$\sigma$	0.297
Knoop Hardness	<b>Hk</b>	740 [7]
Abrasion	<b>Aa</b>	64
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.31

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	395				
Specific Gravity	<b>d</b>	4.58		$\lambda_5$	320				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.9	4.6	4.6	4.9	5.2	5.8	6.5		
-20 ~ 0	3.8	4.6	4.7	4.9	5.2	5.9	6.6		
0 ~ 20	3.8	4.6	4.7	4.9	5.2	6.0	6.7		
20 ~ 40	3.8	4.6	4.7	5.0	5.3	6.0	6.8		
40 ~ 60	3.9	4.8	4.8	5.1	5.4	6.2	7.0		
60 ~ 80	4.0	4.9	5.0	5.3	5.6	6.4	7.3		

Refractive Index	$n_d$	<b>1.88300</b>	Abbe Number	$V_d$	<b>40.76</b>	Dispersion	$n_F - n_C$	<b>0.02166</b>
		1.882997			$V_e$		40.52	
	$n_e$	1.888146					$n_{F'} - n_{C'}$	0.021919

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.83590
$n_{1970}$	1.97009	1.84264
$n_{1530}$	1.52958	1.85023
$n_{1129}$	1.12864	1.85776
$n_t$	1.01398	1.86054
$n_s$	0.85211	1.86572
$n_{A'}$	0.76819	1.86946
$n_r$	0.70652	1.87298
$n_c$	0.65627	<b>1.87656</b>
$n_{c'}$	0.64385	1.87757
$n_{\text{He-Ne}}$	0.6328	1.87852
$n_D$	0.58929	1.88281
$n_d$	0.58756	<b>1.88300</b>
$n_e$	0.54607	1.88815
$n_F$	0.48613	<b>1.89822</b>
$n_{F'}$	0.47999	1.89949
$n_{\text{He-Cd}}$	0.44157	1.90885
$n_g$	0.435835	<b>1.91050</b>
$n_h$	0.404656	1.92092
$n_i$	0.365015	1.93917
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	666
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	714
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	738
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	765
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	803
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	66
	(+10~+300 $^{\circ}\text{C}$ )	78
Thermal Conductivity (W/m·K)	<b>k</b>	0.827

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1268
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	487
Poisson's Ratio	$\sigma$	0.301
Knoop Hardness	<b>Hk</b>	710 [7]
Abrasion	<b>Aa</b>	61
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.3

Partial Dispersions	
$n_c - n_t$	0.016022
$n_c - n_{A'}$	0.007103
$n_d - n_c$	0.006437
$n_e - n_c$	0.011586
$n_g - n_d$	0.027500
$n_g - n_F$	0.012276
$n_h - n_g$	0.010422
$n_i - n_g$	0.028677
$n_{c'} - n_t$	0.017035
$n_e - n_{c'}$	0.010573
$n_{F'} - n_e$	0.011346
$n_i - n_{F'}$	0.039682

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0018
$\Delta\theta_{c,A'}$	0.0026
$\Delta\theta_{g,d}$	-0.0105
$\Delta\theta_{g,F}$	-0.0088
$\Delta\theta_{i,g}$	-0.0598

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.78764964	
A 2	6.52635600	E-1
A 3	1.79914564	
B 1	8.47378536	E-3
B 2	3.13126408	E-2
B 3	1.32788001	E2
1129 ~ 2325 nm		
A 1	1.78764964	
A 2	6.52635600	E-1
A 3	1.79914564	
B 1	8.47378536	E-3
B 2	3.13126408	E-2
B 3	1.32788001	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	2.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7397
$\theta_{c,A'}$	0.3279
$\theta_{d,c}$	0.2972
$\theta_{e,c}$	0.5349
$\theta_{g,d}$	1.2696
$\theta_{g,F}$	0.5667
$\theta_{h,g}$	0.4811
$\theta_{i,g}$	1.3239
$\theta'_{c,t}$	0.7772
$\theta'_{e,c'}$	0.4824
$\theta'_{F',e}$	0.5176
$\theta'_{i,F'}$	1.8104

Internal Transmittance			
$\lambda_{80}$	374	$\lambda_5$	320

CCI		
B	G	R
0.00	1.69	1.75

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.050	
330	0.170	
340	0.340	
350	0.510	
360	0.660	
365		
370	0.770	
380	0.840	
390	0.890	
400	0.924	
420	0.951	
440	0.965	
460	0.974	
480	0.982	
500	0.988	
550	0.995	
600	0.995	
650	0.995	
700	0.995	
800	0.995	
900	0.995	
1000	0.995	
1200	0.996	
1400	0.996	
1600	0.996	
1800	0.992	
2000	0.980	
2200	0.956	
2400	0.840	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					375
Specific Gravity	<b>d</b>	5.52		$\lambda_5$					315
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.3	4.1	4.1	4.4	4.7	5.4	6.2		
-20 ~ 0	3.4	4.2	4.3	4.6	4.9	5.6	6.4		
0 ~ 20	3.6	4.3	4.4	4.7	5.0	5.8	6.6		
20 ~ 40	3.7	4.5	4.5	4.9	5.2	6.0	6.8		
40 ~ 60	3.9	4.6	4.6	5.0	5.3	6.2	7.1		
60 ~ 80	4.0	4.7	4.8	5.2	5.5	6.4	7.3		

Refractive Index	$n_d$	<b>1.81600</b>	Abbe Number	$V_d$	<b>46.62</b>	Dispersion	$n_F - n_C$	<b>0.01750</b>
		1.816000			$V_e$		46.37	
	$n_e$	1.820167					$n_{F'} - n_{C'}$	0.017688

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.77345
$n_{1970}$	1.97009	1.78033
$n_{1530}$	1.52958	1.78784
$n_{1129}$	1.12864	1.79483
$n_t$	1.01398	1.79729
$n_s$	0.85211	1.80174
$n_{A'}$	0.76819	1.80488
$n_r$	0.70652	1.80780
$n_c$	0.65627	<b>1.81075</b>
$n_{c'}$	0.64385	1.81158
$n_{\text{He-Ne}}$	0.6328	1.81236
$n_D$	0.58929	1.81585
$n_d$	0.58756	<b>1.81600</b>
$n_e$	0.54607	1.82017
$n_F$	0.48613	<b>1.82825</b>
$n_{F'}$	0.47999	1.82927
$n_{\text{He-Cd}}$	0.44157	1.83670
$n_g$	0.435835	<b>1.83800</b>
$n_h$	0.404656	1.84619
$n_i$	0.365015	1.86034
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.013459
$n_c - n_{A'}$	0.005870
$n_d - n_c$	0.005251
$n_e - n_c$	0.009418
$n_g - n_d$	0.021997
$n_g - n_F$	0.009745
$n_h - n_g$	0.008188
$n_i - n_g$	0.022341
$n_{c'} - n_t$	0.014289
$n_e - n_{c'}$	0.008588
$n_{F'} - n_e$	0.009100
$n_i - n_{F'}$	0.031071

Relative Partial Dispersions	
$\theta_{c,t}$	0.7690
$\theta_{c,A'}$	0.3354
$\theta_{d,c}$	0.3000
$\theta_{e,c}$	0.5381
$\theta_{g,d}$	1.2568
$\theta_{g,F}$	0.5568
$\theta_{h,g}$	0.4678
$\theta_{i,g}$	1.2764
$\theta'_{c,t}$	0.8078
$\theta'_{e,c'}$	0.4855
$\theta'_{F',e}$	0.5145
$\theta'_{i,F'}$	1.7566

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0036
$\Delta\theta_{c,A'}$	0.0030
$\Delta\theta_{g,d}$	-0.0111
$\Delta\theta_{g,F}$	-0.0092
$\Delta\theta_{i,g}$	-0.0582

Internal Transmittance			
$\lambda_{80}$	359	$\lambda_5$	298

CCI		
B	G	R
0.00	0.94	0.93

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.51372967	
A 2	7.02462343	E-1
A 3	1.33600982	
B 1	7.05246901	E-3
B 2	2.49488689	E-2
B 3	1.00085908	E2
1129 ~ 2325 nm		
A 1	1.51372967	
A 2	7.02462343	E-1
A 3	1.33600982	
B 1	7.05246901	E-3
B 2	2.49488689	E-2
B 3	1.00085908	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290	0.020	
300	0.060	
310	0.090	
320	0.280	
330	0.430	
340	0.580	
350	0.710	
360	0.810	
365		
370	0.880	
380	0.921	
390	0.943	
400	0.958	
420	0.973	
440	0.979	
460	0.984	
480	0.989	
500	0.994	
550	0.997	
600	0.996	
650	0.996	
700	0.996	
800	0.996	
900	0.995	
1000	0.995	
1200	0.995	
1400	0.995	
1600	0.994	
1800	0.989	
2000	0.973	
2200	0.938	
2400	0.760	

Thermal Properties		
Strain Point (°C)	StP	644
Annealing Point (°C)	AP	690
Transformation Temperature (°C)	Tg	714
Yield Point (°C)	At	737
Softening Point (°C)	SP	773
Expansion Coefficient $\alpha$ (-30~+70°C)		63
(10-7 /°C) (+100~+300°C)		76
Thermal Conductivity (W/m·K)	k	0.816

Chemical Properties		
Water Resistance (Powder Group)	RW(P)	1
Acid Resistance (Powder Group)	RA(P)	2
Weathering Resistance (Surface Group)	W(S)	1
Acid Resistance (Surface Group)	SR	3.0
Phosphate Resistance	PR	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	E	1250
Rigidity Modulus (108N/m <sup>2</sup> )	G	482
Poisson's Ratio	$\sigma$	0.298
Knoop Hardness	Hk	750 [7]
Abrasion	Aa	57
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.37

Other Properties									
Bubble Quality Group	B		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	d	5.07		$\lambda_5$	290				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.1	4.6	4.6	4.9	5.1	5.6	6.2		
-20 ~ 0	4.1	4.7	4.7	5.0	5.2	5.8	6.4		
0 ~ 20	4.2	4.8	4.8	5.1	5.3	5.9	6.5		
20 ~ 40	4.3	4.9	4.9	5.2	5.4	6.1	6.7		
40 ~ 60	4.3	5.0	5.0	5.3	5.6	6.2	6.9		
60 ~ 80	4.4	5.1	5.1	5.4	5.7	6.4	7.0		

Refractive Index	$n_d$	<b>1.83400</b>	Abbe Number	$V_d$	<b>37.16</b>	Dispersion	$n_F - n_C$	<b>0.02244</b>
		1.834000			$V_e$		36.92	
	$n_e$	1.839323					$n_{F'} - n_{C'}$	0.022736

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78473
$n_{1970}$	1.97009	1.79205
$n_{1530}$	1.52958	1.80018
$n_{1129}$	1.12864	1.80807
$n_t$	1.01398	1.81094
$n_s$	0.85211	1.81627
$n_{A'}$	0.76819	1.82009
$n_r$	0.70652	1.82370
$n_C$	0.65627	<b>1.82738</b>
$n_{C'}$	0.64385	1.82842
$n_{\text{He-Ne}}$	0.6328	1.82939
$n_D$	0.58929	1.83380
$n_d$	0.58756	<b>1.83400</b>
$n_e$	0.54607	1.83932
$n_F$	0.48613	<b>1.84982</b>
$n_{F'}$	0.47999	1.85115
$n_{\text{He-Cd}}$	0.44157	1.86103
$n_g$	0.435835	<b>1.86278</b>
$n_h$	0.404656	1.87396
$n_i$	0.365015	1.89403
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.016437
$n_C - n_{A'}$	0.007283
$n_d - n_C$	0.006624
$n_e - n_C$	0.011947
$n_g - n_d$	0.028781
$n_g - n_F$	0.012962
$n_h - n_g$	0.011183
$n_i - n_g$	0.031249
$n_{C'} - n_t$	0.017477
$n_e - n_{C'}$	0.010907
$n_{F'} - n_e$	0.011829
$n_i - n_{F'}$	0.042878

Relative Partial Dispersions	
$\theta_{C,t}$	0.7324
$\theta_{C,A'}$	0.3245
$\theta_{d,C}$	0.2951
$\theta_{e,C}$	0.5323
$\theta_{g,d}$	1.2824
$\theta_{g,F}$	0.5776
$\theta_{h,g}$	0.4983
$\theta_{i,g}$	1.3924
$\theta'_{C,t}$	0.7687
$\theta'_{e,C'}$	0.4797
$\theta'_{F',e}$	0.5203
$\theta'_{i,F'}$	1.8859

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0114
$\Delta\theta_{C,A'}$	0.0036
$\Delta\theta_{g,d}$	-0.0051
$\Delta\theta_{g,F}$	-0.0037
$\Delta\theta_{i,g}$	-0.0215

Internal Transmittance			
$\lambda_{80}$	377	$\lambda_5$	341

CCI		
B	G	R
0.00	1.57	1.66

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.95243469	
A 2	3.07100210	E-1
A 3	1.56578094	
B 1	1.06442437	E-2
B 2	4.56735302	E-2
B 3	1.10281410	E2
1129 ~ 2325 nm		
A 1	1.95243469	
A 2	3.07100210	E-1
A 3	1.56578094	
B 1	1.06442437	E-2
B 2	4.56735302	E-2
B 3	1.10281410	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.030	
350	0.270	
360	0.540	
365		
370	0.720	
380	0.830	
390	0.880	
400	0.924	
420	0.957	
440	0.972	
460	0.980	
480	0.986	
500	0.990	
550	0.996	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.996	
1400	0.993	
1600	0.992	
1800	0.984	
2000	0.964	
2200	0.906	
2400	0.720	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	612
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	632
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	676
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		56
(10-7 $^{\circ}\text{C}$ )		71
Thermal Conductivity (W/m·K)	<b>k</b>	0.872

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	4.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1248
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	481
Poisson's Ratio	$\sigma$	0.296
Knoop Hardness	<b>Hk</b>	670 [7]
Abrasion	<b>Aa</b>	78
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.15

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	420				
Specific Gravity	<b>d</b>	4.43		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	6.0	6.9	6.9	7.3	7.6	8.4	9.3		
-20 ~ 0	6.3	7.0	7.1	7.4	7.7	8.6	9.6		
0 ~ 20	6.3	7.1	7.2	7.6	7.9	8.8	9.8		
20 ~ 40	6.4	7.3	7.3	7.7	8.1	9.0	10.1		
40 ~ 60	6.6	7.4	7.5	7.9	8.3	9.3	10.3		
60 ~ 80	6.7	7.5	7.6	8.0	8.4	9.5	10.6		



Refractive Index	$n_d$	<b>1.83400</b>	Abbe Number	$V_d$	<b>37.21</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.022416
	$n_e$	1.834000		$V_e$	36.95			0.022716

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78608
$n_{1970}$	1.97009	1.79301
$n_{1530}$	1.52958	1.80073
$n_{1129}$	1.12864	1.80833
$n_t$	1.01398	1.81114
$n_s$	0.85211	1.81638
$n_{A'}$	0.76819	1.82016
$n_r$	0.70652	1.82375
$n_C$	0.65627	<b>1.82740</b>
$n_{C'}$	0.64385	1.82844
$n_{\text{He-Ne}}$	0.6328	1.82941
$n_D$	0.58929	1.83380
$n_d$	0.58756	<b>1.83400</b>
$n_e$	0.54607	1.83931
$n_F$	0.48613	<b>1.84982</b>
$n_{F'}$	0.47999	1.85115
$n_{\text{He-Cd}}$	0.44157	1.86107
$n_g$	0.435835	<b>1.86283</b>
$n_h$	0.404656	1.87412
$n_i$	0.365015	1.89457
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.016264
$n_C - n_{A'}$	0.007235
$n_d - n_C$	0.006601
$n_e - n_C$	0.011914
$n_g - n_d$	0.028833
$n_g - n_F$	0.013018
$n_h - n_g$	0.011289
$n_i - n_g$	0.031732
$n_{C'} - n_t$	0.017300
$n_e - n_{C'}$	0.010878
$n_{F'} - n_e$	0.011838
$n_i - n_{F'}$	0.043414

Relative Partial Dispersions	
$\theta_{C,t}$	0.7256
$\theta_{C,A'}$	0.3228
$\theta_{d,C}$	0.2945
$\theta_{e,C}$	0.5315
$\theta_{g,d}$	1.2863
$\theta_{g,F}$	0.5807
$\theta_{h,g}$	0.5036
$\theta_{i,g}$	1.4156
$\theta'_{C,t}$	0.7616
$\theta'_{e,C'}$	0.4789
$\theta'_{F',e}$	0.5211
$\theta'_{i,F'}$	1.9112

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0043
$\Delta\theta_{C,A'}$	0.0018
$\Delta\theta_{g,d}$	-0.0011
$\Delta\theta_{g,F}$	-0.0006
$\Delta\theta_{i,g}$	0.0022

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.05081962	
A 2	2.08475257	E-1
A 3	1.31486394	
B 1	1.16035991	E-2
B 2	5.26489359	E-2
B 3	9.93806500	E1
1129 ~ 2325 nm		
A 1	2.05081962	
A 2	2.08475257	E-1
A 3	1.31486394	
B 1	1.16035991	E-2
B 2	5.26489359	E-2
B 3	9.93806500	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.050	
360	0.290	
365		
370	0.590	
380	0.770	
390	0.860	
400	0.909	
420	0.951	
440	0.968	
460	0.979	
480	0.986	
500	0.991	
550	0.996	
600	0.996	
650	0.996	
700	0.997	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.993	
1800	0.984	
2000	0.961	
2200	0.905	
2400	0.720	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	570
Annealing Point (°C)	<b>AP</b>	588
Transformation Temperature (°C)	<b>Tg</b>	603
Yield Point (°C)	<b>At</b>	635
Softening Point (°C)	<b>SP</b>	669
Expansion Coefficient $\alpha$ (-30~+70°C)		58
Expansion Coefficient $\alpha$ (+100~+300°C)		73
Thermal Conductivity (W/m·K)	<b>k</b>	0.880

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1114
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	445
Poisson's Ratio	$\sigma$	0.253
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	57
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	1.0

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	430				
Specific Gravity	<b>d</b>	4.43		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	7.4	8.4	8.5	8.8	9.2	10.1	11.2		
-20 ~ 0	7.5	8.5	8.6	8.9	9.4	10.4	11.5		
0 ~ 20	7.5	8.6	8.7	9.0	9.5	10.5	11.7		
20 ~ 40	7.5	8.7	8.7	9.1	9.5	10.6	11.9		
40 ~ 60	7.7	8.8	8.9	9.2	9.7	10.8	12.1		
60 ~ 80	7.8	9.0	9.1	9.5	10.0	11.2	12.5		

Refractive Index	$n_d$	<b>1.80440</b>	Abbe Number	$V_d$	<b>39.58</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.020323
		1.804400			$V_e$			
	$n_e$	1.809220						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.76063
$n_{1970}$	1.97009	1.76695
$n_{1530}$	1.52958	1.77401
$n_{1129}$	1.12864	1.78098
$n_t$	1.01398	1.78355
$n_s$	0.85211	1.78834
$n_{A'}$	0.76819	1.79180
$n_r$	0.70652	1.79507
$n_c$	0.65627	<b>1.79840</b>
$n_{c'}$	0.64385	1.79934
$n_{\text{He-Ne}}$	0.6328	1.80023
$n_D$	0.58929	1.80422
$n_d$	0.58756	<b>1.80440</b>
$n_e$	0.54607	1.80922
$n_F$	0.48613	<b>1.81872</b>
$n_{F'}$	0.47999	1.81993
$n_{\text{He-Cd}}$	0.44157	1.82885
$n_g$	0.435835	<b>1.83043</b>
$n_h$	0.404656	1.84052
$n_i$	0.365015	1.85862
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	626
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	654
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	669
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	701
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	732
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	79
	(+100~+300 $^{\circ}\text{C}$ )	93
Thermal Conductivity (W/m·K)	<b>k</b>	0.738

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1026
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	395
Poisson's Ratio	$\sigma$	0.300
Knoop Hardness	<b>Hk</b>	580 [6]
Abrasion	<b>Aa</b>	121
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.39

Partial Dispersions	
$n_c - n_t$	0.014851
$n_c - n_{A'}$	0.006597
$n_d - n_c$	0.006003
$n_e - n_c$	0.010825
$n_g - n_d$	0.026030
$n_g - n_F$	0.011710
$n_h - n_g$	0.010090
$n_i - n_g$	0.028188
$n_{c'} - n_t$	0.015794
$n_e - n_{c'}$	0.009882
$n_{F'} - n_e$	0.010704
$n_i - n_{F'}$	0.038692

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0017
$\Delta\theta_{c,A'}$	0.0008
$\Delta\theta_{g,d}$	-0.0017
$\Delta\theta_{g,F}$	-0.0012
$\Delta\theta_{i,g}$	-0.0066

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.96723017	
A 2	1.94953915	E-1
A 3	1.25386282	
B 1	1.10456086	E-2
B 2	4.97137061	E-2
B 3	1.04843520	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7307
$\theta_{c,A'}$	0.3246
$\theta_{d,c}$	0.2954
$\theta_{e,c}$	0.5326
$\theta_{g,d}$	1.2808
$\theta_{g,F}$	0.5762
$\theta_{h,g}$	0.4965
$\theta_{i,g}$	1.3870
$\theta'_{c,t}$	0.7672
$\theta'_{e,c'}$	0.4800
$\theta'_{F',e}$	0.5200
$\theta'_{i,F'}$	1.8795

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.010	
350	0.140	
360	0.440	
365		
370	0.690	
380	0.820	
390	0.890	
400	0.927	
420	0.959	
440	0.973	
460	0.981	
480	0.987	
500	0.991	
550	0.996	
600	0.996	
650	0.996	
700	0.997	
800	0.998	
900	0.998	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.995	
1800	0.987	
2000	0.968	
2200	0.923	
2400	0.770	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	415				
Specific Gravity	<b>d</b>	4.45		$\lambda_5$	345				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.4	1.2	1.2	1.5	1.8	2.5	3.3		
-20 ~ 0	0.4	1.1	1.2	1.4	1.7	2.5	3.3		
0 ~ 20	0.4	1.2	1.2	1.5	1.8	2.6	3.5		
20 ~ 40	0.4	1.2	1.3	1.5	1.9	2.7	3.6		
40 ~ 60	0.4	1.3	1.3	1.6	2.0	2.8	3.8		
60 ~ 80	0.5	1.4	1.5	1.7	2.1	3.0	4.0		

Refractive Index	$n_d$	<b>1.80440</b>	Abbe Number	$V_d$	<b>39.59</b>	Dispersion	$n_F - n_C$	<b>0.02032</b>
		1.804398			$V_e$		39.33	
	$n_e$	1.809221					$n_{F'} - n_{C'}$	0.020573

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.75781
$n_{1970}$	1.97009	1.76505
$n_{1530}$	1.52958	1.77300
$n_{1129}$	1.12864	1.78056
$n_t$	1.01398	1.78325
$n_s$	0.85211	1.78820
$n_{A'}$	0.76819	1.79172
$n_r$	0.70652	1.79502
$n_C$	0.65627	<b>1.79838</b>
$n_{C'}$	0.64385	1.79932
$n_{\text{He-Ne}}$	0.6328	1.80021
$n_D$	0.58929	1.80422
$n_d$	0.58756	<b>1.80440</b>
$n_e$	0.54607	1.80922
$n_F$	0.48613	<b>1.81870</b>
$n_{F'}$	0.47999	1.81990
$n_{\text{He-Cd}}$	0.44157	1.82877
$n_g$	0.435835	<b>1.83034</b>
$n_h$	0.404656	1.84033
$n_i$	0.365015	1.85815
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	558
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	588
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	607
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	630
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	675
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	58
	(+10~+300 $^{\circ}\text{C}$ )	70
Thermal Conductivity (W/m·K)	<b>k</b>	0.849

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1121
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	433
Poisson's Ratio	$\sigma$	0.295
Knoop Hardness	<b>Hk</b>	640 [6]
Abrasion	<b>Aa</b>	82
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.18

Partial Dispersions	
$n_C - n_t$	0.015124
$n_C - n_{A'}$	0.006658
$n_d - n_C$	0.006022
$n_e - n_C$	0.010845
$n_g - n_d$	0.025940
$n_g - n_F$	0.011642
$n_h - n_g$	0.009994
$n_i - n_g$	0.027810
$n_{C'} - n_t$	0.016071
$n_e - n_{C'}$	0.009898
$n_{F'} - n_e$	0.010675
$n_i - n_{F'}$	0.038252

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0119
$\Delta\theta_{C,A'}$	0.0039
$\Delta\theta_{g,d}$	-0.0059
$\Delta\theta_{g,F}$	-0.0045
$\Delta\theta_{i,g}$	-0.0249

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.89458276	
A 2	2.68702978	E-1
A 3	1.45705526	
B 1	1.02277048	E-2
B 2	4.42801243	E-2
B 3	1.04874927	E2
1129 ~ 2325 nm		
A 1	1.89458276	
A 2	2.68702978	E-1
A 3	1.45705526	
B 1	1.02277048	E-2
B 2	4.42801243	E-2
B 3	1.04874927	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	4.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.7443
$\theta_{C,A'}$	0.3277
$\theta_{d,C}$	0.2964
$\theta_{e,C}$	0.5337
$\theta_{g,d}$	1.2766
$\theta_{g,F}$	0.5729
$\theta_{h,g}$	0.4918
$\theta_{i,g}$	1.3686
$\theta'_{C,t}$	0.7812
$\theta'_{e,C'}$	0.4811
$\theta'_{F',e}$	0.5189
$\theta'_{i,F'}$	1.8593

Internal Transmittance			
$\lambda_{80}$	374	$\lambda_5$	340

CCI		
B	G	R
0.00	1.31	1.39

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.060	
350	0.310	
360	0.590	
365		
370	0.760	
380	0.860	
390	0.909	
400	0.937	
420	0.965	
440	0.976	
460	0.983	
480	0.988	
500	0.992	
550	0.997	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.993	
1600	0.992	
1800	0.984	
2000	0.963	
2200	0.890	
2400	0.700	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	410				
Specific Gravity	<b>d</b>	4.34		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.5	6.6	6.6	6.8	7.3	8.0	8.7		
-20 ~ 0	5.7	6.7	6.7	6.9	7.3	8.1	8.9		
0 ~ 20	5.8	6.8	6.8	7.0	7.5	8.3	9.1		
20 ~ 40	5.9	6.9	6.9	7.2	7.6	8.5	9.4		
40 ~ 60	6.2	7.1	7.2	7.5	7.8	8.8	9.7		
60 ~ 80	6.4	7.3	7.4	7.7	8.1	9.1	10.1		

Refractive Index	$n_d$	<b>1.78800</b>	Abbe Number	$V_d$	<b>47.37</b>	Dispersion	$n_F - n_C$	<b>0.01663</b>
		1.788001			$V_e$		47.12	
	$n_e$	1.791961					$n_{F'} - n_{C'}$	0.016806

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.74466
$n_{1970}$	1.97009	1.75220
$n_{1530}$	1.52958	1.76026
$n_{1129}$	1.12864	1.76750
$n_t$	1.01398	1.76996
$n_s$	0.85211	1.77433
$n_{A'}$	0.76819	1.77737
$n_r$	0.70652	1.78018
$n_c$	0.65627	<b>1.78300</b>
$n_{c'}$	0.64385	1.78379
$n_{\text{He-Ne}}$	0.6328	1.78453
$n_D$	0.58929	1.78785
$n_d$	0.58756	<b>1.78800</b>
$n_e$	0.54607	1.79196
$n_F$	0.48613	<b>1.79963</b>
$n_{F'}$	0.47999	1.80060
$n_{\text{He-Cd}}$	0.44157	1.80765
$n_g$	0.435835	<b>1.80888</b>
$n_h$	0.404656	1.81666
$n_i$	0.365015	1.83016
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.013038
$n_c - n_{A'}$	0.005628
$n_d - n_c$	0.005003
$n_e - n_c$	0.008963
$n_g - n_d$	0.020881
$n_g - n_F$	0.009248
$n_h - n_g$	0.007782
$n_i - n_g$	0.021279
$n_{c'} - n_t$	0.013830
$n_e - n_{c'}$	0.008171
$n_{F'} - n_e$	0.008635
$n_i - n_{F'}$	0.029565

Relative Partial Dispersions	
$\theta_{c,t}$	0.7837
$\theta_{c,A'}$	0.3383
$\theta_{d,c}$	0.3007
$\theta_{e,c}$	0.5388
$\theta_{g,d}$	1.2552
$\theta_{g,F}$	0.5559
$\theta_{h,g}$	0.4678
$\theta_{i,g}$	1.2791
$\theta'_{c,t}$	0.8229
$\theta'_{e,c'}$	0.4862
$\theta'_{F',e}$	0.5138
$\theta'_{i,F'}$	1.7592

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0148
$\Delta\theta_{c,A'}$	0.0050
$\Delta\theta_{g,d}$	-0.0111
$\Delta\theta_{g,F}$	-0.0089
$\Delta\theta_{i,g}$	-0.0493

Internal Transmittance			
$\lambda_{80}$	354	$\lambda_5$	317

CCI		
B	G	R
0.00	0.63	0.65

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.83021453	
A 2	2.91563590	E-1
A 3	1.28544024	
B 1	9.04823290	E-3
B 2	3.30756689	E-2
B 3	8.93675501	E1
1129 ~ 2325 nm		
A 1	1.83021453	
A 2	2.91563590	E-1
A 3	1.28544024	
B 1	9.04823290	E-3
B 2	3.30756689	E-2
B 3	8.93675501	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.130	
330	0.400	
340	0.630	
350	0.770	
360	0.850	
365		
370	0.912	
380	0.943	
390	0.961	
400	0.972	
420	0.981	
440	0.986	
460	0.990	
480	0.993	
500	0.996	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.996	
1400	0.995	
1600	0.993	
1800	0.987	
2000	0.966	
2200	0.915	
2400	0.680	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	644
Annealing Point (°C)	<b>AP</b>	660
Transformation Temperature (°C)	<b>Tg</b>	685
Yield Point (°C)	<b>At</b>	705
Softening Point (°C)	<b>SP</b>	732
Expansion Coefficient $\alpha$ (-30~+70°C)		61
(10-7 /°C) (+100~+300°C)		74
Thermal Conductivity (W/m·K)	<b>k</b>	0.856

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1224
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	473
Poisson's Ratio	$\sigma$	0.294
Knoop Hardness	<b>Hk</b>	750 [7]
Abrasion	<b>Aa</b>	61
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.4

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	4.30		$\lambda_5$	315				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.5	3.9	3.9	4.1	4.3	4.8	5.3		
-20 ~ 0	3.5	4.0	4.0	4.2	4.4	5.0	5.5		
0 ~ 20	3.6	4.1	4.1	4.3	4.6	5.1	5.7		
20 ~ 40	3.7	4.2	4.2	4.4	4.7	5.3	5.8		
40 ~ 60	3.8	4.3	4.3	4.5	4.8	5.4	6.0		
60 ~ 80	3.9	4.4	4.4	4.6	4.9	5.5	6.2		

Refractive Index	$n_d$	<b>1.80400</b>	Abbe Number	$V_d$	<b>46.58</b>	Dispersion	$n_F - n_C$	<b>0.01726</b>
		1.804000			$V_e$		46.34	
	$n_e$	1.808107					$n_{F'} - n_{C'}$	0.017440

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.75987
$n_{1970}$	1.97009	1.76741
$n_{1530}$	1.52958	1.77552
$n_{1129}$	1.12864	1.78286
$n_t$	1.01398	1.78538
$n_s$	0.85211	1.78987
$n_{A'}$	0.76819	1.79300
$n_r$	0.70652	1.79590
$n_c$	0.65627	<b>1.79882</b>
$n_{c'}$	0.64385	1.79964
$n_{\text{He-Ne}}$	0.6328	1.80041
$n_D$	0.58929	1.80385
$n_d$	0.58756	<b>1.80400</b>
$n_e$	0.54607	1.80811
$n_F$	0.48613	<b>1.81608</b>
$n_{F'}$	0.47999	1.81708
$n_{\text{He-Cd}}$	0.44157	1.82441
$n_g$	0.435835	<b>1.82569</b>
$n_h$	0.404656	1.83380
$n_i$	0.365015	1.84786
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.013439
$n_c - n_{A'}$	0.005818
$n_d - n_c$	0.005183
$n_e - n_c$	0.009290
$n_g - n_d$	0.021694
$n_g - n_F$	0.009618
$n_h - n_g$	0.008101
$n_i - n_g$	0.022167
$n_{c'} - n_t$	0.014259
$n_e - n_{c'}$	0.008470
$n_{F'} - n_e$	0.008970
$n_i - n_{F'}$	0.030784

Relative Partial Dispersions	
$\theta_{c,t}$	0.7787
$\theta_{c,A'}$	0.3371
$\theta_{d,c}$	0.3003
$\theta_{e,c}$	0.5383
$\theta_{g,d}$	1.2570
$\theta_{g,F}$	0.5573
$\theta_{h,g}$	0.4694
$\theta_{i,g}$	1.2844
$\theta'_{c,t}$	0.8176
$\theta'_{e,c'}$	0.4857
$\theta'_{F',e}$	0.5143
$\theta'_{i,F'}$	1.7651

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0135
$\Delta\theta_{c,A'}$	0.0048
$\Delta\theta_{g,d}$	-0.0110
$\Delta\theta_{g,F}$	-0.0088
$\Delta\theta_{i,g}$	-0.0506

Internal Transmittance			
$\lambda_{80}$	355	$\lambda_5$	319

CCI		
B	G	R
0.00	0.65	0.67

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.81419034	E0
A 2	3.61376301	E-1
A 3	1.32729484	E0
B 1	8.74935029	E-3
B 2	3.18352836	E-2
B 3	9.13406898	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.110	
330	0.370	
340	0.600	
350	0.750	
360	0.850	
365		
370	0.906	
380	0.939	
390	0.959	
400	0.970	
420	0.981	
440	0.986	
460	0.990	
480	0.993	
500	0.996	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.989	
2000	0.967	
2200	0.910	
2400	0.680	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	639
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	664
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	691
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	711
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	740
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	60
	(+100~+300 $^{\circ}\text{C}$ )	74
Thermal Conductivity (W/m·K)	<b>k</b>	0.841

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	4.1
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1220
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	470
Poisson's Ratio	$\sigma$	0.298
Knoop Hardness	<b>Hk</b>	730 [7]
Abrasion	<b>Aa</b>	55
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.44

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	4.72		$\lambda_5$	315				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.6	4.1	4.2	4.4	4.6	5.2	5.7		
-20 ~ 0	3.7	4.3	4.4	4.6	4.8	5.4	6.0		
0 ~ 20	3.8	4.4	4.5	4.7	4.9	5.5	6.1		
20 ~ 40	3.8	4.5	4.5	4.7	5.0	5.6	6.2		
40 ~ 60	3.8	4.5	4.6	4.8	5.1	5.7	6.4		
60 ~ 80	3.9	4.7	4.7	5.0	5.3	5.9	6.6		

Refractive Index	$n_d$	<b>1.80400</b>	Abbe Number	$V_d$	<b>46.53</b>	Dispersion	$n_F - n_C$	0.017281
	$n_e$	1.804000		$V_e$	46.28		$n_{F'} - n_{C'}$	0.017463

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.76127
$n_{1970}$	1.97009	1.76833
$n_{1530}$	1.52958	1.77597
$n_{1129}$	1.12864	1.78303
$n_t$	1.01398	1.78548
$n_s$	0.85211	1.78991
$n_{A'}$	0.76819	1.79302
$n_r$	0.70652	1.79591
$n_C$	0.65627	<b>1.79882</b>
$n_{C'}$	0.64385	1.79964
$n_{\text{He-Ne}}$	0.6328	1.80040
$n_D$	0.58929	1.80385
$n_d$	0.58756	<b>1.80400</b>
$n_e$	0.54607	1.80811
$n_F$	0.48613	<b>1.81610</b>
$n_{F'}$	0.47999	1.81710
$n_{\text{He-Cd}}$	0.44157	1.82445
$n_g$	0.435835	<b>1.82573</b>
$n_h$	0.404656	1.83385
$n_i$	0.365015	1.84792
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.013334
$n_C - n_{A'}$	0.005801
$n_d - n_C$	0.005184
$n_e - n_C$	0.009296
$n_g - n_d$	0.021734
$n_g - n_F$	0.009637
$n_h - n_g$	0.008114
$n_i - n_g$	0.022188
$n_{C'} - n_t$	0.014154
$n_e - n_{C'}$	0.008476
$n_{F'} - n_e$	0.008987
$n_i - n_{F'}$	0.030823

Relative Partial Dispersions	
$\theta_{C,t}$	0.7716
$\theta_{C,A'}$	0.3357
$\theta_{d,C}$	0.3000
$\theta_{e,C}$	0.5379
$\theta_{g,d}$	1.2577
$\theta_{g,F}$	0.5577
$\theta_{h,g}$	0.4695
$\theta_{i,g}$	1.2840
$\theta'_{C,t}$	0.8105
$\theta'_{e,C'}$	0.4854
$\theta'_{F',e}$	0.5146
$\theta'_{i,F'}$	1.7650

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0066
$\Delta\theta_{C,A'}$	0.0034
$\Delta\theta_{g,d}$	-0.0104
$\Delta\theta_{g,F}$	-0.0085
$\Delta\theta_{i,g}$	-0.0514

Internal Transmittance			
$\lambda_{80}$	347	$\lambda_5$	310

CCI		
B	G	R
0.00	0.40	0.42

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.76068422	
A 2	4.14128906	E-1
A 3	1.33415439	
B 1	8.53607198	E-3
B 2	3.01826383	E-2
B 3	9.80942100	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310	0.050	
320	0.250	
330	0.530	
340	0.720	
350	0.830	
360	0.890	
365		
370	0.934	
380	0.957	
390	0.971	
400	0.979	
420	0.987	
440	0.991	
460	0.993	
480	0.996	
500	0.997	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.996	
1800	0.989	
2000	0.968	
2200	0.916	
2400	0.720	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	648
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	677
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	691
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	720
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	745
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		61
(10-7 / $^{\circ}\text{C}$ )		75
Thermal Conductivity (W/m·K)	<b>k</b>	0.856

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1223
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	471
Poisson's Ratio	$\sigma$	0.300
Knoop Hardness	<b>Hk</b>	730 [7]
Abrasion	<b>Aa</b>	58
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.27

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80} / \lambda_{70}$	380				
Specific Gravity	<b>d</b>	4.46		$\lambda_5$	310				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6} / ^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.6	4.2	4.3	4.4	4.7	5.2	5.8		
-20 ~ 0	3.5	4.2	4.2	4.4	4.7	5.3	5.9		
0 ~ 20	3.5	4.2	4.2	4.4	4.7	5.3	5.9		
20 ~ 40	3.5	4.2	4.2	4.4	4.7	5.3	6.0		
40 ~ 60	3.5	4.3	4.3	4.5	4.8	5.5	6.1		
60 ~ 80	3.7	4.4	4.5	4.7	5.0	5.7	6.4		



Refractive Index	$n_d$	<b>1.77250</b>	Abbe Number	$V_d$	<b>49.60</b>	Dispersion	$n_F - n_C$	<b>0.01557</b>
		1.772499			$V_e$		49.36	
	$n_e$	1.776208					$n_{F'} - n_{C'}$	0.015727

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.73031
$n_{1970}$	1.97009	1.73786
$n_{1530}$	1.52958	1.74590
$n_{1129}$	1.12864	1.75303
$n_t$	1.01398	1.75541
$n_s$	0.85211	1.75960
$n_{A'}$	0.76819	1.76248
$n_r$	0.70652	1.76514
$n_c$	0.65627	<b>1.76780</b>
$n_{c'}$	0.64385	1.76854
$n_{\text{He-Ne}}$	0.6328	1.76924
$n_D$	0.58929	1.77236
$n_d$	0.58756	<b>1.77250</b>
$n_e$	0.54607	1.77621
$n_F$	0.48613	<b>1.78337</b>
$n_{F'}$	0.47999	1.78427
$n_{\text{He-Cd}}$	0.44157	1.79083
$n_g$	0.435835	<b>1.79197</b>
$n_h$	0.404656	1.79917
$n_i$	0.365015	1.81158
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	641
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	660
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	686
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	706
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	726
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	62
	(+100~+300 $^{\circ}\text{C}$ )	74
Thermal Conductivity (W/m·K)	<b>k</b>	0.845

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1219
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	472
Poisson's Ratio	$\sigma$	0.291
Knoop Hardness	<b>Hk</b>	700 [7]
Abrasion	<b>Aa</b>	65
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.43

Partial Dispersions	
$n_c - n_t$	0.012391
$n_c - n_{A'}$	0.005314
$n_d - n_c$	0.004701
$n_e - n_c$	0.008410
$n_g - n_d$	0.019473
$n_g - n_F$	0.008598
$n_h - n_g$	0.007202
$n_i - n_g$	0.019610
$n_{c'} - n_t$	0.013137
$n_e - n_{c'}$	0.007664
$n_{F'} - n_e$	0.008063
$n_i - n_{F'}$	0.027311

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0161
$\Delta\theta_{c,A'}$	0.0052
$\Delta\theta_{g,d}$	-0.0115
$\Delta\theta_{g,F}$	-0.0092
$\Delta\theta_{i,g}$	-0.0507

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.39280586	
A 2	6.79577094	E-1
A 3	1.38702069	
B 1	6.08475118	E-3
B 2	2.33925351	E-2
B 3	9.58354094	E1
1129 ~ 2325 nm		
A 1	1.39280586	
A 2	6.79577094	E-1
A 3	1.38702069	
B 1	6.08475118	E-3
B 2	2.33925351	E-2
B 3	9.58354094	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7955
$\theta_{c,A'}$	0.3412
$\theta_{d,c}$	0.3018
$\theta_{e,c}$	0.5399
$\theta_{g,d}$	1.2502
$\theta_{g,F}$	0.5520
$\theta_{h,g}$	0.4624
$\theta_{i,g}$	1.2590
$\theta'_{c,t}$	0.8353
$\theta'_{e,c'}$	0.4873
$\theta'_{F',e}$	0.5127
$\theta'_{i,F'}$	1.7366

Internal Transmittance			
$\lambda_{80}$	349	$\lambda_5$	308

CCI		
B	G	R
0.00	0.44	0.42

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.100	
320	0.330	
330	0.550	
340	0.710	
350	0.810	
360	0.880	
365		
370	0.930	
380	0.956	
390	0.971	
400	0.979	
420	0.987	
440	0.991	
460	0.994	
480	0.996	
500	0.997	
550	0.999	
600	0.998	
650	0.998	
700	0.999	
800	0.998	
900	0.998	
1000	0.998	
1200	0.997	
1400	0.993	
1600	0.993	
1800	0.983	
2000	0.958	
2200	0.880	
2400	0.640	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	4.23		$\lambda_5$	305				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.4	3.8	3.8	4.0	4.2	4.7	5.1		
-20 ~ 0	3.5	3.9	4.0	4.2	4.4	4.8	5.3		
0 ~ 20	3.6	4.1	4.1	4.3	4.5	5.0	5.5		
20 ~ 40	3.7	4.2	4.3	4.5	4.7	5.2	5.7		
40 ~ 60	3.8	4.4	4.4	4.7	4.9	5.4	5.9		
60 ~ 80	3.9	4.5	4.6	4.8	5.0	5.6	6.1		

Refractive Index	$n_d$	<b>1.85026</b>	Abbe Number	$V_d$	<b>32.27</b>	Dispersion	$n_F - n_C$	<b>0.02634</b>
	$n_e$	1.850259		$V_e$	32.00		$n_{F'} - n_{C'}$	0.026349
		1.856493						0.026744

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.80095
$n_{1970}$	1.97009	1.80685
$n_{1530}$	1.52958	1.81380
$n_{1129}$	1.12864	1.82133
$n_t$	1.01398	1.82429
$n_s$	0.85211	1.83004
$n_{A'}$	0.76819	1.83430
$n_r$	0.70652	1.83838
$n_c$	0.65627	<b>1.84259</b>
$n_{c'}$	0.64385	1.84378
$n_{\text{He-Ne}}$	0.6328	1.84491
$n_D$	0.58929	1.85003
$n_d$	0.58756	<b>1.85026</b>
$n_e$	0.54607	1.85649
$n_F$	0.48613	<b>1.86894</b>
$n_{F'}$	0.47999	1.87053
$n_{\text{He-Cd}}$	0.44157	1.88243
$n_g$	0.435835	<b>1.88456</b>
$n_h$	0.404656	1.89827
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.018292
$n_c - n_{A'}$	0.008288
$n_d - n_c$	0.007673
$n_e - n_c$	0.013907
$n_g - n_d$	0.034299
$n_g - n_F$	0.015623
$n_h - n_g$	0.013716
$n_i - n_g$	
$n_{c'} - n_t$	0.019490
$n_e - n_{c'}$	0.012709
$n_{F'} - n_e$	0.014035
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6942
$\theta_{c,A'}$	0.3145
$\theta_{d,c}$	0.2912
$\theta_{e,c}$	0.5278
$\theta_{g,d}$	1.3017
$\theta_{g,F}$	0.5929
$\theta_{h,g}$	0.5206
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7288
$\theta'_{e,c'}$	0.4752
$\theta'_{F',e}$	0.5248
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0039
$\Delta\theta_{c,A'}$	-0.0005
$\Delta\theta_{g,d}$	0.0040
$\Delta\theta_{g,F}$	0.0036
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	417	$\lambda_5$	364

CCI		
B	G	R
0.00	6.64	6.89

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.98280031	
A 2	3.16758450	E-1
A 3	2.44472646	
B 1	1.18987459	E-2
B 2	5.27156001	E-2
B 3	2.13220697	E2
1129 ~ 2325 nm		
A 1	1.98280031	
A 2	3.16758450	E-1
A 3	2.44472646	
B 1	1.18987459	E-2
B 2	5.27156001	E-2
B 3	2.13220697	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.010	
365		
370	0.110	
380	0.290	
390	0.490	
400	0.650	
420	0.830	
440	0.913	
460	0.945	
480	0.963	
500	0.976	
550	0.992	
600	0.995	
650	0.995	
700	0.997	
800	0.998	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.998	
1800	0.993	
2000	0.989	
2200	0.982	
2400	0.959	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	656
Annealing Point (°C)	<b>AP</b>	685
Transformation Temperature (°C)	<b>Tg</b>	707
Yield Point (°C)	<b>At</b>	752
Softening Point (°C)	<b>SP</b>	802
Expansion Coefficient $\alpha$ (-30~+70°C)		77
Expansion Coefficient $\alpha$ (+10~+300°C)		91
Thermal Conductivity (W/m·K)	<b>k</b>	0.874

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	2.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1100
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	429
Poisson's Ratio	$\sigma$	0.281
Knoop Hardness	<b>Hk</b>	590 [6]
Abrasion	<b>Aa</b>	140
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.52

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					425
Specific Gravity	<b>d</b>	4.36		$\lambda_5$					
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.9	2.9	2.9	3.3	3.7	4.7	5.8		
-20 ~ 0	2.0	3.0	3.0	3.4	3.8	4.9	6.0		
0 ~ 20	2.0	3.0	3.1	3.5	3.9	5.0	6.3		
20 ~ 40	2.0	3.1	3.2	3.6	4.1	5.2	6.5		
40 ~ 60	2.0	3.2	3.3	3.7	4.2	5.4	6.8		
60 ~ 80	2.1	3.3	3.4	3.8	4.3	5.6	7.0		

Refractive Index	$n_d$	<b>2.00330</b>	Abbe Number	$V_d$	<b>28.27</b>	Dispersion	$n_F - n_C$	<b>0.03549</b>
	$n_e$	2.003300		$V_e$	28.07		$n_F' - n_C'$	0.035486
		2.011689						0.036041

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.93904
$n_{1970}$	1.97009	1.94642
$n_{1530}$	1.52958	1.95518
$n_{1129}$	1.12864	1.96486
$n_t$	1.01398	1.96873
$n_s$	0.85211	1.97630
$n_{A'}$	0.76819	1.98195
$n_r$	0.70652	1.98739
$n_c$	0.65627	<b>1.99301</b>
$n_{c'}$	0.64385	1.99461
$n_{\text{He-Ne}}$	0.6328	1.99613
$n_D$	0.58929	2.00299
$n_d$	0.58756	<b>2.00330</b>
$n_e$	0.54607	2.01169
$n_F$	0.48613	<b>2.02850</b>
$n_{F'}$	0.47999	2.03066
$n_{\text{He-Cd}}$	0.44157	2.04682
$n_g$	0.435835	<b>2.04972</b>
$n_h$	0.404656	2.06844
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	699
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	731
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	60
	(+100~+300 $^{\circ}\text{C}$ )	71
Thermal Conductivity (W/m·K)	<b>k</b>	0.957

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1255
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	484
Poisson's Ratio	$\sigma$	0.297
Knoop Hardness	<b>Hk</b>	700 [7]
Abrasion	<b>Aa</b>	61
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.89

Partial Dispersions	
$n_c - n_t$	0.024281
$n_c - n_{A'}$	0.011059
$n_d - n_c$	0.010289
$n_e - n_c$	0.018678
$n_g - n_d$	0.046416
$n_g - n_F$	0.021219
$n_h - n_g$	0.018725
$n_i - n_g$	
$n_{c'} - n_t$	0.025885
$n_e - n_{c'}$	0.017074
$n_{F'} - n_e$	0.018967
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0049
$\Delta\theta_{c,A'}$	0.0015
$\Delta\theta_{g,d}$	0.0020
$\Delta\theta_{g,F}$	0.0023
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.32557148	
A 2	5.07967133	E-1
A 3	2.43087198	
B 1	1.32895208	E-2
B 2	5.28335449	E-2
B 3	1.61122408	E2
1129 ~ 2325 nm		
A 1	2.32557148	
A 2	5.07967133	E-1
A 3	2.43087198	
B 1	1.32895208	E-2
B 2	5.28335449	E-2
B 3	1.61122408	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.6842
$\theta_{c,A'}$	0.3116
$\theta_{d,c}$	0.2899
$\theta_{e,c}$	0.5263
$\theta_{g,d}$	1.3080
$\theta_{g,F}$	0.5980
$\theta_{h,g}$	0.5277
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7182
$\theta'_{e,c'}$	0.4737
$\theta'_{F',e}$	0.5263
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	435	$\lambda_5$	371

CCI		
B	G	R
0.00	10.86	11.57

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.030	
380	0.160	
390	0.330	
400	0.500	
420	0.720	
440	0.830	
460	0.880	
480	0.921	
500	0.945	
550	0.979	
600	0.988	
650	0.991	
700	0.993	
800	0.996	
900	0.997	
1000	0.997	
1200	0.998	
1400	0.998	
1600	0.997	
1800	0.994	
2000	0.986	
2200	0.966	
2400	0.890	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					
Specific Gravity	<b>d</b>	5.23		$\lambda_5$		37			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	6.5	8.0	8.1	8.6	9.2	10.7	12.4		
-20 ~ 0	6.7	8.2	8.3	8.9	9.5	11.1	12.9		
0 ~ 20	6.9	8.5	8.6	9.2	9.8	11.5	13.4		
20 ~ 40	7.0	8.7	8.9	9.4	10.1	11.9	13.8		
40 ~ 60	7.2	9.0	9.1	9.7	10.4	12.2	14.3		
60 ~ 80	7.4	9.2	9.4	10.0	10.7	12.6	14.8		

Refractive Index	$n_d$	<b>1.91650</b>	Abbe Number	$V_d$	<b>31.60</b>	Dispersion	$n_F - n_C$	<b>0.02900</b>
		1.916500			$V_e$		31.38	
	$n_e$	1.923361					$n_{F'} - n_{C'}$	0.029426

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.85814
$n_{1970}$	1.97009	1.86607
$n_{1530}$	1.52958	1.87503
$n_{1129}$	1.12864	1.88413
$n_t$	1.01398	1.88756
$n_s$	0.85211	1.89408
$n_{A'}$	0.76819	1.89884
$n_r$	0.70652	1.90338
$n_c$	0.65627	<b>1.90804</b>
$n_{c'}$	0.64385	1.90936
$n_{\text{He-Ne}}$	0.6328	1.91060
$n_D$	0.58929	1.91625
$n_d$	0.58756	<b>1.91650</b>
$n_e$	0.54607	1.92336
$n_F$	0.48613	<b>1.93703</b>
$n_{F'}$	0.47999	1.93878
$n_{\text{He-Cd}}$	0.44157	1.95185
$n_g$	0.435835	<b>1.95418</b>
$n_h$	0.404656	1.96921
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.020471
$n_c - n_{A'}$	0.009192
$n_d - n_c$	0.008465
$n_e - n_c$	0.015326
$n_g - n_d$	0.037676
$n_g - n_F$	0.017142
$n_h - n_g$	0.015029
$n_i - n_g$	
$n_{c'} - n_t$	0.021794
$n_e - n_{c'}$	0.014003
$n_{F'} - n_e$	0.015423
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.7059
$\theta_{c,A'}$	0.3170
$\theta_{d,c}$	0.2919
$\theta_{e,c}$	0.5285
$\theta_{g,d}$	1.2992
$\theta_{g,F}$	0.5911
$\theta_{h,g}$	0.5183
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7406
$\theta'_{e,c'}$	0.4759
$\theta'_{F',e}$	0.5241
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0110
$\Delta\theta_{c,A'}$	0.0029
$\Delta\theta_{g,d}$	0.0001
$\Delta\theta_{g,F}$	0.0008
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	389	$\lambda_5$	353

CCI		
B	G	R
0.00	2.51	2.67

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.12844340	E0
A 2	4.05082139	E-1
A 3	1.67918461	E0
B 1	1.17309815	E-2
B 2	5.08706599	E-2
B 3	1.07091456	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.010	
360	0.160	
365		
370	0.450	
380	0.680	
390	0.810	
400	0.870	
420	0.936	
440	0.961	
460	0.973	
480	0.981	
500	0.987	
550	0.994	
600	0.996	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.995	
1600	0.994	
1800	0.985	
2000	0.963	
2200	0.890	
2400	0.710	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	581
Annealing Point (°C)	<b>AP</b>	601
Transformation Temperature (°C)	<b>Tg</b>	616
Yield Point (°C)	<b>At</b>	642
Softening Point (°C)	<b>SP</b>	677
Expansion Coefficient $\alpha$ (-30~+70°C)		57
(10 <sup>-7</sup> /°C)	(+100~+300°C)	71
Thermal Conductivity (W/m·K)	<b>k</b>	0.894

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	3.2
Phosphate Resistance	<b>PR</b>	1.1

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1135
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	457
Poisson's Ratio	$\sigma$	0.242
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	68
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.9

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					400
Specific Gravity	<b>d</b>	4.74		$\lambda_5$					355
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.3	6.4	6.5	6.8	7.3	8.5	9.7		
-20 ~ 0	5.4	6.6	6.6	7.0	7.5	8.7	10.1		
0 ~ 20	5.4	6.7	6.8	7.2	7.7	9.0	10.4		
20 ~ 40	5.5	6.8	6.9	7.3	7.8	9.1	10.6		
40 ~ 60	5.6	6.9	7.0	7.4	8.0	9.4	10.9		
60 ~ 80	5.8	7.1	7.2	7.7	8.3	9.7	11.3		

Refractive Index	$n_d$	<b>1.85150</b>	Abbe Number	$V_d$	<b>40.78</b>	Dispersion	$n_F - n_C$	<b>0.02088</b>
	$n_e$	1.851500		$V_e$	40.53		$n_{F'} - n_{C'}$	0.020880
		1.856460						0.021134

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.80561
$n_{1970}$	1.97009	1.81233
$n_{1530}$	1.52958	1.81983
$n_{1129}$	1.12864	1.82718
$n_t$	1.01398	1.82987
$n_s$	0.85211	1.83487
$n_{A'}$	0.76819	1.83847
$n_r$	0.70652	1.84186
$n_c$	0.65627	<b>1.84530</b>
$n_{c'}$	0.64385	1.84628
$n_{\text{He-Ne}}$	0.6328	1.84719
$n_D$	0.58929	1.85132
$n_d$	0.58756	<b>1.85150</b>
$n_e$	0.54607	1.85646
$n_F$	0.48613	<b>1.86618</b>
$n_{F'}$	0.47999	1.86741
$n_{\text{He-Cd}}$	0.44157	1.87648
$n_g$	0.435835	<b>1.87808</b>
$n_h$	0.404656	1.88822
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	634
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	660
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	669
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	702
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	743
Expansion Coefficient ( $\alpha$ )		68
	( $-30^{\circ}\sim+70^{\circ}\text{C}$ )	
	( $+100^{\circ}\sim+300^{\circ}\text{C}$ )	80
Thermal Conductivity (W/m·K)	<b>k</b>	0.861

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1208
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	463
Poisson's Ratio	$\sigma$	0.303
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	70
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.27

Partial Dispersions	
$n_c - n_t$	0.015434
$n_c - n_{A'}$	0.006834
$n_d - n_c$	0.006196
$n_e - n_c$	0.011156
$n_g - n_d$	0.026575
$n_g - n_F$	0.011891
$n_h - n_g$	0.010143
$n_i - n_g$	
$n_{c'} - n_t$	0.016409
$n_e - n_{c'}$	0.010181
$n_{F'} - n_e$	0.010953
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0012
$\Delta\theta_{c,A'}$	0.0020
$\Delta\theta_{g,d}$	-0.0073
$\Delta\theta_{g,F}$	-0.0060
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.95118827	
A 2	3.77607223	E-1
A 3	1.47757262	
B 1	9.76560799	E-3
B 2	3.82232043	E-2
B 3	1.12236720	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7392
$\theta_{c,A'}$	0.3273
$\theta_{d,c}$	0.2967
$\theta_{e,c}$	0.5343
$\theta_{g,d}$	1.2727
$\theta_{g,F}$	0.5695
$\theta_{h,g}$	0.4858
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7764
$\theta'_{e,c'}$	0.4817
$\theta'_{F',e}$	0.5183
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	376	$\lambda_5$	339

CCI		
B	G	R
0.00	1.47	1.52

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.070	
350	0.310	
360	0.570	
365		
370	0.740	
380	0.840	
390	0.890	
400	0.930	
420	0.962	
440	0.975	
460	0.983	
480	0.989	
500	0.993	
550	0.998	
600	0.999	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.992	
2000	0.975	
2200	0.938	
2400	0.780	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					380
Specific Gravity	<b>d</b>	4.70		$\lambda_5$					340
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.0	4.9	4.9	5.2	5.5	6.3	7.1		
-20 ~ 0	4.0	4.9	5.0	5.2	5.6	6.4	7.2		
0 ~ 20	4.0	4.9	5.0	5.3	5.7	6.5	7.4		
20 ~ 40	4.0	5.0	5.0	5.3	5.7	6.6	7.5		
40 ~ 60	4.1	5.1	5.1	5.4	5.8	6.7	7.6		
60 ~ 80	4.2	5.2	5.3	5.6	6.0	7.0	7.9		

Refractive Index	$n_d$	<b>1.89190</b>	Abbe Number	$V_d$	<b>37.13</b>	Dispersion	$n_F - n_C$	<b>0.02402</b>
		1.891900			$V_e$		36.88	
	$n_e$	1.897597					$n_{F'} - n_{C'}$	0.024337

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.84259
$n_{1970}$	1.97009	1.84927
$n_{1530}$	1.52958	1.85686
$n_{1129}$	1.12864	1.86460
$n_t$	1.01398	1.86752
$n_s$	0.85211	1.87305
$n_{A'}$	0.76819	1.87709
$n_r$	0.70652	1.88091
$n_c$	0.65627	<b>1.88482</b>
$n_{c'}$	0.64385	1.88593
$n_{\text{He-Ne}}$	0.6328	1.88698
$n_D$	0.58929	1.89169
$n_d$	0.58756	<b>1.89190</b>
$n_e$	0.54607	1.89760
$n_F$	0.48613	<b>1.90884</b>
$n_{F'}$	0.47999	1.91027
$n_{\text{He-Cd}}$	0.44157	1.92085
$n_g$	0.435835	<b>1.92273</b>
$n_h$	0.404656	1.93469
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.017302
$n_c - n_{A'}$	0.007739
$n_d - n_c$	0.007076
$n_e - n_c$	0.012773
$n_g - n_d$	0.030827
$n_g - n_F$	0.013884
$n_h - n_g$	0.011965
$n_i - n_g$	
$n_{c'} - n_t$	0.018412
$n_e - n_{c'}$	0.011663
$n_{F'} - n_e$	0.012674
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.7203
$\theta_{c,A'}$	0.3222
$\theta_{d,c}$	0.2946
$\theta_{e,c}$	0.5318
$\theta_{g,d}$	1.2834
$\theta_{g,F}$	0.5780
$\theta_{h,g}$	0.4981
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7565
$\theta'_{e,c'}$	0.4792
$\theta'_{F',e}$	0.5208
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0006
$\Delta\theta_{c,A'}$	0.0013
$\Delta\theta_{g,d}$	-0.0042
$\Delta\theta_{g,F}$	-0.0034
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	390	$\lambda_5$	349

CCI		
B	G	R
0.00	2.55	2.68

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.10440311	
A 2	3.58346161	E-1
A 3	1.63010064	
B 1	1.08531811	E-2
B 2	4.43405920	E-2
B 3	1.23249800	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.080	
360	0.280	
365		
370	0.520	
380	0.690	
390	0.800	
400	0.870	
420	0.936	
440	0.962	
460	0.976	
480	0.984	
500	0.990	
550	0.997	
600	0.998	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.992	
2000	0.977	
2200	0.946	
2400	0.820	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	646
Annealing Point (°C)	<b>AP</b>	678
Transformation Temperature (°C)	<b>Tg</b>	689
Yield Point (°C)	<b>At</b>	730
Softening Point (°C)	<b>SP</b>	761
Expansion Coefficient $\alpha$ (-30~+70°C)		75
(10 <sup>-7</sup> /°C)	(+100~+300°C)	87
Thermal Conductivity (W/m·K)	<b>k</b>	0.873

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1230
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	471
Poisson's Ratio	$\sigma$	0.306
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	51
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.12

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					400
Specific Gravity	<b>d</b>	4.87		$\lambda_5$					350
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.8	4.7	4.8	5.1	5.5	6.4	7.4		
-20 ~ 0	3.7	4.7	4.8	5.1	5.5	6.5	7.5		
0 ~ 20	3.7	4.8	4.8	5.1	5.6	6.6	7.7		
20 ~ 40	3.7	4.8	4.8	5.2	5.6	6.7	7.8		
40 ~ 60	3.7	4.9	4.9	5.3	5.7	6.8	8.0		
60 ~ 80	3.9	5.1	5.2	5.5	6.0	7.1	8.4		



Refractive Index	$n_d$	<b>1.90525</b>	Abbe Number	$V_d$	<b>35.04</b>	Dispersion	$n_F - n_C$	<b>0.02583</b>
	$n_e$	1.905250		$V_e$	34.79		$n_{F'} - n_{C'}$	0.025838
		1.911372						0.026200

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.85401
$n_{1970}$	1.97009	1.86068
$n_{1530}$	1.52958	1.86834
$n_{1129}$	1.12864	1.87630
$n_t$	1.01398	1.87935
$n_s$	0.85211	1.88517
$n_{A'}$	0.76819	1.88944
$n_r$	0.70652	1.89350
$n_c$	0.65627	<b>1.89768</b>
$n_{c'}$	0.64385	1.89886
$n_{\text{He-Ne}}$	0.6328	1.89998
$n_D$	0.58929	1.90502
$n_d$	0.58756	<b>1.90525</b>
$n_e$	0.54607	1.91137
$n_F$	0.48613	<b>1.92351</b>
$n_{F'}$	0.47999	1.92506
$n_{\text{He-Cd}}$	0.44157	1.93658
$n_g$	0.435835	<b>1.93862</b>
$n_h$	0.404656	1.95176
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	645
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	672
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	677
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	716
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	761
Expansion Coefficient ( $10^{-7}/^{\circ}\text{C}$ )	$\alpha$	70 (-30~+70 $^{\circ}\text{C}$ ) 86 (+100~+300 $^{\circ}\text{C}$ )
Thermal Conductivity (W/m·K)	<b>k</b>	0.892

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1247
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	478
Poisson's Ratio	$\sigma$	0.304
Knoop Hardness	<b>Hk</b>	680 [7]
Abrasion	<b>Aa</b>	51
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.1

Partial Dispersions	
$n_c - n_t$	0.018330
$n_c - n_{A'}$	0.008240
$n_d - n_c$	0.007573
$n_e - n_c$	0.013695
$n_g - n_d$	0.033374
$n_g - n_F$	0.015109
$n_h - n_g$	0.013137
$n_i - n_g$	
$n_{c'} - n_t$	0.019516
$n_e - n_{c'}$	0.012509
$n_{F'} - n_e$	0.013691
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0017
$\Delta\theta_{c,A'}$	0.0006
$\Delta\theta_{g,d}$	-0.0002
$\Delta\theta_{g,F}$	0.0000
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.17884378	E0
A 2	3.25508683	E-1
A 3	1.70608646	E0
B 1	1.15760879	E-2
B 2	4.95982503	E-2
B 3	1.28913580	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7094
$\theta_{c,A'}$	0.3189
$\theta_{d,c}$	0.2931
$\theta_{e,c}$	0.5300
$\theta_{g,d}$	1.2917
$\theta_{g,F}$	0.5848
$\theta_{h,g}$	0.5084
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7449
$\theta'_{e,c'}$	0.4774
$\theta'_{F',e}$	0.5226
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.220	
365		
370	0.480	
380	0.650	
390	0.750	
400	0.820	
420	0.901	
440	0.938	
460	0.959	
480	0.974	
500	0.984	
550	0.996	
600	0.998	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.998	
1800	0.993	
2000	0.979	
2200	0.952	
2400	0.840	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					410
Specific Gravity	<b>d</b>	4.83		$\lambda_5$					355
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.9	5.0	5.0	5.4	5.8	6.8	7.9		
-20 ~ 0	3.9	5.0	5.1	5.4	5.9	6.9	8.2		
0 ~ 20	3.9	5.1	5.2	5.5	6.0	7.1	8.4		
20 ~ 40	3.9	5.1	5.2	5.5	6.0	7.2	8.5		
40 ~ 60	4.0	5.2	5.3	5.7	6.2	7.4	8.8		
60 ~ 80	4.2	5.5	5.6	6.0	6.5	7.7	9.2		

Refractive Index	$n_d$	<b>1.90366</b>	Abbe Number	$V_d$	<b>31.34</b>	Dispersion	$n_F - n_C$	<b>0.02883</b>
	$n_e$	1.903660		$V_e$	31.10		$n_{F'} - n_{C'}$	0.028832
		1.910476						0.029272

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.84825
$n_{1970}$	1.97009	1.85530
$n_{1530}$	1.52958	1.86342
$n_{1129}$	1.12864	1.87194
$n_t$	1.01398	1.87523
$n_s$	0.85211	1.88155
$n_{A'}$	0.76819	1.88622
$n_r$	0.70652	1.89068
$n_C$	0.65627	<b>1.89528</b>
$n_{C'}$	0.64385	1.89659
$n_{\text{He-Ne}}$	0.6328	1.89782
$n_D$	0.58929	1.90341
$n_d$	0.58756	<b>1.90366</b>
$n_e$	0.54607	1.91048
$n_F$	0.48613	<b>1.92411</b>
$n_{F'}$	0.47999	1.92586
$n_{\text{He-Cd}}$	0.44157	1.93896
$n_g$	0.435835	<b>1.94130</b>
$n_h$	0.404656	1.95648
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	615
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	638
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	649
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	684
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	713
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	73
	(+100~+300 $^{\circ}\text{C}$ )	87
Thermal Conductivity (W/m·K)	<b>k</b>	0.861

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1177
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	452
Poisson's Ratio	$\sigma$	0.302
Knoop Hardness	<b>Hk</b>	630 [6]
Abrasion	<b>Aa</b>	87
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.43

Partial Dispersions	
$n_C - n_t$	0.020047
$n_C - n_{A'}$	0.009057
$n_d - n_C$	0.008383
$n_e - n_C$	0.015199
$n_g - n_d$	0.037641
$n_g - n_F$	0.017192
$n_h - n_g$	0.015178
$n_i - n_g$	
$n_{C'} - n_t$	0.021356
$n_e - n_{C'}$	0.013890
$n_{F'} - n_e$	0.015382
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0016
$\Delta\theta_{C,A'}$	0.0003
$\Delta\theta_{g,d}$	0.0059
$\Delta\theta_{g,F}$	0.0055
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.15636617	E0
A 2	3.29558178	E-1
A 3	1.72178935	E0
B 1	1.22880510	E-2
B 2	5.55507835	E-2
B 3	1.24439340	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6953
$\theta_{C,A'}$	0.3141
$\theta_{d,C}$	0.2908
$\theta_{e,C}$	0.5272
$\theta_{g,d}$	1.3055
$\theta_{g,F}$	0.5963
$\theta_{h,g}$	0.5264
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7296
$\theta'_{e,C'}$	0.4745
$\theta'_{F',e}$	0.5255
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.060	
365		
370	0.310	
380	0.560	
390	0.710	
400	0.800	
420	0.890	
440	0.934	
460	0.956	
480	0.970	
500	0.980	
550	0.992	
600	0.995	
650	0.996	
700	0.997	
800	0.998	
900	0.998	
1000	0.998	
1200	0.999	
1400	0.997	
1600	0.995	
1800	0.988	
2000	0.972	
2200	0.933	
2400	0.810	

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$					410
Specific Gravity	<b>d</b>	4.64		$\lambda_5$					360
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.9	4.0	4.0	4.4	4.9	6.1	7.3		
-20 ~ 0	2.9	4.1	4.2	4.6	5.1	6.3	7.7		
0 ~ 20	3.0	4.2	4.3	4.7	5.2	6.5	8.0		
20 ~ 40	3.0	4.3	4.4	4.8	5.3	6.7	8.2		
40 ~ 60	3.1	4.4	4.5	5.0	5.5	7.0	8.6		
60 ~ 80	3.3	4.7	4.8	5.2	5.8	7.3	9.0		

Refractive Index	$n_d$	<b>1.76385</b>	Abbe Number	$V_d$	<b>48.49</b>	Dispersion	$n_F - n_C$	<b>0.01575</b>
	$n_e$	1.763850		$V_e$	48.21		$n_{F'} - n_{C'}$	0.015753
		1.767599						0.015923

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.72543
$n_{1970}$	1.97009	1.73168
$n_{1530}$	1.52958	1.73848
$n_{1129}$	1.12864	1.74481
$n_t$	1.01398	1.74702
$n_s$	0.85211	1.75103
$n_{A'}$	0.76819	1.75385
$n_r$	0.70652	1.75648
$n_c$	0.65627	<b>1.75913</b>
$n_{c'}$	0.64385	1.75988
$n_{\text{He-Ne}}$	0.6328	1.76058
$n_D$	0.58929	1.76371
$n_d$	0.58756	<b>1.76385</b>
$n_e$	0.54607	1.76760
$n_F$	0.48613	<b>1.77488</b>
$n_{F'}$	0.47999	1.77580
$n_{\text{He-Cd}}$	0.44157	1.78251
$n_g$	0.435835	<b>1.78369</b>
$n_h$	0.404656	1.79112
$n_i$	0.365015	1.80405
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.012108
$n_c - n_{A'}$	0.005277
$n_d - n_c$	0.004721
$n_e - n_c$	0.008470
$n_g - n_d$	0.019837
$n_g - n_F$	0.008805
$n_h - n_g$	0.007429
$n_i - n_g$	0.020364
$n_{c'} - n_t$	0.012854
$n_e - n_{c'}$	0.007724
$n_{F'} - n_e$	0.008199
$n_i - n_{F'}$	0.028253

Relative Partial Dispersions	
$\theta_{c,t}$	0.7686
$\theta_{c,A'}$	0.3350
$\theta_{d,c}$	0.2997
$\theta_{e,c}$	0.5377
$\theta_{g,d}$	1.2593
$\theta_{g,F}$	0.5589
$\theta_{h,g}$	0.4716
$\theta_{i,g}$	1.2927
$\theta'_{c,t}$	0.8073
$\theta'_{e,c'}$	0.4851
$\theta'_{F',e}$	0.5149
$\theta'_{i,F'}$	1.7744

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0056
$\Delta\theta_{c,A'}$	0.0004
$\Delta\theta_{g,d}$	-0.0047
$\Delta\theta_{g,F}$	-0.0041
$\Delta\theta_{i,g}$	-0.0263

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.85078519	E0
A 2	1.89204854	E-1
A 3	1.19763137	E0
B 1	9.40657541	E-3
B 2	3.80345187	E-2
B 3	1.01426835	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.020	
350	0.190	
360	0.480	
365		
370	0.710	
380	0.830	
390	0.905	
400	0.941	
420	0.972	
440	0.982	
460	0.988	
480	0.992	
500	0.994	
550	0.996	
600	0.996	
650	0.996	
700	0.997	
800	0.997	
900	0.996	
1000	0.996	
1200	0.997	
1400	0.995	
1600	0.995	
1800	0.989	
2000	0.972	
2200	0.930	
2400	0.760	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	629
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	655
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		70
(10-7 / $^{\circ}\text{C}$ )		84
(+100~+300 $^{\circ}\text{C}$ )		
Thermal Conductivity (W/m·K)	<b>k</b>	0.890

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	5.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1187
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	458
Poisson's Ratio	$\sigma$	0.296
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	73
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.12

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	4.54		$\lambda_5$	345				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.6	3.2	3.2	3.4	3.7	4.2	4.7	4.7	
-20 ~ 0	2.5	3.1	3.2	3.3	3.6	4.1	4.7	4.7	
0 ~ 20	2.4	3.1	3.1	3.3	3.5	4.1	4.7	4.7	
20 ~ 40	2.4	3.0	3.1	3.3	3.5	4.1	4.7	4.7	
40 ~ 60	2.4	3.1	3.1	3.3	3.6	4.2	4.8	4.8	
60 ~ 80	2.5	3.2	3.2	3.4	3.7	4.3	5.0	5.0	

Refractive Index	$n_d$	<b>1.75500</b>	Abbe Number	$V_d$	<b>52.32</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.014431
	$n_e$	1.755000		$V_e$	52.08			0.014562

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.71414
$n_{1970}$	1.97009	1.72171
$n_{1530}$	1.52958	1.72970
$n_{1129}$	1.12864	1.73666
$n_t$	1.01398	1.73895
$n_s$	0.85211	1.74293
$n_{A'}$	0.76819	1.74565
$n_r$	0.70652	1.74814
$n_c$	0.65627	<b>1.75063</b>
$n_{c'}$	0.64385	1.75132
$n_{\text{He-Ne}}$	0.6328	1.75197
$n_D$	0.58929	1.75487
$n_d$	0.58756	<b>1.75500</b>
$n_e$	0.54607	1.75844
$n_F$	0.48613	<b>1.76506</b>
$n_{F'}$	0.47999	1.76588
$n_{\text{He-Cd}}$	0.44157	1.77191
$n_g$	0.435835	<b>1.77296</b>
$n_h$	0.404656	1.77954
$n_i$	0.365015	1.79082
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.011678
$n_c - n_{A'}$	0.004974
$n_d - n_c$	0.004373
$n_e - n_c$	0.007813
$n_g - n_d$	0.017958
$n_g - n_F$	0.007900
$n_h - n_g$	0.006585
$n_i - n_g$	0.017860
$n_{c'} - n_t$	0.012373
$n_e - n_{c'}$	0.007118
$n_{F'} - n_e$	0.007444
$n_i - n_{F'}$	0.024934

Relative Partial Dispersions	
$\theta_{c,t}$	0.8092
$\theta_{c,A'}$	0.3447
$\theta_{d,c}$	0.3030
$\theta_{e,c}$	0.5414
$\theta_{g,d}$	1.2444
$\theta_{g,F}$	0.5474
$\theta_{h,g}$	0.4563
$\theta_{i,g}$	1.2376
$\theta'_{c,t}$	0.8497
$\theta'_{e,c'}$	0.4888
$\theta'_{F',e}$	0.5112
$\theta'_{i,F'}$	1.7123

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0170
$\Delta\theta_{c,A'}$	0.0054
$\Delta\theta_{g,d}$	-0.0117
$\Delta\theta_{g,F}$	-0.0094
$\Delta\theta_{i,g}$	-0.0493

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.02730180	
A 2	9.89293564	E-1
A 3	1.25781057	
B 1	1.83406129	E-2
B 2	3.71264195	E-3
B 3	8.78510500	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.280	
290	0.430	
300	0.550	
310	0.650	
320	0.740	
330	0.820	
340	0.880	
350	0.923	
360	0.951	
365		
370	0.969	
380	0.980	
390	0.986	
400	0.990	
420	0.993	
440	0.995	
460	0.997	
480	0.998	
500	0.999	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.995	
1600	0.994	
1800	0.984	
2000	0.956	
2200	0.870	
2400	0.610	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	644
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	670
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	692
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	709
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	721
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		58
(+100~+300 $^{\circ}\text{C}$ )		72
Thermal Conductivity (W/m·K)	<b>k</b>	0.863

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1209
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	467
Poisson's Ratio	$\sigma$	0.295
Knoop Hardness	<b>Hk</b>	730 [7]
Abrasion	<b>Aa</b>	64
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.39

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	355				
Specific Gravity	<b>d</b>	4.17		$\lambda_5$					
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.4	3.8	3.9	4.0	4.2	4.6	5.0		
-20 ~ 0	3.3	3.8	3.9	4.0	4.2	4.6	5.1		
0 ~ 20	3.3	3.9	3.9	4.1	4.3	4.7	5.2		
20 ~ 40	3.4	3.9	4.0	4.1	4.3	4.8	5.3		
40 ~ 60	3.5	4.0	4.1	4.3	4.5	4.9	5.4		
60 ~ 80	3.6	4.2	4.2	4.4	4.6	5.1	5.6		

Refractive Index	$n_d$	<b>1.65160</b> 1.651597	Abbe Number	$V_d$	<b>58.55</b> 58.31	Dispersion	$n_F - n_C$	<b>0.01113</b> 0.011129
		$n_e$		1.654251			$V_e$	58.31

Refractive Indices		
	$\lambda$ (μm)	
$n_{2325}$	2.32542	1.61850
$n_{1970}$	1.97009	1.62479
$n_{1530}$	1.52958	1.63144
$n_{1129}$	1.12864	1.63715
$n_t$	1.01398	1.63900
$n_s$	0.85211	1.64218
$n_{A'}$	0.76819	1.64432
$n_r$	0.70652	1.64627
$n_c$	0.65627	<b>1.64821</b>
$n_{c'}$	0.64385	1.64875
$n_{He-Ne}$	0.6328	1.64925
$n_D$	0.58929	1.65150
$n_d$	0.58756	<b>1.65160</b>
$n_e$	0.54607	1.65425
$n_F$	0.48613	<b>1.65934</b>
$n_{F'}$	0.47999	1.65997
$n_{He-Cd}$	0.44157	1.66457
$n_g$	0.435835	<b>1.66537</b>
$n_h$	0.404656	1.67038
$n_i$	0.365015	1.67892
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009204
$n_c - n_{A'}$	0.003884
$n_d - n_c$	0.003390
$n_e - n_c$	0.006044
$n_g - n_d$	0.013777
$n_g - n_F$	0.006038
$n_h - n_g$	0.005010
$n_i - n_g$	0.013542
$n_{c'} - n_t$	0.009744
$n_e - n_{c'}$	0.005504
$n_{F'} - n_e$	0.005717
$n_i - n_{F'}$	0.018948

Relative Partial Dispersions	
$\theta_{c,t}$	0.8270
$\theta_{c,A'}$	0.3490
$\theta_{d,c}$	0.3046
$\theta_{e,c}$	0.5431
$\theta_{g,d}$	1.2379
$\theta_{g,F}$	0.5425
$\theta_{h,g}$	0.4502
$\theta_{i,g}$	1.2168
$\theta'_{c,t}$	0.8684
$\theta'_{e,c'}$	0.4905
$\theta'_{F',e}$	0.5095
$\theta'_{i,F'}$	1.6886

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0056
$\Delta\theta_{c,A'}$	0.0022
$\Delta\theta_{g,d}$	-0.0052
$\Delta\theta_{g,F}$	-0.0042
$\Delta\theta_{i,g}$	-0.0179

Internal Transmittance			
$\lambda_{80}$	330	$\lambda_5$	277

CCI		
B	G	R
0.00	0.18	0.16

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.16121247	E-1
A 2	7.65948319	E-1
A 3	1.27745023	
B 1	3.95889743	E-3
B 2	1.67547425	E-2
B 3	1.10762706	E2
1129 ~ 2325 nm		
A 1	9.16121247	E-1
A 2	7.65948319	E-1
A 3	1.27745023	
B 1	3.95889743	E-3
B 2	1.67547425	E-2
B 3	1.10762706	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 mm}$	$\tau_{i 25 mm}$
280	0.090	
290	0.220	
300	0.380	
310	0.550	
320	0.690	
330	0.800	
340	0.880	
350	0.929	
360	0.957	
365		
370	0.974	
380	0.984	
390	0.990	
400	0.992	
420	0.994	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.997	
1400	0.991	
1600	0.993	
1800	0.984	
2000	0.968	
2200	0.903	
2400	0.740	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	582
Annealing Point (°C)	<b>AP</b>	603
Transformation Temperature (°C)	<b>Tg</b>	617
Yield Point (°C)	<b>At</b>	658
Softening Point (°C)	<b>SP</b>	694
Expansion Coefficient $\alpha$ (-30~+70°C)		67
(10-7 /°C) (+100~+300°C)		81
Thermal Conductivity (W/m·K)	<b>k</b>	0.825

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	53.0
Phosphate Resistance	<b>PR</b>	4.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	958
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	377
Poisson's Ratio	$\sigma$	0.271
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	136
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.72

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	3.73		$\lambda_5$	275				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.5	1.8	1.8	1.9	2.0	2.3	2.6		
-20 ~ 0	1.5	1.8	1.9	2.0	2.1	2.4	2.7		
0 ~ 20	1.6	1.9	2.0	2.1	2.2	2.5	2.8		
20 ~ 40	1.8	2.0	2.0	2.2	2.3	2.6	3.0		
40 ~ 60	1.8	2.1	2.1	2.3	2.4	2.8	3.1		
60 ~ 80	1.8	2.2	2.2	2.4	2.5	2.9	3.2		

Refractive Index	$n_d$	<b>1.71300</b>	Abbe Number	$V_d$	<b>53.87</b>	Dispersion	$n_F - n_C$	<b>0.01324</b>
		1.712995			$V_e$		53.64	
	$n_e$	1.716150					$n_{F'} - n_{C'}$	0.013352

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.67418
$n_{1970}$	1.97009	1.68155
$n_{1530}$	1.52958	1.68930
$n_{1129}$	1.12864	1.69597
$n_t$	1.01398	1.69813
$n_s$	0.85211	1.70186
$n_{A'}$	0.76819	1.70438
$n_r$	0.70652	1.70669
$n_C$	0.65627	<b>1.70897</b>
$n_{C'}$	0.64385	1.70961
$n_{\text{He-Ne}}$	0.6328	1.71021
$n_D$	0.58929	1.71288
$n_d$	0.58756	<b>1.71300</b>
$n_e$	0.54607	1.71615
$n_F$	0.48613	<b>1.72221</b>
$n_{F'}$	0.47999	1.72297
$n_{\text{He-Cd}}$	0.44157	1.72848
$n_g$	0.435835	<b>1.72943</b>
$n_h$	0.404656	1.73545
$n_i$	0.365015	1.74575
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.010846
$n_C - n_{A'}$	0.004591
$n_d - n_C$	0.004021
$n_e - n_C$	0.007176
$n_g - n_d$	0.016440
$n_g - n_F$	0.007225
$n_h - n_g$	0.006016
$n_i - n_g$	0.016311
$n_{C'} - n_t$	0.011486
$n_{e'} - n_{C'}$	0.006536
$n_{F'} - n_e$	0.006816
$n_i - n_{F'}$	0.022780

Relative Partial Dispersions	
$\theta_{C,t}$	0.8194
$\theta_{C,A'}$	0.3469
$\theta_{d,C}$	0.3038
$\theta_{e,C}$	0.5422
$\theta_{g,d}$	1.2421
$\theta_{g,F}$	0.5459
$\theta_{h,g}$	0.4545
$\theta_{i,g}$	1.2323
$\theta'_{C',t}$	0.8602
$\theta'_{e,C'}$	0.4895
$\theta'_{F',e}$	0.5105
$\theta'_{i,F'}$	1.7061

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0200
$\Delta\theta_{C,A'}$	0.0057
$\Delta\theta_{g,d}$	-0.0107
$\Delta\theta_{g,F}$	-0.0084
$\Delta\theta_{i,g}$	-0.0416

Internal Transmittance			
$\lambda_{80}$	356	$\lambda_5$	295

CCI		
B	G	R
0.00	0.42	0.39

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.30663291	
A 2	5.71377253	E-1
A 3	1.24303605	
B 1	6.11862448	E-3
B 2	2.12721470	E-2
B 3	9.06285686	E1
1129 ~ 2325 nm		
A 1	1.30663291	
A 2	5.71377253	E-1
A 3	1.24303605	
B 1	6.11862448	E-3
B 2	2.12721470	E-2
B 3	9.06285686	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290	0.030	
300	0.070	
310	0.150	
320	0.280	
330	0.440	
340	0.600	
350	0.740	
360	0.840	
365		
370	0.905	
380	0.944	
390	0.965	
400	0.977	
420	0.988	
440	0.991	
460	0.994	
480	0.996	
500	0.997	
550	0.998	
600	0.996	
650	0.997	
700	0.997	
800	0.998	
900	0.997	
1000	0.997	
1200	0.997	
1400	0.991	
1600	0.991	
1800	0.981	
2000	0.955	
2200	0.870	
2400	0.620	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	590
Annealing Point (°C)	<b>AP</b>	617
Transformation Temperature (°C)	<b>Tg</b>	643
Yield Point (°C)	<b>At</b>	668
Softening Point (°C)	<b>SP</b>	698
Expansion Coefficient $\alpha$ (-30~+70°C)		61
(10-7 / °C) (+100~+300°C)		74
Thermal Conductivity (W/m·K)	<b>k</b>	0.894

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.0
Phosphate Resistance	<b>PR</b>	3.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1140
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	442
Poisson's Ratio	$\sigma$	0.289
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	81
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.75

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	375				
Specific Gravity	<b>d</b>	3.79		$\lambda_5$	295				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.3	3.6	3.6	3.8	4.0	4.3	4.7		
-20 ~ 0	3.4	3.7	3.8	3.9	4.1	4.5	4.9		
0 ~ 20	3.5	3.9	3.9	4.0	4.2	4.6	5.0		
20 ~ 40	3.6	4.0	4.0	4.1	4.3	4.8	5.2		
40 ~ 60	3.6	4.1	4.1	4.3	4.5	4.9	5.4		
60 ~ 80	3.7	4.2	4.2	4.4	4.6	5.1	5.5		



Refractive Index	$n_d$	<b>1.69100</b>	Abbe Number	$V_d$	<b>54.82</b>	Dispersion	$n_F - n_C$	<b>0.01260</b>
		1.691002			$V_e$		54.59	
	$n_e$	1.694007					$n_{F'} - n_{C'}$	0.012714

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65343
$n_{1970}$	1.97009	1.66064
$n_{1530}$	1.52958	1.66822
$n_{1129}$	1.12864	1.67470
$n_t$	1.01398	1.67678
$n_s$	0.85211	1.68037
$n_{A'}$	0.76819	1.68279
$n_r$	0.70652	1.68499
$n_c$	0.65627	<b>1.68717</b>
$n_{c'}$	0.64385	1.68778
$n_{\text{He-Ne}}$	0.6328	1.68835
$n_D$	0.58929	1.69089
$n_d$	0.58756	<b>1.69100</b>
$n_e$	0.54607	1.69401
$n_F$	0.48613	<b>1.69977</b>
$n_{F'}$	0.47999	1.70049
$n_{\text{He-Cd}}$	0.44157	1.70573
$n_g$	0.435835	<b>1.70664</b>
$n_h$	0.404656	1.71236
$n_i$	0.365015	1.72212
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010384
$n_c - n_{A'}$	0.004384
$n_d - n_c$	0.003833
$n_e - n_c$	0.006838
$n_g - n_d$	0.015640
$n_g - n_F$	0.006868
$n_h - n_g$	0.005714
$n_i - n_g$	0.015476
$n_{c'} - n_t$	0.010994
$n_{e'} - n_{c'}$	0.006228
$n_{F'} - n_e$	0.006486
$n_i - n_{F'}$	0.021625

Relative Partial Dispersions	
$\theta_{c,t}$	0.8238
$\theta_{c,A'}$	0.3478
$\theta_{d,c}$	0.3041
$\theta_{e,c}$	0.5425
$\theta_{g,d}$	1.2408
$\theta_{g,F}$	0.5449
$\theta_{h,g}$	0.4533
$\theta_{i,g}$	1.2278
$\theta'_{c',t}$	0.8647
$\theta'_{e',c'}$	0.4899
$\theta'_{F',e}$	0.5101
$\theta'_{i',F'}$	1.7009

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0199
$\Delta\theta_{c,A'}$	0.0055
$\Delta\theta_{g,d}$	-0.0101
$\Delta\theta_{g,F}$	-0.0079
$\Delta\theta_{i,g}$	-0.0382

Internal Transmittance			
$\lambda_{80}$	358	$\lambda_5$	301

CCI		
B	G	R
0.00	0.51	0.52

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.16195687	
A 2	6.44860099	E-1
A 3	1.25062221	
B 1	1.59659509	E-2
B 2	5.05502467	E-4
B 3	9.38284169	E1
1129 ~ 2325 nm		
A 1	1.16195687	
A 2	6.44860099	E-1
A 3	1.25062221	
B 1	1.59659509	E-2
B 2	5.05502467	E-4
B 3	9.38284169	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290	0.010	
300	0.040	
310	0.110	
320	0.220	
330	0.380	
340	0.550	
350	0.700	
360	0.820	
365		
370	0.890	
380	0.936	
390	0.960	
400	0.973	
420	0.985	
440	0.988	
460	0.992	
480	0.994	
500	0.995	
550	0.997	
600	0.996	
650	0.997	
700	0.998	
800	0.998	
900	0.997	
1000	0.996	
1200	0.996	
1400	0.992	
1600	0.992	
1800	0.984	
2000	0.963	
2200	0.890	
2400	0.660	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	606
Annealing Point (°C)	<b>AP</b>	630
Transformation Temperature (°C)	<b>Tg</b>	653
Yield Point (°C)	<b>At</b>	679
Softening Point (°C)	<b>SP</b>	707
Expansion Coefficient $\alpha$ (-30~+70°C)		61
(10-7 /°C) (+100~+300°C)		74
Thermal Conductivity (W/m·K)	<b>k</b>	0.895

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.0
Phosphate Resistance	<b>PR</b>	4.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1075
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	418
Poisson's Ratio	$\sigma$	0.287
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	88
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.85

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	375				
Specific Gravity	<b>d</b>	3.63		$\lambda_5$	295				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.4	3.8	3.8	3.9	4.1	4.4	4.8		
-20 ~ 0	3.4	3.8	3.8	4.0	4.1	4.5	4.9		
0 ~ 20	3.5	3.9	3.9	4.0	4.2	4.6	5.0		
20 ~ 40	3.5	3.9	3.9	4.1	4.3	4.7	5.1		
40 ~ 60	3.6	4.0	4.0	4.2	4.3	4.8	5.2		
60 ~ 80	3.7	4.0	4.0	4.2	4.4	4.8	5.3		

Refractive Index	$n_d$	<b>1.72000</b> 1.719995	Abbe Number	$V_d$	<b>50.23</b> 49.98	Dispersion	$n_F - n_C$	<b>0.01433</b> 0.014334
		$n_e$		1.723409			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68159
$n_{1970}$	1.97009	1.68841
$n_{1530}$	1.52958	1.69567
$n_{1129}$	1.12864	1.70213
$n_t$	1.01398	1.70430
$n_s$	0.85211	1.70814
$n_{A'}$	0.76819	1.71079
$n_r$	0.70652	1.71323
$n_c$	0.65627	<b>1.71567</b>
$n_{c'}$	0.64385	1.71636
$n_{\text{He-Ne}}$	0.6328	1.71700
$n_D$	0.58929	1.71987
$n_d$	0.58756	<b>1.72000</b>
$n_e$	0.54607	1.72341
$n_F$	0.48613	<b>1.73000</b>
$n_{F'}$	0.47999	1.73083
$n_{\text{He-Cd}}$	0.44157	1.73686
$n_g$	0.435835	<b>1.73792</b>
$n_h$	0.404656	1.74455
$n_i$	0.365015	1.75597
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.011368
$n_c - n_{A'}$	0.004885
$n_d - n_c$	0.004325
$n_e - n_c$	0.007739
$n_g - n_d$	0.017923
$n_g - n_F$	0.007914
$n_h - n_g$	0.006628
$n_i - n_g$	0.018051
$n_{c'} - n_t$	0.012054
$n_e - n_{c'}$	0.007053
$n_{F'} - n_e$	0.007421
$n_i - n_{F'}$	0.025139

Relative Partial Dispersions	
$\theta_{c,t}$	0.7931
$\theta_{c,A'}$	0.3408
$\theta_{d,c}$	0.3017
$\theta_{e,c}$	0.5399
$\theta_{g,d}$	1.2504
$\theta_{g,F}$	0.5521
$\theta_{h,g}$	0.4624
$\theta_{i,g}$	1.2593
$\theta'_{c,t}$	0.8328
$\theta'_{e,c'}$	0.4873
$\theta'_{F',e}$	0.5127
$\theta'_{i,F'}$	1.7368

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0107
$\Delta\theta_{c,A'}$	0.0040
$\Delta\theta_{g,d}$	-0.0100
$\Delta\theta_{g,F}$	-0.0081
$\Delta\theta_{i,g}$	-0.0451

Internal Transmittance			
$\lambda_{80}$	357	$\lambda_5$	309

CCI		
B	G	R
0.00	0.59	0.60

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.52812575	
A 2	3.67965267	E-1
A 3	1.11751784	
B 1	7.76817644	E-3
B 2	2.72026548	E-2
B 3	8.88697400	E1
1129 ~ 2325 nm		
A 1	1.52812575	
A 2	3.67965267	E-1
A 3	1.11751784	
B 1	7.76817644	E-3
B 2	2.72026548	E-2
B 3	8.88697400	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.070	
320	0.220	
330	0.400	
340	0.580	
350	0.720	
360	0.830	
365		
370	0.890	
380	0.937	
390	0.959	
400	0.972	
420	0.983	
440	0.988	
460	0.991	
480	0.994	
500	0.996	
550	0.998	
600	0.997	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.997	
1600	0.996	
1800	0.990	
2000	0.971	
2200	0.922	
2400	0.710	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	582
Annealing Point (°C)	<b>AP</b>	600
Transformation Temperature (°C)	<b>Tg</b>	624
Yield Point (°C)	<b>At</b>	657
Softening Point (°C)	<b>SP</b>	692
Expansion Coefficient $\alpha$	(-30~+70°C)	61
	(+100~+300°C)	76
Thermal Conductivity (W/m·K)	<b>k</b>	0.850

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	3.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1061
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	410
Poisson's Ratio	$\sigma$	0.294
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	86
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.17

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	3.86		$\lambda_5$	310				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.4	5.0	5.0	5.1	5.4	5.8	6.3		
-20 ~ 0	4.5	5.0	5.1	5.2	5.5	5.9	6.4		
0 ~ 20	4.5	5.1	5.2	5.3	5.5	6.0	6.5		
20 ~ 40	4.6	5.2	5.2	5.4	5.6	6.1	6.7		
40 ~ 60	4.6	5.2	5.3	5.5	5.7	6.3	6.8		
60 ~ 80	4.6	5.3	5.4	5.5	5.8	6.4	6.9		

Refractive Index	$n_d$	<b>1.67790</b>	Abbe Number	$V_d$	<b>55.34</b>	Dispersion	$n_F - n_C$	<b>0.01225</b>
		1.677900			$V_e$		55.08	
	$n_e$	1.680820					$n_{F'} - n_{C'}$	0.012361

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.64414
$n_{1970}$	1.97009	1.65021
$n_{1530}$	1.52958	1.65669
$n_{1129}$	1.12864	1.66242
$n_t$	1.01398	1.66433
$n_s$	0.85211	1.66768
$n_{A'}$	0.76819	1.66998
$n_r$	0.70652	1.67208
$n_c$	0.65627	<b>1.67419</b>
$n_{c'}$	0.64385	1.67478
$n_{\text{He-Ne}}$	0.6328	1.67533
$n_D$	0.58929	1.67779
$n_d$	0.58756	<b>1.67790</b>
$n_e$	0.54607	1.68082
$n_F$	0.48613	<b>1.68644</b>
$n_{F'}$	0.47999	1.68714
$n_{\text{He-Cd}}$	0.44157	1.69225
$n_g$	0.435835	<b>1.69314</b>
$n_h$	0.404656	1.69872
$n_i$	0.365015	1.70826
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009855
$n_c - n_{A'}$	0.004212
$n_d - n_c$	0.003712
$n_e - n_c$	0.006632
$n_g - n_d$	0.015241
$n_g - n_F$	0.006703
$n_h - n_g$	0.005580
$n_i - n_g$	0.015119
$n_{c'} - n_t$	0.010445
$n_e - n_{c'}$	0.006042
$n_{F'} - n_e$	0.006319
$n_i - n_{F'}$	0.021121

Relative Partial Dispersions	
$\theta_{c,t}$	0.8045
$\theta_{c,A'}$	0.3438
$\theta_{d,c}$	0.3030
$\theta_{e,c}$	0.5414
$\theta_{g,d}$	1.2442
$\theta_{g,F}$	0.5472
$\theta_{h,g}$	0.4555
$\theta_{i,g}$	1.2342
$\theta'_{c,t}$	0.8450
$\theta'_{e,c'}$	0.4888
$\theta'_{F',e}$	0.5112
$\theta'_{i,F'}$	1.7087

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0018
$\Delta\theta_{c,A'}$	0.0008
$\Delta\theta_{g,d}$	-0.0056
$\Delta\theta_{g,F}$	-0.0047
$\Delta\theta_{i,g}$	-0.0274

Internal Transmittance			
$\lambda_{80}$	337	$\lambda_5$	279

CCI		
B	G	R
0.00	0.26	0.24

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.92053895	E-1
A 2	7.71377731	E-1
A 3	1.18296264	
B 1	1.67095063	E-2
B 2	2.36750156	E-3
B 3	1.05901080	E2
1129 ~ 2325 nm		
A 1	9.92053895	E-1
A 2	7.71377731	E-1
A 3	1.18296264	
B 1	1.67095063	E-2
B 2	2.36750156	E-3
B 3	1.05901080	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.060	
290	0.150	
300	0.290	
310	0.450	
320	0.610	
330	0.730	
340	0.830	
350	0.890	
360	0.938	
365		
370	0.962	
380	0.976	
390	0.984	
400	0.988	
420	0.992	
440	0.994	
460	0.995	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.997	
1000	0.996	
1200	0.996	
1400	0.991	
1600	0.991	
1800	0.981	
2000	0.963	
2200	0.901	
2400	0.730	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	604
Annealing Point (°C)	<b>AP</b>	630
Transformation Temperature (°C)	<b>Tg</b>	652
Yield Point (°C)	<b>At</b>	679
Softening Point (°C)	<b>SP</b>	716
Expansion Coefficient $\alpha$ (-30~+70°C)		72
(10-7 /°C) (+100~+300°C)		86
Thermal Conductivity (W/m·K)	<b>k</b>	0.717

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	53.0
Phosphate Resistance	<b>PR</b>	4.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	910
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	354
Poisson's Ratio	$\sigma$	0.284
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	166
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.61

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	4.01		$\lambda_5$	285				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.4	0.6	0.7	0.8	0.9	1.2	1.5		
-20 ~ 0	0.5	0.7	0.7	0.8	1.0	1.3	1.7		
0 ~ 20	0.5	0.8	0.8	0.9	1.1	1.4	1.8		
20 ~ 40	0.5	0.8	0.9	1.0	1.1	1.5	1.9		
40 ~ 60	0.5	0.9	0.9	1.1	1.2	1.6	2.0		
60 ~ 80	0.6	1.0	1.0	1.1	1.3	1.7	2.1		

Refractive Index	$n_d$	<b>1.69350</b> 1.693501	Abbe Number	$V_d$	<b>53.21</b> 52.97	Dispersion	$n_F - n_C$	<b>0.01303</b> 0.013034
		$n_e$		1.696607			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65605
$n_{1970}$	1.97009	1.66304
$n_{1530}$	1.52958	1.67044
$n_{1129}$	1.12864	1.67685
$n_t$	1.01398	1.67894
$n_s$	0.85211	1.68258
$n_{A'}$	0.76819	1.68504
$n_r$	0.70652	1.68730
$n_c$	0.65627	<b>1.68955</b>
$n_{c'}$	0.64385	1.69018
$n_{\text{He-Ne}}$	0.6328	1.69076
$n_D$	0.58929	1.69339
$n_d$	0.58756	<b>1.69350</b>
$n_e$	0.54607	1.69661
$n_F$	0.48613	<b>1.70258</b>
$n_{F'}$	0.47999	1.70333
$n_{\text{He-Cd}}$	0.44157	1.70877
$n_g$	0.435835	<b>1.70972</b>
$n_h$	0.404656	1.71566
$n_i$	0.365015	1.72585
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010604
$n_c - n_{A'}$	0.004503
$n_d - n_c$	0.003953
$n_e - n_c$	0.007059
$n_g - n_d$	0.016214
$n_g - n_F$	0.007133
$n_h - n_g$	0.005947
$n_i - n_g$	0.016134
$n_{c'} - n_t$	0.011232
$n_e - n_{c'}$	0.006431
$n_{F'} - n_e$	0.006721
$n_i - n_{F'}$	0.022521

Relative Partial Dispersions	
$\theta_{c,t}$	0.8136
$\theta_{c,A'}$	0.3455
$\theta_{d,c}$	0.3033
$\theta_{e,c}$	0.5416
$\theta_{g,d}$	1.2440
$\theta_{g,F}$	0.5473
$\theta_{h,g}$	0.4563
$\theta_{i,g}$	1.2378
$\theta'_{c,t}$	0.8540
$\theta'_{e,c'}$	0.4890
$\theta'_{F',e}$	0.5110
$\theta'_{i,F'}$	1.7124

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0173
$\Delta\theta_{c,A'}$	0.0051
$\Delta\theta_{g,d}$	-0.0102
$\Delta\theta_{g,F}$	-0.0081
$\Delta\theta_{i,g}$	-0.0417

Internal Transmittance			
$\lambda_{80}$	360	$\lambda_5$	304

CCI		
B	G	R
0.00	0.48	0.42

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.80071267	E-1
A 2	8.32904776	E-1
A 3	1.28111995	
B 1	3.89123698	E-3
B 2	1.89164592	E-2
B 3	9.89052676	E1
1129 ~ 2325 nm		
A 1	9.80071267	E-1
A 2	8.32904776	E-1
A 3	1.28111995	
B 1	3.89123698	E-3
B 2	1.89164592	E-2
B 3	9.89052676	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290	0.010	
300	0.030	
310	0.080	
320	0.190	
330	0.340	
340	0.520	
350	0.680	
360	0.800	
365		
370	0.880	
380	0.932	
390	0.958	
400	0.972	
420	0.986	
440	0.990	
460	0.993	
480	0.995	
500	0.996	
550	0.997	
600	0.995	
650	0.995	
700	0.996	
800	0.997	
900	0.996	
1000	0.995	
1200	0.995	
1400	0.990	
1600	0.990	
1800	0.981	
2000	0.958	
2200	0.880	
2400	0.660	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	591
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	616
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	641
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	666
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	701
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	57
	(+100~+300 $^{\circ}\text{C}$ )	72
Thermal Conductivity (W/m·K)	<b>k</b>	0.893

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	52.0
Phosphate Resistance	<b>PR</b>	3.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1073
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	416
Poisson's Ratio	$\sigma$	0.290
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	87
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.13

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	375				
Specific Gravity	<b>d</b>	3.60		$\lambda_5$	300				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.6	4.8	4.8	4.9	5.1	5.5	5.9		
-20 ~ 0	4.7	4.9	5.0	5.1	5.3	5.7	6.1		
0 ~ 20	4.8	5.1	5.1	5.3	5.5	5.9	6.4		
20 ~ 40	4.9	5.3	5.3	5.5	5.7	6.1	6.6		
40 ~ 60	5.0	5.4	5.5	5.6	5.8	6.3	6.8		
60 ~ 80	5.1	5.6	5.6	5.8	6.0	6.5	7.0		

Refractive Index	$n_d$	<b>1.69680</b> 1.696797	Abbe Number	$V_d$	<b>55.53</b> 55.31	Dispersion	$n_F - n_C$	<b>0.01255</b> 0.012548
		$n_e$		1.699788			$V_e$	55.31

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65820
$n_{1970}$	1.97009	1.66578
$n_{1530}$	1.52958	1.67369
$n_{1129}$	1.12864	1.68039
$n_t$	1.01398	1.68252
$n_s$	0.85211	1.68615
$n_{A'}$	0.76819	1.68858
$n_r$	0.70652	1.69079
$n_c$	0.65627	<b>1.69297</b>
$n_{c'}$	0.64385	1.69358
$n_{\text{He-Ne}}$	0.6328	1.69415
$n_D$	0.58929	1.69669
$n_d$	0.58756	<b>1.69680</b>
$n_e$	0.54607	1.69979
$n_F$	0.48613	<b>1.70552</b>
$n_{F'}$	0.47999	1.70624
$n_{\text{He-Cd}}$	0.44157	1.71144
$n_g$	0.435835	<b>1.71234</b>
$n_h$	0.404656	1.71800
$n_i$	0.365015	1.72767
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010452
$n_c - n_{A'}$	0.004389
$n_d - n_c$	0.003823
$n_e - n_c$	0.006814
$n_g - n_d$	0.015543
$n_g - n_F$	0.006818
$n_h - n_g$	0.005665
$n_i - n_g$	0.015333
$n_{c'} - n_t$	0.011061
$n_e - n_{c'}$	0.006205
$n_{F'} - n_e$	0.006448
$n_i - n_{F'}$	0.021437

Relative Partial Dispersions	
$\theta_{c,t}$	0.8330
$\theta_{c,A'}$	0.3498
$\theta_{d,c}$	0.3047
$\theta_{e,c}$	0.5430
$\theta_{g,d}$	1.2387
$\theta_{g,F}$	0.5434
$\theta_{h,g}$	0.4515
$\theta_{i,g}$	1.2219
$\theta'_{c,t}$	0.8742
$\theta'_{e,c'}$	0.4904
$\theta'_{F',e}$	0.5096
$\theta'_{i,F'}$	1.6942

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0258
$\Delta\theta_{c,A'}$	0.0066
$\Delta\theta_{g,d}$	-0.0107
$\Delta\theta_{g,F}$	-0.0082
$\Delta\theta_{i,g}$	-0.0381

Internal Transmittance			
$\lambda_{80}$	349	$\lambda_5$	285

CCI		
B	G	R
0.00	0.32	0.29

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.23720970	
A 2	5.89722623	E-1
A 3	1.31921880	
B 1	1.53551320	E-2
B 2	-3.07896250	E-4
B 3	9.37202947	E1
1129 ~ 2325 nm		
A 1	1.23720970	
A 2	5.89722623	E-1
A 3	1.31921880	
B 1	1.53551320	E-2
B 2	-3.07896250	E-4
B 3	9.37202947	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.030	
290	0.070	
300	0.150	
310	0.270	
320	0.410	
330	0.560	
340	0.700	
350	0.810	
360	0.880	
365		
370	0.931	
380	0.959	
390	0.974	
400	0.982	
420	0.990	
440	0.993	
460	0.995	
480	0.997	
500	0.998	
550	0.998	
600	0.997	
650	0.997	
700	0.998	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.991	
1600	0.992	
1800	0.982	
2000	0.954	
2200	0.860	
2400	0.590	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	650
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	668
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	700
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		57
(+10~+300 $^{\circ}\text{C}$ )		71
Thermal Conductivity (W/m·K)	<b>k</b>	0.908

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	3.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1118
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	435
Poisson's Ratio	$\sigma$	0.284
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	81
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.86

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	365				
Specific Gravity	<b>d</b>	3.70		$\lambda_5$	285				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.5	3.7	3.8	3.9	4.0	4.2	4.7		
-20 ~ 0	3.4	3.7	3.8	3.9	4.0	4.3	4.7		
0 ~ 20	3.4	3.7	3.8	4.0	4.1	4.4	4.8		
20 ~ 40	3.4	3.8	3.9	4.1	4.2	4.6	4.9		
40 ~ 60	3.5	4.0	4.0	4.2	4.3	4.8	5.1		
60 ~ 80	3.7	4.2	4.2	4.4	4.5	5.0	5.4		

Refractive Index	$n_d$	<b>1.72916</b>	Abbe Number	$V_d$	<b>54.68</b>	Dispersion	$n_F - n_C$	<b>0.01334</b>
	$n_e$	1.729157		$V_e$	54.45		$n_{F'} - n_{C'}$	0.013335
		1.732336					$n_{F'} - n_{C'}$	0.013449

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68936
$n_{1970}$	1.97009	1.69701
$n_{1530}$	1.52958	1.70504
$n_{1129}$	1.12864	1.71190
$n_t$	1.01398	1.71411
$n_s$	0.85211	1.71790
$n_{A'}$	0.76819	1.72046
$n_r$	0.70652	1.72279
$n_c$	0.65627	<b>1.72510</b>
$n_{c'}$	0.64385	1.72575
$n_{\text{He-Ne}}$	0.6328	1.72635
$n_D$	0.58929	1.72904
$n_d$	0.58756	<b>1.72916</b>
$n_e$	0.54607	1.73234
$n_F$	0.48613	<b>1.73844</b>
$n_{F'}$	0.47999	1.73920
$n_{\text{He-Cd}}$	0.44157	1.74473
$n_g$	0.435835	<b>1.74570</b>
$n_h$	0.404656	1.75173
$n_i$	0.365015	1.76203
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	632
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	655
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	685
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	699
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	731
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	59
	(+10~+300 $^{\circ}\text{C}$ )	69
Thermal Conductivity (W/m·K)	<b>k</b>	0.871

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1204
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	467
Poisson's Ratio	$\sigma$	0.289
Knoop Hardness	<b>Hk</b>	720 [7]
Abrasion	<b>Aa</b>	70
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.58

Partial Dispersions	
$n_c - n_t$	0.010994
$n_c - n_{A'}$	0.004641
$n_d - n_c$	0.004056
$n_e - n_c$	0.007235
$n_g - n_d$	0.016539
$n_g - n_F$	0.007260
$n_h - n_g$	0.006035
$n_i - n_g$	0.016335
$n_{c'} - n_t$	0.011640
$n_e - n_{c'}$	0.006589
$n_{F'} - n_e$	0.006860
$n_i - n_{F'}$	0.022835

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0212
$\Delta\theta_{c,A'}$	0.0058
$\Delta\theta_{g,d}$	-0.0109
$\Delta\theta_{g,F}$	-0.0086
$\Delta\theta_{i,g}$	-0.0422

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.50276318	
A 2	4.30224497	E-1
A 3	1.34726060	
B 1	1.45462356	E-2
B 2	-3.32784153	E-3
B 3	9.33508342	E1
1129 ~ 2325 nm		
A 1	1.50276318	
A 2	4.30224497	E-1
A 3	1.34726060	
B 1	1.45462356	E-2
B 2	-3.32784153	E-3
B 3	9.33508342	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8244
$\theta_{c,A'}$	0.3480
$\theta_{d,c}$	0.3042
$\theta_{e,c}$	0.5426
$\theta_{g,d}$	1.2403
$\theta_{g,F}$	0.5444
$\theta_{h,g}$	0.4526
$\theta_{i,g}$	1.2250
$\theta'_{c,t}$	0.8655
$\theta'_{e,c'}$	0.4899
$\theta'_{F',e}$	0.5101
$\theta'_{i,F'}$	1.6979

Internal Transmittance			
$\lambda_{80}$	343	$\lambda_5$	281

CCI		
B	G	R
0.00	0.30	0.31

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280	0.040	
290	0.210	
300	0.300	
310	0.320	
320	0.550	
330	0.680	
340	0.780	
350	0.860	
360	0.912	
365		
370	0.946	
380	0.967	
390	0.978	
400	0.984	
420	0.991	
440	0.994	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.999	
700	0.999	
800	0.998	
900	0.998	
1000	0.997	
1200	0.996	
1400	0.991	
1600	0.991	
1800	0.982	
2000	0.956	
2200	0.870	
2400	0.600	

Other Properties								
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	365			
Specific Gravity	<b>d</b>	4.18		$\lambda_5$	280			
Temperature Coefficients of Refractive Index								
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20		3.8		3.9	4.1	4.5	4.8	
-20 ~ 0		3.8		3.9	4.1	4.5	4.9	
0 ~ 20		3.8		4.0	4.2	4.6	4.9	
20 ~ 40		3.9		4.1	4.3	4.7	5.1	
40 ~ 60		4.0		4.2	4.4	4.9	5.3	
60 ~ 80		4.2		4.4	4.6	5.1	5.5	



Refractive Index	$n_d$	<b>1.72916</b>	Abbe Number	$V_d$	<b>54.09</b>	Dispersion	$n_F - n_C$	<b>0.01348</b>
		1.729160			$V_e$		53.87	
	$n_e$	1.732373					$n_{F'} - n_{C'}$	0.013596

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68912
$n_{1970}$	1.97009	1.69682
$n_{1530}$	1.52958	1.70487
$n_{1129}$	1.12864	1.71175
$n_t$	1.01398	1.71397
$n_s$	0.85211	1.71779
$n_{A'}$	0.76819	1.72038
$n_r$	0.70652	1.72273
$n_c$	0.65627	<b>1.72506</b>
$n_{c'}$	0.64385	1.72571
$n_{\text{He-Ne}}$	0.6328	1.72632
$n_D$	0.58929	1.72904
$n_d$	0.58756	<b>1.72916</b>
$n_e$	0.54607	1.73237
$n_F$	0.48613	<b>1.73854</b>
$n_{F'}$	0.47999	1.73931
$n_{\text{He-Cd}}$	0.44157	1.74491
$n_g$	0.435835	<b>1.74589</b>
$n_h$	0.404656	1.75199
$n_i$	0.365015	1.76243
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.011088
$n_c - n_{A'}$	0.004686
$n_d - n_c$	0.004099
$n_e - n_c$	0.007312
$n_g - n_d$	0.016725
$n_g - n_F$	0.007344
$n_h - n_g$	0.006108
$n_i - n_g$	0.016544
$n_{c'} - n_t$	0.011740
$n_e - n_{c'}$	0.006660
$n_{F'} - n_e$	0.006936
$n_i - n_{F'}$	0.023120

Relative Partial Dispersions	
$\theta_{c,t}$	0.8226
$\theta_{c,A'}$	0.3476
$\theta_{d,c}$	0.3041
$\theta_{e,c}$	0.5424
$\theta_{g,d}$	1.2407
$\theta_{g,F}$	0.5448
$\theta_{h,g}$	0.4531
$\theta_{i,g}$	1.2273
$\theta'_{c,t}$	0.8635
$\theta'_{e,c'}$	0.4898
$\theta'_{F',e}$	0.5102
$\theta'_{i,F'}$	1.7005

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0221
$\Delta\theta_{c,A'}$	0.0062
$\Delta\theta_{g,d}$	-0.0117
$\Delta\theta_{g,F}$	-0.0092
$\Delta\theta_{i,g}$	-0.0448

Internal Transmittance			
$\lambda_{80}$	327	$\lambda_5$	

CCI		
B	G	R
0.00	0.21	0.21

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.73997577	E-1
A 2	9.58186322	E-1
A 3	1.20163359	E0
B 1	3.79332678	E-3
B 2	1.77574581	E-2
B 3	8.37989600	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.290	
290	0.430	
300	0.550	
310	0.660	
320	0.750	
330	0.820	
340	0.880	
350	0.925	
360	0.953	
365		
370	0.970	
380	0.980	
390	0.986	
400	0.990	
420	0.993	
440	0.995	
460	0.997	
480	0.998	
500	0.999	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.993	
1600	0.993	
1800	0.981	
2000	0.951	
2200	0.850	
2400	0.580	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	610
Annealing Point (°C)	<b>AP</b>	634
Transformation Temperature (°C)	<b>Tg</b>	644
Yield Point (°C)	<b>At</b>	672
Softening Point (°C)	<b>SP</b>	708
Expansion Coefficient $\alpha$ (-30~+70°C)		54
(10 <sup>-7</sup> /°C)	(+100~+300°C)	69
Thermal Conductivity (W/m·K)	<b>k</b>	0.895

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.0
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1198
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	463
Poisson's Ratio	$\sigma$	0.295
Knoop Hardness	<b>Hk</b>	720 [7]
Abrasion	<b>Aa</b>	61
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.61

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	355				
Specific Gravity	<b>d</b>	3.98		$\lambda_5$					
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.3	4.7	4.7	4.9	5.0	5.4	5.8		
-20 ~ 0	4.2	4.7	4.7	4.8	5.0	5.4	5.8		
0 ~ 20	4.2	4.7	4.7	4.9	5.0	5.5	5.9		
20 ~ 40	4.2	4.7	4.7	4.9	5.1	5.5	5.9		
40 ~ 60	4.2	4.8	4.8	4.9	5.1	5.6	6.0		
60 ~ 80	4.4	4.9	5.0	5.1	5.3	5.8	6.3		

Refractive Index	$n_d$	<b>1.69930</b>	Abbe Number	$V_d$	<b>51.11</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.013682
		1.699300			$V_e$		50.82	
	$n_e$	1.702559						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.66804
$n_{1970}$	1.97009	1.67270
$n_{1530}$	1.52958	1.67791
$n_{1129}$	1.12864	1.68297
$n_t$	1.01398	1.68481
$n_s$	0.85211	1.68820
$n_{A'}$	0.76819	1.69063
$n_r$	0.70652	1.69290
$n_C$	0.65627	<b>1.69520</b>
$n_{C'}$	0.64385	1.69584
$n_{\text{He-Ne}}$	0.6328	1.69645
$n_D$	0.58929	1.69918
$n_d$	0.58756	<b>1.69930</b>
$n_e$	0.54607	1.70256
$n_F$	0.48613	<b>1.70888</b>
$n_{F'}$	0.47999	1.70967
$n_{\text{He-Cd}}$	0.44157	1.71546
$n_g$	0.435835	<b>1.71647</b>
$n_h$	0.404656	1.72283
$n_i$	0.365015	1.73376
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.010389
$n_C - n_{A'}$	0.004570
$n_d - n_C$	0.004104
$n_e - n_C$	0.007363
$n_g - n_d$	0.017174
$n_g - n_F$	0.007596
$n_h - n_g$	0.006359
$n_i - n_g$	0.017290
$n_{C'} - n_t$	0.011038
$n_e - n_{C'}$	0.006714
$n_{F'} - n_e$	0.007111
$n_i - n_{F'}$	0.024094

Relative Partial Dispersions	
$\theta_{C,t}$	0.7593
$\theta_{C,A'}$	0.3340
$\theta_{d,C}$	0.3000
$\theta_{e,C}$	0.5382
$\theta_{g,d}$	1.2552
$\theta_{g,F}$	0.5552
$\theta_{h,g}$	0.4648
$\theta_{i,g}$	1.2637
$\theta'_{C,t}$	0.7984
$\theta'_{e,C'}$	0.4856
$\theta'_{F',e}$	0.5144
$\theta'_{i,F'}$	1.7428

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.0272
$\Delta\theta_{C,A'}$	-0.0038
$\Delta\theta_{g,d}$	-0.0034
$\Delta\theta_{g,F}$	-0.0036
$\Delta\theta_{i,g}$	-0.0333

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.06788467	
A 2	7.58735350	E-1
A 3	1.02804682	
B 1	5.18896058	E-3
B 2	2.04004357	E-2
B 3	1.20826320	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300	0.010	
310	0.090	
320	0.270	
330	0.490	
340	0.670	
350	0.800	
360	0.880	
365		
370	0.934	
380	0.960	
390	0.974	
400	0.982	
420	0.987	
440	0.987	
460	0.989	
480	0.992	
500	0.994	
550	0.996	
600	0.995	
650	0.994	
700	0.996	
800	0.998	
900	0.997	
1000	0.997	
1200	0.998	
1400	0.997	
1600	0.995	
1800	0.985	
2000	0.969	
2200	0.935	
2400	0.840	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	593
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	621
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	628
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	676
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	717
Expansion Coefficient ( $\alpha$ )		90
	(-30~+70 $^{\circ}\text{C}$ )	
	(+100~+300 $^{\circ}\text{C}$ )	105
Thermal Conductivity (W/m·K)	<b>k</b>	0.602

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	53.1
Phosphate Resistance	<b>PR</b>	4.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	787
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	302
Poisson's Ratio	$\sigma$	0.302
Knoop Hardness	<b>Hk</b>	490 [5]
Abrasion	<b>Aa</b>	243
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.23

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	4.38		$\lambda_5$	310				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.8	-1.3	-1.3	-1.1	-1.0	-0.5	-0.1		
-20 ~ 0	-1.9	-1.4	-1.4	-1.2	-1.0	-0.6	-0.1		
0 ~ 20	-1.9	-1.4	-1.4	-1.2	-1.0	-0.5	-0.1		
20 ~ 40	-2.0	-1.5	-1.4	-1.3	-1.0	-0.6	-0.1		
40 ~ 60	-2.0	-1.4	-1.4	-1.2	-1.0	-0.5	0.0		
60 ~ 80	-1.9	-1.3	-1.3	-1.1	-0.9	-0.4	0.2		

Refractive Index	$n_d$	<b>1.65100</b>	Abbe Number	$V_d$	<b>56.16</b>	Dispersion	$n_F - n_C$	<b>0.01159</b>
		1.650996			$V_e$		55.89	
	$n_e$	1.653758					$n_{F'} - n_{C'}$	0.011697

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.61893
$n_{1970}$	1.97009	1.62472
$n_{1530}$	1.52958	1.63089
$n_{1129}$	1.12864	1.63634
$n_t$	1.01398	1.63815
$n_s$	0.85211	1.64133
$n_{A'}$	0.76819	1.64350
$n_r$	0.70652	1.64549
$n_c$	0.65627	<b>1.64749</b>
$n_{c'}$	0.64385	1.64804
$n_{\text{He-Ne}}$	0.6328	1.64856
$n_D$	0.58929	1.65089
$n_d$	0.58756	<b>1.65100</b>
$n_e$	0.54607	1.65376
$n_F$	0.48613	<b>1.65908</b>
$n_{F'}$	0.47999	1.65974
$n_{\text{He-Cd}}$	0.44157	1.66459
$n_g$	0.435835	<b>1.66543</b>
$n_h$	0.404656	1.67073
$n_i$	0.365015	1.67982
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009330
$n_c - n_{A'}$	0.003985
$n_d - n_c$	0.003511
$n_e - n_c$	0.006273
$n_g - n_d$	0.014434
$n_g - n_F$	0.006354
$n_h - n_g$	0.005299
$n_i - n_g$	0.014389
$n_{c'} - n_t$	0.009888
$n_e - n_{c'}$	0.005715
$n_{F'} - n_e$	0.005982
$n_i - n_{F'}$	0.020079

Relative Partial Dispersions	
$\theta_{c,t}$	0.8049
$\theta_{c,A'}$	0.3438
$\theta_{d,c}$	0.3029
$\theta_{e,c}$	0.5412
$\theta_{g,d}$	1.2453
$\theta_{g,F}$	0.5482
$\theta_{h,g}$	0.4572
$\theta_{i,g}$	1.2414
$\theta'_{c,t}$	0.8453
$\theta'_{e,c'}$	0.4886
$\theta'_{F',e}$	0.5114
$\theta'_{i,F'}$	1.7166

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0053
$\Delta\theta_{c,A'}$	-0.0001
$\Delta\theta_{g,d}$	-0.0028
$\Delta\theta_{g,F}$	-0.0024
$\Delta\theta_{i,g}$	-0.0134

Internal Transmittance			
$\lambda_{80}$	356	$\lambda_5$	327

CCI		
B	G	R
0.00	0.45	0.43

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.41910189	
A 2	2.58416881	E-1
A 3	1.07385537	
B 1	7.26647428	E-3
B 2	2.63842499	E-2
B 3	1.02555463	E2
1129 ~ 2325 nm		
A 1	1.41910189	
A 2	2.58416881	E-1
A 3	1.07385537	
B 1	7.26647428	E-3
B 2	2.63842499	E-2
B 3	1.02555463	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.130	
340	0.440	
350	0.710	
360	0.850	
365		
370	0.919	
380	0.953	
390	0.970	
400	0.980	
420	0.988	
440	0.991	
460	0.993	
480	0.995	
500	0.997	
550	0.999	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.993	
1600	0.993	
1800	0.985	
2000	0.969	
2200	0.913	
2400	0.780	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	604
Annealing Point (°C)	<b>AP</b>	631
Transformation Temperature (°C)	<b>Tg</b>	651
Yield Point (°C)	<b>At</b>	675
Softening Point (°C)	<b>SP</b>	723
Expansion Coefficient $\alpha$ (-30~+70°C)		71
(10-7 /°C) (+100~+300°C)		83
Thermal Conductivity (W/m·K)	<b>k</b>	0.761

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	53.0
Phosphate Resistance	<b>PR</b>	4.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	877
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	343
Poisson's Ratio	$\sigma$	0.277
Knoop Hardness	<b>Hk</b>	530 [5]
Abrasion	<b>Aa</b>	171
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.66

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	365				
Specific Gravity	<b>d</b>	3.82		$\lambda_5$	325				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.6	0.8	0.8	0.9	1.0	1.4	1.7		
-20 ~ 0	0.7	0.9	0.9	1.0	1.2	1.5	1.8		
0 ~ 20	0.7	1.0	1.0	1.1	1.3	1.6	1.9		
20 ~ 40	0.7	1.1	1.1	1.2	1.4	1.7	2.1		
40 ~ 60	0.8	1.2	1.2	1.3	1.5	1.8	2.2		
60 ~ 80	0.9	1.3	1.3	1.4	1.6	2.0	2.4		

Refractive Index	$n_d$	<b>1.65100</b>	Abbe Number	$V_d$	<b>56.24</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.011576
		1.651000			$V_e$		56.02	
	$n_e$	1.653761						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.61532
$n_{1970}$	1.97009	1.62234
$n_{1530}$	1.52958	1.62966
$n_{1129}$	1.12864	1.63584
$n_t$	1.01398	1.63781
$n_s$	0.85211	1.64117
$n_{A'}$	0.76819	1.64341
$n_r$	0.70652	1.64545
$n_c$	0.65627	<b>1.64747</b>
$n_{c'}$	0.64385	1.64803
$n_{\text{He-Ne}}$	0.6328	1.64856
$n_D$	0.58929	1.65090
$n_d$	0.58756	<b>1.65100</b>
$n_e$	0.54607	1.65376
$n_F$	0.48613	<b>1.65905</b>
$n_{F'}$	0.47999	1.65970
$n_{\text{He-Cd}}$	0.44157	1.66449
$n_g$	0.435835	<b>1.66532</b>
$n_h$	0.404656	1.67053
$n_i$	0.365015	1.67940
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009660
$n_c - n_{A'}$	0.004056
$n_d - n_c$	0.003530
$n_e - n_c$	0.006291
$n_g - n_d$	0.014320
$n_g - n_F$	0.006274
$n_h - n_g$	0.005206
$n_i - n_g$	0.014075
$n_{c'} - n_t$	0.010223
$n_e - n_{c'}$	0.005728
$n_{F'} - n_e$	0.005942
$n_i - n_{F'}$	0.019692

Relative Partial Dispersions	
$\theta_{c,t}$	0.8345
$\theta_{c,A'}$	0.3504
$\theta_{d,c}$	0.3049
$\theta_{e,c}$	0.5435
$\theta_{g,d}$	1.2370
$\theta_{g,F}$	0.5420
$\theta_{h,g}$	0.4497
$\theta_{i,g}$	1.2159
$\theta'_{c,t}$	0.8760
$\theta'_{e,c'}$	0.4908
$\theta'_{F',e}$	0.5092
$\theta'_{i,F'}$	1.6874

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0239
$\Delta\theta_{c,A'}$	0.0064
$\Delta\theta_{g,d}$	-0.0109
$\Delta\theta_{g,F}$	-0.0085
$\Delta\theta_{i,g}$	-0.0382

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.20085087	E-1
A 2	7.58646115	E-1
A 3	1.07073096	
B 1	1.60829667	E-2
B 2	2.92059306	E-3
B 3	8.51211200	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310	0.040	
320	0.110	
330	0.240	
340	0.410	
350	0.580	
360	0.730	
365		
370	0.830	
380	0.900	
390	0.938	
400	0.962	
420	0.984	
440	0.991	
460	0.995	
480	0.997	
500	0.997	
550	0.998	
600	0.997	
650	0.998	
700	0.997	
800	0.997	
900	0.995	
1000	0.993	
1200	0.994	
1400	0.976	
1600	0.986	
1800	0.973	
2000	0.942	
2200	0.810	
2400	0.580	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	646
Annealing Point (°C)	<b>AP</b>	679
Transformation Temperature (°C)	<b>Tg</b>	688
Yield Point (°C)	<b>At</b>	718
Softening Point (°C)	<b>SP</b>	748
Expansion Coefficient $\alpha$ (-30~+70°C)		43
(10 <sup>-7</sup> /°C)	(+100~+300°C)	55
Thermal Conductivity (W/m·K)	<b>k</b>	0.921

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	3.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1019
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	396
Poisson's Ratio	$\sigma$	0.287
Knoop Hardness	<b>Hk</b>	680 [7]
Abrasion	<b>Aa</b>	53
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.17

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	3.36		$\lambda_5$					
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.9	6.4	6.4	6.5	6.7	7.0	7.3		
-20 ~ 0	5.9	6.3	6.3	6.5	6.6	7.0	7.3		
0 ~ 20	5.9	6.3	6.4	6.5	6.7	7.0	7.4		
20 ~ 40	5.9	6.4	6.4	6.6	6.7	7.1	7.5		
40 ~ 60	6.1	6.5	6.6	6.7	6.9	7.3	7.7		
60 ~ 80	6.3	6.8	6.8	6.9	7.1	7.5	7.9		

Refractive Index	$n_d$	<b>1.69350</b> 1.693495	Abbe Number	$V_d$	<b>50.81</b> 50.53	Dispersion	$n_F - n_C$	<b>0.01365</b> 0.013649
		$n_e$		1.696745			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65998
$n_{1970}$	1.97009	1.66538
$n_{1530}$	1.52958	1.67133
$n_{1129}$	1.12864	1.67689
$n_t$	1.01398	1.67883
$n_s$	0.85211	1.68233
$n_{A'}$	0.76819	1.68480
$n_r$	0.70652	1.68709
$n_c$	0.65627	<b>1.68939</b>
$n_{c'}$	0.64385	1.69004
$n_{\text{He-Ne}}$	0.6328	1.69065
$n_D$	0.58929	1.69337
$n_d$	0.58756	<b>1.69350</b>
$n_e$	0.54607	1.69675
$n_F$	0.48613	<b>1.70304</b>
$n_{F'}$	0.47999	1.70383
$n_{\text{He-Cd}}$	0.44157	1.70960
$n_g$	0.435835	<b>1.71061</b>
$n_h$	0.404656	1.71696
$n_i$	0.365015	1.72788
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010565
$n_c - n_{A'}$	0.004596
$n_d - n_c$	0.004102
$n_e - n_c$	0.007352
$n_g - n_d$	0.017117
$n_g - n_F$	0.007570
$n_h - n_g$	0.006343
$n_i - n_g$	0.017264
$n_{c'} - n_t$	0.011214
$n_e - n_{c'}$	0.006703
$n_{F'} - n_e$	0.007086
$n_i - n_{F'}$	0.024045

Relative Partial Dispersions	
$\theta_{c,t}$	0.7740
$\theta_{c,A'}$	0.3367
$\theta_{d,c}$	0.3005
$\theta_{e,c}$	0.5386
$\theta_{g,d}$	1.2541
$\theta_{g,F}$	0.5546
$\theta_{h,g}$	0.4647
$\theta_{i,g}$	1.2649
$\theta'_{c,t}$	0.8133
$\theta'_{e,c'}$	0.4861
$\theta'_{F',e}$	0.5139
$\theta'_{i,F'}$	1.7438

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0111
$\Delta\theta_{c,A'}$	-0.0008
$\Delta\theta_{g,d}$	-0.0051
$\Delta\theta_{g,F}$	-0.0047
$\Delta\theta_{i,g}$	-0.0347

Internal Transmittance			
$\lambda_{80}$	354	$\lambda_5$	322

CCI		
B	G	R
0.00	0.30	0.28

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.06368789	
A 2	7.44939067	E-1
A 3	1.59178942	
B 1	1.85199640	E-2
B 2	1.16295862	E-3
B 3	1.56636025	E2
1129 ~ 2325 nm		
A 1	1.06368789	
A 2	7.44939067	E-1
A 3	1.59178942	
B 1	1.85199640	E-2
B 2	1.16295862	E-3
B 3	1.56636025	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.020	
330	0.220	
340	0.530	
350	0.750	
360	0.870	
365		
370	0.935	
380	0.962	
390	0.977	
400	0.986	
420	0.991	
440	0.992	
460	0.994	
480	0.996	
500	0.997	
550	0.998	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.989	
2000	0.977	
2200	0.942	
2400	0.840	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	633
Annealing Point (°C)	<b>AP</b>	659
Transformation Temperature (°C)	<b>Tg</b>	676
Yield Point (°C)	<b>At</b>	718
Softening Point (°C)	<b>SP</b>	770
Expansion Coefficient $\alpha$ (-30~+70°C)		75
Expansion Coefficient $\alpha$ (+10~+300°C)		86
Thermal Conductivity (W/m·K)	<b>k</b>	0.728

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	2.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	928
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	361
Poisson's Ratio	$\sigma$	0.285
Knoop Hardness	<b>Hk</b>	580 [6]
Abrasion	<b>Aa</b>	167
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.7

Other Properties								
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370			
Specific Gravity	<b>d</b>	4.03		$\lambda_5$		320		
Temperature Coefficients of Refractive Index								
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20		2.0	2.1	2.2	2.4	2.9	3.3	
-20 ~ 0		2.1	2.1	2.3	2.4	2.9	3.4	
0 ~ 20		2.1	2.1	2.3	2.5	2.9	3.4	
20 ~ 40		2.1	2.1	2.3	2.5	3.0	3.5	
40 ~ 60		2.1	2.1	2.3	2.5	3.0	3.5	
60 ~ 80		2.1	2.1	2.3	2.6	3.1	3.6	

Refractive Index	$n_d$	<b>1.73400</b>	Abbe Number	$V_d$	<b>51.47</b>	Dispersion	$n_F - n_C$	<b>0.01426</b>
		1.733997			$V_e$		51.24	
	$n_e$	1.737395					$n_{F'} - n_{C'}$	0.014392

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.69393
$n_{1970}$	1.97009	1.70130
$n_{1530}$	1.52958	1.70911
$n_{1129}$	1.12864	1.71593
$n_t$	1.01398	1.71817
$n_s$	0.85211	1.72210
$n_{A'}$	0.76819	1.72477
$n_r$	0.70652	1.72723
$n_c$	0.65627	<b>1.72968</b>
$n_{c'}$	0.64385	1.73036
$n_{\text{He-Ne}}$	0.6328	1.73101
$n_D$	0.58929	1.73387
$n_d$	0.58756	<b>1.73400</b>
$n_e$	0.54607	1.73739
$n_F$	0.48613	<b>1.74394</b>
$n_{F'}$	0.47999	1.74476
$n_{\text{He-Cd}}$	0.44157	1.75072
$n_g$	0.435835	<b>1.75176</b>
$n_h$	0.404656	1.75829
$n_i$	0.365015	1.76950
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	591
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	620
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	635
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	663
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	696
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	55
	(+10~+300 $^{\circ}\text{C}$ )	68
Thermal Conductivity (W/m·K)	<b>k</b>	0.863

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1137
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	440
Poisson's Ratio	$\sigma$	0.293
Knoop Hardness	<b>Hk</b>	700 [7]
Abrasion	<b>Aa</b>	77
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.87

Partial Dispersions	
$n_c - n_t$	0.011504
$n_c - n_{A'}$	0.004905
$n_d - n_c$	0.004318
$n_e - n_c$	0.007716
$n_g - n_d$	0.017767
$n_g - n_F$	0.007824
$n_h - n_g$	0.006531
$n_i - n_g$	0.017734
$n_{c'} - n_t$	0.012190
$n_e - n_{c'}$	0.007030
$n_{F'} - n_e$	0.007362
$n_i - n_{F'}$	0.024741

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0185
$\Delta\theta_{c,A'}$	0.0056
$\Delta\theta_{g,d}$	-0.0120
$\Delta\theta_{g,F}$	-0.0096
$\Delta\theta_{i,g}$	-0.0505

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.13962742	
A 2	8.05227838	E-1
A 3	1.29488061	
B 1	4.93294862	E-3
B 2	2.02479960	E-2
B 3	9.34746507	E1
1129 ~ 2325 nm		
A 1	1.13962742	
A 2	8.05227838	E-1
A 3	1.29488061	
B 1	4.93294862	E-3
B 2	2.02479960	E-2
B 3	9.34746507	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8067
$\theta_{c,A'}$	0.3439
$\theta_{d,c}$	0.3028
$\theta_{e,c}$	0.5411
$\theta_{g,d}$	1.2458
$\theta_{g,F}$	0.5486
$\theta_{h,g}$	0.4580
$\theta_{i,g}$	1.2435
$\theta'_{c,t}$	0.8470
$\theta'_{e,c'}$	0.4885
$\theta'_{F',e}$	0.5115
$\theta'_{i,F'}$	1.7191

Internal Transmittance			
$\lambda_{80}$	347	$\lambda_5$	283

CCI		
B	G	R
0.00	0.36	0.33

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280	0.020	
290	0.110	
300	0.200	
310	0.340	
320	0.480	
330	0.620	
340	0.740	
350	0.830	
360	0.890	
365		
370	0.934	
380	0.959	
390	0.973	
400	0.982	
420	0.990	
440	0.993	
460	0.995	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.994	
1600	0.994	
1800	0.986	
2000	0.964	
2200	0.905	
2400	0.650	

Other Properties								
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	365			
Specific Gravity	<b>d</b>	4.04		$\lambda_5$	280			
Temperature Coefficients of Refractive Index								
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20		5.0		5.2	5.4	5.8	6.3	
-20 ~ 0		5.2		5.4	5.6	6.0	6.5	
0 ~ 20		5.5		5.7	5.9	6.3	6.8	
20 ~ 40		5.7		6.0	6.2	6.7	7.2	
40 ~ 60		6.1		6.3	6.5	7.1	7.6	
60 ~ 80		6.4		6.7	6.9	7.5	8.0	



Refractive Index	$n_d$	<b>1.74100</b>	Abbe Number	$V_d$	<b>52.64</b>	Dispersion	$n_F - n_C$	<b>0.01407</b>
		1.740999			$V_e$		52.41	
	$n_e$	1.744354					$n_{F'} - n_{C'}$	0.014203

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70016
$n_{1970}$	1.97009	1.70787
$n_{1530}$	1.52958	1.71598
$n_{1129}$	1.12864	1.72297
$n_t$	1.01398	1.72525
$n_s$	0.85211	1.72918
$n_{A'}$	0.76819	1.73186
$n_r$	0.70652	1.73430
$n_c$	0.65627	<b>1.73673</b>
$n_{c'}$	0.64385	1.73741
$n_{\text{He-Ne}}$	0.6328	1.73804
$n_D$	0.58929	1.74087
$n_d$	0.58756	<b>1.74100</b>
$n_e$	0.54607	1.74435
$n_F$	0.48613	<b>1.75080</b>
$n_{F'}$	0.47999	1.75161
$n_{\text{He-Cd}}$	0.44157	1.75748
$n_g$	0.435835	<b>1.75850</b>
$n_h$	0.404656	1.76491
$n_i$	0.365015	1.77589
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	631
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	646
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	653
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	688
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	724
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		57
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	70
Thermal Conductivity (W/m·K)	<b>k</b>	0.861

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1190
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	461
Poisson's Ratio	$\sigma$	0.291
Knoop Hardness	<b>Hk</b>	720 [7]
Abrasion	<b>Aa</b>	65
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.55

Partial Dispersions	
$n_c - n_t$	0.011481
$n_c - n_{A'}$	0.004871
$n_d - n_c$	0.004272
$n_e - n_c$	0.007627
$n_g - n_d$	0.017502
$n_g - n_F$	0.007696
$n_h - n_g$	0.006413
$n_i - n_g$	0.017393
$n_{c'} - n_t$	0.012160
$n_e - n_{c'}$	0.006948
$n_{F'} - n_e$	0.007255
$n_i - n_{F'}$	0.024285

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0218
$\Delta\theta_{c,A'}$	0.0063
$\Delta\theta_{g,d}$	-0.0122
$\Delta\theta_{g,F}$	-0.0096
$\Delta\theta_{i,g}$	-0.0487

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.11073292	
A 2	8.59347773	E-1
A 3	1.26707433	
B 1	4.64181248	E-3
B 2	1.92989261	E-2
B 3	8.73917698	E1
1129 ~ 2325 nm		
A 1	1.11073292	
A 2	8.59347773	E-1
A 3	1.26707433	
B 1	4.64181248	E-3
B 2	1.92989261	E-2
B 3	8.73917698	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	51.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8155
$\theta_{c,A'}$	0.3460
$\theta_{d,c}$	0.3035
$\theta_{e,c}$	0.5418
$\theta_{g,d}$	1.2432
$\theta_{g,F}$	0.5467
$\theta_{h,g}$	0.4555
$\theta_{i,g}$	1.2355
$\theta'_{c,t}$	0.8562
$\theta'_{e,c'}$	0.4892
$\theta'_{F',e}$	0.5108
$\theta'_{i,F'}$	1.7099

Internal Transmittance			
$\lambda_{80}$	358	$\lambda_5$	296

CCI		
B	G	R
0.00	0.58	0.59

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290	0.020	
300	0.070	
310	0.150	
320	0.270	
330	0.430	
340	0.590	
350	0.720	
360	0.820	
365		
370	0.890	
380	0.935	
390	0.958	
400	0.971	
420	0.982	
440	0.988	
460	0.991	
480	0.994	
500	0.996	
550	0.997	
600	0.997	
650	0.997	
700	0.998	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.994	
1600	0.994	
1800	0.985	
2000	0.959	
2200	0.880	
2400	0.620	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	365				
Specific Gravity	<b>d</b>	4.04		$\lambda_5$	280				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.3	3.7	3.7	3.9	4.0	4.4	4.8		
-20 ~ 0	3.4	3.8	3.9	4.0	4.2	4.6	5.0		
0 ~ 20	3.5	3.9	4.0	4.1	4.3	4.7	5.1		
20 ~ 40	3.6	4.1	4.1	4.2	4.4	4.9	5.3		
40 ~ 60	3.7	4.2	4.2	4.4	4.6	5.0	5.5		
60 ~ 80	3.8	4.3	4.3	4.5	4.7	5.2	5.6		

Refractive Index	$n_d$	<b>1.74400</b>	Abbe Number	$V_d$	<b>44.78</b>	Dispersion	$n_F - n_C$	<b>0.01661</b>
		1.743997			$V_e$		44.50	
	$n_e$	1.747946					$n_{F'} - n_{C'}$	0.016806

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70597
$n_{1970}$	1.97009	1.71177
$n_{1530}$	1.52958	1.71820
$n_{1129}$	1.12864	1.72436
$n_t$	1.01398	1.72658
$n_s$	0.85211	1.73065
$n_{A'}$	0.76819	1.73356
$n_r$	0.70652	1.73629
$n_c$	0.65627	<b>1.73905</b>
$n_{c'}$	0.64385	1.73983
$n_{\text{He-Ne}}$	0.6328	1.74056
$n_D$	0.58929	1.74385
$n_d$	0.58756	<b>1.74400</b>
$n_e$	0.54607	1.74795
$n_F$	0.48613	<b>1.75566</b>
$n_{F'}$	0.47999	1.75663
$n_{\text{He-Cd}}$	0.44157	1.76380
$n_g$	0.435835	<b>1.76506</b>
$n_h$	0.404656	1.77304
$n_i$	0.365015	1.78708
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	590
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	617
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	633
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	670
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	711
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		74
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	87
Thermal Conductivity (W/m·K)	<b>k</b>	0.698

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	935
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	361
Poisson's Ratio	$\sigma$	0.295
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	158
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.72

Partial Dispersions	
$n_c - n_t$	0.012472
$n_c - n_{A'}$	0.005488
$n_d - n_c$	0.004949
$n_e - n_c$	0.008898
$n_g - n_d$	0.021058
$n_g - n_F$	0.009394
$n_h - n_g$	0.007986
$n_i - n_g$	0.022027
$n_{c'} - n_t$	0.013252
$n_e - n_{c'}$	0.008118
$n_{F'} - n_e$	0.008688
$n_i - n_{F'}$	0.030448

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0061
$\Delta\theta_{c,A'}$	0.0002
$\Delta\theta_{g,d}$	-0.0041
$\Delta\theta_{g,F}$	-0.0035
$\Delta\theta_{i,g}$	-0.0242

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.77130000	
A 2	1.95814230	E-1
A 3	1.19487834	
B 1	9.76652444	E-3
B 2	4.12718628	E-2
B 3	1.10458122	E2
1129 ~ 2325 nm		
A 1	1.77130000	
A 2	1.95814230	E-1
A 3	1.19487834	
B 1	9.76652444	E-3
B 2	4.12718628	E-2
B 3	1.10458122	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	3.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7507
$\theta_{c,A'}$	0.3303
$\theta_{d,c}$	0.2979
$\theta_{e,c}$	0.5356
$\theta_{g,d}$	1.2676
$\theta_{g,F}$	0.5655
$\theta_{h,g}$	0.4807
$\theta_{i,g}$	1.3259
$\theta'_{c,t}$	0.7885
$\theta'_{e,c'}$	0.4830
$\theta'_{F',e}$	0.5170
$\theta'_{i,F'}$	1.8117

Internal Transmittance			
$\lambda_{80}$	372	$\lambda_5$	340

CCI		
B	G	R
0.00	1.00	1.02

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.040	
350	0.290	
360	0.590	
365		
370	0.780	
380	0.870	
390	0.925	
400	0.950	
420	0.973	
440	0.983	
460	0.987	
480	0.992	
500	0.995	
550	0.997	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.997	
1000	0.997	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.988	
2000	0.971	
2200	0.928	
2400	0.790	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	395				
Specific Gravity	<b>d</b>	4.32		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.9	2.5	2.5	2.7	3.0	3.5	4.1		
-20 ~ 0	2.0	2.6	2.6	2.8	3.1	3.7	4.3		
0 ~ 20	2.0	2.6	2.7	2.9	3.2	3.8	4.5		
20 ~ 40	2.1	2.7	2.8	3.0	3.3	3.9	4.6		
40 ~ 60	2.2	2.8	2.8	3.1	3.4	4.1	4.8		
60 ~ 80	2.2	2.9	2.9	3.2	3.5	4.2	4.9		

Refractive Index	$n_d$	<b>1.71700</b>	Abbe Number	$V_d$	<b>47.92</b>	Dispersion	$n_F - n_C$	<b>0.01496</b>
		1.717004			$V_e$		47.64	
	$n_e$	1.720563					$n_{F'} - n_{C'}$	0.015124

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68133
$n_{1970}$	1.97009	1.68699
$n_{1530}$	1.52958	1.69320
$n_{1129}$	1.12864	1.69905
$n_t$	1.01398	1.70111
$n_s$	0.85211	1.70488
$n_{A'}$	0.76819	1.70754
$n_r$	0.70652	1.71002
$n_c$	0.65627	<b>1.71253</b>
$n_{c'}$	0.64385	1.71323
$n_{\text{He-Ne}}$	0.6328	1.71390
$n_D$	0.58929	1.71687
$n_d$	0.58756	<b>1.71700</b>
$n_e$	0.54607	1.72056
$n_F$	0.48613	<b>1.72749</b>
$n_{F'}$	0.47999	1.72836
$n_{\text{He-Cd}}$	0.44157	1.73475
$n_g$	0.435835	<b>1.73587</b>
$n_h$	0.404656	1.74296
$n_i$	0.365015	1.75531
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.011413
$n_c - n_{A'}$	0.004990
$n_d - n_c$	0.004476
$n_e - n_c$	0.008035
$n_g - n_d$	0.018871
$n_g - n_F$	0.008386
$n_h - n_g$	0.007085
$n_i - n_g$	0.019433
$n_{c'} - n_t$	0.012120
$n_e - n_{c'}$	0.007328
$n_{F'} - n_e$	0.007796
$n_i - n_{F'}$	0.026949

Relative Partial Dispersions	
$\theta_{c,t}$	0.7629
$\theta_{c,A'}$	0.3335
$\theta_{d,c}$	0.2992
$\theta_{e,c}$	0.5371
$\theta_{g,d}$	1.2613
$\theta_{g,F}$	0.5605
$\theta_{h,g}$	0.4736
$\theta_{i,g}$	1.2989
$\theta'_{c,t}$	0.8014
$\theta'_{e,c'}$	0.4845
$\theta'_{F',e}$	0.5155
$\theta'_{i,F'}$	1.7819

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0086
$\Delta\theta_{c,A'}$	-0.0004
$\Delta\theta_{g,d}$	-0.0039
$\Delta\theta_{g,F}$	-0.0034
$\Delta\theta_{i,g}$	-0.0249

Internal Transmittance			
$\lambda_{80}$	368	$\lambda_5$	338

CCI		
B	G	R
0.00	0.65	0.63

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.64258713	
A 2	2.39634610	E-1
A 3	1.22483026	
B 1	8.68246020	E-3
B 2	3.51226242	E-2
B 3	1.16604369	E2
1129 ~ 2325 nm		
A 1	1.64258713	
A 2	2.39634610	E-1
A 3	1.22483026	
B 1	8.68246020	E-3
B 2	3.51226242	E-2
B 3	1.16604369	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.100	
350	0.410	
360	0.690	
365		
370	0.830	
380	0.916	
390	0.951	
400	0.968	
420	0.982	
440	0.987	
460	0.990	
480	0.993	
500	0.995	
550	0.997	
600	0.996	
650	0.996	
700	0.997	
800	0.999	
900	0.997	
1000	0.997	
1200	0.996	
1400	0.994	
1600	0.992	
1800	0.983	
2000	0.966	
2200	0.920	
2400	0.770	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	588
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	614
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	630
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	661
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	701
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	80
	(+10~+300 $^{\circ}\text{C}$ )	94
Thermal Conductivity (W/m·K)	<b>k</b>	0.655

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	53.2
Phosphate Resistance	<b>PR</b>	4.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	868
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	335
Poisson's Ratio	$\sigma$	0.294
Knoop Hardness	<b>Hk</b>	510 [5]
Abrasion	<b>Aa</b>	202
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.51

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	4.25		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.8	-0.5	-0.5	-0.3	-0.1	0.3	0.8		
-20 ~ 0	-0.8	-0.4	-0.4	-0.3		0.4	0.9		
0 ~ 20	-0.8	-0.4	-0.4	-0.2		0.5	1.0		
20 ~ 40	-0.8	-0.4	-0.3	-0.2	0.1	0.6	1.1		
40 ~ 60	-0.8	-0.3	-0.3	-0.1	0.1	0.7	1.2		
60 ~ 80	-0.8	-0.3	-0.3	-0.1	0.2	0.7	1.3		

Refractive Index	$n_d$	<b>1.74950</b> 1.749497	Abbe Number	$V_d$	<b>35.28</b> 35.02	Dispersion	$n_F - n_C$	<b>0.02124</b> 0.021243
		$n_e$		1.754527			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70583
$n_{1970}$	1.97009	1.71184
$n_{1530}$	1.52958	1.71866
$n_{1129}$	1.12864	1.72553
$n_t$	1.01398	1.72811
$n_s$	0.85211	1.73296
$n_{A'}$	0.76819	1.73649
$n_r$	0.70652	1.73984
$n_c$	0.65627	<b>1.74328</b>
$n_{c'}$	0.64385	1.74425
$n_{\text{He-Ne}}$	0.6328	1.74517
$n_D$	0.58929	1.74931
$n_d$	0.58756	<b>1.74950</b>
$n_e$	0.54607	1.75453
$n_F$	0.48613	<b>1.76452</b>
$n_{F'}$	0.47999	1.76579
$n_{\text{He-Cd}}$	0.44157	1.77530
$n_g$	0.435835	<b>1.77699</b>
$n_h$	0.404656	1.78787
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	583
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	615
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	628
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	673
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	739
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	67
	(+10~+300 $^{\circ}\text{C}$ )	79
Thermal Conductivity (W/m·K)	<b>k</b>	0.871

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	970
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	381
Poisson's Ratio	$\sigma$	0.273
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	147
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.53

Partial Dispersions	
$n_c - n_t$	0.015167
$n_c - n_{A'}$	0.006783
$n_d - n_c$	0.006222
$n_e - n_c$	0.011252
$n_g - n_d$	0.027489
$n_g - n_F$	0.012468
$n_h - n_g$	0.010884
$n_i - n_g$	
$n_{c'} - n_t$	0.016141
$n_e - n_{c'}$	0.010278
$n_{F'} - n_e$	0.011266
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0018
$\Delta\theta_{c,A'}$	0.0007
$\Delta\theta_{g,d}$	0.0026
$\Delta\theta_{g,F}$	0.0025
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.71014712	
A 2	2.56943292	E-1
A 3	1.63986271	
B 1	1.05161080	E-2
B 2	5.02809636	E-2
B 3	1.46181217	E2
1129 ~ 2325 nm		
A 1	1.71014712	
A 2	2.56943292	E-1
A 3	1.63986271	
B 1	1.05161080	E-2
B 2	5.02809636	E-2
B 3	1.46181217	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7140
$\theta_{c,A'}$	0.3193
$\theta_{d,c}$	0.2929
$\theta_{e,c}$	0.5297
$\theta_{g,d}$	1.2940
$\theta_{g,F}$	0.5869
$\theta_{h,g}$	0.5124
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7492
$\theta'_{e,c'}$	0.4771
$\theta'_{F',e}$	0.5229
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	396	$\lambda_5$	359

CCI		
B	G	R
0.00	2.84	2.97

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.080	
365		
370	0.340	
380	0.590	
390	0.750	
400	0.840	
420	0.935	
440	0.965	
460	0.977	
480	0.984	
500	0.989	
550	0.996	
600	0.997	
650	0.998	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.996	
1800	0.990	
2000	0.982	
2200	0.950	
2400	0.880	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	420				
Specific Gravity	<b>d</b>	3.81		$\lambda_5$	355				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.2	5.0	5.1	5.3	5.7	6.5	7.5		
-20 ~ 0	4.4	5.2	5.2	5.5	5.9	6.7	7.7		
0 ~ 20	4.4	5.3	5.3	5.6	6.0	6.9	8.0		
20 ~ 40	4.5	5.4	5.5	5.8	6.2	7.1	8.2		
40 ~ 60	4.6	5.5	5.6	6.0	6.3	7.3	8.4		
60 ~ 80	4.6	5.6	5.7	6.2	6.5	7.5	8.7		

Refractive Index	$n_d$	<b>1.72000</b>	Abbe Number	$V_d$	<b>43.69</b>	Dispersion	$n_F - n_C$	<b>0.01648</b>
	$n_e$	1.720000		$V_e$	43.40		$n_{F'} - n_{C'}$	0.016480
		1.723914						0.016679

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68281
$n_{1970}$	1.97009	1.68840
$n_{1530}$	1.52958	1.69463
$n_{1129}$	1.12864	1.70065
$n_t$	1.01398	1.70282
$n_s$	0.85211	1.70683
$n_{A'}$	0.76819	1.70969
$n_r$	0.70652	1.71238
$n_c$	0.65627	<b>1.71511</b>
$n_{c'}$	0.64385	1.71588
$n_{\text{He-Ne}}$	0.6328	1.71660
$n_D$	0.58929	1.71986
$n_d$	0.58756	<b>1.72000</b>
$n_e$	0.54607	1.72391
$n_F$	0.48613	<b>1.73159</b>
$n_{F'}$	0.47999	1.73256
$n_{\text{He-Cd}}$	0.44157	1.73972
$n_g$	0.435835	<b>1.74098</b>
$n_h$	0.404656	1.74901
$n_i$	0.365015	1.76328
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.012285
$n_c - n_{A'}$	0.005415
$n_d - n_c$	0.004895
$n_e - n_c$	0.008809
$n_g - n_d$	0.020977
$n_g - n_F$	0.009392
$n_h - n_g$	0.008035
$n_i - n_g$	0.022303
$n_{c'} - n_t$	0.013056
$n_e - n_{c'}$	0.008038
$n_{F'} - n_e$	0.008641
$n_i - n_{F'}$	0.030725

Relative Partial Dispersions	
$\theta_{c,t}$	0.7454
$\theta_{c,A'}$	0.3286
$\theta_{d,c}$	0.2970
$\theta_{e,c}$	0.5345
$\theta_{g,d}$	1.2729
$\theta_{g,F}$	0.5699
$\theta_{h,g}$	0.4876
$\theta_{i,g}$	1.3533
$\theta'_{c,t}$	0.7828
$\theta'_{e,c'}$	0.4819
$\theta'_{F',e}$	0.5181
$\theta'_{i,F'}$	1.8421

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0063
$\Delta\theta_{c,A'}$	-0.0002
$\Delta\theta_{g,d}$	-0.0011
$\Delta\theta_{g,F}$	-0.0009
$\Delta\theta_{i,g}$	-0.0059

Internal Transmittance			
$\lambda_{80}$	380	$\lambda_5$	348

CCI		
B	G	R
0.00	1.40	1.41

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.73442942	
A 2	1.51553910	E-1
A 3	1.46225433	
B 1	1.00690928	E-2
B 2	4.70634701	E-2
B 3	1.40084396	E2
1129 ~ 2325 nm		
A 1	1.73442942	
A 2	1.51553910	E-1
A 3	1.46225433	
B 1	1.00690928	E-2
B 2	4.70634701	E-2
B 3	1.40084396	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.100	
360	0.390	
365		
370	0.650	
380	0.800	
390	0.880	
400	0.930	
420	0.965	
440	0.977	
460	0.984	
480	0.988	
500	0.992	
550	0.996	
600	0.996	
650	0.995	
700	0.997	
800	0.998	
900	0.997	
1000	0.997	
1200	0.998	
1400	0.997	
1600	0.996	
1800	0.990	
2000	0.979	
2200	0.947	
2400	0.850	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	604
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	632
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	644
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	685
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	743
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	77
	(+100~+300 $^{\circ}\text{C}$ )	88
Thermal Conductivity (W/m·K)	<b>k</b>	0.801

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	1.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	957
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	374
Poisson's Ratio	$\sigma$	0.278
Knoop Hardness	<b>Hk</b>	530 [5]
Abrasion	<b>Aa</b>	160
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.53

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	3.95		$\lambda_5$	345				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.1	1.6	1.6	1.8	2.0	2.6	3.2		
-20 ~ 0	1.1	1.6	1.7	1.9	2.1	2.7	3.3		
0 ~ 20	1.1	1.7	1.8	2.0	2.2	2.8	3.5		
20 ~ 40	1.1	1.8	1.8	2.0	2.3	3.0	3.6		
40 ~ 60	1.2	1.9	1.9	2.1	2.4	3.1	3.8		
60 ~ 80	1.2	1.9	2.0	2.2	2.5	3.2	3.9		

Refractive Index	$n_d$	<b>1.75700</b>	Abbe Number	$V_d$	<b>47.82</b>	Dispersion	$n_F - n_C$	<b>0.01583</b>
		1.756998			$V_e$		47.57	
	$n_e$	1.760765					$n_{F'} - n_{C'}$	0.015991

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.71415
$n_{1970}$	1.97009	1.72188
$n_{1530}$	1.52958	1.73007
$n_{1129}$	1.12864	1.73729
$n_t$	1.01398	1.73970
$n_s$	0.85211	1.74394
$n_{A'}$	0.76819	1.74686
$n_r$	0.70652	1.74954
$n_c$	0.65627	<b>1.75223</b>
$n_{c'}$	0.64385	1.75299
$n_{\text{He-Ne}}$	0.6328	1.75370
$n_D$	0.58929	1.75686
$n_d$	0.58756	<b>1.75700</b>
$n_e$	0.54607	1.76076
$n_F$	0.48613	<b>1.76806</b>
$n_{F'}$	0.47999	1.76898
$n_{\text{He-Cd}}$	0.44157	1.77570
$n_g$	0.435835	<b>1.77687</b>
$n_h$	0.404656	1.78431
$n_i$	0.365015	1.79726
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	614
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	637
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	664
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	687
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	721
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		57
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	69
Thermal Conductivity (W/m·K)	<b>k</b>	0.891

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1172
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	454
Poisson's Ratio	$\sigma$	0.292
Knoop Hardness	<b>Hk</b>	700 [7]
Abrasion	<b>Aa</b>	62
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.7

Partial Dispersions	
$n_c - n_t$	0.012530
$n_c - n_{A'}$	0.005376
$n_d - n_c$	0.004764
$n_e - n_c$	0.008531
$n_g - n_d$	0.019876
$n_g - n_F$	0.008810
$n_h - n_g$	0.007433
$n_i - n_g$	0.020388
$n_{c'} - n_t$	0.013285
$n_e - n_{c'}$	0.007776
$n_{F'} - n_e$	0.008215
$n_i - n_{F'}$	0.028282

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0205
$\Delta\theta_{c,A'}$	0.0058
$\Delta\theta_{g,d}$	-0.0098
$\Delta\theta_{g,F}$	-0.0076
$\Delta\theta_{i,g}$	-0.0367

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.84213306	
A 2	1.75468631	E-1
A 3	1.25750878	
B 1	9.43993220	E-3
B 2	3.95281122	E-2
B 3	8.65463013	E1
1129 ~ 2325 nm		
A 1	1.84213306	
A 2	1.75468631	E-1
A 3	1.25750878	
B 1	9.43993220	E-3
B 2	3.95281122	E-2
B 3	8.65463013	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	51.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7915
$\theta_{c,A'}$	0.3396
$\theta_{d,c}$	0.3009
$\theta_{e,c}$	0.5389
$\theta_{g,d}$	1.2556
$\theta_{g,F}$	0.5565
$\theta_{h,g}$	0.4696
$\theta_{i,g}$	1.2879
$\theta'_{c,t}$	0.8308
$\theta'_{e,c'}$	0.4863
$\theta'_{F',e}$	0.5137
$\theta'_{i,F'}$	1.7686

Internal Transmittance			
$\lambda_{80}$	369	$\lambda_5$	340

CCI		
B	G	R
0.00	0.75	0.80

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.050	
350	0.330	
360	0.650	
365		
370	0.820	
380	0.909	
390	0.945	
400	0.963	
420	0.979	
440	0.985	
460	0.990	
480	0.993	
500	0.995	
550	0.997	
600	0.997	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.991	
1600	0.991	
1800	0.981	
2000	0.954	
2200	0.870	
2400	0.620	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	<b>d</b>	4.08		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.8	4.2	4.3	4.4	4.7	5.1	5.6		
-20 ~ 0	4.0	4.4	4.5	4.7	4.9	5.4	5.9		
0 ~ 20	4.2	4.7	4.7	4.9	5.1	5.6	6.2		
20 ~ 40	4.4	4.9	4.9	5.1	5.3	5.9	6.4		
40 ~ 60	4.5	5.1	5.1	5.3	5.6	6.1	6.7		
60 ~ 80	4.7	5.3	5.3	5.5	5.8	6.4	7.0		



Refractive Index	$n_d$	<b>1.76200</b> 1.762001	Abbe Number	$V_d$	<b>40.10</b> 39.82	Dispersion	$n_F - n_C$	<b>0.01900</b> 0.019003
		$n_e$		1.766509			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.72020
$n_{1970}$	1.97009	1.72640
$n_{1530}$	1.52958	1.73328
$n_{1129}$	1.12864	1.73998
$n_t$	1.01398	1.74242
$n_s$	0.85211	1.74695
$n_{A'}$	0.76819	1.75020
$n_r$	0.70652	1.75327
$n_c$	0.65627	<b>1.75639</b>
$n_{c'}$	0.64385	1.75727
$n_{\text{He-Ne}}$	0.6328	1.75810
$n_D$	0.58929	1.76183
$n_d$	0.58756	<b>1.76200</b>
$n_e$	0.54607	1.76651
$n_F$	0.48613	<b>1.77539</b>
$n_{F'}$	0.47999	1.77652
$n_{\text{He-Cd}}$	0.44157	1.78487
$n_g$	0.435835	<b>1.78634</b>
$n_h$	0.404656	1.79580
$n_i$	0.365015	1.81280
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	589
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	617
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	632
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	662
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	709
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		71
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	84
Thermal Conductivity (W/m·K)	<b>k</b>	0.741

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	967
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	374
Poisson's Ratio	$\sigma$	0.292
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	145
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.88

Partial Dispersions	
$n_c - n_t$	0.013960
$n_c - n_{A'}$	0.006182
$n_d - n_c$	0.005616
$n_e - n_c$	0.010124
$n_g - n_d$	0.024342
$n_g - n_F$	0.010955
$n_h - n_g$	0.009453
$n_i - n_g$	0.026457
$n_{c'} - n_t$	0.014843
$n_e - n_{c'}$	0.009241
$n_{F'} - n_e$	0.010006
$n_i - n_{F'}$	0.036285

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0002
$\Delta\theta_{c,A'}$	0.0008
$\Delta\theta_{g,d}$	-0.0004
$\Delta\theta_{g,F}$	-0.0001
$\Delta\theta_{i,g}$	0.0031

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.85412979	
A 2	1.65450323	E-1
A 3	1.27255422	
B 1	1.08438152	E-2
B 2	5.14050980	E-2
B 3	1.09986837	E2
1129 ~ 2325 nm		
A 1	1.85412979	
A 2	1.65450323	E-1
A 3	1.27255422	
B 1	1.08438152	E-2
B 2	5.14050980	E-2
B 3	1.09986837	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7346
$\theta_{c,A'}$	0.3253
$\theta_{d,c}$	0.2955
$\theta_{e,c}$	0.5328
$\theta_{g,d}$	1.2810
$\theta_{g,F}$	0.5765
$\theta_{h,g}$	0.4974
$\theta_{i,g}$	1.3923
$\theta'_{c,t}$	0.7712
$\theta'_{e,c'}$	0.4801
$\theta'_{F',e}$	0.5199
$\theta'_{i,F'}$	1.8852

Internal Transmittance			
$\lambda_{80}$	378	$\lambda_5$	350

CCI		
B	G	R
0.00	1.43	1.46

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.060	
360	0.370	
365		
370	0.670	
380	0.820	
390	0.890	
400	0.932	
420	0.963	
440	0.976	
460	0.984	
480	0.989	
500	0.993	
550	0.997	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.995	
1600	0.994	
1800	0.986	
2000	0.970	
2200	0.923	
2400	0.780	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	405				
Specific Gravity	<b>d</b>	4.22		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.5	3.1	3.1	3.3	3.6	4.3	5.1		
-20 ~ 0	2.6	3.2	3.2	3.5	3.8	4.5	5.3		
0 ~ 20	2.6	3.3	3.3	3.6	3.9	4.7	5.5		
20 ~ 40	2.7	3.4	3.4	3.7	4.0	4.8	5.7		
40 ~ 60	2.8	3.5	3.5	3.8	4.2	5.0	5.9		
60 ~ 80	2.8	3.6	3.6	3.9	4.3	5.2	6.1		

Refractive Index	$n_d$	<b>1.72000</b>	Abbe Number	$V_d$	<b>41.98</b>	Dispersion	$n_F - n_C$	<b>0.01715</b>
	$n_e$	1.720000		$V_e$	41.69		$n_{F'} - n_{C'}$	0.017152
		1.724072						0.017366

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68205
$n_{1970}$	1.97009	1.68764
$n_{1530}$	1.52958	1.69390
$n_{1129}$	1.12864	1.70001
$n_t$	1.01398	1.70224
$n_s$	0.85211	1.70636
$n_{A'}$	0.76819	1.70931
$n_r$	0.70652	1.71209
$n_c$	0.65627	<b>1.71492</b>
$n_{c'}$	0.64385	1.71572
$n_{\text{He-Ne}}$	0.6328	1.71647
$n_D$	0.58929	1.71985
$n_d$	0.58756	<b>1.72000</b>
$n_e$	0.54607	1.72407
$n_F$	0.48613	<b>1.73207</b>
$n_{F'}$	0.47999	1.73308
$n_{\text{He-Cd}}$	0.44157	1.74058
$n_g$	0.435835	<b>1.74190</b>
$n_h$	0.404656	1.75033
$n_i$	0.365015	1.76538
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	632
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	658
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	681
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	726
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	791
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	66
	(+10~+300 $^{\circ}\text{C}$ )	77
Thermal Conductivity (W/m·K)	<b>k</b>	0.771

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	919
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	359
Poisson's Ratio	$\sigma$	0.279
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	151
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.03

Partial Dispersions	
$n_c - n_t$	0.012680
$n_c - n_{A'}$	0.005606
$n_d - n_c$	0.005081
$n_e - n_c$	0.009153
$n_g - n_d$	0.021898
$n_g - n_F$	0.009827
$n_h - n_g$	0.008436
$n_i - n_g$	0.023484
$n_{c'} - n_t$	0.013479
$n_e - n_{c'}$	0.008354
$n_{F'} - n_e$	0.009012
$n_i - n_{F'}$	0.032298

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0043
$\Delta\theta_{c,A'}$	0.0001
$\Delta\theta_{g,d}$	-0.0008
$\Delta\theta_{g,F}$	-0.0006
$\Delta\theta_{i,g}$	-0.0043

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.70984856	
A 2	1.73342897	E-1
A 3	1.64833565	
B 1	1.00852127	E-2
B 2	4.70890831	E-2
B 3	1.57468520	E2
1129 ~ 2325 nm		
A 1	1.70984856	
A 2	1.73342897	E-1
A 3	1.64833565	
B 1	1.00852127	E-2
B 2	4.70890831	E-2
B 3	1.57468520	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	2
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	3.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7393
$\theta_{c,A'}$	0.3268
$\theta_{d,c}$	0.2962
$\theta_{e,c}$	0.5336
$\theta_{g,d}$	1.2767
$\theta_{g,F}$	0.5729
$\theta_{h,g}$	0.4918
$\theta_{i,g}$	1.3692
$\theta'_{c,t}$	0.7762
$\theta'_{e,c'}$	0.4811
$\theta'_{F',e}$	0.5189
$\theta'_{i,F'}$	1.8598

Internal Transmittance			
$\lambda_{80}$	385	$\lambda_5$	350

CCI		
B	G	R
0.00	1.68	1.70

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.040	
360	0.270	
365		
370	0.550	
380	0.740	
390	0.850	
400	0.911	
420	0.960	
440	0.976	
460	0.983	
480	0.988	
500	0.991	
550	0.996	
600	0.996	
650	0.995	
700	0.997	
800	0.998	
900	0.998	
1000	0.998	
1200	0.999	
1400	0.997	
1600	0.997	
1800	0.992	
2000	0.984	
2200	0.956	
2400	0.890	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	410				
Specific Gravity	<b>d</b>	4.00		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.3	3.9	3.9	4.1	4.4	5.0	5.7		
-20 ~ 0	3.4	4.0	4.0	4.3	4.6	5.2	5.9		
0 ~ 20	3.4	4.1	4.2	4.4	4.7	5.4	6.1		
20 ~ 40	3.6	4.3	4.3	4.6	4.9	5.6	6.3		
40 ~ 60	3.6	4.4	4.5	4.7	5.0	5.7	6.5		
60 ~ 80	3.7	4.5	4.6	4.8	5.2	5.9	6.8		

Refractive Index	$n_d$	<b>1.69700</b> 1.697002	Abbe Number	$V_d$	<b>48.52</b> 48.24	Dispersion	$n_F - n_C$	<b>0.01436</b> 0.014366
		$n_e$		1.700421			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.66174
$n_{1970}$	1.97009	1.66748
$n_{1530}$	1.52958	1.67376
$n_{1129}$	1.12864	1.67959
$n_t$	1.01398	1.68163
$n_s$	0.85211	1.68530
$n_{A'}$	0.76819	1.68788
$n_r$	0.70652	1.69028
$n_c$	0.65627	<b>1.69270</b>
$n_{c'}$	0.64385	1.69338
$n_{\text{He-Ne}}$	0.6328	1.69401
$n_D$	0.58929	1.69688
$n_d$	0.58756	<b>1.69700</b>
$n_e$	0.54607	1.70042
$n_F$	0.48613	<b>1.70706</b>
$n_{F'}$	0.47999	1.70790
$n_{\text{He-Cd}}$	0.44157	1.71402
$n_g$	0.435835	<b>1.71509</b>
$n_h$	0.404656	1.72187
$n_i$	0.365015	1.73366
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	594
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	623
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	634
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	678
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	735
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	71
	(+10~+300 $^{\circ}\text{C}$ )	83
Thermal Conductivity (W/m·K)	<b>k</b>	0.847

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1006
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	394
Poisson's Ratio	$\sigma$	0.277
Knoop Hardness	<b>Hk</b>	600 [6]
Abrasion	<b>Aa</b>	142
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.69

Partial Dispersions	
$n_c - n_t$	0.011071
$n_c - n_{A'}$	0.004818
$n_d - n_c$	0.004306
$n_e - n_c$	0.007725
$n_g - n_d$	0.018089
$n_g - n_F$	0.008029
$n_h - n_g$	0.006774
$n_i - n_g$	0.018569
$n_{c'} - n_t$	0.011751
$n_e - n_{c'}$	0.007045
$n_{F'} - n_e$	0.007476
$n_i - n_{F'}$	0.025763

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0037
$\Delta\theta_{c,A'}$	0.0007
$\Delta\theta_{g,d}$	-0.0047
$\Delta\theta_{g,F}$	-0.0041
$\Delta\theta_{i,g}$	-0.0261

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.63056133	
A 2	1.86994897	E-1
A 3	1.30014289	
B 1	8.99690705	E-3
B 2	3.68011993	E-2
B 3	1.22239544	E2
1129 ~ 2325 nm		
A 1	1.63056133	
A 2	1.86994897	E-1
A 3	1.30014289	
B 1	8.99690705	E-3
B 2	3.68011993	E-2
B 3	1.22239544	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	5.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7706
$\theta_{c,A'}$	0.3354
$\theta_{d,c}$	0.2997
$\theta_{e,c}$	0.5377
$\theta_{g,d}$	1.2592
$\theta_{g,F}$	0.5589
$\theta_{h,g}$	0.4715
$\theta_{i,g}$	1.2926
$\theta'_{c,t}$	0.8092
$\theta'_{e,c'}$	0.4852
$\theta'_{F',e}$	0.5148
$\theta'_{i,F'}$	1.7742

Internal Transmittance			
$\lambda_{80}$	365	$\lambda_5$	337

CCI		
B	G	R
0.00	0.65	0.60

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.140	
350	0.470	
360	0.730	
365		
370	0.860	
380	0.923	
390	0.954	
400	0.969	
420	0.982	
440	0.986	
460	0.989	
480	0.992	
500	0.995	
550	0.997	
600	0.996	
650	0.995	
700	0.997	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.996	
1600	0.996	
1800	0.991	
2000	0.982	
2200	0.952	
2400	0.850	

Other Properties								
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380			
Specific Gravity	<b>d</b>	3.77		$\lambda_5$	330			
Temperature Coefficients of Refractive Index								
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20		2.7	2.7	2.9	3.1	3.5	4.0	
-20 ~ 0		2.8	2.8	3.0	3.2	3.7	4.2	
0 ~ 20		2.9	2.9	3.1	3.3	3.8	4.3	
20 ~ 40		3.0	3.0	3.2	3.4	3.9	4.5	
40 ~ 60		3.1	3.1	3.3	3.5	4.1	4.6	
60 ~ 80		3.1	3.2	3.4	3.6	4.2	4.8	

Refractive Index	$n_d$	<b>1.74320</b>	Abbe Number	$V_d$	<b>49.34</b>	Dispersion	$n_F - n_C$	<b>0.01507</b>
		1.743198			$V_e$		49.10	
	$n_e$	1.746784					$n_{F'} - n_{C'}$	0.015210

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70181
$n_{1970}$	1.97009	1.70932
$n_{1530}$	1.52958	1.71730
$n_{1129}$	1.12864	1.72431
$n_t$	1.01398	1.72663
$n_s$	0.85211	1.73071
$n_{A'}$	0.76819	1.73351
$n_r$	0.70652	1.73608
$n_c$	0.65627	<b>1.73865</b>
$n_{c'}$	0.64385	1.73937
$n_{\text{He-Ne}}$	0.6328	1.74005
$n_D$	0.58929	1.74306
$n_d$	0.58756	<b>1.74320</b>
$n_e$	0.54607	1.74678
$n_F$	0.48613	<b>1.75372</b>
$n_{F'}$	0.47999	1.75458
$n_{\text{He-Cd}}$	0.44157	1.76094
$n_g$	0.435835	<b>1.76205</b>
$n_h$	0.404656	1.76904
$n_i$	0.365015	1.78113
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	594
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	615
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	643
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	658
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	693
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	54
	(+100~+300 $^{\circ}\text{C}$ )	66
Thermal Conductivity (W/m·K)	<b>k</b>	0.845

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1132
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	438
Poisson's Ratio	$\sigma$	0.294
Knoop Hardness	<b>Hk</b>	730 [7]
Abrasion	<b>Aa</b>	71
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.9

Partial Dispersions	
$n_c - n_t$	0.012019
$n_c - n_{A'}$	0.005143
$n_d - n_c$	0.004545
$n_e - n_c$	0.008131
$n_g - n_d$	0.018849
$n_g - n_F$	0.008331
$n_h - n_g$	0.006993
$n_i - n_g$	0.019083
$n_{c'} - n_t$	0.012740
$n_e - n_{c'}$	0.007410
$n_{F'} - n_e$	0.007800
$n_i - n_{F'}$	0.026546

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0197
$\Delta\theta_{c,A'}$	0.0057
$\Delta\theta_{g,d}$	-0.0109
$\Delta\theta_{g,F}$	-0.0085
$\Delta\theta_{i,g}$	-0.0450

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.60673056	
A 2	3.66415640	E-1
A 3	1.31761804	
B 1	7.75046140	E-3
B 2	2.89967611	E-2
B 3	9.30720709	E1
1129 ~ 2325 nm		
A 1	1.60673056	
A 2	3.66415640	E-1
A 3	1.31761804	
B 1	7.75046140	E-3
B 2	2.89967611	E-2
B 3	9.30720709	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7979
$\theta_{c,A'}$	0.3414
$\theta_{d,c}$	0.3017
$\theta_{e,c}$	0.5398
$\theta_{g,d}$	1.2513
$\theta_{g,F}$	0.5531
$\theta_{h,g}$	0.4643
$\theta_{i,g}$	1.2669
$\theta'_{c,t}$	0.8376
$\theta'_{e,c'}$	0.4872
$\theta'_{F',e}$	0.5128
$\theta'_{i,F'}$	1.7453

Internal Transmittance			
$\lambda_{80}$	360	$\lambda_5$	331

CCI		
B	G	R
0.00	0.51	0.52

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.030	
340	0.290	
350	0.600	
360	0.790	
365		
370	0.890	
380	0.937	
390	0.961	
400	0.974	
420	0.985	
440	0.990	
460	0.993	
480	0.995	
500	0.997	
550	0.998	
600	0.997	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.991	
1600	0.991	
1800	0.980	
2000	0.953	
2200	0.870	
2400	0.620	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	375				
Specific Gravity	<b>d</b>	4.06		$\lambda_5$	330				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.3	5.7	5.7	5.9	6.1	6.6	7.1		
-20 ~ 0	5.4	5.8	5.9	6.1	6.3	6.8	7.3		
0 ~ 20	5.5	6.0	6.0	6.2	6.4	7.0	7.5		
20 ~ 40	5.6	6.1	6.2	6.4	6.6	7.2	7.7		
40 ~ 60	5.7	6.3	6.3	6.5	6.8	7.4	7.9		
60 ~ 80	5.9	6.5	6.5	6.6	7.0	7.5	8.1		

Refractive Index	$n_d$	<b>1.72000</b>	Abbe Number	$V_d$	<b>46.02</b>	Dispersion	$n_F - n_C$	<b>0.01564</b>
	$n_e$	1.720002		$V_e$	45.75		$n_{F'} - n_{C'}$	0.015644
		1.723721						0.015820

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68252
$n_{1970}$	1.97009	1.68854
$n_{1530}$	1.52958	1.69511
$n_{1129}$	1.12864	1.70126
$n_t$	1.01398	1.70342
$n_s$	0.85211	1.70735
$n_{A'}$	0.76819	1.71012
$n_r$	0.70652	1.71271
$n_c$	0.65627	<b>1.71533</b>
$n_{c'}$	0.64385	1.71607
$n_{\text{He-Ne}}$	0.6328	1.71676
$n_D$	0.58929	1.71986
$n_d$	0.58756	<b>1.72000</b>
$n_e$	0.54607	1.72372
$n_F$	0.48613	<b>1.73097</b>
$n_{F'}$	0.47999	1.73189
$n_{\text{He-Cd}}$	0.44157	1.73861
$n_g$	0.435835	<b>1.73979</b>
$n_h$	0.404656	1.74727
$n_i$	0.365015	1.76042
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	585
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	602
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	629
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	665
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	713
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		66
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	80
Thermal Conductivity (W/m·K)	<b>k</b>	0.732

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	937
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	363
Poisson's Ratio	$\sigma$	0.290
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	144
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.99

Partial Dispersions	
$n_c - n_t$	0.011910
$n_c - n_{A'}$	0.005206
$n_d - n_c$	0.004672
$n_e - n_c$	0.008391
$n_g - n_d$	0.019787
$n_g - n_F$	0.008815
$n_h - n_g$	0.007485
$n_i - n_g$	0.020636
$n_{c'} - n_t$	0.012647
$n_e - n_{c'}$	0.007654
$n_{F'} - n_e$	0.008166
$n_i - n_{F'}$	0.028538

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0013
$\Delta\theta_{c,A'}$	0.0012
$\Delta\theta_{g,d}$	-0.0043
$\Delta\theta_{g,F}$	-0.0035
$\Delta\theta_{i,g}$	-0.0206

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.73883330	
A 2	1.50937430	E-1
A 3	1.12118445	
B 1	9.80244105	E-3
B 2	4.33179685	E-2
B 3	1.01214625	E2
1129 ~ 2325 nm		
A 1	1.73883330	
A 2	1.50937430	E-1
A 3	1.12118445	
B 1	9.80244105	E-3
B 2	4.33179685	E-2
B 3	1.01214625	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	2.2

Relative Partial Dispersions	
$\theta_{c,t}$	0.7613
$\theta_{c,A'}$	0.3328
$\theta_{d,c}$	0.2986
$\theta_{e,c}$	0.5364
$\theta_{g,d}$	1.2648
$\theta_{g,F}$	0.5635
$\theta_{h,g}$	0.4785
$\theta_{i,g}$	1.3191
$\theta'_{c,t}$	0.7994
$\theta'_{e,c'}$	0.4838
$\theta'_{F',e}$	0.5162
$\theta'_{i,F'}$	1.8039

Internal Transmittance			
$\lambda_{80}$	375	$\lambda_5$	341

CCI		
B	G	R
0.00	1.17	1.20

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.030	
350	0.260	
360	0.560	
365		
370	0.750	
380	0.860	
390	0.914	
400	0.943	
420	0.969	
440	0.979	
460	0.985	
480	0.989	
500	0.993	
550	0.997	
600	0.996	
650	0.997	
700	0.997	
800	0.998	
900	0.999	
1000	0.998	
1200	0.999	
1400	0.997	
1600	0.997	
1800	0.991	
2000	0.978	
2200	0.942	
2400	0.800	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	395				
Specific Gravity	<b>d</b>	4.10		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.9	3.5	3.5	3.7	3.9	4.5	5.1		
-20 ~ 0	3.0	3.6	3.7	3.9	4.1	4.7	5.3		
0 ~ 20	3.2	3.8	3.8	4.0	4.3	4.8	5.5		
20 ~ 40	3.2	3.9	3.9	4.1	4.4	5.0	5.7		
40 ~ 60	3.3	4.0	4.1	4.3	4.6	5.2	5.9		
60 ~ 80	3.4	4.2	4.2	4.4	4.7	5.4	6.1		

Refractive Index	$n_d$	<b>1.80100</b>	Abbe Number	$V_d$	<b>34.97</b>	Dispersion	$n_F - n_C$	<b>0.02291</b>
	$n_e$	1.800999		$V_e$	34.72		$n_{F'} - n_{C'}$	0.022907
		1.806423						0.023227

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.75094
$n_{1970}$	1.97009	1.75842
$n_{1530}$	1.52958	1.76672
$n_{1129}$	1.12864	1.77475
$n_t$	1.01398	1.77766
$n_s$	0.85211	1.78304
$n_{A'}$	0.76819	1.78691
$n_r$	0.70652	1.79055
$n_c$	0.65627	<b>1.79427</b>
$n_{c'}$	0.64385	1.79533
$n_{\text{He-Ne}}$	0.6328	1.79632
$n_D$	0.58929	1.80080
$n_d$	0.58756	<b>1.80100</b>
$n_e$	0.54607	1.80642
$n_F$	0.48613	<b>1.81718</b>
$n_{F'}$	0.47999	1.81856
$n_{\text{He-Cd}}$	0.44157	1.82879
$n_g$	0.435835	<b>1.83061</b>
$n_h$	0.404656	1.84236
$n_i$	0.365015	1.86391
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.016620
$n_c - n_{A'}$	0.007369
$n_d - n_c$	0.006724
$n_e - n_c$	0.012148
$n_g - n_d$	0.029615
$n_g - n_F$	0.013432
$n_h - n_g$	0.011747
$n_i - n_g$	0.033294
$n_{c'} - n_t$	0.017674
$n_e - n_{c'}$	0.011094
$n_{F'} - n_e$	0.012133
$n_i - n_{F'}$	0.045352

Relative Partial Dispersions	
$\theta_{c,t}$	0.7255
$\theta_{c,A'}$	0.3217
$\theta_{d,c}$	0.2935
$\theta_{e,c}$	0.5303
$\theta_{g,d}$	1.2928
$\theta_{g,F}$	0.5864
$\theta_{h,g}$	0.5128
$\theta_{i,g}$	1.4534
$\theta'_{c,t}$	0.7609
$\theta'_{e,c'}$	0.4776
$\theta'_{F',e}$	0.5224
$\theta'_{i,F'}$	1.9526

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0148
$\Delta\theta_{c,A'}$	0.0035
$\Delta\theta_{g,d}$	0.0007
$\Delta\theta_{g,F}$	0.0015
$\Delta\theta_{i,g}$	0.0212

Internal Transmittance			
$\lambda_{80}$	388	$\lambda_5$	351

CCI		
B	G	R
0.00	2.58	2.67

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.92094221	
A 2	2.19901208	E-1
A 3	1.72705231	
B 1	1.15075241	E-2
B 2	5.47993543	E-2
B 3	1.20133674	E2
1129 ~ 2325 nm		
A 1	1.92094221	
A 2	2.19901208	E-1
A 3	1.72705231	
B 1	1.15075241	E-2
B 2	5.47993543	E-2
B 3	1.20133674	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.030	
360	0.280	
365		
370	0.570	
380	0.730	
390	0.820	
400	0.870	
420	0.932	
440	0.954	
460	0.968	
480	0.977	
500	0.985	
550	0.994	
600	0.994	
650	0.994	
700	0.997	
800	0.998	
900	0.998	
1000	0.998	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.992	
2000	0.976	
2200	0.937	
2400	0.770	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	514
Annealing Point (°C)	<b>AP</b>	544
Transformation Temperature (°C)	<b>Tg</b>	554
Yield Point (°C)	<b>At</b>	586
Softening Point (°C)	<b>SP</b>	629
Expansion Coefficient $\alpha$ (-30~+70°C)		79
(10-7 /°C) (+100~+300°C)		95
Thermal Conductivity (W/m·K)	<b>k</b>	1.062

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	4.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1210
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	473
Poisson's Ratio	$\sigma$	0.280
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	92
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.92

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	430				
Specific Gravity	<b>d</b>	3.55		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.2	3.0	3.1	3.3	3.7	4.5	5.5		
-20 ~ 0	2.2	3.1	3.1	3.4	3.8	4.7	5.7		
0 ~ 20	2.2	3.2	3.2	3.5	3.9	4.9	5.9		
20 ~ 40	2.3	3.2	3.3	3.6	4.0	5.0	6.1		
40 ~ 60	2.3	3.3	3.4	3.7	4.1	5.2	6.4		
60 ~ 80	2.4	3.4	3.5	3.8	4.3	5.4	6.6		



Refractive Index	$n_d$	<b>1.79360</b> 1.793600	Abbe Number	$V_d$	<b>37.09</b> 36.82	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.021397 0.021692
		$n_e$		1.798672			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.75073
$n_{1970}$	1.97009	1.75638
$n_{1530}$	1.52958	1.76285
$n_{1129}$	1.12864	1.76952
$n_t$	1.01398	1.77207
$n_s$	0.85211	1.77692
$n_{A'}$	0.76819	1.78047
$n_r$	0.70652	1.78385
$n_c$	0.65627	<b>1.78732</b>
$n_{c'}$	0.64385	1.78830
$n_{\text{He-Ne}}$	0.6328	1.78923
$n_D$	0.58929	1.79341
$n_d$	0.58756	<b>1.79360</b>
$n_e$	0.54607	1.79867
$n_F$	0.48613	<b>1.80872</b>
$n_{F'}$	0.47999	1.81000
$n_{\text{He-Cd}}$	0.44157	1.81950
$n_g$	0.435835	<b>1.82119</b>
$n_h$	0.404656	1.83200
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	584
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	607
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	623
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	658
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	695
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		89
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	105
Thermal Conductivity (W/m·K)	<b>k</b>	0.648

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	868
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	332
Poisson's Ratio	$\sigma$	0.306
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	182
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.52

Partial Dispersions	
$n_c - n_t$	0.015250
$n_c - n_{A'}$	0.006846
$n_d - n_c$	0.006281
$n_e - n_c$	0.011353
$n_g - n_d$	0.027586
$n_g - n_F$	0.012470
$n_h - n_g$	0.010815
$n_i - n_g$	
$n_{c'} - n_t$	0.016234
$n_e - n_{c'}$	0.010369
$n_{F'} - n_e$	0.011323
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0080
$\Delta\theta_{c,A'}$	-0.0008
$\Delta\theta_{g,d}$	0.0015
$\Delta\theta_{g,F}$	0.0013
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.86353123	
A 2	2.55215617	E-1
A 3	1.23399133	
B 1	1.07620673	E-2
B 2	4.87248679	E-2
B 3	1.17125110	E2
1129 ~ 2325 nm		
A 1	1.86353123	
A 2	2.55215617	E-1
A 3	1.23399133	
B 1	1.07620673	E-2
B 2	4.87248679	E-2
B 3	1.17125110	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	2.2

Relative Partial Dispersions	
$\theta_{c,t}$	0.7127
$\theta_{c,A'}$	0.3200
$\theta_{d,c}$	0.2935
$\theta_{e,c}$	0.5306
$\theta_{g,d}$	1.2892
$\theta_{g,F}$	0.5828
$\theta_{h,g}$	0.5054
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7484
$\theta'_{e,c'}$	0.4780
$\theta'_{F',e}$	0.5220
$\theta'_{i,F'}$	

Internal Transmittance		
$\lambda_{80}$		$\lambda_5$

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.080	
360	0.340	
365		
370	0.620	
380	0.780	
390	0.870	
400	0.916	
420	0.954	
440	0.968	
460	0.976	
480	0.983	
500	0.989	
550	0.995	
600	0.994	
650	0.994	
700	0.996	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.997	
1600	0.995	
1800	0.984	
2000	0.964	
2200	0.925	
2400	0.800	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	415				
Specific Gravity	<b>d</b>	4.45		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.9	-1.1	-1.1	-0.8	-0.5	0.3	1.1		
-20 ~ 0	-2.0	-1.2	-1.1	-0.9	-0.5	0.3	1.2		
0 ~ 20	-2.0	-1.2	-1.1	-0.9	-0.5	0.4	1.3		
20 ~ 40	-2.1	-1.2	-1.1	-0.9	-0.5	0.4	1.4		
40 ~ 60	-2.1	-1.2	-1.1	-0.8	-0.4	0.5	1.6		
60 ~ 80	-2.0	-1.0	-1.0	-0.7	-0.3	0.7	1.8		

Refractive Index	$n_d$	<b>1.65412</b>	Abbe Number	$V_d$	<b>39.68</b>	Dispersion	$n_F - n_C$	<b>0.01648</b>
		1.654115			$V_e$		39.43	
	$n_e$	1.658026					$n_{F'} - n_{C'}$	0.016687

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.61410
$n_{1970}$	1.97009	1.62070
$n_{1530}$	1.52958	1.62787
$n_{1129}$	1.12864	1.63448
$n_t$	1.01398	1.63677
$n_s$	0.85211	1.64090
$n_{A'}$	0.76819	1.64379
$n_r$	0.70652	1.64649
$n_c$	0.65627	<b>1.64923</b>
$n_{c'}$	0.64385	1.65000
$n_{\text{He-Ne}}$	0.6328	1.65072
$n_D$	0.58929	1.65397
$n_d$	0.58756	<b>1.65412</b>
$n_e$	0.54607	1.65803
$n_F$	0.48613	<b>1.66571</b>
$n_{F'}$	0.47999	1.66668
$n_{\text{He-Cd}}$	0.44157	1.67389
$n_g$	0.435835	<b>1.67517</b>
$n_h$	0.404656	1.68331
$n_i$	0.365015	1.69791
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.012452
$n_c - n_{A'}$	0.005432
$n_d - n_c$	0.004890
$n_e - n_c$	0.008801
$n_g - n_d$	0.021051
$n_g - n_F$	0.009457
$n_h - n_g$	0.008144
$n_i - n_g$	0.022741
$n_{c'} - n_t$	0.013223
$n_e - n_{c'}$	0.008030
$n_{F'} - n_e$	0.008657
$n_i - n_{F'}$	0.031224

Relative Partial Dispersions	
$\theta_{c,t}$	0.7554
$\theta_{c,A'}$	0.3295
$\theta_{d,c}$	0.2967
$\theta_{e,c}$	0.5339
$\theta_{g,d}$	1.2771
$\theta_{g,F}$	0.5737
$\theta_{h,g}$	0.4941
$\theta_{i,g}$	1.3796
$\theta'_{c,t}$	0.7924
$\theta'_{e,c'}$	0.4812
$\theta'_{F',e}$	0.5188
$\theta'_{i,F'}$	1.8712

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0226
$\Delta\theta_{c,A'}$	0.0056
$\Delta\theta_{g,d}$	-0.0052
$\Delta\theta_{g,F}$	-0.0036
$\Delta\theta_{i,g}$	-0.0132

Internal Transmittance			
$\lambda_{80}$	357	$\lambda_5$	328

CCI		
B	G	R
0.00	0.66	0.69

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.47544521	
A 2	1.93060095	E-1
A 3	1.50939010	
B 1	9.55836740	E-3
B 2	4.60430483	E-2
B 3	1.26422746	E2
1129 ~ 2325 nm		
A 1	1.47544521	
A 2	1.93060095	E-1
A 3	1.50939010	
B 1	9.55836740	E-3
B 2	4.60430483	E-2
B 3	1.26422746	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.120	
340	0.470	
350	0.710	
360	0.830	
365		
370	0.902	
380	0.936	
390	0.957	
400	0.969	
420	0.980	
440	0.985	
460	0.988	
480	0.991	
500	0.994	
550	0.997	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.991	
1600	0.994	
1800	0.989	
2000	0.976	
2200	0.919	
2400	0.800	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	489
Annealing Point (°C)	<b>AP</b>	511
Transformation Temperature (°C)	<b>Tg</b>	524
Yield Point (°C)	<b>At</b>	575
Softening Point (°C)	<b>SP</b>	645
Expansion Coefficient $\alpha$ (-30~+70°C)		66
(10-7 /°C) (+100~+300°C)		84
Thermal Conductivity (W/m·K)	<b>k</b>	0.965

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	902
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	361
Poisson's Ratio	$\sigma$	0.248
Knoop Hardness	<b>Hk</b>	580 [6]
Abrasion	<b>Aa</b>	130
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.22

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	3.02		$\lambda_5$		325			
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.5	4.1	4.1	4.3	4.6	5.1	5.8		
-20 ~ 0	3.6	4.2	4.2	4.5	4.7	5.3	6.0		
0 ~ 20	3.7	4.3	4.4	4.6	4.9	5.5	6.2		
20 ~ 40	3.8	4.4	4.5	4.8	5.0	5.7	6.4		
40 ~ 60	3.9	4.6	4.6	4.9	5.1	5.8	6.6		
60 ~ 80	3.9	4.7	4.7	5.0	5.3	6.0	6.8		

Refractive Index	$n_d$	<b>1.72047</b> 1.720467	Abbe Number	$V_d$	<b>34.71</b> 34.47	Dispersion	$n_F - n_C$	<b>0.02075</b> 0.020758
		$n_e$		1.725385			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.67534
$n_{1970}$	1.97009	1.68198
$n_{1530}$	1.52958	1.68941
$n_{1129}$	1.12864	1.69665
$n_t$	1.01398	1.69928
$n_s$	0.85211	1.70416
$n_{A'}$	0.76819	1.70767
$n_r$	0.70652	1.71099
$n_C$	0.65627	<b>1.71437</b>
$n_{C'}$	0.64385	1.71532
$n_{\text{He-Ne}}$	0.6328	1.71622
$n_D$	0.58929	1.72029
$n_d$	0.58756	<b>1.72047</b>
$n_e$	0.54607	1.72538
$n_F$	0.48613	<b>1.73512</b>
$n_{F'}$	0.47999	1.73636
$n_{\text{He-Cd}}$	0.44157	1.74559
$n_g$	0.435835	<b>1.74723</b>
$n_h$	0.404656	1.75777
$n_i$	0.365015	1.77689
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	476
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	499
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	508
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	555
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	611
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	81
	(+10~+300 $^{\circ}\text{C}$ )	100
Thermal Conductivity (W/m·K)	<b>k</b>	1.052

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1017
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	407
Poisson's Ratio	$\sigma$	0.250
Knoop Hardness	<b>Hk</b>	590 [6]
Abrasion	<b>Aa</b>	155
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.9

Partial Dispersions	
$n_C - n_t$	0.015084
$n_C - n_{A'}$	0.006690
$n_d - n_C$	0.006102
$n_e - n_C$	0.011020
$n_g - n_d$	0.026767
$n_g - n_F$	0.012111
$n_h - n_g$	0.010534
$n_i - n_g$	0.029660
$n_{C'} - n_t$	0.016041
$n_e - n_{C'}$	0.010063
$n_{F'} - n_e$	0.010979
$n_i - n_{F'}$	0.040530

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0172
$\Delta\theta_{C,A'}$	0.0044
$\Delta\theta_{g,d}$	-0.0031
$\Delta\theta_{g,F}$	-0.0019
$\Delta\theta_{i,g}$	-0.0056

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.61344136	
A 2	2.57295888	E-1
A 3	1.98364455	
B 1	1.06386752	E-2
B 2	4.87071624	E-2
B 3	1.59784404	E2
1129 ~ 2325 nm		
A 1	1.61344136	
A 2	2.57295888	E-1
A 3	1.98364455	
B 1	1.06386752	E-2
B 2	4.87071624	E-2
B 3	1.59784404	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.7267
$\theta_{C,A'}$	0.3223
$\theta_{d,C}$	0.2940
$\theta_{e,C}$	0.5309
$\theta_{g,d}$	1.2895
$\theta_{g,F}$	0.5834
$\theta_{h,g}$	0.5075
$\theta_{i,g}$	1.4288
$\theta'_{C,t}$	0.7623
$\theta'_{e,C'}$	0.4782
$\theta'_{F',e}$	0.5218
$\theta'_{i,F'}$	1.9261

Internal Transmittance			
$\lambda_{80}$	371	$\lambda_5$	331

CCI		
B	G	R
0.00	1.38	1.48

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.030	
340	0.240	
350	0.490	
360	0.670	
365		
370	0.790	
380	0.860	
390	0.908	
400	0.936	
420	0.962	
440	0.972	
460	0.979	
480	0.984	
500	0.989	
550	0.996	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.997	
1800	0.992	
2000	0.984	
2200	0.955	
2400	0.880	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	<b>d</b>	3.19		$\lambda_5$	330				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.2	3.0	3.0	3.3	3.6	4.3	5.2		
-20 ~ 0	2.2	3.0	3.1	3.4	3.7	4.5	5.4		
0 ~ 20	2.2	3.1	3.1	3.4	3.8	4.6	5.5		
20 ~ 40	2.2	3.1	3.2	3.5	3.9	4.7	5.7		
40 ~ 60	2.3	3.2	3.3	3.6	3.9	4.9	5.9		
60 ~ 80	2.4	3.3	3.3	3.6	4.0	5.0	6.1		

Refractive Index	$n_d$	<b>1.74950</b>	Abbe Number	$V_d$	<b>35.33</b>	Dispersion	$n_F - n_C$	<b>0.02121</b>
	$n_e$	1.749505		$V_e$	35.10		$n_{F'} - n_{C'}$	0.021214
		1.754531						0.021498

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70260
$n_{1970}$	1.97009	1.70965
$n_{1530}$	1.52958	1.71748
$n_{1129}$	1.12864	1.72503
$n_t$	1.01398	1.72776
$n_s$	0.85211	1.73279
$n_{A'}$	0.76819	1.73640
$n_r$	0.70652	1.73980
$n_c$	0.65627	<b>1.74326</b>
$n_{c'}$	0.64385	1.74424
$n_{\text{He-Ne}}$	0.6328	1.74516
$n_D$	0.58929	1.74932
$n_d$	0.58756	<b>1.74950</b>
$n_e$	0.54607	1.75453
$n_F$	0.48613	<b>1.76447</b>
$n_{F'}$	0.47999	1.76574
$n_{\text{He-Cd}}$	0.44157	1.77515
$n_g$	0.435835	<b>1.77681</b>
$n_h$	0.404656	1.78753
$n_i$	0.365015	1.80695
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	500
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	521
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	535
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	578
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	631
Expansion Coefficient ( $10^{-7}/^{\circ}\text{C}$ )	$\alpha$	73
Thermal Conductivity (W/m·K)	<b>k</b>	1.124

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1097
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	438
Poisson's Ratio	$\sigma$	0.253
Knoop Hardness	<b>Hk</b>	610 [6]
Abrasion	<b>Aa</b>	115
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.66

Partial Dispersions	
$n_c - n_t$	0.015503
$n_c - n_{A'}$	0.006860
$n_d - n_c$	0.006246
$n_e - n_c$	0.011272
$n_g - n_d$	0.027310
$n_g - n_F$	0.012342
$n_h - n_g$	0.010718
$n_i - n_g$	0.030139
$n_{c'} - n_t$	0.016484
$n_e - n_{c'}$	0.010291
$n_{F'} - n_e$	0.011207
$n_i - n_{F'}$	0.041216

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0184
$\Delta\theta_{c,A'}$	0.0047
$\Delta\theta_{g,d}$	-0.0039
$\Delta\theta_{g,F}$	-0.0025
$\Delta\theta_{i,g}$	-0.0085

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.71203689	
A 2	2.55989588	E-1
A 3	1.81456998	
B 1	1.07724134	E-2
B 2	4.88593504	E-2
B 3	1.36359013	E2
1129 ~ 2325 nm		
A 1	1.71203689	
A 2	2.55989588	E-1
A 3	1.81456998	
B 1	1.07724134	E-2
B 2	4.88593504	E-2
B 3	1.36359013	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7308
$\theta_{c,A'}$	0.3234
$\theta_{d,c}$	0.2944
$\theta_{e,c}$	0.5313
$\theta_{g,d}$	1.2874
$\theta_{g,F}$	0.5818
$\theta_{h,g}$	0.5052
$\theta_{i,g}$	1.4207
$\theta'_{c,t}$	0.7668
$\theta'_{e,c'}$	0.4787
$\theta'_{F',e}$	0.5213
$\theta'_{i,F'}$	1.9172

Internal Transmittance			
$\lambda_{80}$	370	$\lambda_5$	331

CCI		
B	G	R
0.00	1.22	1.30

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.020	
340	0.220	
350	0.490	
360	0.680	
365		
370	0.800	
380	0.870	
390	0.918	
400	0.943	
420	0.967	
440	0.976	
460	0.982	
480	0.987	
500	0.991	
550	0.997	
600	0.997	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.995	
1600	0.994	
1800	0.989	
2000	0.980	
2200	0.945	
2400	0.870	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	3.29		$\lambda_5$	330				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn/dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.1	4.9	4.9	5.2	5.5	6.3	7.1		
-20 ~ 0	4.1	4.9	5.0	5.2	5.6	6.4	7.3		
0 ~ 20	4.1	4.9	5.0	5.3	5.6	6.5	7.5		
20 ~ 40	4.1	5.0	5.0	5.3	5.7	6.6	7.6		
40 ~ 60	4.1	5.0	5.1	5.4	5.8	6.7	7.8		
60 ~ 80	4.1	5.1	5.1	5.4	5.9	6.9	8.0		

Refractive Index	$n_d$	<b>1.67300</b>	Abbe Number	$V_d$	<b>38.15</b>	Dispersion	$n_F - n_C$	<b>0.01764</b>
		1.673000			$V_e$		37.90	
	$n_e$	1.677185					$n_{F'} - n_{C'}$	0.017866

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.63291
$n_{1970}$	1.97009	1.63904
$n_{1530}$	1.52958	1.64585
$n_{1129}$	1.12864	1.65237
$n_t$	1.01398	1.65470
$n_s$	0.85211	1.65897
$n_{A'}$	0.76819	1.66202
$n_r$	0.70652	1.66488
$n_c$	0.65627	<b>1.66778</b>
$n_{c'}$	0.64385	1.66860
$n_{\text{He-Ne}}$	0.6328	1.66937
$n_D$	0.58929	1.67285
$n_d$	0.58756	<b>1.67300</b>
$n_e$	0.54607	1.67719
$n_F$	0.48613	<b>1.68542</b>
$n_{F'}$	0.47999	1.68647
$n_{\text{He-Cd}}$	0.44157	1.69420
$n_g$	0.435835	<b>1.69557</b>
$n_h$	0.404656	1.70432
$n_i$	0.365015	1.71997
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.013084
$n_c - n_{A'}$	0.005763
$n_d - n_c$	0.005220
$n_e - n_c$	0.009405
$n_g - n_d$	0.022573
$n_g - n_F$	0.010151
$n_h - n_g$	0.008743
$n_i - n_g$	0.024400
$n_{c'} - n_t$	0.013905
$n_e - n_{c'}$	0.008584
$n_{F'} - n_e$	0.009282
$n_i - n_{F'}$	0.033506

Relative Partial Dispersions	
$\theta_{c,t}$	0.7416
$\theta_{c,A'}$	0.3267
$\theta_{d,c}$	0.2959
$\theta_{e,c}$	0.5331
$\theta_{g,d}$	1.2795
$\theta_{g,F}$	0.5754
$\theta_{h,g}$	0.4956
$\theta_{i,g}$	1.3831
$\theta'_{c,t}$	0.7783
$\theta'_{e,c'}$	0.4805
$\theta'_{F',e}$	0.5195
$\theta'_{i,F'}$	1.8754

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0159
$\Delta\theta_{c,A'}$	0.0046
$\Delta\theta_{g,d}$	-0.0060
$\Delta\theta_{g,F}$	-0.0043
$\Delta\theta_{i,g}$	-0.0225

Internal Transmittance			
$\lambda_{80}$	347	$\lambda_5$	320

CCI		
B	G	R
0.00	0.25	0.23

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.50305799	
A 2	2.21715926	E-1
A 3	1.84496391	
B 1	9.99021738	E-3
B 2	4.50327698	E-2
B 3	1.63722302	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310		
320	0.040	
330	0.370	
340	0.690	
350	0.850	
360	0.923	
365		
370	0.958	
380	0.976	
390	0.985	
400	0.990	
420	0.993	
440	0.994	
460	0.995	
480	0.996	
500	0.997	
550	0.999	
600	0.999	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.995	
1800	0.983	
2000	0.971	
2200	0.932	
2400	0.912	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	486
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	510
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	520
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	556
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	646
Expansion Coefficient ( $\alpha$ )		86
	(-30~+70 $^{\circ}\text{C}$ )	
	(+100~+300 $^{\circ}\text{C}$ )	109
Thermal Conductivity (W/m·K)	<b>k</b>	1.115

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	4
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	979
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	396
Poisson's Ratio	$\sigma$	0.236
Knoop Hardness	<b>Hk</b>	590 [6]
Abrasion	<b>Aa</b>	123
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	3.09		$\lambda_5$		320			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.1	3.7	3.8	4.0	4.3	4.9	5.6		
-20 ~ 0	3.0	3.7	3.7	3.9	4.2	4.9	5.6		
0 ~ 20	2.9	3.7	3.7	3.9	4.2	4.9	5.7		
20 ~ 40	2.8	3.6	3.7	3.8	4.2	5.0	5.8		
40 ~ 60	2.8	3.6	3.6	3.8	4.2	5.0	5.8		
60 ~ 80	2.7	3.5	3.6	3.8	4.2	5.0	5.9		

Refractive Index	$n_d$	<b>1.67300</b>	Abbe Number	$V_d$	<b>38.26</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.017592
	$n_e$	1.673000		$V_e$	38.01			0.017815

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.63149
$n_{1970}$	1.97009	1.63815
$n_{1530}$	1.52958	1.64544
$n_{1129}$	1.12864	1.65225
$n_t$	1.01398	1.65463
$n_s$	0.85211	1.65896
$n_{A'}$	0.76819	1.66203
$n_r$	0.70652	1.66489
$n_c$	0.65627	<b>1.66779</b>
$n_{c'}$	0.64385	1.66861
$n_{\text{He-Ne}}$	0.6328	1.66938
$n_D$	0.58929	1.67285
$n_d$	0.58756	<b>1.67300</b>
$n_e$	0.54607	1.67717
$n_F$	0.48613	<b>1.68538</b>
$n_{F'}$	0.47999	1.68643
$n_{\text{He-Cd}}$	0.44157	1.69415
$n_g$	0.435835	<b>1.69551</b>
$n_h$	0.404656	1.70425
$n_i$	0.365015	1.71995
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.013160
$n_c - n_{A'}$	0.005766
$n_d - n_c$	0.005208
$n_e - n_c$	0.009380
$n_g - n_d$	0.022512
$n_g - n_F$	0.010128
$n_h - n_g$	0.008738
$n_i - n_g$	0.024433
$n_{c'} - n_t$	0.013979
$n_e - n_{c'}$	0.008561
$n_{F'} - n_e$	0.009254
$n_i - n_{F'}$	0.033519

Relative Partial Dispersions	
$\theta_{c,t}$	0.7481
$\theta_{c,A'}$	0.3278
$\theta_{d,c}$	0.2960
$\theta_{e,c}$	0.5332
$\theta_{g,d}$	1.2797
$\theta_{g,F}$	0.5757
$\theta_{h,g}$	0.4967
$\theta_{i,g}$	1.3889
$\theta'_{c,t}$	0.7847
$\theta'_{e,c'}$	0.4806
$\theta'_{F',e}$	0.5194
$\theta'_{i,F'}$	1.8815

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0219
$\Delta\theta_{c,A'}$	0.0056
$\Delta\theta_{g,d}$	-0.0055
$\Delta\theta_{g,F}$	-0.0039
$\Delta\theta_{i,g}$	-0.0158

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.51336868	
A 2	2.12341478	E-1
A 3	1.54149143	
B 1	9.87077827	E-3
B 2	4.62843662	E-2
B 3	1.26978510	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310		
320	0.040	
330	0.310	
340	0.650	
350	0.840	
360	0.919	
365		
370	0.956	
380	0.974	
390	0.983	
400	0.988	
420	0.992	
440	0.993	
460	0.995	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.992	
1600	0.993	
1800	0.986	
2000	0.973	
2200	0.922	
2400	0.820	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	460
Annealing Point (°C)	<b>AP</b>	483
Transformation Temperature (°C)	<b>Tg</b>	497
Yield Point (°C)	<b>At</b>	538
Softening Point (°C)	<b>SP</b>	592
Expansion Coefficient $\alpha$ (-30~+70°C)		77
Expansion Coefficient $\alpha$ (+100~+300°C)		98
Thermal Conductivity (W/m·K)	<b>k</b>	1.032

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	963
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	386
Poisson's Ratio	$\sigma$	0.246
Knoop Hardness	<b>Hk</b>	600 [6]
Abrasion	<b>Aa</b>	124
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.11

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	3.01		$\lambda_5$	320				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.9	3.6	3.6	3.8	4.1	4.7	5.4		
-20 ~ 0	2.9	3.6	3.6	3.8	4.1	4.8	5.5		
0 ~ 20	2.8	3.5	3.6	3.8	4.1	4.8	5.6		
20 ~ 40	2.8	3.5	3.5	3.8	4.1	4.8	5.6		
40 ~ 60	2.8	3.5	3.6	3.8	4.2	4.9	5.7		
60 ~ 80	2.8	3.6	3.6	3.9	4.3	5.1	5.9		



Refractive Index	$n_d$	<b>1.73800</b>	Abbe Number	$V_d$	<b>32.26</b>	Dispersion	$n_F - n_C$	<b>0.02287</b>
		1.738000			$V_e$		32.03	
	$n_e$	1.743413					$n_{F'} - n_{C'}$	0.023207

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.69016
$n_{1970}$	1.97009	1.69693
$n_{1530}$	1.52958	1.70457
$n_{1129}$	1.12864	1.71215
$n_t$	1.01398	1.71496
$n_s$	0.85211	1.72021
$n_{A'}$	0.76819	1.72401
$n_r$	0.70652	1.72762
$n_c$	0.65627	<b>1.73131</b>
$n_{c'}$	0.64385	1.73236
$n_{\text{He-Ne}}$	0.6328	1.73334
$n_D$	0.58929	1.73780
$n_d$	0.58756	<b>1.73800</b>
$n_e$	0.54607	1.74341
$n_F$	0.48613	<b>1.75419</b>
$n_{F'}$	0.47999	1.75556
$n_{\text{He-Cd}}$	0.44157	1.76585
$n_g$	0.435835	<b>1.76768</b>
$n_h$	0.404656	1.77951
$n_i$	0.365015	1.80125
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	527
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	547
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	578
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	620
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	688
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		69
(10 $^{-7}$ / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	89
Thermal Conductivity (W/m·K)	<b>k</b>	1.117

Mechanical Properties		
Young's Modulus (108N/m $^2$ )	<b>E</b>	1031
Rigidity Modulus (108N/m $^2$ )	<b>G</b>	417
Poisson's Ratio	$\sigma$	0.236
Knoop Hardness	<b>Hk</b>	600 [6]
Abrasion	<b>Aa</b>	114
Photoelastic Constant (nm/cm/10 $^5$ Pa)	$\beta$	

Partial Dispersions	
$n_c - n_t$	0.016351
$n_c - n_{A'}$	0.007295
$n_d - n_c$	0.006691
$n_e - n_c$	0.012104
$n_g - n_d$	0.029679
$n_g - n_F$	0.013494
$n_h - n_g$	0.011832
$n_i - n_g$	0.033567
$n_{c'} - n_t$	0.017398
$n_e - n_{c'}$	0.011057
$n_{F'} - n_e$	0.012150
$n_i - n_{F'}$	0.045683

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0168
$\Delta\theta_{c,A'}$	0.0040
$\Delta\theta_{g,d}$	-0.0003
$\Delta\theta_{g,F}$	0.0006
$\Delta\theta_{i,g}$	0.0124

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.65828340	
A 2	2.63275666	E-1
A 3	2.10142759	
B 1	1.13872516	E-2
B 2	5.22108137	E-2
B 3	1.65523649	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7148
$\theta_{c,A'}$	0.3189
$\theta_{d,c}$	0.2925
$\theta_{e,c}$	0.5291
$\theta_{g,d}$	1.2974
$\theta_{g,F}$	0.5899
$\theta_{h,g}$	0.5172
$\theta_{i,g}$	1.4673
$\theta'_{c,t}$	0.7497
$\theta'_{e,c'}$	0.4765
$\theta'_{F',e}$	0.5235
$\theta'_{i,F'}$	1.9685

Internal Transmittance			
$\lambda_{80}$	365	$\lambda_5$	331

CCI		
B	G	R
0.00	0.70	0.74

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.030	
340	0.170	
350	0.520	
360	0.740	
365		
370	0.850	
380	0.915	
390	0.947	
400	0.965	
420	0.981	
440	0.986	
460	0.988	
480	0.991	
500	0.993	
550	0.997	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.996	
1800	0.990	
2000	0.985	
2200	0.952	
2400	0.949	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	3.28		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.1	4.9	5.0	5.3	5.6	6.4	7.4		
-20 ~ 0	4.1	5.0	5.0	5.3	5.7	6.6	7.6		
0 ~ 20	4.1	5.0	5.1	5.4	5.8	6.7	7.8		
20 ~ 40	4.1	5.1	5.2	5.5	5.9	6.9	8.0		
40 ~ 60	4.2	5.2	5.2	5.5	6.0	7.0	8.2		
60 ~ 80	4.2	5.2	5.3	5.6	6.1	7.2	8.4		

Refractive Index	$n_d$	<b>1.73800</b>	Abbe Number	$V_d$	<b>32.33</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.022830
		1.738000			$V_e$		32.10	
	$n_e$	1.743402						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.69006
$n_{1970}$	1.97009	1.69688
$n_{1530}$	1.52958	1.70457
$n_{1129}$	1.12864	1.71218
$n_t$	1.01398	1.71499
$n_s$	0.85211	1.72024
$n_{A'}$	0.76819	1.72404
$n_r$	0.70652	1.72764
$n_C$	0.65627	<b>1.73132</b>
$n_{C'}$	0.64385	1.73237
$n_{\text{He-Ne}}$	0.6328	1.73335
$n_D$	0.58929	1.73780
$n_d$	0.58756	<b>1.73800</b>
$n_e$	0.54607	1.74340
$n_F$	0.48613	<b>1.75415</b>
$n_{F'}$	0.47999	1.75553
$n_{\text{He-Cd}}$	0.44157	1.76579
$n_g$	0.435835	<b>1.76762</b>
$n_h$	0.404656	1.77943
$n_i$	0.365015	1.80114
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	501
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	523
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	538
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	582
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	640
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		71
(10 $^{-7}$ / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	93
Thermal Conductivity (W/m·K)	<b>k</b>	1.127

Mechanical Properties		
Young's Modulus (108N/m $^2$ )	<b>E</b>	1027
Rigidity Modulus (108N/m $^2$ )	<b>G</b>	415
Poisson's Ratio	$\sigma$	0.237
Knoop Hardness	<b>Hk</b>	600 [6]
Abrasion	<b>Aa</b>	110
Photoelastic Constant (nm/cm/10 $^5$ Pa)	$\beta$	2.99

Partial Dispersions	
$n_C - n_t$	0.016332
$n_C - n_{A'}$	0.007282
$n_d - n_C$	0.006678
$n_e - n_C$	0.012080
$n_g - n_d$	0.029621
$n_g - n_F$	0.013469
$n_h - n_g$	0.011812
$n_i - n_g$	0.033515
$n_{C'} - n_t$	0.017378
$n_e - n_{C'}$	0.011034
$n_{F'} - n_e$	0.012125
$n_i - n_{F'}$	0.045609

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0170
$\Delta\theta_{C,A'}$	0.0040
$\Delta\theta_{g,d}$	-0.0001
$\Delta\theta_{g,F}$	0.0008
$\Delta\theta_{i,g}$	0.0137

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.65444141	
A 2	2.67453927	E-1
A 3	2.14530347	
B 1	1.12485533	E-2
B 2	5.20272740	E-2
B 3	1.67366100	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.7154
$\theta_{C,A'}$	0.3190
$\theta_{d,C}$	0.2925
$\theta_{e,C}$	0.5291
$\theta_{g,d}$	1.2975
$\theta_{g,F}$	0.5900
$\theta_{h,g}$	0.5174
$\theta_{i,g}$	1.4680
$\theta'_{C,t}$	0.7504
$\theta'_{e,C'}$	0.4764
$\theta'_{F',e}$	0.5236
$\theta'_{i,F'}$	1.9694

Internal Transmittance		
$\lambda_{80}$		$\lambda_5$

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.030	
340	0.280	
350	0.610	
360	0.790	
365		
370	0.880	
380	0.927	
390	0.952	
400	0.968	
420	0.982	
440	0.988	
460	0.991	
480	0.993	
500	0.995	
550	0.997	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.995	
1600	0.995	
1800	0.990	
2000	0.984	
2200	0.951	
2400	0.928	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	3.19		$\lambda_5$	330				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.0	4.8	4.8	5.1	5.5	6.3	7.3		
-20 ~ 0	3.9	4.7	4.8	5.1	5.5	6.4	7.5		
0 ~ 20	3.8	4.7	4.8	5.1	5.5	6.5	7.6		
20 ~ 40	3.8	4.7	4.8	5.1	5.5	6.6	7.7		
40 ~ 60	3.8	4.8	4.9	5.2	5.6	6.7	7.8		
60 ~ 80	3.8	4.9	4.9	5.3	5.8	6.9	8.1		

Refractive Index	$n_d$	<b>1.80000</b>	Abbe Number	$V_d$	<b>29.84</b>	Dispersion	$n_F - n_C$	<b>0.02680</b>
		1.800000			$V_e$		29.61	
	$n_e$	1.806331					$n_{F'} - n_{C'}$	0.027232

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.74989
$n_{1970}$	1.97009	1.75600
$n_{1530}$	1.52958	1.76316
$n_{1129}$	1.12864	1.77082
$n_t$	1.01398	1.77381
$n_s$	0.85211	1.77959
$n_{A'}$	0.76819	1.78388
$n_r$	0.70652	1.78799
$n_c$	0.65627	<b>1.79224</b>
$n_{c'}$	0.64385	1.79345
$n_{\text{He-Ne}}$	0.6328	1.79459
$n_D$	0.58929	1.79977
$n_d$	0.58756	<b>1.80000</b>
$n_e$	0.54607	1.80633
$n_F$	0.48613	<b>1.81904</b>
$n_{F'}$	0.47999	1.82068
$n_{\text{He-Cd}}$	0.44157	1.83297
$n_g$	0.435835	<b>1.83517</b>
$n_h$	0.404656	1.84951
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.018427
$n_c - n_{A'}$	0.008355
$n_d - n_c$	0.007763
$n_e - n_c$	0.014094
$n_g - n_d$	0.035172
$n_g - n_F$	0.016129
$n_h - n_g$	0.014338
$n_i - n_g$	
$n_{c'} - n_t$	0.019637
$n_e - n_{c'}$	0.012884
$n_{F'} - n_e$	0.014348
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6874
$\theta_{c,A'}$	0.3117
$\theta_{d,c}$	0.2896
$\theta_{e,c}$	0.5258
$\theta_{g,d}$	1.3121
$\theta_{g,F}$	0.6017
$\theta_{h,g}$	0.5349
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7211
$\theta'_{e,c'}$	0.4731
$\theta'_{F',e}$	0.5269
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0007
$\Delta\theta_{c,A'}$	-0.0003
$\Delta\theta_{g,d}$	0.0094
$\Delta\theta_{g,F}$	0.0085
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	392	$\lambda_5$	360

CCI		
B	G	R
0.00	2.72	2.91

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.83145156	
A 2	2.87818024	E-1
A 3	2.15208300	
B 1	1.22443139	E-2
B 2	5.73877310	E-2
B 3	1.86099124	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.040	
365		
370	0.340	
380	0.630	
390	0.780	
400	0.860	
420	0.931	
440	0.958	
460	0.970	
480	0.978	
500	0.983	
550	0.992	
600	0.995	
650	0.995	
700	0.997	
800	0.998	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.991	
2000	0.985	
2200	0.969	
2400	0.943	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	613
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	663
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		82
(10-7 / $^{\circ}\text{C}$ )		(+100~+300 $^{\circ}\text{C}$ ) 90
Thermal Conductivity (W/m·K)	<b>k</b>	0.994

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1053
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	415
Poisson's Ratio	$\sigma$	0.269
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	143
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.5

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80} / \lambda_{70}$	435				
Specific Gravity	<b>d</b>	3.68		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6} / ^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.9	3.8	3.9	4.2	4.7	5.7	7.0		
-20 ~ 0	2.8	3.9	3.9	4.3	4.8	5.9	7.2		
0 ~ 20	2.8	3.9	4.0	4.3	4.8	6.1	7.4		
20 ~ 40	2.8	3.9	4.0	4.4	4.9	6.2	7.6		
40 ~ 60	2.8	4.0	4.0	4.4	5.0	6.3	7.8		
60 ~ 80	2.9	4.1	4.2	4.6	5.2	6.6	8.2		

Refractive Index	$n_d$	<b>1.85478</b>	Abbe Number	$V_d$	<b>24.80</b>	Dispersion	$n_F - n_C$	<b>0.03447</b>
	$n_e$	1.854780		$V_e$	24.61		$n_{F'} - n_{C'}$	0.034469
		1.862904						0.035057

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.79234
$n_{1970}$	1.97009	1.79974
$n_{1530}$	1.52958	1.80847
$n_{1129}$	1.12864	1.81792
$n_t$	1.01398	1.82165
$n_s$	0.85211	1.82889
$n_{A'}$	0.76819	1.83429
$n_r$	0.70652	1.83949
$n_c$	0.65627	<b>1.84488</b>
$n_{c'}$	0.64385	1.84642
$n_{\text{He-Ne}}$	0.6328	1.84787
$n_D$	0.58929	1.85448
$n_d$	0.58756	<b>1.85478</b>
$n_e$	0.54607	1.86290
$n_F$	0.48613	<b>1.87935</b>
$n_{F'}$	0.47999	1.88147
$n_{\text{He-Cd}}$	0.44157	1.89755
$n_g$	0.435835	<b>1.90045</b>
$n_h$	0.404656	1.91944
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.023230
$n_c - n_{A'}$	0.010586
$n_d - n_c$	0.009904
$n_e - n_c$	0.018028
$n_g - n_d$	0.045668
$n_g - n_F$	0.021103
$n_h - n_g$	0.018989
$n_i - n_g$	
$n_{c'} - n_t$	0.024770
$n_e - n_{c'}$	0.016488
$n_{F'} - n_e$	0.018569
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6739
$\theta_{c,A'}$	0.3071
$\theta_{d,c}$	0.2873
$\theta_{e,c}$	0.5230
$\theta_{g,d}$	1.3249
$\theta_{g,F}$	0.6122
$\theta_{h,g}$	0.5509
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7066
$\theta'_{e,c'}$	0.4703
$\theta'_{F',e}$	0.5297
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0109
$\Delta\theta_{c,A'}$	0.0012
$\Delta\theta_{g,d}$	0.0117
$\Delta\theta_{g,F}$	0.0109
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	389	$\lambda_5$	358

CCI		
B	G	R
0.00	2.57	2.76

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.85191438	
A 2	4.31102852	E-1
A 3	3.45278284	
B 1	1.32732620	E-2
B 2	5.85944644	E-2
B 3	2.39357089	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.110	
365		
370	0.440	
380	0.690	
390	0.810	
400	0.870	
420	0.933	
440	0.958	
460	0.970	
480	0.978	
500	0.983	
550	0.993	
600	0.996	
650	0.996	
700	0.997	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.997	
1800	0.993	
2000	0.991	
2200	0.977	
2400	0.966	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	578
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	612
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		77
(+10~+300 $^{\circ}\text{C}$ )		94
Thermal Conductivity (W/m·K)	<b>k</b>	1.120

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1067
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	427
Poisson's Ratio	$\sigma$	0.249
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	127
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.35

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					395
Specific Gravity	<b>d</b>	3.49		$\lambda_5$					360
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.4	3.5	3.6	4.0	4.6	6.0	7.7		
-20 ~ 0	2.3	3.6	3.7	4.1	4.7	6.3	8.1		
0 ~ 20	2.3	3.6	3.7	4.2	4.8	6.5	8.5		
20 ~ 40	2.3	3.7	3.8	4.3	4.9	6.7	8.7		
40 ~ 60	2.3	3.8	3.9	4.4	5.1	6.8	9.0		
60 ~ 80	2.4	3.9	4.0	4.5	5.2	7.1	9.4		

Refractive Index	$n_d$	<b>1.85025</b>	Abbe Number	$V_d$	<b>30.05</b>	Dispersion	$n_F - n_C$	<b>0.02830</b>
	$n_e$	1.850250		$V_e$	29.82		$n_{F'} - n_{C'}$	0.028299
		1.856938						0.028738

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.79733
$n_{1970}$	1.97009	1.80374
$n_{1530}$	1.52958	1.81127
$n_{1129}$	1.12864	1.81935
$n_t$	1.01398	1.82252
$n_s$	0.85211	1.82864
$n_{A'}$	0.76819	1.83319
$n_r$	0.70652	1.83754
$n_c$	0.65627	<b>1.84204</b>
$n_{c'}$	0.64385	1.84332
$n_{\text{He-Ne}}$	0.6328	1.84453
$n_D$	0.58929	1.85000
$n_d$	0.58756	<b>1.85025</b>
$n_e$	0.54607	1.85694
$n_F$	0.48613	<b>1.87034</b>
$n_{F'}$	0.47999	1.87206
$n_{\text{He-Cd}}$	0.44157	1.88495
$n_g$	0.435835	<b>1.88726</b>
$n_h$	0.404656	1.90220
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.019520
$n_c - n_{A'}$	0.008849
$n_d - n_c$	0.008213
$n_e - n_c$	0.014901
$n_g - n_d$	0.037005
$n_g - n_F$	0.016919
$n_h - n_g$	0.014947
$n_i - n_g$	
$n_{c'} - n_t$	0.020801
$n_e - n_{c'}$	0.013620
$n_{F'} - n_e$	0.015118
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6898
$\theta_{c,A'}$	0.3127
$\theta_{d,c}$	0.2902
$\theta_{e,c}$	0.5266
$\theta_{g,d}$	1.3076
$\theta_{g,F}$	0.5979
$\theta_{h,g}$	0.5282
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7238
$\theta'_{e,c'}$	0.4739
$\theta'_{F',e}$	0.5261
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0021
$\Delta\theta_{c,A'}$	0.0004
$\Delta\theta_{g,d}$	0.0053
$\Delta\theta_{g,F}$	0.0051
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	399	$\lambda_5$	355

CCI		
B	G	R
0.00	3.97	4.14

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.92026488	
A 2	3.71535240	E-1
A 3	2.55205704	
B 1	1.18468028	E-2
B 2	5.32105472	E-2
B 3	2.04549300	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.170	
365		
370	0.420	
380	0.600	
390	0.720	
400	0.810	
420	0.890	
440	0.936	
460	0.955	
480	0.968	
500	0.978	
550	0.993	
600	0.994	
650	0.994	
700	0.996	
800	0.998	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.992	
2000	0.984	
2200	0.968	
2400	0.921	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	625
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	679
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		77
(+10~+300 $^{\circ}\text{C}$ )		92
Thermal Conductivity (W/m·K)	<b>k</b>	0.988

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	3.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1117
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	438
Poisson's Ratio	$\sigma$	0.275
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	140
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.95

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					410
Specific Gravity	<b>d</b>	4.00		$\lambda_5$					355
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.5	2.5	2.5	2.8	3.3	4.3	5.6		
-20 ~ 0	1.5	2.5	2.6	2.9	3.4	4.5	5.9		
0 ~ 20	1.4	2.5	2.6	3.0	3.4	4.7	6.1		
20 ~ 40	1.4	2.6	2.6	3.0	3.5	4.8	6.3		
40 ~ 60	1.5	2.7	2.7	3.1	3.7	5.0	6.6		
60 ~ 80	1.6	2.8	2.9	3.3	3.9	5.3	6.9		

Refractive Index	$n_d$	<b>1.61340</b>	Abbe Number	$V_d$	<b>44.27</b>	Dispersion	$n_F - n_C$	<b>0.01386</b>
	$n_e$	1.613397		$V_e$	44.02		$n_{F'} - n_{C'}$	0.013857
		1.616690						0.014008

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.57660
$n_{1970}$	1.97009	1.58313
$n_{1530}$	1.52958	1.59012
$n_{1129}$	1.12864	1.59633
$n_t$	1.01398	1.59841
$n_s$	0.85211	1.60206
$n_{A'}$	0.76819	1.60459
$n_r$	0.70652	1.60691
$n_c$	0.65627	<b>1.60925</b>
$n_{c'}$	0.64385	1.60990
$n_{\text{He-Ne}}$	0.6328	1.61052
$n_D$	0.58929	1.61328
$n_d$	0.58756	<b>1.61340</b>
$n_e$	0.54607	1.61669
$n_F$	0.48613	<b>1.62311</b>
$n_{F'}$	0.47999	1.62391
$n_{\text{He-Cd}}$	0.44157	1.62986
$n_g$	0.435835	<b>1.63091</b>
$n_h$	0.404656	1.63755
$n_i$	0.365015	1.64927
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.010843
$n_C - n_{A'}$	0.004663
$n_d - n_C$	0.004149
$n_e - n_C$	0.007442
$n_g - n_d$	0.017514
$n_g - n_F$	0.007806
$n_h - n_g$	0.006644
$n_i - n_g$	0.018359
$n_{C'} - n_t$	0.011500
$n_e - n_{C'}$	0.006785
$n_{F'} - n_e$	0.007223
$n_i - n_{F'}$	0.025357

Relative Partial Dispersions	
$\theta_{C,t}$	0.7825
$\theta_{C,A'}$	0.3365
$\theta_{d,C}$	0.2994
$\theta_{e,C}$	0.5371
$\theta_{g,d}$	1.2639
$\theta_{g,F}$	0.5633
$\theta_{h,g}$	0.4795
$\theta_{i,g}$	1.3249
$\theta'_{C,t}$	0.8210
$\theta'_{e,C'}$	0.4844
$\theta'_{F',e}$	0.5156
$\theta'_{i,F'}$	1.8102

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0281
$\Delta\theta_{C,A'}$	0.0070
$\Delta\theta_{g,d}$	-0.0089
$\Delta\theta_{g,F}$	-0.0065
$\Delta\theta_{i,g}$	-0.0294

Internal Transmittance			
$\lambda_{80}$	344	$\lambda_5$	319

CCI		
B	G	R
0.00	0.38	0.40

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.37023101	
A 2	1.77665568	E-1
A 3	1.30515471	
B 1	8.71920342	E-3
B 2	4.05725552	E-2
B 3	1.12703058	E2
1129 ~ 2325 nm		
A 1	1.37023101	
A 2	1.77665568	E-1
A 3	1.30515471	
B 1	8.71920342	E-3
B 2	4.05725552	E-2
B 3	1.12703058	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.080	
330	0.480	
340	0.750	
350	0.870	
360	0.925	
365		
370	0.953	
380	0.968	
390	0.978	
400	0.984	
420	0.989	
440	0.992	
460	0.993	
480	0.995	
500	0.997	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.994	
1800	0.987	
2000	0.972	
2200	0.890	
2400	0.760	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	509
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	531
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	554
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	611
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	693
Expansion Coefficient ( $10^{-7}/^{\circ}\text{C}$ )	$\alpha$	65 (-30~+70 $^{\circ}\text{C}$ ) 78 (+100~+300 $^{\circ}\text{C}$ )
Thermal Conductivity (W/m·K)	<b>k</b>	0.904

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	817
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	329
Poisson's Ratio	$\sigma$	0.243
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	121
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.47

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	350				
Specific Gravity	<b>d</b>	2.93		$\lambda_5$	320				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.0	3.4	3.4	3.6	3.8	4.2	4.7		
-20 ~ 0	3.1	3.6	3.6	3.7	3.9	4.4	4.9		
0 ~ 20	3.2	3.7	3.7	3.9	4.1	4.6	5.1		
20 ~ 40	3.2	3.8	3.8	4.0	4.2	4.8	5.3		
40 ~ 60	3.4	3.9	4.0	4.2	4.4	4.9	5.5		
60 ~ 80	3.5	4.1	4.1	4.3	4.5	5.1	5.7		



Refractive Index	$n_d$	<b>1.80809</b>	Abbe Number	$V_d$	<b>22.76</b>	Dispersion	$n_F - n_C$	<b>0.03550</b>
	$n_e$	1.808095		$V_e$	22.57		$n_{F'} - n_{C'}$	0.035504
		1.816434						0.036174

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.74455
$n_{1970}$	1.97009	1.75226
$n_{1530}$	1.52958	1.76125
$n_{1129}$	1.12864	1.77084
$n_t$	1.01398	1.77459
$n_s$	0.85211	1.78187
$n_{A'}$	0.76819	1.78731
$n_r$	0.70652	1.79256
$n_C$	0.65627	<b>1.79801</b>
$n_{C'}$	0.64385	1.79957
$n_{\text{He-Ne}}$	0.6328	1.80105
$n_D$	0.58929	1.80779
$n_d$	0.58756	<b>1.80809</b>
$n_e$	0.54607	1.81643
$n_F$	0.48613	<b>1.83351</b>
$n_{F'}$	0.47999	1.83575
$n_{\text{He-Cd}}$	0.44157	1.85279
$n_g$	0.435835	<b>1.85590</b>
$n_h$	0.404656	1.87658
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.023420
$n_C - n_{A'}$	0.010701
$n_d - n_C$	0.010086
$n_e - n_C$	0.018425
$n_g - n_d$	0.047809
$n_g - n_F$	0.022391
$n_h - n_g$	0.020676
$n_i - n_g$	
$n_{C'} - n_t$	0.024983
$n_e - n_{C'}$	0.016862
$n_{F'} - n_e$	0.019312
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6596
$\theta_{C,A'}$	0.3014
$\theta_{d,C}$	0.2841
$\theta_{e,C}$	0.5190
$\theta_{g,d}$	1.3466
$\theta_{g,F}$	0.6307
$\theta_{h,g}$	0.5824
$\theta_{i,g}$	
$\theta'_{C,t}$	0.6906
$\theta'_{e,C'}$	0.4661
$\theta'_{F',e}$	0.5339
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0061
$\Delta\theta_{C,A'}$	-0.0020
$\Delta\theta_{g,d}$	0.0292
$\Delta\theta_{g,F}$	0.0261
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	404	$\lambda_5$	378

CCI		
B	G	R
0.00	4.24	4.43

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.75156623	
A 2	3.64006304	E-1
A 3	2.47874141	
B 1	1.35004681	E-2
B 2	6.68245147	E-2
B 3	1.70756006	E2
1129 ~ 2325 nm		
A 1	1.75156623	
A 2	3.64006304	E-1
A 3	2.47874141	
B 1	1.35004681	E-2
B 2	6.68245147	E-2
B 3	1.70756006	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370		
380	0.140	
390	0.530	
400	0.770	
420	0.917	
440	0.952	
460	0.967	
480	0.975	
500	0.982	
550	0.992	
600	0.994	
650	0.995	
700	0.996	
800	0.997	
900	0.997	
1000	0.996	
1200	0.997	
1400	0.994	
1600	0.992	
1800	0.984	
2000	0.973	
2200	0.934	
2400	0.880	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	516
Annealing Point (°C)	<b>AP</b>	547
Transformation Temperature (°C)	<b>Tg</b>	552
Yield Point (°C)	<b>At</b>	589
Softening Point (°C)	<b>SP</b>	645
Expansion Coefficient $\alpha$ (-30~+70°C)		83
(10-7 /°C) (+100~+300°C)		104
Thermal Conductivity (W/m·K)	<b>k</b>	0.882

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	893
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	357
Poisson's Ratio	$\sigma$	0.250
Knoop Hardness	<b>Hk</b>	460 [5]
Abrasion	<b>Aa</b>	291
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.23

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	445				
Specific Gravity	<b>d</b>	3.29		$\lambda_5$	375				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.9	-1.2	-1.1	-0.7	-0.2	1.2	3.0		
-20 ~ 0	-1.9	-1.1	-1.0	-0.6		1.5	3.4		
0 ~ 20	-1.8	-0.9	-0.8	-0.4	0.2	1.8	3.8		
20 ~ 40	-1.8	-0.8	-0.7	-0.3	0.4	2.1	4.3		
40 ~ 60	-1.8	-0.7	-0.6	-0.1	0.6	2.4	4.7		
60 ~ 80	-1.7	-0.5	-0.4	0.1	0.8	2.7	5.1		

Refractive Index	$n_d$	<b>1.80809</b>	Abbe Number	$V_d$	<b>22.76</b>	Dispersion	$n_F - n_C$	<b>0.03550</b>
	$n_e$	1.808095		$V_e$	22.57		$n_{F'} - n_{C'}$	0.035504
		1.816434						0.036174

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.74455
$n_{1970}$	1.97009	1.75226
$n_{1530}$	1.52958	1.76125
$n_{1129}$	1.12864	1.77084
$n_t$	1.01398	1.77459
$n_s$	0.85211	1.78187
$n_{A'}$	0.76819	1.78731
$n_r$	0.70652	1.79256
$n_c$	0.65627	<b>1.79801</b>
$n_{c'}$	0.64385	1.79957
$n_{\text{He-Ne}}$	0.6328	1.80105
$n_D$	0.58929	1.80779
$n_d$	0.58756	<b>1.80809</b>
$n_e$	0.54607	1.81643
$n_F$	0.48613	<b>1.83351</b>
$n_{F'}$	0.47999	1.83575
$n_{\text{He-Cd}}$	0.44157	1.85279
$n_g$	0.435835	<b>1.85590</b>
$n_h$	0.404656	1.87658
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.023420
$n_c - n_{A'}$	0.010701
$n_d - n_c$	0.010086
$n_e - n_c$	0.018425
$n_g - n_d$	0.047809
$n_g - n_F$	0.022391
$n_h - n_g$	0.020676
$n_i - n_g$	
$n_{c'} - n_t$	0.024983
$n_e - n_{c'}$	0.016862
$n_{F'} - n_e$	0.019312
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6596
$\theta_{c,A'}$	0.3014
$\theta_{d,c}$	0.2841
$\theta_{e,c}$	0.5190
$\theta_{g,d}$	1.3466
$\theta_{g,F}$	0.6307
$\theta_{h,g}$	0.5824
$\theta_{i,g}$	
$\theta'_{c,t}$	0.6906
$\theta'_{e,c'}$	0.4661
$\theta'_{F',e}$	0.5339
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0061
$\Delta\theta_{c,A'}$	-0.0020
$\Delta\theta_{g,d}$	0.0292
$\Delta\theta_{g,F}$	0.0261
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	395	$\lambda_5$	372

CCI		
B	G	R
0.00	2.65	2.84

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.75156623	
A 2	3.64006304	E-1
A 3	2.47874141	
B 1	1.35004681	E-2
B 2	6.68245147	E-2
B 3	1.70756006	E2
1129 ~ 2325 nm		
A 1	1.75156623	
A 2	3.64006304	E-1
A 3	2.47874141	
B 1	1.35004681	E-2
B 2	6.68245147	E-2
B 3	1.70756006	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370		
380	0.280	
390	0.670	
400	0.870	
420	0.956	
440	0.972	
460	0.978	
480	0.983	
500	0.986	
550	0.993	
600	0.996	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.994	
1800	0.986	
2000	0.973	
2200	0.932	
2400	0.880	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	516
Annealing Point (°C)	<b>AP</b>	547
Transformation Temperature (°C)	<b>Tg</b>	552
Yield Point (°C)	<b>At</b>	589
Softening Point (°C)	<b>SP</b>	645
Expansion Coefficient $\alpha$ (-30~+70°C)		83
(10-7 /°C) (+100~+300°C)		104
Thermal Conductivity (W/m·K)	<b>k</b>	0.882

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	893
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	357
Poisson's Ratio	$\sigma$	0.250
Knoop Hardness	<b>Hk</b>	460 [5]
Abrasion	<b>Aa</b>	291
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.23

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	420				
Specific Gravity	<b>d</b>	3.29		$\lambda_5$	375				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.9	-1.2	-1.1	-0.7	-0.2	1.2	3.0		
-20 ~ 0	-1.9	-1.1	-1.0	-0.6	0.0	1.5	3.4		
0 ~ 20	-1.8	-0.9	-0.8	-0.4	0.2	1.8	3.8		
20 ~ 40	-1.8	-0.8	-0.7	-0.3	0.4	2.1	4.3		
40 ~ 60	-1.8	-0.7	-0.6	-0.1	0.6	2.4	4.7		
60 ~ 80	-1.7	-0.5	-0.4	0.1	0.8	2.7	5.1		

Refractive Index	$n_d$	<b>1.92286</b>	Abbe Number	$V_d$	<b>18.90</b>	Dispersion	$n_F - n_C$	<b>0.04884</b>
		1.922860			$V_e$		18.74	
	$n_e$	1.934291					$n_{F'} - n_{C'}$	0.049853

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.84214
$n_{1970}$	1.97009	1.85093
$n_{1530}$	1.52958	1.86146
$n_{1129}$	1.12864	1.87327
$n_t$	1.01398	1.87807
$n_s$	0.85211	1.88758
$n_{A'}$	0.76819	1.89479
$n_r$	0.70652	1.90181
$n_c$	0.65627	<b>1.90916</b>
$n_{c'}$	0.64385	1.91127
$n_{\text{He-Ne}}$	0.6328	1.91327
$n_D$	0.58929	1.92245
$n_d$	0.58756	<b>1.92286</b>
$n_e$	0.54607	1.93429
$n_F$	0.48613	<b>1.95800</b>
$n_{F'}$	0.47999	1.96112
$n_{\text{He-Cd}}$	0.44157	1.98526
$n_g$	0.435835	<b>1.98972</b>
$n_h$	0.404656	2.01976
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.031086
$n_c - n_{A'}$	0.014367
$n_d - n_c$	0.013702
$n_e - n_c$	0.025133
$n_g - n_d$	0.066857
$n_g - n_F$	0.031721
$n_h - n_g$	0.030046
$n_i - n_g$	
$n_{c'} - n_t$	0.033200
$n_e - n_{c'}$	0.023019
$n_{F'} - n_e$	0.026834
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6365
$\theta_{c,A'}$	0.2942
$\theta_{d,c}$	0.2806
$\theta_{e,c}$	0.5146
$\theta_{g,d}$	1.3690
$\theta_{g,F}$	0.6495
$\theta_{h,g}$	0.6152
$\theta_{i,g}$	
$\theta'_{c,t}$	0.6660
$\theta'_{e,c'}$	0.4617
$\theta'_{F',e}$	0.5383
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0012
$\Delta\theta_{c,A'}$	-0.0045
$\Delta\theta_{g,d}$	0.0436
$\Delta\theta_{g,F}$	0.0386
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	433	$\lambda_5$	391

CCI		
B	G	R
0.00	12.87	13.51

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.03869510	
A 2	4.37269641	E-1
A 3	2.96711461	
B 1	1.70796224	E-2
B 2	7.49254813	E-2
B 3	1.74155354	E2
1129 ~ 2325 nm		
A 1	2.03869510	
A 2	4.37269641	E-1
A 3	2.96711461	
B 1	1.70796224	E-2
B 2	7.49254813	E-2
B 3	1.74155354	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370		
380		
390	0.020	
400	0.240	
420	0.700	
440	0.850	
460	0.910	
480	0.936	
500	0.953	
550	0.978	
600	0.988	
650	0.990	
700	0.993	
800	0.996	
900	0.996	
1000	0.996	
1200	0.997	
1400	0.997	
1600	0.996	
1800	0.992	
2000	0.988	
2200	0.977	
2400	0.961	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	604
Annealing Point (°C)	<b>AP</b>	631
Transformation Temperature (°C)	<b>Tg</b>	650
Yield Point (°C)	<b>At</b>	676
Softening Point (°C)	<b>SP</b>	716
Expansion Coefficient $\alpha$ (-30~+70°C)		67
(10-7 /°C) (+100~+300°C)		83
Thermal Conductivity (W/m·K)	<b>k</b>	0.969

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	991
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	397
Poisson's Ratio	$\sigma$	0.249
Knoop Hardness	<b>Hk</b>	450 [5]
Abrasion	<b>Aa</b>	224
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.31

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					440
Specific Gravity	<b>d</b>	3.58		$\lambda_5$					390
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.6	0.4	0.5	1.2	1.8	3.8	6.6		
-20 ~ 0	-0.6	0.6	0.7	1.4	2.1	4.3	7.4		
0 ~ 20	-0.4	0.9	1.0	1.8	2.5	4.8	8.1		
20 ~ 40	-0.2	1.1	1.3	2.1	2.8	5.4	8.8		
40 ~ 60	0.0	1.4	1.5	2.3	3.2	5.9	9.6		
60 ~ 80	0.2	1.6	1.8	2.7	3.6	6.4	10.3		

Refractive Index	$n_d$	<b>1.95906</b>	Abbe Number	$V_d$	<b>17.47</b>	Dispersion	$n_F - n_C$	<b>0.05490</b>
	$n_e$	1.959060		$V_e$	17.33		$n_{F'} - n_{C'}$	0.054895
		1.971885						0.056091

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.87064
$n_{1970}$	1.97009	1.88003
$n_{1530}$	1.52958	1.89131
$n_{1129}$	1.12864	1.90412
$n_t$	1.01398	1.90937
$n_s$	0.85211	1.91984
$n_{A'}$	0.76819	1.92780
$n_r$	0.70652	1.93559
$n_c$	0.65627	<b>1.94376</b>
$n_{c'}$	0.64385	1.94612
$n_{\text{He-Ne}}$	0.6328	1.94835
$n_D$	0.58929	1.95860
$n_d$	0.58756	<b>1.95906</b>
$n_e$	0.54607	1.97189
$n_F$	0.48613	<b>1.99866</b>
$n_{F'}$	0.47999	2.00221
$n_{\text{He-Cd}}$	0.44157	2.02976
$n_g$	0.435835	<b>2.03488</b>
$n_h$	0.404656	2.06965
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.034388
$n_C - n_{A'}$	0.015956
$n_d - n_C$	0.015300
$n_e - n_C$	0.028125
$n_g - n_d$	0.075817
$n_g - n_F$	0.036222
$n_h - n_g$	0.034773
$n_i - n_g$	
$n_{C'} - n_t$	0.036744
$n_e - n_{C'}$	0.025769
$n_{F'} - n_e$	0.030322
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6264
$\theta_{C,A'}$	0.2907
$\theta_{d,C}$	0.2787
$\theta_{e,C}$	0.5123
$\theta_{g,d}$	1.3811
$\theta_{g,F}$	0.6598
$\theta_{h,g}$	0.6334
$\theta_{i,g}$	
$\theta'_{C,t}$	0.6551
$\theta'_{e,C'}$	0.4594
$\theta'_{F',e}$	0.5406
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.0022
$\Delta\theta_{C,A'}$	-0.0063
$\Delta\theta_{g,d}$	0.0527
$\Delta\theta_{g,F}$	0.0466
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	430	$\lambda_5$	398

CCI		
B	G	R
0.00	13.14	13.56

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.09834903	
A 2	4.89088388	E-1
A 3	2.94009268	
B 1	1.79123869	E-2
B 2	7.76653353	E-2
B 3	1.60930428	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370		
380		
390	0.040	
400	0.120	
420	0.720	
440	0.880	
460	0.932	
480	0.956	
500	0.970	
550	0.990	
600	0.996	
650	0.997	
700	0.999	
800	0.999	
900	0.998	
1000	0.998	
1200	0.999	
1400	0.998	
1600	0.995	
1800	0.989	
2000	0.983	
2200	0.968	
2400	0.949	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	671
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	704
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		59
(+100~+300 $^{\circ}\text{C}$ )		65
Thermal Conductivity (W/m·K)	<b>k</b>	1.007

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1022
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	411
Poisson's Ratio	$\sigma$	0.243
Knoop Hardness	<b>Hk</b>	450 [5]
Abrasion	<b>Aa</b>	194
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.35

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80} / \lambda_{70}$					440
Specific Gravity	<b>d</b>	3.59		$\lambda_5$					395
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6} / ^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.6	2.1	2.2	2.8	3.7	6.2	9.6		
-20 ~ 0	0.8	2.4	2.6	3.2	4.2	6.9	10.6		
0 ~ 20	1.1	2.8	2.9	3.6	4.6	7.6	11.6		
20 ~ 40	1.2	3.1	3.2	3.9	5.0	8.2	12.4		
40 ~ 60	1.4	3.4	3.5	4.3	5.5	8.8	13.3		
60 ~ 80	1.7	3.8	3.9	4.8	6.0	9.5	14.3		

Refractive Index	$n_d$	<b>1.89286</b>	Abbe Number	$V_d$	<b>20.36</b>	Dispersion	$n_F - n_C$	<b>0.04385</b>
		1.892860			$V_e$		20.20	
	$n_e$	1.903144					$n_{F'} - n_{C'}$	0.044721

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.81864
$n_{1970}$	1.97009	1.82694
$n_{1530}$	1.52958	1.83681
$n_{1129}$	1.12864	1.84777
$n_t$	1.01398	1.85218
$n_s$	0.85211	1.86088
$n_{A'}$	0.76819	1.86745
$n_r$	0.70652	1.87383
$n_c$	0.65627	<b>1.88048</b>
$n_{c'}$	0.64385	1.88240
$n_{\text{He-Ne}}$	0.6328	1.88421
$n_D$	0.58929	1.89249
$n_d$	0.58756	<b>1.89286</b>
$n_e$	0.54607	1.90314
$n_F$	0.48613	<b>1.92434</b>
$n_{F'}$	0.47999	1.92712
$n_{\text{He-Cd}}$	0.44157	1.94846
$n_g$	0.435835	<b>1.95237</b>
$n_h$	0.404656	1.97853
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.028304
$n_c - n_{A'}$	0.013036
$n_d - n_c$	0.012376
$n_e - n_c$	0.022660
$n_g - n_d$	0.059511
$n_g - n_F$	0.028036
$n_h - n_g$	0.026158
$n_i - n_g$	
$n_{c'} - n_t$	0.030217
$n_e - n_{c'}$	0.020747
$n_{F'} - n_e$	0.023974
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6455
$\theta_{c,A'}$	0.2973
$\theta_{d,c}$	0.2822
$\theta_{e,c}$	0.5167
$\theta_{g,d}$	1.3571
$\theta_{g,F}$	0.6393
$\theta_{h,g}$	0.5965
$\theta_{i,g}$	
$\theta'_{c,t}$	0.6757
$\theta'_{e,c'}$	0.4639
$\theta'_{F',e}$	0.5361
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0033
$\Delta\theta_{c,A'}$	-0.0032
$\Delta\theta_{g,d}$	0.0347
$\Delta\theta_{g,F}$	0.0308
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	409	$\lambda_5$	380

CCI		
B	G	R
0.00	4.93	5.17

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.93563931	
A 2	4.49596478	E-1
A 3	2.71828573	
B 1	1.52585289	E-2
B 2	6.96815778	E-2
B 3	1.70327149	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370		
380	0.060	
390	0.390	
400	0.710	
420	0.915	
440	0.951	
460	0.966	
480	0.975	
500	0.982	
550	0.993	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.995	
1800	0.984	
2000	0.971	
2200	0.948	
2400	0.915	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	638
Yield Point (°C)	<b>At</b>	668
Softening Point (°C)	<b>SP</b>	711
Expansion Coefficient $\alpha$ (-30~+70°C)		73
(10 <sup>-7</sup> /°C)	(+100~+300°C)	88
Thermal Conductivity (W/m·K)	<b>k</b>	0.925

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	945
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	377
Poisson's Ratio	$\sigma$	0.254
Knoop Hardness	<b>Hk</b>	440 [4]
Abrasion	<b>Aa</b>	213
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.39

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					410
Specific Gravity	<b>d</b>	3.61		$\lambda_5$					380
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.1	0.1	0.2	0.6	1.3	3.0	5.3		
-20 ~ 0	-1.1	0.2	0.3	0.7	1.5	3.4	5.8		
0 ~ 20	-1.0	0.3	0.4	0.9	1.7	3.7	6.3		
20 ~ 40	-1.0	0.4	0.5	1.1	1.9	4.1	6.8		
40 ~ 60	-0.9	0.6	0.7	1.3	2.1	4.4	7.4		
60 ~ 80	-0.7	0.8	0.9	1.6	2.4	4.9	8.0		

Refractive Index	$n_d$	<b>1.85896</b>	Abbe Number	$V_d$	<b>22.73</b>	Dispersion	$n_F - n_C$	<b>0.03779</b>
		1.858956			$V_e$		22.54	
	$n_e$	1.867836					$n_{F'} - n_{C'}$	0.038499

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.79247
$n_{1970}$	1.97009	1.80027
$n_{1530}$	1.52958	1.80944
$n_{1129}$	1.12864	1.81938
$n_t$	1.01398	1.82333
$n_s$	0.85211	1.83104
$n_{A'}$	0.76819	1.83681
$n_r$	0.70652	1.84240
$n_c$	0.65627	<b>1.84821</b>
$n_{c'}$	0.64385	1.84987
$n_{\text{He-Ne}}$	0.6328	1.85145
$n_D$	0.58929	1.85863
$n_d$	0.58756	<b>1.85896</b>
$n_e$	0.54607	1.86784
$n_F$	0.48613	<b>1.88600</b>
$n_{F'}$	0.47999	1.88837
$n_{\text{He-Cd}}$	0.44157	1.90645
$n_g$	0.435835	<b>1.90975</b>
$n_h$	0.404656	1.93160
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.024883
$n_c - n_{A'}$	0.011397
$n_d - n_c$	0.010747
$n_e - n_c$	0.019627
$n_g - n_d$	0.050792
$n_g - n_F$	0.023747
$n_h - n_g$	0.021851
$n_i - n_g$	
$n_{c'} - n_t$	0.026548
$n_e - n_{c'}$	0.017962
$n_{F'} - n_e$	0.020537
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6584
$\theta_{c,A'}$	0.3016
$\theta_{d,c}$	0.2844
$\theta_{e,c}$	0.5193
$\theta_{g,d}$	1.3440
$\theta_{g,F}$	0.6284
$\theta_{h,g}$	0.5782
$\theta_{i,g}$	
$\theta'_{c,t}$	0.6896
$\theta'_{e,c'}$	0.4666
$\theta'_{F',e}$	0.5334
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0051
$\Delta\theta_{c,A'}$	-0.0018
$\Delta\theta_{g,d}$	0.0265
$\Delta\theta_{g,F}$	0.0237
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	397	$\lambda_5$	364

CCI		
B	G	R
0.00	3.38	3.62

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.89108996	
A 2	3.95220126	E-1
A 3	2.20492127	
B 1	1.41164499	E-2
B 2	6.62834445	E-2
B 3	1.48680700	E2
1129 ~ 2325 nm		
A 1	1.89108996	
A 2	3.95220126	E-1
A 3	2.20492127	
B 1	1.41164499	E-2
B 2	6.62834445	E-2
B 3	1.48680700	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.030	
365		
370	0.080	
380	0.410	
390	0.720	
400	0.840	
420	0.924	
440	0.949	
460	0.962	
480	0.971	
500	0.979	
550	0.991	
600	0.994	
650	0.995	
700	0.996	
800	0.998	
900	0.998	
1000	0.998	
1200	0.999	
1400	0.996	
1600	0.993	
1800	0.984	
2000	0.972	
2200	0.944	
2400	0.915	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	573
Annealing Point (°C)	<b>AP</b>	599
Transformation Temperature (°C)	<b>Tg</b>	609
Yield Point (°C)	<b>At</b>	651
Softening Point (°C)	<b>SP</b>	704
Expansion Coefficient $\alpha$ (-30~+70°C)		76
Expansion Coefficient $\alpha$ (+100~+300°C)		84
Thermal Conductivity (W/m·K)	<b>k</b>	0.877

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	929
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	370
Poisson's Ratio	$\sigma$	0.256
Knoop Hardness	<b>Hk</b>	470 [5]
Abrasion	<b>Aa</b>	224
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.18

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					400
Specific Gravity	<b>d</b>	3.71		$\lambda_5$					370
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.0	1.0	1.1	1.5	2.0	3.5	5.3		
-20 ~ 0	0.0	1.1	1.2	1.6	2.2	3.8	5.8		
0 ~ 20	0.0	1.2	1.3	1.7	2.4	4.1	6.2		
20 ~ 40	0.1	1.3	1.4	1.9	2.6	4.4	6.6		
40 ~ 60	0.2	1.5	1.6	2.1	2.8	4.7	7.0		
60 ~ 80	0.3	1.7	1.8	2.3	3.1	5.1	7.6		



Refractive Index	$n_d$	<b>1.84666</b>	Abbe Number	$V_d$	<b>23.88</b>	Dispersion	$n_F - n_C$	<b>0.03545</b>
	$n_e$	1.846660		$V_e$	23.69		$n_{F'} - n_{C'}$	0.035449
		1.855001						0.036088

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78347
$n_{1970}$	1.97009	1.79094
$n_{1530}$	1.52958	1.79971
$n_{1129}$	1.12864	1.80921
$n_t$	1.01398	1.81297
$n_s$	0.85211	1.82029
$n_{A'}$	0.76819	1.82577
$n_r$	0.70652	1.83105
$n_C$	0.65627	<b>1.83654</b>
$n_{C'}$	0.64385	1.83811
$n_{\text{He-Ne}}$	0.6328	1.83959
$n_D$	0.58929	1.84636
$n_d$	0.58756	<b>1.84666</b>
$n_e$	0.54607	1.85500
$n_F$	0.48613	<b>1.87199</b>
$n_{F'}$	0.47999	1.87420
$n_{\text{He-Cd}}$	0.44157	1.89098
$n_g$	0.435835	<b>1.89403</b>
$n_h$	0.404656	1.91412
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	569
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	590
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	621
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	663
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	715
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		74
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	90
Thermal Conductivity (W/m·K)	<b>k</b>	0.830

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	886
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	352
Poisson's Ratio	$\sigma$	0.258
Knoop Hardness	<b>Hk</b>	420 [4]
Abrasion	<b>Aa</b>	286
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.18

Partial Dispersions	
$n_C - n_t$	0.023568
$n_C - n_{A'}$	0.010771
$n_d - n_C$	0.010123
$n_e - n_C$	0.018464
$n_g - n_d$	0.047367
$n_g - n_F$	0.022041
$n_h - n_g$	0.020094
$n_i - n_g$	
$n_{C'} - n_t$	0.025139
$n_e - n_{C'}$	0.016893
$n_{F'} - n_e$	0.019195
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0061
$\Delta\theta_{C,A'}$	-0.0010
$\Delta\theta_{g,d}$	0.0211
$\Delta\theta_{g,F}$	0.0190
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.85484904	
A 2	3.96194484	E-1
A 3	2.43512461	
B 1	1.34621486	E-2
B 2	6.31945361	E-2
B 3	1.70864886	E2
1129 ~ 2325 nm		
A 1	1.85484904	
A 2	3.96194484	E-1
A 3	2.43512461	
B 1	1.34621486	E-2
B 2	6.31945361	E-2
B 3	1.70864886	E-2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	2.3
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6648
$\theta_{C,A'}$	0.3038
$\theta_{d,C}$	0.2856
$\theta_{e,C}$	0.5209
$\theta_{g,d}$	1.3362
$\theta_{g,F}$	0.6218
$\theta_{h,g}$	0.5668
$\theta_{i,g}$	
$\theta'_{C,t}$	0.6966
$\theta'_{e,C'}$	0.4681
$\theta'_{F',e}$	0.5319
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	394	$\lambda_5$	360

CCI		
B	G	R
0.00	3.24	3.66

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.050	
365		
370	0.340	
380	0.630	
390	0.770	
400	0.850	
420	0.914	
440	0.940	
460	0.953	
480	0.962	
500	0.971	
550	0.988	
600	0.994	
650	0.996	
700	0.997	
800	0.998	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.995	
1800	0.986	
2000	0.976	
2200	0.952	
2400	0.927	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					400
Specific Gravity	<b>d</b>	3.78		$\lambda_5$					360
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.9	0.1	0.2	0.5	1.1	2.4	4.0		
-20 ~ 0	-0.8	0.2	0.3	0.7	1.2	2.6	4.4		
0 ~ 20	-0.8	0.3	0.4	0.8	1.4	2.9	4.8		
20 ~ 40	-0.8	0.4	0.5	1.0	1.6	3.2	5.2		
40 ~ 60	-0.7	0.6	0.7	1.1	1.8	3.5	5.6		
60 ~ 80	-0.7	0.7	0.8	1.3	2.0	3.7	6.0		

Refractive Index	$n_d$	<b>1.51823</b>	Abbe Number	$V_d$	<b>58.90</b>	Dispersion	$n_F - n_C$	<b>0.00879</b>
	$n_e$	1.518229		$V_e$	58.63		$n_{F'} - n_{C'}$	0.008798
		1.520326						0.008875

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.49273
$n_{1970}$	1.97009	1.49747
$n_{1530}$	1.52958	1.50252
$n_{1129}$	1.12864	1.50692
$n_t$	1.01398	1.50835
$n_s$	0.85211	1.51083
$n_{A'}$	0.76819	1.51250
$n_r$	0.70652	1.51403
$n_c$	0.65627	<b>1.51556</b>
$n_{c'}$	0.64385	1.51598
$n_{\text{He-Ne}}$	0.6328	1.51638
$n_D$	0.58929	1.51815
$n_d$	0.58756	<b>1.51823</b>
$n_e$	0.54607	1.52033
$n_F$	0.48613	<b>1.52435</b>
$n_{F'}$	0.47999	1.52486
$n_{\text{He-Cd}}$	0.44157	1.52852
$n_g$	0.435835	<b>1.52915</b>
$n_h$	0.404656	1.53315
$n_i$	0.365015	1.53999
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.007206
$n_c - n_{A'}$	0.003052
$n_d - n_c$	0.002673
$n_e - n_c$	0.004770
$n_g - n_d$	0.010926
$n_g - n_F$	0.004801
$n_h - n_g$	0.003996
$n_i - n_g$	0.010832
$n_{c'} - n_t$	0.007631
$n_{e'} - n_{c'}$	0.004345
$n_{F'} - n_e$	0.004530
$n_i - n_{F'}$	0.015131

Relative Partial Dispersions	
$\theta_{c,t}$	0.8190
$\theta_{c,A'}$	0.3469
$\theta_{d,c}$	0.3038
$\theta_{e,c}$	0.5422
$\theta_{g,d}$	1.2419
$\theta_{g,F}$	0.5457
$\theta_{h,g}$	0.4542
$\theta_{i,g}$	1.2312
$\theta'_{c',t}$	0.8598
$\theta'_{e,c'}$	0.4896
$\theta'_{F',e}$	0.5104
$\theta'_{i,F'}$	1.7049

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0040
$\Delta\theta_{c,A'}$	-0.0004
$\Delta\theta_{g,d}$	-0.0005
$\Delta\theta_{g,F}$	-0.0005
$\Delta\theta_{i,g}$	-0.0006

Internal Transmittance			
$\lambda_{80}$	340	$\lambda_5$	317

CCI		
B	G	R
0.00	0.09	0.06

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	8.82514764	E-1
A 2	3.89271907	E-1
A 3	1.10693448	
B 1	4.64504582	E-3
B 2	2.00551397	E-2
B 3	1.36234339	E2
1129 ~ 2325 nm		
A 1	8.82514764	E-1
A 2	3.89271907	E-1
A 3	1.10693448	
B 1	4.64504582	E-3
B 2	2.00551397	E-2
B 3	1.36234339	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.150	
330	0.530	
340	0.800	
350	0.924	
360	0.968	
365		
370	0.984	
380	0.990	
390	0.995	
400	0.997	
420	0.997	
440	0.997	
460	0.997	
480	0.998	
500	0.998	
550	0.999	
600	0.999	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.992	
1600	0.991	
1800	0.968	
2000	0.930	
2200	0.860	
2400	0.810	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	455
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	492
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	500
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	553
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	668
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	90
	(+10-7~+300 $^{\circ}\text{C}$ )	110
Thermal Conductivity (W/m·K)	<b>k</b>	1.026

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	700
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	288
Poisson's Ratio	$\sigma$	0.217
Knoop Hardness	<b>Hk</b>	510 [5]
Abrasion	<b>Aa</b>	111
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.6

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	340				
Specific Gravity	<b>d</b>	2.48		$\lambda_5$	310				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.3	0.6	0.6	0.7	0.8	1.1	1.4		
-20 ~ 0	0.3	0.6	0.6	0.7	0.8	1.1	1.4		
0 ~ 20	0.3	0.6	0.6	0.7	0.9	1.2	1.5		
20 ~ 40	0.3	0.6	0.6	0.7	0.9	1.2	1.6		
40 ~ 60	0.3	0.6	0.7	0.8	0.9	1.3	1.6		
60 ~ 80	0.3	0.6	0.7	0.8	1.0	1.3	1.7		

Refractive Index	$n_d$	<b>1.52249</b>	Abbe Number	$V_d$	<b>59.84</b>	Dispersion	$n_F - n_C$	<b>0.00874</b>
		1.522494			$V_e$		59.58	
	$n_e$	1.524576					$n_{F'} - n_{C'}$	0.008805

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.49592
$n_{1970}$	1.97009	1.50104
$n_{1530}$	1.52958	1.50646
$n_{1129}$	1.12864	1.51108
$n_t$	1.01398	1.51256
$n_s$	0.85211	1.51509
$n_{A'}$	0.76819	1.51678
$n_r$	0.70652	1.51831
$n_c$	0.65627	<b>1.51983</b>
$n_{c'}$	0.64385	1.52026
$n_{\text{He-Ne}}$	0.6328	1.52065
$n_D$	0.58929	1.52242
$n_d$	0.58756	<b>1.52249</b>
$n_e$	0.54607	1.52458
$n_F$	0.48613	<b>1.52857</b>
$n_{F'}$	0.47999	1.52906
$n_{\text{He-Cd}}$	0.44157	1.53269
$n_g$	0.435835	<b>1.53332</b>
$n_h$	0.404656	1.53727
$n_i$	0.365015	1.54403
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.007270
$n_c - n_{A'}$	0.003054
$n_d - n_c$	0.002660
$n_e - n_c$	0.004742
$n_g - n_d$	0.010822
$n_g - n_F$	0.004750
$n_h - n_g$	0.003952
$n_i - n_g$	0.010715
$n_{c'} - n_t$	0.007694
$n_e - n_{c'}$	0.004318
$n_{F'} - n_e$	0.004487
$n_i - n_{F'}$	0.014968

Relative Partial Dispersions	
$\theta_{c,t}$	0.8326
$\theta_{c,A'}$	0.3497
$\theta_{d,c}$	0.3046
$\theta_{e,c}$	0.5431
$\theta_{g,d}$	1.2393
$\theta_{g,F}$	0.5440
$\theta_{h,g}$	0.4526
$\theta_{i,g}$	1.2271
$\theta'_{c,t}$	0.8738
$\theta'_{e,c'}$	0.4904
$\theta'_{F',e}$	0.5096
$\theta'_{i,F'}$	1.6999

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0052
$\Delta\theta_{c,A'}$	0.0013
$\Delta\theta_{g,d}$	-0.0011
$\Delta\theta_{g,F}$	-0.0007
$\Delta\theta_{i,g}$	0.0032

Internal Transmittance			
$\lambda_{80}$	347	$\lambda_5$	320

CCI		
B	G	R
0.00	0.11	0.08

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.04574577	
A 2	2.39613026	E-1
A 3	1.15906850	
B 1	5.85232280	E-3
B 2	2.36858752	E-2
B 3	1.31329061	E2
1129 ~ 2325 nm		
A 1	1.04574577	
A 2	2.39613026	E-1
A 3	1.15906850	
B 1	5.85232280	E-3
B 2	2.36858752	E-2
B 3	1.31329061	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.040	
330	0.320	
340	0.670	
350	0.860	
360	0.941	
365		
370	0.972	
380	0.984	
390	0.992	
400	0.995	
420	0.996	
440	0.996	
460	0.996	
480	0.997	
500	0.998	
550	0.998	
600	0.998	
650	0.997	
700	0.998	
800	0.998	
900	0.998	
1000	0.998	
1200	0.997	
1400	0.988	
1600	0.992	
1800	0.972	
2000	0.939	
2200	0.860	
2400	0.810	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	502
Annealing Point (°C)	<b>AP</b>	536
Transformation Temperature (°C)	<b>Tg</b>	548
Yield Point (°C)	<b>At</b>	596
Softening Point (°C)	<b>SP</b>	700
Expansion Coefficient $\alpha$ (-30~+70°C)		82
(10-7 /°C) (+100~+300°C)		95
Thermal Conductivity (W/m·K)	<b>k</b>	1.058

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	691
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	303
Poisson's Ratio	$\sigma$	0.140
Knoop Hardness	<b>Hk</b>	540 [5]
Abrasion	<b>Aa</b>	114
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.67

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	2.49		$\lambda_5$	320				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.0	1.1	1.2	1.2	1.4	1.6	1.9		
-20 ~ 0	1.0	1.2	1.2	1.3	1.4	1.7	2.0		
0 ~ 20	1.0	1.2	1.3	1.4	1.5	1.8	2.1		
20 ~ 40	1.0	1.3	1.3	1.4	1.6	1.9	2.2		
40 ~ 60	1.0	1.4	1.4	1.5	1.6	2.0	2.3		
60 ~ 80	1.1	1.4	1.4	1.5	1.7	2.0	2.4		

Refractive Index	$n_d$	<b>1.51742</b>	Abbe Number	$V_d$	<b>52.43</b>	Dispersion	$n_F - n_C$	<b>0.00987</b>
		1.517417			$V_e$		52.14	
	$n_e$	1.519765					$n_{F'} - n_{C'}$	0.009968

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.49004
$n_{1970}$	1.97009	1.49501
$n_{1530}$	1.52958	1.50033
$n_{1129}$	1.12864	1.50501
$n_t$	1.01398	1.50656
$n_s$	0.85211	1.50924
$n_{A'}$	0.76819	1.51108
$n_r$	0.70652	1.51276
$n_c$	0.65627	<b>1.51444</b>
$n_{c'}$	0.64385	1.51492
$n_{\text{He-Ne}}$	0.6328	1.51536
$n_D$	0.58929	1.51733
$n_d$	0.58756	<b>1.51742</b>
$n_e$	0.54607	1.51976
$n_F$	0.48613	<b>1.52431</b>
$n_{F'}$	0.47999	1.52488
$n_{\text{He-Cd}}$	0.44157	1.52907
$n_g$	0.435835	<b>1.52980</b>
$n_h$	0.404656	1.53444
$n_i$	0.365015	1.54252
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.007887
$n_c - n_{A'}$	0.003365
$n_d - n_c$	0.002973
$n_e - n_c$	0.005321
$n_g - n_d$	0.012387
$n_g - n_F$	0.005491
$n_h - n_g$	0.004635
$n_i - n_g$	0.012715
$n_{c'} - n_t$	0.008359
$n_{e'} - n_{c'}$	0.004849
$n_{F'} - n_e$	0.005119
$n_i - n_{F'}$	0.017635

Relative Partial Dispersions	
$\theta_{c,t}$	0.7992
$\theta_{c,A'}$	0.3410
$\theta_{d,c}$	0.3012
$\theta_{e,c}$	0.5392
$\theta_{g,d}$	1.2551
$\theta_{g,F}$	0.5564
$\theta_{h,g}$	0.4697
$\theta_{i,g}$	1.2884
$\theta'_{c,t}$	0.8386
$\theta'_{e,c'}$	0.4865
$\theta'_{F',e}$	0.5135
$\theta'_{i,F'}$	1.7692

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0065
$\Delta\theta_{c,A'}$	0.0016
$\Delta\theta_{g,d}$	-0.0007
$\Delta\theta_{g,F}$	-0.0002
$\Delta\theta_{i,g}$	0.0024

Internal Transmittance			
$\lambda_{80}$	360	$\lambda_5$	337

CCI		
B	G	R
0.00	0.22	0.20

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.09666153	
A 2	1.68990073	E-1
A 3	1.20580827	
B 1	6.67491123	E-3
B 2	3.36095450	E-2
B 3	1.41668738	E2
1129 ~ 2325 nm		
A 1	1.09666153	
A 2	1.68990073	E-1
A 3	1.20580827	
B 1	6.67491123	E-3
B 2	3.36095450	E-2
B 3	1.41668738	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.180	
350	0.570	
360	0.810	
365		
370	0.917	
380	0.960	
390	0.980	
400	0.989	
420	0.995	
440	0.996	
460	0.997	
480	0.998	
500	0.998	
550	0.999	
600	0.999	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.996	
1600	0.994	
1800	0.978	
2000	0.950	
2200	0.890	
2400	0.860	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	429
Annealing Point (°C)	<b>AP</b>	465
Transformation Temperature (°C)	<b>Tg</b>	464
Yield Point (°C)	<b>At</b>	522
Softening Point (°C)	<b>SP</b>	655
Expansion Coefficient $\alpha$ (-30~+70°C)		80
(10-7 /°C) (+100~+300°C)		93
Thermal Conductivity (W/m·K)	<b>k</b>	1.089

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	640
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	281
Poisson's Ratio	$\sigma$	0.139
Knoop Hardness	<b>Hk</b>	480 [5]
Abrasion	<b>Aa</b>	103
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.82

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	2.46		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.8	2.2	2.2	2.3	2.5	2.8	3.2		
-20 ~ 0	1.8	2.2	2.2	2.3	2.5	2.9	3.3		
0 ~ 20	1.8	2.2	2.3	2.4	2.6	2.9	3.3		
20 ~ 40	1.9	2.3	2.3	2.4	2.6	3.0	3.4		
40 ~ 60	1.9	2.3	2.3	2.5	2.7	3.1	3.5		
60 ~ 80	1.9	2.3	2.3	2.5	2.7	3.1	3.6		

Refractive Index	$n_d$	<b>1.61800</b>	Abbe Number	$V_d$	<b>63.33</b>	Dispersion	$n_F - n_C$	<b>0.00975</b>
	$n_e$	1.618000		$V_e$	63.02		$n_{F'} - n_{C'}$	0.009758
		1.620327						0.009844

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.59108
$n_{1970}$	1.97009	1.59587
$n_{1530}$	1.52958	1.60103
$n_{1129}$	1.12864	1.60561
$n_t$	1.01398	1.60714
$n_s$	0.85211	1.60983
$n_{A'}$	0.76819	1.61167
$n_r$	0.70652	1.61335
$n_c$	0.65627	<b>1.61504</b>
$n_{c'}$	0.64385	1.61551
$n_{\text{He-Ne}}$	0.6328	1.61595
$n_D$	0.58929	1.61791
$n_d$	0.58756	<b>1.61800</b>
$n_e$	0.54607	1.62033
$n_F$	0.48613	<b>1.62479</b>
$n_{F'}$	0.47999	1.62535
$n_{\text{He-Cd}}$	0.44157	1.62940
$n_g$	0.435835	<b>1.63010</b>
$n_h$	0.404656	1.63451
$n_i$	0.365015	1.64199
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.007893
$n_C - n_{A'}$	0.003370
$n_d - n_C$	0.002964
$n_e - n_C$	0.005291
$n_g - n_d$	0.012103
$n_g - n_F$	0.005309
$n_h - n_g$	0.004403
$n_i - n_g$	0.011891
$n_{C'} - n_t$	0.008364
$n_e - n_{C'}$	0.004820
$n_{F'} - n_e$	0.005024
$n_i - n_{F'}$	0.016643

Relative Partial Dispersions	
$\theta_{C,t}$	0.8089
$\theta_{C,A'}$	0.3454
$\theta_{d,C}$	0.3038
$\theta_{e,C}$	0.5422
$\theta_{g,d}$	1.2403
$\theta_{g,F}$	0.5441
$\theta_{h,g}$	0.4512
$\theta_{i,g}$	1.2186
$\theta'_{C',t}$	0.8497
$\theta'_{e,C'}$	0.4896
$\theta'_{F',e}$	0.5104
$\theta'_{i,F'}$	1.6907

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.0349
$\Delta\theta_{C,A'}$	-0.0072
$\Delta\theta_{g,d}$	0.0071
$\Delta\theta_{g,F}$	0.0051
$\Delta\theta_{i,g}$	0.0239

Internal Transmittance			
$\lambda_{80}$	366	$\lambda_5$	330

CCI		
B	G	R
0.00	0.55	0.57

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.09966550	
A 2	4.78125422	E-1
A 3	1.13214074	
B 1	1.32718559	E-2
B 2	-6.01649685	E-4
B 3	1.30595472	E2
1129 ~ 2325 nm		
A 1	1.09966550	
A 2	4.78125422	E-1
A 3	1.13214074	
B 1	1.32718559	E-2
B 2	-6.01649685	E-4
B 3	1.30595472	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330	0.050	
340	0.250	
350	0.510	
360	0.720	
365		
370	0.850	
380	0.923	
390	0.957	
400	0.974	
420	0.986	
440	0.990	
460	0.992	
480	0.994	
500	0.996	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.997	
900	0.996	
1000	0.996	
1200	0.996	
1400	0.996	
1600	0.991	
1800	0.979	
2000	0.961	
2200	0.926	
2400	0.890	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	587
Yield Point (°C)	<b>At</b>	617
Softening Point (°C)	<b>SP</b>	
Expansion Coefficient $\alpha$ (-30~+70°C)		101
(+100~+300°C)		120
Thermal Conductivity (W/m·K)	<b>k</b>	0.599

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	715
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	277
Poisson's Ratio	$\sigma$	0.292
Knoop Hardness	<b>Hk</b>	390 [4]
Abrasion	<b>Aa</b>	434
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	5.0
Phosphate Resistance	<b>PR</b>	4.0

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	3.67		$\lambda_5$	325				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-3.7	-3.6	-3.6	-3.6	-3.4	-3.2	-3.0		
-20 ~ 0	-3.8	-3.7	-3.7	-3.6	-3.5	-3.2	-3.0		
0 ~ 20	-4.0	-3.7	-3.7	-3.6	-3.5	-3.2	-3.0		
20 ~ 40	-4.1	-3.7	-3.7	-3.6	-3.5	-3.2	-3.0		
40 ~ 60	-4.2	-3.8	-3.8	-3.6	-3.5	-3.2	-3.0		
60 ~ 80	-4.2	-3.8	-3.8	-3.7	-3.6	-3.3	-3.0		

Refractive Index	$n_d$	<b>1.60300</b>	Abbe Number	$V_d$	<b>65.44</b>	Dispersion	$n_F - n_C$	<b>0.00921</b>
	$n_e$	1.603001		$V_e$	65.15		$n_{F'} - n_{C'}$	0.009215
		1.605200						0.009289

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.57583
$n_{1970}$	1.97009	1.58092
$n_{1530}$	1.52958	1.58634
$n_{1129}$	1.12864	1.59103
$n_t$	1.01398	1.59256
$n_s$	0.85211	1.59519
$n_{A'}$	0.76819	1.59697
$n_r$	0.70652	1.59858
$n_c$	0.65627	<b>1.60019</b>
$n_{c'}$	0.64385	1.60064
$n_{\text{He-Ne}}$	0.6328	1.60106
$n_D$	0.58929	1.60292
$n_d$	0.58756	<b>1.60300</b>
$n_e$	0.54607	1.60520
$n_F$	0.48613	<b>1.60940</b>
$n_{F'}$	0.47999	1.60993
$n_{\text{He-Cd}}$	0.44157	1.61372
$n_g$	0.435835	<b>1.61438</b>
$n_h$	0.404656	1.61850
$n_i$	0.365015	1.62547
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.007630
$n_c - n_{A'}$	0.003223
$n_d - n_c$	0.002812
$n_e - n_c$	0.005011
$n_g - n_d$	0.011380
$n_g - n_F$	0.004977
$n_h - n_g$	0.004114
$n_i - n_g$	0.011090
$n_{c'} - n_t$	0.008078
$n_e - n_{c'}$	0.004563
$n_{F'} - n_e$	0.004726
$n_i - n_{F'}$	0.015545

Relative Partial Dispersions	
$\theta_{c,t}$	0.8280
$\theta_{c,A'}$	0.3498
$\theta_{d,c}$	0.3052
$\theta_{e,c}$	0.5438
$\theta_{g,d}$	1.2349
$\theta_{g,F}$	0.5401
$\theta_{h,g}$	0.4464
$\theta_{i,g}$	1.2035
$\theta'_{c,t}$	0.8696
$\theta'_{e,c'}$	0.4912
$\theta'_{F',e}$	0.5088
$\theta'_{i,F'}$	1.6735

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0257
$\Delta\theta_{c,A'}$	-0.0054
$\Delta\theta_{g,d}$	0.0061
$\Delta\theta_{g,F}$	0.0045
$\Delta\theta_{i,g}$	0.0265

Internal Transmittance			
$\lambda_{80}$	362	$\lambda_5$	313

CCI		
B	G	R
0.00	0.56	0.52

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.09775423	
A 2	4.34816432	E-1
A 3	1.13894976	
B 1	1.23369400	E-2
B 2	-3.72522903	E-4
B 3	1.24276984	E2
1129 ~ 2325 nm		
A 1	1.09775423	
A 2	4.34816432	E-1
A 3	1.13894976	
B 1	1.23369400	E-2
B 2	-3.72522903	E-4
B 3	1.24276984	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280		
290		
300		
310	0.030	
320	0.100	
330	0.250	
340	0.450	
350	0.640	
360	0.780	
365		
370	0.880	
380	0.935	
390	0.963	
400	0.977	
420	0.986	
440	0.987	
460	0.989	
480	0.992	
500	0.994	
550	0.998	
600	0.997	
650	0.996	
700	0.996	
800	0.997	
900	0.997	
1000	0.996	
1200	0.997	
1400	0.993	
1600	0.987	
1800	0.967	
2000	0.941	
2200	0.870	
2400	0.830	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	610
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	644
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	681
Expansion Coefficient ( $10^{-7}/^{\circ}\text{C}$ )	$\alpha$	93 (-30~+70 $^{\circ}\text{C}$ ) 109 (+100~+300 $^{\circ}\text{C}$ )
Thermal Conductivity (W/m·K)	<b>k</b>	0.615

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	708
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	275
Poisson's Ratio	$\sigma$	0.285
Knoop Hardness	<b>Hk</b>	390 [4]
Abrasion	<b>Aa</b>	378
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.21

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	5
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	51.0
Phosphate Resistance	<b>PR</b>	4.0

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	3.51		$\lambda_5$	300				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-3.1	-2.8	-2.8	-2.7	-2.6	-2.4	-2.2		
-20 ~ 0	-3.0	-2.8	-2.8	-2.7	-2.6	-2.4	-2.1		
0 ~ 20	-3.0	-2.7	-2.7	-2.6	-2.5	-2.3	-2.0		
20 ~ 40	-2.9	-2.6	-2.6	-2.5	-2.4	-2.1	-1.9		
40 ~ 60	-2.9	-2.5	-2.5	-2.4	-2.2	-1.9	-1.7		
60 ~ 80	-2.7	-2.3	-2.3	-2.2	-2.0	-1.7	-1.5		



Refractive Index	$n_d$	<b>1.71736</b>	Abbe Number	$V_d$	<b>29.52</b>	Dispersion	$n_F - n_C$	<b>0.02430</b>
	$n_e$	1.717362		$V_e$	29.28		$n_{F'} - n_{C'}$	0.024303
		1.723098						0.024694

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.67018
$n_{1970}$	1.97009	1.67636
$n_{1530}$	1.52958	1.68344
$n_{1129}$	1.12864	1.69075
$n_t$	1.01398	1.69353
$n_s$	0.85211	1.69885
$n_{A'}$	0.76819	1.70275
$n_r$	0.70652	1.70649
$n_C$	0.65627	<b>1.71033</b>
$n_{C'}$	0.64385	1.71143
$n_{\text{He-Ne}}$	0.6328	1.71246
$n_D$	0.58929	1.71715
$n_d$	0.58756	<b>1.71736</b>
$n_e$	0.54607	1.72310
$n_F$	0.48613	<b>1.73463</b>
$n_{F'}$	0.47999	1.73612
$n_{\text{He-Cd}}$	0.44157	1.74732
$n_g$	0.435835	<b>1.74933</b>
$n_h$	0.404656	1.76247
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	569
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	597
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	622
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	653
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	703
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		82
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	96
Thermal Conductivity (W/m·K)	<b>k</b>	1.018

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	884
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	355
Poisson's Ratio	$\sigma$	0.247
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	161
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.85

Partial Dispersions	
$n_C - n_t$	0.016798
$n_C - n_{A'}$	0.007579
$n_d - n_C$	0.007030
$n_e - n_C$	0.012766
$n_g - n_d$	0.031970
$n_g - n_F$	0.014697
$n_h - n_g$	0.013136
$n_i - n_g$	
$n_{C'} - n_t$	0.017894
$n_e - n_{C'}$	0.011670
$n_{F'} - n_e$	0.013024
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0060
$\Delta\theta_{C,A'}$	0.0003
$\Delta\theta_{g,d}$	0.0121
$\Delta\theta_{g,F}$	0.0110
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.60326759	
A 2	2.42980935	E-1
A 3	1.81313592	
B 1	1.18019139	E-2
B 2	5.91363658	E-2
B 3	1.61218747	E2
1129 ~ 2325 nm		
A 1	1.60326759	
A 2	2.42980935	E-1
A 3	1.81313592	
B 1	1.18019139	E-2
B 2	5.91363658	E-2
B 3	1.61218747	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6912
$\theta_{C,A'}$	0.3119
$\theta_{d,C}$	0.2893
$\theta_{e,C}$	0.5253
$\theta_{g,d}$	1.3155
$\theta_{g,F}$	0.6047
$\theta_{h,g}$	0.5405
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7246
$\theta'_{e,C'}$	0.4726
$\theta'_{F',e}$	0.5274
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	392	$\lambda_5$	366

CCI		
B	G	R
0.00	2.31	2.29

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.190	
380	0.560	
390	0.780	
400	0.880	
420	0.952	
440	0.971	
460	0.978	
480	0.982	
500	0.987	
550	0.994	
600	0.994	
650	0.991	
700	0.993	
800	0.998	
900	0.999	
1000	0.998	
1200	0.998	
1400	0.996	
1600	0.995	
1800	0.988	
2000	0.981	
2200	0.957	
2400	0.941	

Other Properties								
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	405			
Specific Gravity	<b>d</b>	3.06		$\lambda_5$	360			
Temperature Coefficients of Refractive Index								
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20		3.2	3.3	3.6	4.0	5.1	6.2	
-20 ~ 0		3.4	3.5	3.8	4.3	5.4	6.7	
0 ~ 20		3.7	3.7	4.1	4.6	5.7	7.1	
20 ~ 40		3.9	4.0	4.3	4.8	6.0	7.5	
40 ~ 60		4.1	4.2	4.6	5.1	6.4	7.9	
60 ~ 80		4.3	4.4	4.8	5.3	6.7	8.3	

Refractive Index	$n_d$	<b>1.74000</b>	Abbe Number	$V_d$	<b>28.30</b>	Dispersion	$n_F - n_C$	<b>0.02616</b>
		1.739998			$V_e$		28.07	
	$n_e$	1.746167					$n_{F'} - n_{C'}$	0.026584

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.69065
$n_{1970}$	1.97009	1.69685
$n_{1530}$	1.52958	1.70405
$n_{1129}$	1.12864	1.71162
$n_t$	1.01398	1.71455
$n_s$	0.85211	1.72018
$n_{A'}$	0.76819	1.72434
$n_r$	0.70652	1.72833
$n_C$	0.65627	<b>1.73245</b>
$n_{C'}$	0.64385	1.73363
$n_{\text{He-Ne}}$	0.6328	1.73474
$n_D$	0.58929	1.73977
$n_d$	0.58756	<b>1.74000</b>
$n_e$	0.54607	1.74617
$n_F$	0.48613	<b>1.75861</b>
$n_{F'}$	0.47999	1.76021
$n_{\text{He-Cd}}$	0.44157	1.77232
$n_g$	0.435835	<b>1.77450</b>
$n_h$	0.404656	1.78876
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.017900
$n_C - n_{A'}$	0.008108
$n_d - n_C$	0.007545
$n_e - n_C$	0.013714
$n_g - n_d$	0.034504
$n_g - n_F$	0.015897
$n_h - n_g$	0.014254
$n_i - n_g$	
$n_{C'} - n_t$	0.019075
$n_e - n_{C'}$	0.012539
$n_{F'} - n_e$	0.014045
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6845
$\theta_{C,A'}$	0.3100
$\theta_{d,C}$	0.2885
$\theta_{e,C}$	0.5244
$\theta_{g,d}$	1.3194
$\theta_{g,F}$	0.6079
$\theta_{h,g}$	0.5450
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7175
$\theta'_{e,C'}$	0.4717
$\theta'_{F',e}$	0.5283
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0051
$\Delta\theta_{C,A'}$	-0.0001
$\Delta\theta_{g,d}$	0.0135
$\Delta\theta_{g,F}$	0.0122
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	395	$\lambda_5$	367

CCI		
B	G	R
0.00	2.81	2.86

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.64797648	
A 2	2.67261917	E-1
A 3	2.19772845	
B 1	1.21917693	E-2
B 2	5.97893039	E-2
B 3	1.92158340	E2
1129 ~ 2325 nm		
A 1	1.64797648	
A 2	2.67261917	E-1
A 3	2.19772845	
B 1	1.21917693	E-2
B 2	5.97893039	E-2
B 3	1.92158340	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.160	
380	0.510	
390	0.740	
400	0.850	
420	0.940	
440	0.964	
460	0.975	
480	0.981	
500	0.986	
550	0.994	
600	0.994	
650	0.993	
700	0.995	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.988	
2000	0.980	
2200	0.955	
2400	0.933	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	566
Annealing Point (°C)	<b>AP</b>	591
Transformation Temperature (°C)	<b>Tg</b>	615
Yield Point (°C)	<b>At</b>	644
Softening Point (°C)	<b>SP</b>	723
Expansion Coefficient $\alpha$ (-30~+70°C)		85
(10-7 /°C) (+100~+300°C)		100
Thermal Conductivity (W/m·K)	<b>k</b>	1.027

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	908
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	362
Poisson's Ratio	$\sigma$	0.254
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	165
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	420				
Specific Gravity	<b>d</b>	3.11		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.6	1.5	1.6	1.9	2.3	3.4	4.6		
-20 ~ 0	0.9	1.7	1.7	2.1	2.5	3.6	4.9		
0 ~ 20	0.9	1.8	1.9	2.2	2.7	3.8	5.2		
20 ~ 40	0.9	1.9	2.0	2.4	2.8	4.1	5.5		
40 ~ 60	1.0	2.0	2.1	2.5	3.0	4.3	5.9		
60 ~ 80	1.2	2.2	2.2	2.7	3.2	4.5	6.2		

Refractive Index	$n_d$	<b>1.75520</b>	Abbe Number	$V_d$	<b>27.51</b>	Dispersion	$n_F - n_C$	<b>0.02745</b>
	$n_e$	1.755199		$V_e$	27.29		$n_{F'} - n_{C'}$	0.027450
		1.761671						0.027911

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70430
$n_{1970}$	1.97009	1.71054
$n_{1530}$	1.52958	1.71784
$n_{1129}$	1.12864	1.72561
$n_t$	1.01398	1.72864
$n_s$	0.85211	1.73448
$n_{A'}$	0.76819	1.73882
$n_r$	0.70652	1.74299
$n_C$	0.65627	<b>1.74730</b>
$n_{C'}$	0.64385	1.74853
$n_{\text{He-Ne}}$	0.6328	1.74968
$n_D$	0.58929	1.75496
$n_d$	0.58756	<b>1.75520</b>
$n_e$	0.54607	1.76167
$n_F$	0.48613	<b>1.77475</b>
$n_{F'}$	0.47999	1.77644
$n_{\text{He-Cd}}$	0.44157	1.78920
$n_g$	0.435835	<b>1.79150</b>
$n_h$	0.404656	1.80656
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.018659
$n_C - n_{A'}$	0.008473
$n_d - n_C$	0.007904
$n_e - n_C$	0.014376
$n_g - n_d$	0.036298
$n_g - n_F$	0.016752
$n_h - n_g$	0.015059
$n_i - n_g$	
$n_{C'} - n_t$	0.019889
$n_e - n_{C'}$	0.013146
$n_{F'} - n_e$	0.014765
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6797
$\theta_{C,A'}$	0.3087
$\theta_{d,C}$	0.2879
$\theta_{e,C}$	0.5237
$\theta_{g,d}$	1.3223
$\theta_{g,F}$	0.6103
$\theta_{h,g}$	0.5486
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7126
$\theta'_{e,C'}$	0.4710
$\theta'_{F',e}$	0.5290
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0040
$\Delta\theta_{C,A'}$	-0.0005
$\Delta\theta_{g,d}$	0.0147
$\Delta\theta_{g,F}$	0.0133
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	398	$\lambda_5$	368

CCI		
B	G	R
0.00	3.28	3.30

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.66755531	
A 2	2.94411865	E-1
A 3	2.49422119	
B 1	1.22052137	E-2
B 2	5.97775329	E-2
B 3	2.14869618	E2
1129 ~ 2325 nm		
A 1	1.66755531	
A 2	2.94411865	E-1
A 3	2.49422119	
B 1	1.22052137	E-2
B 2	5.97775329	E-2
B 3	2.14869618	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.120	
380	0.450	
390	0.700	
400	0.820	
420	0.929	
440	0.962	
460	0.973	
480	0.980	
500	0.986	
550	0.995	
600	0.994	
650	0.993	
700	0.995	
800	0.999	
900	0.999	
1000	0.999	
1200	0.997	
1400	0.995	
1600	0.994	
1800	0.987	
2000	0.981	
2200	0.961	
2400	0.942	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	565
Annealing Point (°C)	<b>AP</b>	591
Transformation Temperature (°C)	<b>Tg</b>	613
Yield Point (°C)	<b>At</b>	640
Softening Point (°C)	<b>SP</b>	694
Expansion Coefficient $\alpha$ (-30~+70°C)		85
Expansion Coefficient $\alpha$ (+100~+300°C)		100
Thermal Conductivity (W/m·K)	<b>k</b>	1.010

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	919
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	367
Poisson's Ratio	$\sigma$	0.254
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	168
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.76

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	415				
Specific Gravity	<b>d</b>	3.15		$\lambda_5$	365				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.5	1.2	1.2	1.6	2.0	3.1	4.4		
-20 ~ 0	0.6	1.3	1.4	1.8	2.2	3.3	4.7		
0 ~ 20	0.6	1.4	1.5	1.9	2.4	3.6	5.1		
20 ~ 40	0.7	1.6	1.7	2.1	2.6	3.9	5.4		
40 ~ 60	0.7	1.7	1.8	2.3	2.7	4.1	5.8		
60 ~ 80	0.7	1.8	1.9	2.4	2.9	4.4	6.1		

Refractive Index	$n_d$	<b>1.80518</b>	Abbe Number	$V_d$	<b>25.42</b>	Dispersion	$n_F - n_C$	<b>0.03166</b>
		1.805181			$V_e$		25.22	
	$n_e$	1.812641					$n_{F'} - n_{C'}$	0.032223

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.74917
$n_{1970}$	1.97009	1.75558
$n_{1530}$	1.52958	1.76321
$n_{1129}$	1.12864	1.77160
$n_t$	1.01398	1.77495
$n_s$	0.85211	1.78151
$n_{A'}$	0.76819	1.78643
$n_r$	0.70652	1.79118
$n_C$	0.65627	<b>1.79611</b>
$n_{C'}$	0.64385	1.79752
$n_{\text{He-Ne}}$	0.6328	1.79885
$n_D$	0.58929	1.80491
$n_d$	0.58756	<b>1.80518</b>
$n_e$	0.54607	1.81264
$n_F$	0.48613	<b>1.82777</b>
$n_{F'}$	0.47999	1.82974
$n_{\text{He-Cd}}$	0.44157	1.84460
$n_g$	0.435835	<b>1.84729</b>
$n_h$	0.404656	1.86494
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	571
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	587
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	604
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	630
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	690
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		89
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	107
Thermal Conductivity (W/m·K)	<b>k</b>	1.011

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	931
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	369
Poisson's Ratio	$\sigma$	0.261
Knoop Hardness	<b>Hk</b>	540 [5]
Abrasion	<b>Aa</b>	191
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Partial Dispersions	
$n_C - n_t$	0.021155
$n_C - n_{A'}$	0.009673
$n_d - n_C$	0.009075
$n_e - n_C$	0.016535
$n_g - n_d$	0.042105
$n_g - n_F$	0.019511
$n_h - n_g$	0.017653
$n_i - n_g$	
$n_{C'} - n_t$	0.022564
$n_e - n_{C'}$	0.015126
$n_{F'} - n_e$	0.017097
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0021
$\Delta\theta_{C,A'}$	-0.0012
$\Delta\theta_{g,d}$	0.0176
$\Delta\theta_{g,F}$	0.0158
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.77227611	
A 2	3.45691250	E-1
A 3	2.40788501	
B 1	1.31182633	E-2
B 2	6.14479619	E-2
B 3	2.00753254	E2
1129 ~ 2325 nm		
A 1	1.77227611	
A 2	3.45691250	E-1
A 3	2.40788501	
B 1	1.31182633	E-2
B 2	6.14479619	E-2
B 3	2.00753254	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6680
$\theta_{C,A'}$	0.3054
$\theta_{d,C}$	0.2866
$\theta_{e,C}$	0.5221
$\theta_{g,d}$	1.3295
$\theta_{g,F}$	0.6161
$\theta_{h,g}$	0.5574
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7002
$\theta'_{e,C'}$	0.4694
$\theta'_{F',e}$	0.5306
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	398	$\lambda_5$	368

CCI		
B	G	R
0.00	3.44	3.56

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.120	
380	0.480	
390	0.700	
400	0.820	
420	0.919	
440	0.955	
460	0.970	
480	0.978	
500	0.984	
550	0.993	
600	0.995	
650	0.994	
700	0.996	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.997	
1600	0.995	
1800	0.986	
2000	0.978	
2200	0.958	
2400	0.928	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	440				
Specific Gravity	<b>d</b>	3.37		$\lambda_5$	365				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.6	0.3	0.4	0.7	1.3	2.6	4.1		
-20 ~ 0	-0.6	0.4	0.5	0.9	1.5	2.8	4.4		
0 ~ 20	-0.5	0.5	0.6	1.0	1.6	3.0	4.8		
20 ~ 40	-0.4	0.7	0.8	1.2	1.8	3.3	5.1		
40 ~ 60	-0.4	0.8	0.9	1.3	2.0	3.5	5.5		
60 ~ 80	-0.3	0.9	1.0	1.5	2.1	3.8	5.8		

Refractive Index	$n_d$	<b>1.72825</b> 1.728250	Abbe Number	$V_d$	<b>28.46</b> 28.23	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	<b>0.02559</b> 0.025588 0.026009
		$n_e$		1.734286			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.67934
$n_{1970}$	1.97009	1.68562
$n_{1530}$	1.52958	1.69286
$n_{1129}$	1.12864	1.70040
$n_t$	1.01398	1.70330
$n_s$	0.85211	1.70884
$n_{A'}$	0.76819	1.71292
$n_r$	0.70652	1.71683
$n_C$	0.65627	<b>1.72086</b>
$n_{C'}$	0.64385	1.72202
$n_{\text{He-Ne}}$	0.6328	1.72310
$n_D$	0.58929	1.72803
$n_d$	0.58756	<b>1.72825</b>
$n_e$	0.54607	1.73429
$n_F$	0.48613	<b>1.74645</b>
$n_{F'}$	0.47999	1.74802
$n_{\text{He-Cd}}$	0.44157	1.75987
$n_g$	0.435835	<b>1.76200</b>
$n_h$	0.404656	1.77595
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	569
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	596
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	617
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	642
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	703
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	80
	(+10-7~+300 $^{\circ}\text{C}$ )	97
Thermal Conductivity (W/m·K)	<b>k</b>	1.043

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1024
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	412
Poisson's Ratio	$\sigma$	0.243
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	133
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.88

Partial Dispersions	
$n_C - n_t$	0.017568
$n_C - n_{A'}$	0.007944
$n_d - n_C$	0.007385
$n_e - n_C$	0.013421
$n_g - n_d$	0.033752
$n_g - n_F$	0.015549
$n_h - n_g$	0.013943
$n_i - n_g$	
$n_{C'} - n_t$	0.018718
$n_e - n_{C'}$	0.012271
$n_{F'} - n_e$	0.013738
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0064
$\Delta\theta_{C,A'}$	0.0002
$\Delta\theta_{g,d}$	0.0135
$\Delta\theta_{g,F}$	0.0123
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.61549392	
A 2	2.62433239	E-1
A 3	2.09426189	
B 1	1.19830897	E-2
B 2	5.96510240	E-2
B 3	1.81657554	E2
1129 ~ 2325 nm		
A 1	1.61549392	
A 2	2.62433239	E-1
A 3	2.09426189	
B 1	1.19830897	E-2
B 2	5.96510240	E-2
B 3	1.81657554	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6866
$\theta_{C,A'}$	0.3105
$\theta_{d,C}$	0.2886
$\theta_{e,C}$	0.5245
$\theta_{g,d}$	1.3191
$\theta_{g,F}$	0.6077
$\theta_{h,g}$	0.5449
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7197
$\theta'_{e,C'}$	0.4718
$\theta'_{F',e}$	0.5282
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	399	$\lambda_5$	369

CCI		
B	G	R
0.00	3.34	3.37

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.090	
380	0.410	
390	0.670	
400	0.810	
420	0.931	
440	0.963	
460	0.975	
480	0.982	
500	0.987	
550	0.994	
600	0.995	
650	0.993	
700	0.994	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.994	
1600	0.993	
1800	0.985	
2000	0.977	
2200	0.947	
2400	0.929	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	410				
Specific Gravity	<b>d</b>	3.06		$\lambda_5$		365			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.1	2.0	2.1	2.3	2.8	3.8	5.0		
-20 ~ 0	1.3	2.1	2.2	2.5	3.0	4.0	5.3		
0 ~ 20	1.4	2.3	2.3	2.7	3.1	4.3	5.7		
20 ~ 40	1.5	2.4	2.5	2.8	3.3	4.5	6.0		
40 ~ 60	1.5	2.5	2.6	3.0	3.5	4.8	6.3		
60 ~ 80	1.5	2.6	2.7	3.1	3.7	5.0	6.6		

Refractive Index	$n_d$	<b>1.78472</b>	Abbe Number	$V_d$	<b>25.68</b>	Dispersion	$n_F - n_C$	<b>0.03056</b>
	$n_e$	1.784723		$V_e$	25.47		$n_{F'} - n_{C'}$	0.030554
		1.791920						0.031088

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.72998
$n_{1970}$	1.97009	1.73639
$n_{1530}$	1.52958	1.74397
$n_{1129}$	1.12864	1.75222
$n_t$	1.01398	1.75549
$n_s$	0.85211	1.76186
$n_{A'}$	0.76819	1.76662
$n_r$	0.70652	1.77121
$n_C$	0.65627	<b>1.77596</b>
$n_{C'}$	0.64385	1.77733
$n_{\text{He-Ne}}$	0.6328	1.77861
$n_D$	0.58929	1.78446
$n_d$	0.58756	<b>1.78472</b>
$n_e$	0.54607	1.79192
$n_F$	0.48613	<b>1.80652</b>
$n_{F'}$	0.47999	1.80841
$n_{\text{He-Cd}}$	0.44157	1.82275
$n_g$	0.435835	<b>1.82534</b>
$n_h$	0.404656	1.84239
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	569
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	588
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	602
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	633
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	686
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		89
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	103
Thermal Conductivity (W/m·K)	<b>k</b>	1.017

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	912
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	363
Poisson's Ratio	$\sigma$	0.255
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	171
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Partial Dispersions	
$n_C - n_t$	0.020476
$n_C - n_{A'}$	0.009346
$n_d - n_C$	0.008758
$n_e - n_C$	0.015955
$n_g - n_d$	0.040621
$n_g - n_F$	0.018825
$n_h - n_g$	0.017044
$n_i - n_g$	
$n_{C'} - n_t$	0.021836
$n_e - n_{C'}$	0.014595
$n_{F'} - n_e$	0.016493
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0030
$\Delta\theta_{C,A'}$	-0.0011
$\Delta\theta_{g,d}$	0.0181
$\Delta\theta_{g,F}$	0.0162
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.72677471	
A 2	3.24568628	E-1
A 3	2.65816809	
B 1	1.29369958	E-2
B 2	6.18255245	E-2
B 3	2.21904637	E2
1129 ~ 2325 nm		
A 1	1.72677471	
A 2	3.24568628	E-1
A 3	2.65816809	
B 1	1.29369958	E-2
B 2	6.18255245	E-2
B 3	2.21904637	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6702
$\theta_{C,A'}$	0.3059
$\theta_{d,C}$	0.2866
$\theta_{e,C}$	0.5222
$\theta_{g,d}$	1.3295
$\theta_{g,F}$	0.6161
$\theta_{h,g}$	0.5578
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7024
$\theta'_{e,C'}$	0.4695
$\theta'_{F',e}$	0.5305
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	400	$\lambda_5$	369

CCI		
B	G	R
0.00	3.80	3.85

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.080	
380	0.400	
390	0.660	
400	0.800	
420	0.915	
440	0.948	
460	0.964	
480	0.973	
500	0.980	
550	0.992	
600	0.992	
650	0.990	
700	0.992	
800	0.998	
900	0.998	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.989	
2000	0.982	
2200	0.964	
2400	0.942	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	430				
Specific Gravity	<b>d</b>	3.24		$\lambda_5$	365				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.3	0.5	0.6	0.9	1.4	2.6	4.1		
-20 ~ 0	-0.2	0.7	0.7	1.1	1.6	2.9	4.5		
0 ~ 20	-0.1	0.8	0.9	1.3	1.9	3.2	4.9		
20 ~ 40		1.0	1.1	1.5	2.1	3.5	5.3		
40 ~ 60		1.1	1.2	1.7	2.3	3.8	5.7		
60 ~ 80	0.1	1.3	1.4	1.9	2.5	4.1	6.1		



Refractive Index	$n_d$	<b>1.74077</b>	Abbe Number	$V_d$	<b>27.79</b>	Dispersion	$n_F - n_C$	<b>0.02666</b>
		1.740769			$V_e$		27.56	
	$n_e$	1.747055					$n_{F'} - n_{C'}$	0.027102

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.69062
$n_{1970}$	1.97009	1.69693
$n_{1530}$	1.52958	1.70425
$n_{1129}$	1.12864	1.71193
$n_t$	1.01398	1.71490
$n_s$	0.85211	1.72062
$n_{A'}$	0.76819	1.72485
$n_r$	0.70652	1.72890
$n_C$	0.65627	<b>1.73309</b>
$n_{C'}$	0.64385	1.73428
$n_{\text{He-Ne}}$	0.6328	1.73541
$n_D$	0.58929	1.74054
$n_d$	0.58756	<b>1.74077</b>
$n_e$	0.54607	1.74705
$n_F$	0.48613	<b>1.75975</b>
$n_{F'}$	0.47999	1.76139
$n_{\text{He-Cd}}$	0.44157	1.77376
$n_g$	0.435835	<b>1.77599</b>
$n_h$	0.404656	1.79059
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.018185
$n_C - n_{A'}$	0.008244
$n_d - n_C$	0.007680
$n_e - n_C$	0.013966
$n_g - n_d$	0.035225
$n_g - n_F$	0.016248
$n_h - n_g$	0.014593
$n_i - n_g$	
$n_{C'} - n_t$	0.019380
$n_e - n_{C'}$	0.012771
$n_{F'} - n_e$	0.014331
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6822
$\theta_{C,A'}$	0.3093
$\theta_{d,C}$	0.2881
$\theta_{e,C}$	0.5239
$\theta_{g,d}$	1.3214
$\theta_{g,F}$	0.6095
$\theta_{h,g}$	0.5474
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7151
$\theta'_{e,C'}$	0.4712
$\theta'_{F',e}$	0.5288
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0051
$\Delta\theta_{C,A'}$	-0.0002
$\Delta\theta_{g,d}$	0.0144
$\Delta\theta_{g,F}$	0.0130
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	400	$\lambda_5$	368

CCI		
B	G	R
0.00	3.64	3.67

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.62224674	
A 2	2.93844589	E-1
A 3	1.99225164	
B 1	1.18368386	E-2
B 2	5.90208025	E-2
B 3	1.71959976	E2
1129 ~ 2325 nm		
A 1	1.62224674	
A 2	2.93844589	E-1
A 3	1.99225164	
B 1	1.18368386	E-2
B 2	5.90208025	E-2
B 3	1.71959976	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.080	
380	0.380	
390	0.640	
400	0.800	
420	0.921	
440	0.957	
460	0.970	
480	0.978	
500	0.984	
550	0.993	
600	0.993	
650	0.991	
700	0.994	
800	0.997	
900	0.998	
1000	0.997	
1200	0.998	
1400	0.994	
1600	0.993	
1800	0.983	
2000	0.974	
2200	0.944	
2400	0.920	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	573
Annealing Point (°C)	<b>AP</b>	595
Transformation Temperature (°C)	<b>Tg</b>	616
Yield Point (°C)	<b>At</b>	642
Softening Point (°C)	<b>SP</b>	700
Expansion Coefficient $\alpha$ (-30~+70°C)		83
(10-7 / °C) (+100~+300°C)		96
Thermal Conductivity (W/m·K)	<b>k</b>	1.034

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	899
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	360
Poisson's Ratio	$\sigma$	0.249
Knoop Hardness	<b>Hk</b>	510 [5]
Abrasion	<b>Aa</b>	148
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.83

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	415				
Specific Gravity	<b>d</b>	3.10		$\lambda_5$	365				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.0	1.8	1.8	2.1	2.6	3.6	4.9		
-20 ~ 0	1.0	1.9	1.9	2.3	2.7	3.9	5.2		
0 ~ 20	1.1	2.0	2.1	2.4	2.9	4.1	5.5		
20 ~ 40	1.1	2.1	2.2	2.5	3.0	4.3	5.8		
40 ~ 60	1.2	2.2	2.3	2.7	3.2	4.5	6.1		
60 ~ 80	1.3	2.3	2.4	2.8	3.4	4.7	6.4		

Refractive Index	$n_d$	<b>1.76182</b>	Abbe Number	$V_d$	<b>26.52</b>	Dispersion	$n_F - n_C$	<b>0.02873</b>
	$n_e$	1.761821		$V_e$	26.30		$n_{F'} - n_{C'}$	0.028729
		1.768591						0.029221

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70916
$n_{1970}$	1.97009	1.71554
$n_{1530}$	1.52958	1.72302
$n_{1129}$	1.12864	1.73102
$n_t$	1.01398	1.73415
$n_s$	0.85211	1.74022
$n_{A'}$	0.76819	1.74474
$n_r$	0.70652	1.74908
$n_c$	0.65627	<b>1.75357</b>
$n_{c'}$	0.64385	1.75485
$n_{\text{He-Ne}}$	0.6328	1.75606
$n_D$	0.58929	1.76157
$n_d$	0.58756	<b>1.76182</b>
$n_e$	0.54607	1.76859
$n_F$	0.48613	<b>1.78230</b>
$n_{F'}$	0.47999	1.78407
$n_{\text{He-Cd}}$	0.44157	1.79750
$n_g$	0.435835	<b>1.79992</b>
$n_h$	0.404656	1.81584
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	565
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	590
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	609
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	634
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	693
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		87
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	100
Thermal Conductivity (W/m·K)	<b>k</b>	1.027

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	888
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	354
Poisson's Ratio	$\sigma$	0.254
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	163
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.86

Partial Dispersions	
$n_c - n_t$	0.019413
$n_c - n_{A'}$	0.008831
$n_d - n_c$	0.008254
$n_e - n_c$	0.015024
$n_g - n_d$	0.038102
$n_g - n_F$	0.017627
$n_h - n_g$	0.015917
$n_i - n_g$	
$n_{c'} - n_t$	0.020697
$n_e - n_{c'}$	0.013740
$n_{F'} - n_e$	0.015481
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0046
$\Delta\theta_{c,A'}$	-0.0006
$\Delta\theta_{g,d}$	0.0167
$\Delta\theta_{g,F}$	0.0150
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.68915108	
A 2	2.90462024	E-1
A 3	2.37971516	
B 1	1.28202514	E-2
B 2	6.18090841	E-2
B 3	2.01094352	E2
1129 ~ 2325 nm		
A 1	1.68915108	
A 2	2.90462024	E-1
A 3	2.37971516	
B 1	1.28202514	E-2
B 2	6.18090841	E-2
B 3	2.01094352	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.6757
$\theta_{c,A'}$	0.3074
$\theta_{d,c}$	0.2873
$\theta_{e,c}$	0.5230
$\theta_{g,d}$	1.3263
$\theta_{g,F}$	0.6136
$\theta_{h,g}$	0.5540
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7083
$\theta'_{e,c'}$	0.4702
$\theta'_{F',e}$	0.5298
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	397	$\lambda_5$	368

CCI		
B	G	R
0.00	3.11	3.10

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.100	
380	0.430	
390	0.700	
400	0.840	
420	0.934	
440	0.960	
460	0.971	
480	0.977	
500	0.983	
550	0.993	
600	0.993	
650	0.990	
700	0.992	
800	0.997	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.988	
2000	0.982	
2200	0.961	
2400	0.942	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	420				
Specific Gravity	<b>d</b>	3.17		$\lambda_5$	365				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.2	0.9	1.0	1.4	1.8	2.9	4.3		
-20 ~ 0	0.3	1.1	1.2	1.6	2.0	3.2	4.7		
0 ~ 20	0.4	1.2	1.3	1.7	2.2	3.5	5.1		
20 ~ 40	0.5	1.4	1.5	2.0	2.4	3.8	5.5		
40 ~ 60	0.6	1.6	1.7	2.2	2.7	4.1	5.9		
60 ~ 80	0.7	1.7	1.8	2.4	2.9	4.4	6.2		

Refractive Index	$n_d$	<b>1.72151</b>	Abbe Number	$V_d$	<b>29.23</b>	Dispersion	$n_F - n_C$	<b>0.02468</b>
	$n_e$	1.721507		$V_e$	29.00		$n_{F'} - n_{C'}$	0.024683
		1.727331						0.025081

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.67384
$n_{1970}$	1.97009	1.68002
$n_{1530}$	1.52958	1.68715
$n_{1129}$	1.12864	1.69453
$n_t$	1.01398	1.69734
$n_s$	0.85211	1.70272
$n_{A'}$	0.76819	1.70668
$n_r$	0.70652	1.71047
$n_C$	0.65627	<b>1.71437</b>
$n_{C'}$	0.64385	1.71548
$n_{\text{He-Ne}}$	0.6328	1.71653
$n_D$	0.58929	1.72129
$n_d$	0.58756	<b>1.72151</b>
$n_e$	0.54607	1.72733
$n_F$	0.48613	<b>1.73905</b>
$n_{F'}$	0.47999	1.74057
$n_{\text{He-Cd}}$	0.44157	1.75195
$n_g$	0.435835	<b>1.75399</b>
$n_h$	0.404656	1.76735
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.017028
$n_C - n_{A'}$	0.007687
$n_d - n_C$	0.007136
$n_e - n_C$	0.012960
$n_g - n_d$	0.032488
$n_g - n_F$	0.014941
$n_h - n_g$	0.013358
$n_i - n_g$	
$n_{C'} - n_t$	0.018141
$n_e - n_{C'}$	0.011847
$n_{F'} - n_e$	0.013234
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6899
$\theta_{C,A'}$	0.3114
$\theta_{d,C}$	0.2891
$\theta_{e,C}$	0.5251
$\theta_{g,d}$	1.3162
$\theta_{g,F}$	0.6053
$\theta_{h,g}$	0.5412
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7233
$\theta'_{e,C'}$	0.4723
$\theta'_{F',e}$	0.5277
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0061
$\Delta\theta_{C,A'}$	0.0001
$\Delta\theta_{g,d}$	0.0122
$\Delta\theta_{g,F}$	0.0111
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	393	$\lambda_5$	366

CCI		
B	G	R
0.00	2.43	2.44

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.59921608	
A 2	2.59532164	E-1
A 3	2.12454543	
B 1	1.16469304	E-2
B 2	5.84824883	E-2
B 3	1.86927779	E2
1129 ~ 2325 nm		
A 1	1.59921608	
A 2	2.59532164	E-1
A 3	2.12454543	
B 1	1.16469304	E-2
B 2	5.84824883	E-2
B 3	1.86927779	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.180	
380	0.540	
390	0.770	
400	0.870	
420	0.951	
440	0.971	
460	0.979	
480	0.984	
500	0.988	
550	0.995	
600	0.995	
650	0.993	
700	0.995	
800	0.998	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.995	
1800	0.986	
2000	0.978	
2200	0.948	
2400	0.928	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	570
Annealing Point (°C)	<b>AP</b>	596
Transformation Temperature (°C)	<b>Tg</b>	616
Yield Point (°C)	<b>At</b>	644
Softening Point (°C)	<b>SP</b>	703
Expansion Coefficient $\alpha$ (-30~+70°C)		83
Expansion Coefficient $\alpha$ (+10~+300°C)		98
Thermal Conductivity (W/m·K)	<b>k</b>	1.029

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	891
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	357
Poisson's Ratio	$\sigma$	0.248
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	154
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.87

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	410				
Specific Gravity	<b>d</b>	3.07		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.1	1.8	1.8	2.2	2.5	3.5	4.7		
-20 ~ 0	1.2	1.9	2.0	2.3	2.7	3.8	5.0		
0 ~ 20	1.3	2.0	2.2	2.5	2.9	4.0	5.3		
20 ~ 40	1.4	2.2	2.3	2.7	3.1	4.3	5.7		
40 ~ 60	1.5	2.3	2.5	2.8	3.3	4.5	6.0		
60 ~ 80	1.6	2.4	2.6	3.0	3.5	4.8	6.3		

Refractive Index	$n_d$	<b>1.78470</b>	Abbe Number	$V_d$	<b>26.29</b>	Dispersion	$n_F - n_C$	<b>0.02984</b>
	$n_e$	1.784696		$V_e$	26.08		$n_{F'} - n_{C'}$	0.029847
		1.791730						0.030359

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.73102
$n_{1970}$	1.97009	1.73732
$n_{1530}$	1.52958	1.74475
$n_{1129}$	1.12864	1.75284
$n_t$	1.01398	1.75605
$n_s$	0.85211	1.76230
$n_{A'}$	0.76819	1.76697
$n_r$	0.70652	1.77147
$n_C$	0.65627	<b>1.77613</b>
$n_{C'}$	0.64385	1.77746
$n_{\text{He-Ne}}$	0.6328	1.77871
$n_D$	0.58929	1.78444
$n_d$	0.58756	<b>1.78470</b>
$n_e$	0.54607	1.79173
$n_F$	0.48613	<b>1.80597</b>
$n_{F'}$	0.47999	1.80782
$n_{\text{He-Cd}}$	0.44157	1.82176
$n_g$	0.435835	<b>1.82428</b>
$n_h$	0.404656	1.84081
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	561
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	586
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	604
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	635
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	684
Expansion Coefficient ( $\alpha$ )		88
	(-30~+70 $^{\circ}\text{C}$ )	
	(+10~+300 $^{\circ}\text{C}$ )	106
Thermal Conductivity (W/m·K)	<b>k</b>	0.992

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	922
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	366
Poisson's Ratio	$\sigma$	0.260
Knoop Hardness	<b>Hk</b>	540 [5]
Abrasion	<b>Aa</b>	180
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.69

Partial Dispersions	
$n_C - n_t$	0.020074
$n_C - n_{A'}$	0.009156
$n_d - n_C$	0.008571
$n_e - n_C$	0.015605
$n_g - n_d$	0.039588
$n_g - n_F$	0.018312
$n_h - n_g$	0.016524
$n_i - n_g$	
$n_{C'} - n_t$	0.021407
$n_e - n_{C'}$	0.014272
$n_{F'} - n_e$	0.016087
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0026
$\Delta\theta_{C,A'}$	-0.0009
$\Delta\theta_{g,d}$	0.0163
$\Delta\theta_{g,F}$	0.0146
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.73986485	
A 2	3.13894918	E-1
A 3	2.31093206	
B 1	1.29441300	E-2
B 2	6.12116868	E-2
B 3	1.97420482	E2
1129 ~ 2325 nm		
A 1	1.73986485	
A 2	3.13894918	E-1
A 3	2.31093206	
B 1	1.29441300	E-2
B 2	6.12116868	E-2
B 3	1.97420482	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6726
$\theta_{C,A'}$	0.3068
$\theta_{d,C}$	0.2872
$\theta_{e,C}$	0.5228
$\theta_{g,d}$	1.3264
$\theta_{g,F}$	0.6135
$\theta_{h,g}$	0.5536
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7051
$\theta'_{e,C'}$	0.4701
$\theta'_{F',e}$	0.5299
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	400	$\lambda_5$	368

CCI		
B	G	R
0.00	3.88	3.97

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.120	
380	0.440	
390	0.670	
400	0.800	
420	0.906	
440	0.947	
460	0.962	
480	0.972	
500	0.979	
550	0.992	
600	0.992	
650	0.991	
700	0.993	
800	0.998	
900	0.998	
1000	0.998	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.988	
2000	0.981	
2200	0.962	
2400	0.937	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	435				
Specific Gravity	<b>d</b>	3.30		$\lambda_5$	365				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.3	0.5	0.6	1.0	1.4	2.6	4.1		
-20 ~ 0	-0.2	0.7	0.7	1.1	1.6	2.9	4.4		
0 ~ 20	-0.1	0.8	0.9	1.3	1.8	3.1	4.8		
20 ~ 40	-0.1	0.9	1.0	1.4	2.0	3.4	5.1		
40 ~ 60		1.0	1.1	1.5	2.2	3.7	5.5		
60 ~ 80	0.1	1.2	1.2	1.7	2.3	3.9	5.8		

Refractive Index	$n_d$	<b>1.84666</b> 1.846660	Abbe Number	$V_d$	<b>23.78</b> 23.59	Dispersion	$n_F - n_C$	<b>0.03561</b> 0.035608
		$n_e$		1.855041			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78519
$n_{1970}$	1.97009	1.79199
$n_{1530}$	1.52958	1.80013
$n_{1129}$	1.12864	1.80925
$n_t$	1.01398	1.81294
$n_s$	0.85211	1.82021
$n_{A'}$	0.76819	1.82568
$n_r$	0.70652	1.83098
$n_C$	0.65627	<b>1.83649</b>
$n_{C'}$	0.64385	1.83807
$n_{\text{He-Ne}}$	0.6328	1.83956
$n_D$	0.58929	1.84635
$n_d$	0.58756	<b>1.84666</b>
$n_e$	0.54607	1.85504
$n_F$	0.48613	<b>1.87210</b>
$n_{F'}$	0.47999	1.87431
$n_{\text{He-Cd}}$	0.44157	1.89114
$n_g$	0.435835	<b>1.89419</b>
$n_h$	0.404656	1.91429
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.023550
$n_C - n_{A'}$	0.010806
$n_d - n_C$	0.010172
$n_e - n_C$	0.018553
$n_g - n_d$	0.047529
$n_g - n_F$	0.022093
$n_h - n_g$	0.020105
$n_i - n_g$	
$n_{C'} - n_t$	0.025128
$n_e - n_{C'}$	0.016975
$n_{F'} - n_e$	0.019272
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6614
$\theta_{C,A'}$	0.3035
$\theta_{d,C}$	0.2857
$\theta_{e,C}$	0.5210
$\theta_{g,d}$	1.3348
$\theta_{g,F}$	0.6205
$\theta_{h,g}$	0.5646
$\theta_{i,g}$	
$\theta'_{C,t}$	0.6932
$\theta'_{e,C'}$	0.4683
$\theta'_{F',e}$	0.5317
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0032
$\Delta\theta_{C,A'}$	-0.0012
$\Delta\theta_{g,d}$	0.0195
$\Delta\theta_{g,F}$	0.0175
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	408	$\lambda_5$	370

CCI		
B	G	R
0.00	4.97	5.06

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.87904886	
A 2	3.69719775	E-1
A 3	2.33730863	
B 1	1.44121770	E-2
B 2	6.38817990	E-2
B 3	1.82668180	E2
1129 ~ 2325 nm		
A 1	1.87904886	
A 2	3.69719775	E-1
A 3	2.33730863	
B 1	1.44121770	E-2
B 2	6.38817990	E-2
B 3	1.82668180	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.060	
380	0.350	
390	0.610	
400	0.750	
420	0.870	
440	0.927	
460	0.948	
480	0.961	
500	0.971	
550	0.987	
600	0.989	
650	0.985	
700	0.989	
800	0.997	
900	0.998	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.991	
2000	0.986	
2200	0.974	
2400	0.955	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	576
Annealing Point (°C)	<b>AP</b>	596
Transformation Temperature (°C)	<b>Tg</b>	624
Yield Point (°C)	<b>At</b>	658
Softening Point (°C)	<b>SP</b>	692
Expansion Coefficient $\alpha$ (-30~+70°C)		88
(10-7 /°C) (+100~+300°C)		104
Thermal Conductivity (W/m·K)	<b>k</b>	1.000

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	960
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	379
Poisson's Ratio	$\sigma$	0.266
Knoop Hardness	<b>Hk</b>	520 [5]
Abrasion	<b>Aa</b>	170
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$					420
Specific Gravity	<b>d</b>	3.54		$\lambda_5$					370
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.8	0.4	0.4	0.9	1.4	2.8	4.5		
-20 ~ 0	-0.8	0.5	0.6	1.0	1.6	3.1	5.0		
0 ~ 20	-0.7	0.6	0.7	1.2	1.8	3.4	5.4		
20 ~ 40	-0.7	0.7	0.8	1.3	2.0	3.7	5.8		
40 ~ 60	-0.6	0.9	1.0	1.5	2.2	4.0	6.2		
60 ~ 80	-0.6	1.0	1.1	1.6	2.4	4.3	6.6		

Refractive Index	$n_d$	<b>1.84666</b>	Abbe Number	$V_d$	<b>23.78</b>	Dispersion	$n_F - n_C$	<b>0.03561</b>
	$n_e$	1.846660		$V_e$	23.59		$n_{F'} - n_{C'}$	0.035608
		1.855041						0.036247

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78519
$n_{1970}$	1.97009	1.79199
$n_{1530}$	1.52958	1.80013
$n_{1129}$	1.12864	1.80925
$n_t$	1.01398	1.81294
$n_s$	0.85211	1.82021
$n_{A'}$	0.76819	1.82568
$n_r$	0.70652	1.83098
$n_c$	0.65627	<b>1.83649</b>
$n_{c'}$	0.64385	1.83807
$n_{\text{He-Ne}}$	0.6328	1.83956
$n_D$	0.58929	1.84635
$n_d$	0.58756	<b>1.84666</b>
$n_e$	0.54607	1.85504
$n_F$	0.48613	<b>1.87210</b>
$n_{F'}$	0.47999	1.87431
$n_{\text{He-Cd}}$	0.44157	1.89114
$n_g$	0.435835	<b>1.89419</b>
$n_h$	0.404656	1.91429
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.023550
$n_c - n_{A'}$	0.010806
$n_d - n_c$	0.010172
$n_e - n_c$	0.018553
$n_g - n_d$	0.047529
$n_g - n_F$	0.022093
$n_h - n_g$	0.020105
$n_i - n_g$	
$n_{c'} - n_t$	0.025128
$n_e - n_{c'}$	0.016975
$n_{F'} - n_e$	0.019272
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6614
$\theta_{c,A'}$	0.3035
$\theta_{d,c}$	0.2857
$\theta_{e,c}$	0.5210
$\theta_{g,d}$	1.3348
$\theta_{g,F}$	0.6205
$\theta_{h,g}$	0.5646
$\theta_{i,g}$	
$\theta'_{c,t}$	0.6932
$\theta'_{e,c'}$	0.4683
$\theta'_{F',e}$	0.5317
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0032
$\Delta\theta_{c,A'}$	-0.0012
$\Delta\theta_{g,d}$	0.0195
$\Delta\theta_{g,F}$	0.0175
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	398	$\lambda_5$	368

CCI		
B	G	R
0.00	3.49	3.70

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.87904886	
A 2	3.69719775	E-1
A 3	2.33730863	
B 1	1.44121770	E-2
B 2	6.38817990	E-2
B 3	1.82668180	E2
1129 ~ 2325 nm		
A 1	1.87904886	
A 2	3.69719775	E-1
A 3	2.33730863	
B 1	1.44121770	E-2
B 2	6.38817990	E-2
B 3	1.82668180	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.110	
380	0.450	
390	0.710	
400	0.830	
420	0.918	
440	0.954	
460	0.971	
480	0.980	
500	0.986	
550	0.995	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.999	
1800	0.994	
2000	0.985	
2200	0.961	
2400	0.925	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	576
Annealing Point (°C)	<b>AP</b>	596
Transformation Temperature (°C)	<b>Tg</b>	624
Yield Point (°C)	<b>At</b>	658
Softening Point (°C)	<b>SP</b>	692
Expansion Coefficient $\alpha$ (-30~+70°C)		88
(10-7 /°C) (+100~+300°C)		104
Thermal Conductivity (W/m·K)	<b>k</b>	1.000

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	960
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	379
Poisson's Ratio	$\sigma$	0.266
Knoop Hardness	<b>Hk</b>	520 [5]
Abrasion	<b>Aa</b>	170
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$					404
Specific Gravity	<b>d</b>	3.54		$\lambda_5$					368
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-0.8	0.4	0.4	0.9	1.4	2.8	4.5		
-20 ~ 0	-0.8	0.5	0.6	1.0	1.6	3.1	5.0		
0 ~ 20	-0.7	0.6	0.7	1.2	1.8	3.4	5.4		
20 ~ 40	-0.7	0.7	0.8	1.3	2.0	3.7	5.8		
40 ~ 60	-0.6	0.9	1.0	1.5	2.2	4.0	6.2		
60 ~ 80	-0.6	1.0	1.1	1.6	2.4	4.3	6.6		



Refractive Index	$n_d$	<b>1.96300</b>	Abbe Number	$V_d$	<b>24.11</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.039935
		1.963000			$V_e$		23.92	
	$n_e$	1.972398						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.89394
$n_{1970}$	1.97009	1.90163
$n_{1530}$	1.52958	1.91082
$n_{1129}$	1.12864	1.92106
$n_t$	1.01398	1.92520
$n_s$	0.85211	1.93335
$n_{A'}$	0.76819	1.93949
$n_r$	0.70652	1.94542
$n_C$	0.65627	<b>1.95160</b>
$n_{C'}$	0.64385	1.95337
$n_{\text{He-Ne}}$	0.6328	1.95504
$n_D$	0.58929	1.96266
$n_d$	0.58756	<b>1.96300</b>
$n_e$	0.54607	1.97240
$n_F$	0.48613	<b>1.99153</b>
$n_{F'}$	0.47999	1.99402
$n_{\text{He-Cd}}$	0.44157	2.01291
$n_g$	0.435835	<b>2.01634</b>
$n_h$	0.404656	2.03893
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.026394
$n_C - n_{A'}$	0.012111
$n_d - n_C$	0.011402
$n_e - n_C$	0.020800
$n_g - n_d$	0.053340
$n_g - n_F$	0.024807
$n_h - n_g$	0.022594
$n_i - n_g$	
$n_{C'} - n_t$	0.028162
$n_e - n_{C'}$	0.019032
$n_{F'} - n_e$	0.021624
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6609
$\theta_{C,A'}$	0.3033
$\theta_{d,C}$	0.2855
$\theta_{e,C}$	0.5208
$\theta_{g,d}$	1.3357
$\theta_{g,F}$	0.6212
$\theta_{h,g}$	0.5658
$\theta_{i,g}$	
$\theta'_{C,t}$	0.6927
$\theta'_{e,C'}$	0.4681
$\theta'_{F',e}$	0.5319
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0011
$\Delta\theta_{C,A'}$	-0.0018
$\Delta\theta_{g,d}$	0.0211
$\Delta\theta_{g,F}$	0.0187
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.21103256	E0
A 2	4.50346986	E-1
A 3	2.47746663	E0
B 1	1.42330268	E-2
B 2	6.38573392	E-2
B 3	1.61937600	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.020	
380	0.130	
390	0.330	
400	0.510	
420	0.730	
440	0.840	
460	0.900	
480	0.929	
500	0.950	
550	0.979	
600	0.988	
650	0.991	
700	0.994	
800	0.997	
900	0.997	
1000	0.997	
1200	0.997	
1400	0.997	
1600	0.995	
1800	0.989	
2000	0.977	
2200	0.947	
2400	0.850	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	634
Annealing Point (°C)	<b>AP</b>	661
Transformation Temperature (°C)	<b>Tg</b>	672
Yield Point (°C)	<b>At</b>	707
Softening Point (°C)	<b>SP</b>	732
Expansion Coefficient $\alpha$ (-30~+70°C)		75
Expansion Coefficient $\alpha$ (+100~+300°C)		91
Thermal Conductivity (W/m·K)	<b>k</b>	0.970

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	3.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1170
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	453
Poisson's Ratio	$\sigma$	0.292
Knoop Hardness	<b>Hk</b>	630 [6]
Abrasion	<b>Aa</b>	97
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.73

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					450
Specific Gravity	<b>d</b>	4.20		$\lambda_5$					375
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.5	1.8	1.9	2.4	3.0	4.6	6.6		
-20 ~ 0	0.5	1.9	2.0	2.5	3.2	5.0	7.1		
0 ~ 20	0.6	2.1	2.2	2.8	3.5	5.4	7.6		
20 ~ 40	0.7	2.3	2.4	3.0	3.8	5.8	8.1		
40 ~ 60	0.9	2.6	2.7	3.3	4.1	6.2	8.7		
60 ~ 80	1.1	2.8	2.9	3.6	4.4	6.6	9.3		

Refractive Index	$n_d$	<b>1.54814</b>	Abbe Number	$V_d$	<b>45.79</b>	Dispersion	$n_F - n_C$	<b>0.01197</b>
		1.548141			$V_e$		45.49	
	$n_e$	1.550984					$n_{F'} - n_{C'}$	0.012112

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.51797
$n_{1970}$	1.97009	1.52307
$n_{1530}$	1.52958	1.52861
$n_{1129}$	1.12864	1.53365
$n_t$	1.01398	1.53537
$n_s$	0.85211	1.53844
$n_{A'}$	0.76819	1.54058
$n_r$	0.70652	1.54257
$n_c$	0.65627	<b>1.54457</b>
$n_{c'}$	0.64385	1.54514
$n_{\text{He-Ne}}$	0.6328	1.54566
$n_D$	0.58929	1.54804
$n_d$	0.58756	<b>1.54814</b>
$n_e$	0.54607	1.55098
$n_F$	0.48613	<b>1.55654</b>
$n_{F'}$	0.47999	1.55725
$n_{\text{He-Cd}}$	0.44157	1.56244
$n_g$	0.435835	<b>1.56335</b>
$n_h$	0.404656	1.56918
$n_i$	0.365015	1.57959
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.009202
$n_c - n_{A'}$	0.003988
$n_d - n_c$	0.003569
$n_e - n_c$	0.006412
$n_g - n_d$	0.015210
$n_g - n_F$	0.006807
$n_h - n_g$	0.005833
$n_i - n_g$	0.016236
$n_{c'} - n_t$	0.009765
$n_e - n_{c'}$	0.005849
$n_{F'} - n_e$	0.006263
$n_i - n_{F'}$	0.022340

Relative Partial Dispersions	
$\theta_{c,t}$	0.7686
$\theta_{c,A'}$	0.3331
$\theta_{d,c}$	0.2981
$\theta_{e,c}$	0.5356
$\theta_{g,d}$	1.2705
$\theta_{g,F}$	0.5686
$\theta_{h,g}$	0.4872
$\theta_{i,g}$	1.3562
$\theta'_{c,t}$	0.8062
$\theta'_{e,c'}$	0.4829
$\theta'_{F',e}$	0.5171
$\theta'_{i,F'}$	1.8445

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0071
$\Delta\theta_{c,A'}$	0.0017
$\Delta\theta_{g,d}$	0.0009
$\Delta\theta_{g,F}$	0.0012
$\Delta\theta_{i,g}$	0.0146

Internal Transmittance			
$\lambda_{80}$	366	$\lambda_5$	341

CCI		
B	G	R
0.00	0.32	0.33

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.25088944	
A 2	9.97973327	E-2
A 3	1.20583504	
B 1	8.83921279	E-3
B 2	4.82685052	E-2
B 3	1.37414953	E2
1129 ~ 2325 nm		
A 1	1.25088944	
A 2	9.97973327	E-2
A 3	1.20583504	
B 1	8.83921279	E-3
B 2	4.82685052	E-2
B 3	1.37414953	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.010	
350	0.290	
360	0.690	
365		
370	0.870	
380	0.944	
390	0.972	
400	0.984	
420	0.992	
440	0.994	
460	0.995	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.996	
1600	0.993	
1800	0.977	
2000	0.948	
2200	0.890	
2400	0.850	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	452
Annealing Point (°C)	<b>AP</b>	487
Transformation Temperature (°C)	<b>Tg</b>	501
Yield Point (°C)	<b>At</b>	542
Softening Point (°C)	<b>SP</b>	654
Expansion Coefficient $\alpha$ (-30~+70°C)		86
(10-7 /°C) (+100~+300°C)		101
Thermal Conductivity (W/m·K)	<b>k</b>	1.039

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	705
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	288
Poisson's Ratio	$\sigma$	0.222
Knoop Hardness	<b>Hk</b>	490 [5]
Abrasion	<b>Aa</b>	128
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.68

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	2.54		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.1	1.5	1.5	1.7	1.9	2.3	2.8		
-20 ~ 0	1.1	1.5	1.6	1.7	1.9	2.4	2.9		
0 ~ 20	1.1	1.5	1.6	1.7	2.0	2.4	3.0		
20 ~ 40	1.1	1.6	1.6	1.8	2.0	2.5	3.1		
40 ~ 60	1.1	1.6	1.6	1.8	2.0	2.6	3.1		
60 ~ 80	1.1	1.6	1.6	1.8	2.1	2.6	3.2		

Refractive Index	$n_d$	<b>1.54072</b>	Abbe Number	$V_d$	<b>47.23</b>	Dispersion	$n_F - n_C$	<b>0.01145</b>
		1.540720			$V_e$		46.94	
	$n_e$	1.543440					$n_{F'} - n_{C'}$	0.011577

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.51118
$n_{1970}$	1.97009	1.51626
$n_{1530}$	1.52958	1.52176
$n_{1129}$	1.12864	1.52672
$n_t$	1.01398	1.52841
$n_s$	0.85211	1.53139
$n_{A'}$	0.76819	1.53346
$n_r$	0.70652	1.53537
$n_c$	0.65627	<b>1.53730</b>
$n_{c'}$	0.64385	1.53784
$n_{\text{He-Ne}}$	0.6328	1.53835
$n_D$	0.58929	1.54062
$n_d$	0.58756	<b>1.54072</b>
$n_e$	0.54607	1.54344
$n_F$	0.48613	<b>1.54875</b>
$n_{F'}$	0.47999	1.54942
$n_{\text{He-Cd}}$	0.44157	1.55435
$n_g$	0.435835	<b>1.55522</b>
$n_h$	0.404656	1.56074
$n_i$	0.365015	1.57052
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008891
$n_c - n_{A'}$	0.003839
$n_d - n_c$	0.003423
$n_e - n_c$	0.006143
$n_g - n_d$	0.014496
$n_g - n_F$	0.006470
$n_h - n_g$	0.005521
$n_i - n_g$	0.015308
$n_{c'} - n_t$	0.009432
$n_e - n_{c'}$	0.005602
$n_{F'} - n_e$	0.005975
$n_i - n_{F'}$	0.021109

Relative Partial Dispersions	
$\theta_{c,t}$	0.7766
$\theta_{c,A'}$	0.3353
$\theta_{d,c}$	0.2990
$\theta_{e,c}$	0.5366
$\theta_{g,d}$	1.2661
$\theta_{g,F}$	0.5651
$\theta_{h,g}$	0.4822
$\theta_{i,g}$	1.3371
$\theta'_{c,t}$	0.8147
$\theta'_{e,c'}$	0.4839
$\theta'_{F',e}$	0.5161
$\theta'_{i,F'}$	1.8234

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0083
$\Delta\theta_{c,A'}$	0.0022
$\Delta\theta_{g,d}$	-0.0005
$\Delta\theta_{g,F}$	
$\Delta\theta_{i,g}$	0.0076

Internal Transmittance			
$\lambda_{80}$	368	$\lambda_5$	340

CCI		
B	G	R
0.00	0.40	0.38

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.23401499	
A 2	9.59796833	E-2
A 3	1.20503991	
B 1	8.69507801	E-3
B 2	4.65611429	E-2
B 3	1.37953301	E2
1129 ~ 2325 nm		
A 1	1.23401499	
A 2	9.59796833	E-2
A 3	1.20503991	
B 1	8.69507801	E-3
B 2	4.65611429	E-2
B 3	1.37953301	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.040	
350	0.320	
360	0.660	
365		
370	0.840	
380	0.925	
390	0.962	
400	0.979	
420	0.990	
440	0.994	
460	0.995	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.997	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.997	
1600	0.995	
1800	0.987	
2000	0.970	
2200	0.942	
2400	0.917	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	448
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	484
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	496
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	538
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	658
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	82
	(+10~+300 $^{\circ}\text{C}$ )	98
Thermal Conductivity (W/m·K)	<b>k</b>	1.051

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	699
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	286
Poisson's Ratio	$\sigma$	0.220
Knoop Hardness	<b>Hk</b>	500 [5]
Abrasion	<b>Aa</b>	121
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.74

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	2.52		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.3	1.7	1.7	1.9	2.0	2.5	2.9		
-20 ~ 0	1.3	1.7	1.8	1.9	2.1	2.6	3.0		
0 ~ 20	1.4	1.8	1.8	2.0	2.2	2.6	3.1		
20 ~ 40	1.5	1.9	1.9	2.1	2.3	2.7	3.3		
40 ~ 60	1.5	1.9	1.9	2.1	2.3	2.8	3.4		
60 ~ 80	1.5	2.0	2.0	2.2	2.4	2.9	3.5		

Refractive Index	$n_d$	<b>1.53172</b>	Abbe Number	$V_d$	<b>48.84</b>	Dispersion	$n_F - n_C$	<b>0.01088</b>
	$n_e$	1.531717		$V_e$	48.55		$n_{F'} - n_{C'}$	0.010887
		1.534304						0.011006

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.50292
$n_{1970}$	1.97009	1.50797
$n_{1530}$	1.52958	1.51342
$n_{1129}$	1.12864	1.51829
$n_t$	1.01398	1.51993
$n_s$	0.85211	1.52280
$n_{A'}$	0.76819	1.52479
$n_r$	0.70652	1.52662
$n_C$	0.65627	<b>1.52846</b>
$n_{C'}$	0.64385	1.52897
$n_{\text{He-Ne}}$	0.6328	1.52946
$n_D$	0.58929	1.53162
$n_d$	0.58756	<b>1.53172</b>
$n_e$	0.54607	1.53430
$n_F$	0.48613	<b>1.53934</b>
$n_{F'}$	0.47999	1.53998
$n_{\text{He-Cd}}$	0.44157	1.54465
$n_g$	0.435835	<b>1.54547</b>
$n_h$	0.404656	1.55069
$n_i$	0.365015	1.55989
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	438
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	468
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	479
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	528
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	648
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		82
Expansion Coefficient $\alpha$ (+10~+300 $^{\circ}\text{C}$ )		96
Thermal Conductivity (W/m·K)	<b>k</b>	1.059

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	648
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	283
Poisson's Ratio	$\sigma$	0.146
Knoop Hardness	<b>Hk</b>	490 [5]
Abrasion	<b>Aa</b>	114
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Partial Dispersions	
$n_C - n_t$	0.008529
$n_C - n_{A'}$	0.003667
$n_d - n_C$	0.003261
$n_e - n_C$	0.005848
$n_g - n_d$	0.013756
$n_g - n_F$	0.006130
$n_h - n_g$	0.005216
$n_i - n_g$	0.014418
$n_{C'} - n_t$	0.009045
$n_e - n_{C'}$	0.005332
$n_{F'} - n_e$	0.005674
$n_i - n_{F'}$	0.019913

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0076
$\Delta\theta_{C,A'}$	0.0017
$\Delta\theta_{g,d}$	0.0002
$\Delta\theta_{g,F}$	0.0007
$\Delta\theta_{i,g}$	0.0082

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.17701777	
A 2	1.27958030	E-1
A 3	1.34740124	
B 1	7.71087686	E-3
B 2	4.11325328	E-2
B 3	1.54531692	E2
1129 ~ 2325 nm		
A 1	1.17701777	
A 2	1.27958030	E-1
A 3	1.34740124	
B 1	7.71087686	E-3
B 2	4.11325328	E-2
B 3	1.54531692	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.7834
$\theta_{C,A'}$	0.3368
$\theta_{d,C}$	0.2995
$\theta_{e,C}$	0.5372
$\theta_{g,d}$	1.2635
$\theta_{g,F}$	0.5631
$\theta_{h,g}$	0.4791
$\theta_{i,g}$	1.3243
$\theta'_{C,t}$	0.8218
$\theta'_{e,C'}$	0.4845
$\theta'_{F',e}$	0.5155
$\theta'_{i,F'}$	1.8093

Internal Transmittance			
$\lambda_{80}$	364	$\lambda_5$	339

CCI		
B	G	R
0.00	0.28	0.24

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.070	
350	0.440	
360	0.740	
365		
370	0.880	
380	0.948	
390	0.973	
400	0.985	
420	0.990	
440	0.989	
460	0.990	
480	0.991	
500	0.993	
550	0.994	
600	0.994	
650	0.992	
700	0.996	
800	0.998	
900	0.997	
1000	0.997	
1200	0.996	
1400	0.995	
1600	0.993	
1800	0.977	
2000	0.947	
2200	0.890	
2400	0.850	

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	365				
Specific Gravity	<b>d</b>	2.50		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.4	1.8	1.8	1.9	2.2	2.5	3.0		
-20 ~ 0	1.4	1.8	1.8	1.9	2.2	2.6	3.0		
0 ~ 20	1.4	1.8	1.8	1.9	2.2	2.6	3.1		
20 ~ 40	1.4	1.8	1.8	1.9	2.2	2.7	3.1		
40 ~ 60	1.4	1.8	1.9	1.9	2.2	2.7	3.2		
60 ~ 80	1.4	1.8	1.9	1.9	2.2	2.7	3.3		

Refractive Index	$n_d$	<b>1.58144</b> 1.581439	Abbe Number	$V_d$	<b>40.75</b> 40.47	Dispersion	$n_F - n_C$	<b>0.01427</b> 0.014270
		$n_e$		1.584822			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.54741
$n_{1970}$	1.97009	1.55292
$n_{1530}$	1.52958	1.55895
$n_{1129}$	1.12864	1.56456
$n_t$	1.01398	1.56651
$n_s$	0.85211	1.57005
$n_{A'}$	0.76819	1.57254
$n_r$	0.70652	1.57486
$n_c$	0.65627	<b>1.57722</b>
$n_{c'}$	0.64385	1.57788
$n_{\text{He-Ne}}$	0.6328	1.57850
$n_D$	0.58929	1.58131
$n_d$	0.58756	<b>1.58144</b>
$n_e$	0.54607	1.58482
$n_F$	0.48613	<b>1.59149</b>
$n_{F'}$	0.47999	1.59233
$n_{\text{He-Cd}}$	0.44157	1.59861
$n_g$	0.435835	<b>1.59973</b>
$n_h$	0.404656	1.60687
$n_i$	0.365015	1.61979
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010703
$n_c - n_{A'}$	0.004679
$n_d - n_c$	0.004223
$n_e - n_c$	0.007606
$n_g - n_d$	0.018287
$n_g - n_F$	0.008240
$n_h - n_g$	0.007140
$n_i - n_g$	0.020066
$n_{c'} - n_t$	0.011368
$n_e - n_{c'}$	0.006941
$n_{F'} - n_e$	0.007510
$n_i - n_{F'}$	0.027460

Relative Partial Dispersions	
$\theta_{c,t}$	0.7500
$\theta_{c,A'}$	0.3279
$\theta_{d,c}$	0.2959
$\theta_{e,c}$	0.5330
$\theta_{g,d}$	1.2815
$\theta_{g,F}$	0.5774
$\theta_{h,g}$	0.5004
$\theta_{i,g}$	1.4062
$\theta'_{c,t}$	0.7867
$\theta'_{e,c'}$	0.4803
$\theta'_{F',e}$	0.5197
$\theta'_{i,F'}$	1.9002

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0121
$\Delta\theta_{c,A'}$	0.0027
$\Delta\theta_{g,d}$	0.0014
$\Delta\theta_{g,F}$	0.0019
$\Delta\theta_{i,g}$	0.0224

Internal Transmittance			
$\lambda_{80}$	378	$\lambda_5$	351

CCI		
B	G	R
0.00	0.73	0.73

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.32122534	
A 2	1.23824976	E-1
A 3	1.43685254	
B 1	9.52091436	E-3
B 2	5.16062665	E-2
B 3	1.49064883	E2
1129 ~ 2325 nm		
A 1	1.32122534	
A 2	1.23824976	E-1
A 3	1.43685254	
B 1	9.52091436	E-3
B 2	5.16062665	E-2
B 3	1.49064883	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.010	
360	0.280	
365		
370	0.650	
380	0.850	
390	0.929	
400	0.964	
420	0.986	
440	0.991	
460	0.993	
480	0.994	
500	0.995	
550	0.998	
600	0.998	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.998	
1200	0.998	
1400	0.994	
1600	0.994	
1800	0.981	
2000	0.963	
2200	0.911	
2400	0.890	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	536
Annealing Point (°C)	<b>AP</b>	564
Transformation Temperature (°C)	<b>Tg</b>	588
Yield Point (°C)	<b>At</b>	630
Softening Point (°C)	<b>SP</b>	715
Expansion Coefficient $\alpha$ (-30~+70°C)		74
(10-7 / °C)	(+100~+300°C)	88
Thermal Conductivity (W/m·K)	<b>k</b>	1.054

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	753
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	309
Poisson's Ratio	$\sigma$	0.220
Knoop Hardness	<b>Hk</b>	540 [5]
Abrasion	<b>Aa</b>	117
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.84

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	2.59		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.4	3.0	3.0	3.2	3.4	4.0	4.6		
-20 ~ 0	2.5	3.0	3.1	3.3	3.5	4.1	4.7		
0 ~ 20	2.6	3.1	3.2	3.4	3.6	4.2	4.9		
20 ~ 40	2.7	3.2	3.3	3.5	3.7	4.4	5.1		
40 ~ 60	2.7	3.3	3.3	3.5	3.8	4.5	5.2		
60 ~ 80	2.8	3.4	3.4	3.6	3.9	4.6	5.4		

Refractive Index	$n_d$	<b>1.56732</b>	Abbe Number	$V_d$	<b>42.82</b>	Dispersion	$n_F - n_C$	<b>0.01325</b>
	$n_e$	1.567322		$V_e$	42.54		$n_{F'} - n_{C'}$	0.013250
		1.570466						0.013411

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.53493
$n_{1970}$	1.97009	1.54028
$n_{1530}$	1.52958	1.54611
$n_{1129}$	1.12864	1.55148
$n_t$	1.01398	1.55333
$n_s$	0.85211	1.55667
$n_{A'}$	0.76819	1.55901
$n_r$	0.70652	1.56119
$n_c$	0.65627	<b>1.56339</b>
$n_{c'}$	0.64385	1.56401
$n_{\text{He-Ne}}$	0.6328	1.56459
$n_D$	0.58929	1.56721
$n_d$	0.58756	<b>1.56732</b>
$n_e$	0.54607	1.57047
$n_F$	0.48613	<b>1.57664</b>
$n_{F'}$	0.47999	1.57742
$n_{\text{He-Cd}}$	0.44157	1.58321
$n_g$	0.435835	<b>1.58423</b>
$n_h$	0.404656	1.59077
$n_i$	0.365015	1.60256
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010055
$n_c - n_{A'}$	0.004379
$n_d - n_c$	0.003936
$n_e - n_c$	0.007080
$n_g - n_d$	0.016907
$n_g - n_F$	0.007593
$n_h - n_g$	0.006546
$n_i - n_g$	0.018329
$n_{c'} - n_t$	0.010676
$n_e - n_{c'}$	0.006459
$n_{F'} - n_e$	0.006952
$n_i - n_{F'}$	0.025140

Relative Partial Dispersions	
$\theta_{c,t}$	0.7589
$\theta_{c,A'}$	0.3305
$\theta_{d,c}$	0.2971
$\theta_{e,c}$	0.5343
$\theta_{g,d}$	1.2760
$\theta_{g,F}$	0.5731
$\theta_{h,g}$	0.4940
$\theta_{i,g}$	1.3833
$\theta'_{c,t}$	0.7961
$\theta'_{e,c'}$	0.4816
$\theta'_{F',e}$	0.5184
$\theta'_{i,F'}$	1.8746

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0113
$\Delta\theta_{c,A'}$	0.0027
$\Delta\theta_{g,d}$	0.0002
$\Delta\theta_{g,F}$	0.0009
$\Delta\theta_{i,g}$	0.0168

Internal Transmittance			
$\lambda_{80}$	374	$\lambda_5$	349

CCI		
B	G	R
0.00	0.56	0.54

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.31066488	
A 2	9.41903094	E-2
A 3	1.23292644	
B 1	9.68897812	E-3
B 2	5.27763106	E-2
B 3	1.33296422	E2
1129 ~ 2325 nm		
A 1	1.31066488	
A 2	9.41903094	E-2
A 3	1.23292644	
B 1	9.68897812	E-3
B 2	5.27763106	E-2
B 3	1.33296422	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.070	
360	0.440	
365		
370	0.740	
380	0.880	
390	0.945	
400	0.971	
420	0.989	
440	0.993	
460	0.995	
480	0.995	
500	0.997	
550	0.998	
600	0.998	
650	0.997	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.995	
1600	0.993	
1800	0.977	
2000	0.950	
2200	0.890	
2400	0.860	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	495
Annealing Point (°C)	<b>AP</b>	533
Transformation Temperature (°C)	<b>Tg</b>	552
Yield Point (°C)	<b>At</b>	599
Softening Point (°C)	<b>SP</b>	694
Expansion Coefficient $\alpha$ (-30~+70°C)		79
Expansion Coefficient $\alpha$ (+10~+300°C)		90
Thermal Conductivity (W/m·K)	<b>k</b>	1.054

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	739
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	302
Poisson's Ratio	$\sigma$	0.222
Knoop Hardness	<b>Hk</b>	500 [5]
Abrasion	<b>Aa</b>	123
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.75

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	2.57		$\lambda_5$	345				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.0	2.4	2.4	2.6	2.8	3.3	3.9		
-20 ~ 0	2.0	2.5	2.5	2.7	2.9	3.4	4.0		
0 ~ 20	2.0	2.6	2.6	2.8	3.0	3.5	4.2		
20 ~ 40	2.0	2.6	2.7	2.8	3.1	3.6	4.3		
40 ~ 60	2.1	2.7	2.7	2.9	3.2	3.7	4.4		
60 ~ 80	2.2	2.8	2.8	3.0	3.3	3.8	4.6		



Refractive Index	$n_d$	<b>1.57501</b> 1.575006	Abbe Number	$V_d$	<b>41.50</b> 41.22	Dispersion	$n_F - n_C$	<b>0.01386</b> 0.013854
		$n_e$		1.578291			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.54162
$n_{1970}$	1.97009	1.54707
$n_{1530}$	1.52958	1.55304
$n_{1129}$	1.12864	1.55855
$n_t$	1.01398	1.56047
$n_s$	0.85211	1.56392
$n_{A'}$	0.76819	1.56635
$n_r$	0.70652	1.56861
$n_c$	0.65627	<b>1.57090</b>
$n_{c'}$	0.64385	1.57155
$n_{\text{He-Ne}}$	0.6328	1.57216
$n_D$	0.58929	1.57488
$n_d$	0.58756	<b>1.57501</b>
$n_e$	0.54607	1.57829
$n_F$	0.48613	<b>1.58476</b>
$n_{F'}$	0.47999	1.58558
$n_{\text{He-Cd}}$	0.44157	1.59167
$n_g$	0.435835	<b>1.59275</b>
$n_h$	0.404656	1.59966
$n_i$	0.365015	1.61218
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.010433
$n_C - n_{A'}$	0.004553
$n_d - n_C$	0.004104
$n_e - n_C$	0.007389
$n_g - n_d$	0.017739
$n_g - n_F$	0.007989
$n_h - n_g$	0.006918
$n_i - n_g$	0.019440
$n_{C'} - n_t$	0.011080
$n_e - n_{C'}$	0.006742
$n_{F'} - n_e$	0.007286
$n_i - n_{F'}$	0.026608

Relative Partial Dispersions	
$\theta_{C,t}$	0.7531
$\theta_{C,A'}$	0.3286
$\theta_{d,C}$	0.2962
$\theta_{e,C}$	0.5333
$\theta_{g,d}$	1.2804
$\theta_{g,F}$	0.5767
$\theta_{h,g}$	0.4994
$\theta_{i,g}$	1.4032
$\theta'_{C,t}$	0.7898
$\theta'_{e,C'}$	0.4806
$\theta'_{F',e}$	0.5194
$\theta'_{i,F'}$	1.8968

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0117
$\Delta\theta_{C,A'}$	0.0024
$\Delta\theta_{g,d}$	0.0019
$\Delta\theta_{g,F}$	0.0024
$\Delta\theta_{i,g}$	0.0257

Internal Transmittance			
$\lambda_{80}$	371	$\lambda_5$	350

CCI		
B	G	R
0.00	0.45	0.47

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.31433154	
A 2	1.12300168	E-1
A 3	1.41390100	
B 1	9.50404477	E-3
B 2	5.24112772	E-2
B 3	1.48429972	E2
1129 ~ 2325 nm		
A 1	1.31433154	
A 2	1.12300168	E-1
A 3	1.41390100	
B 1	9.50404477	E-3
B 2	5.24112772	E-2
B 3	1.48429972	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.050	
360	0.440	
365		
370	0.780	
380	0.913	
390	0.961	
400	0.979	
420	0.990	
440	0.993	
460	0.994	
480	0.995	
500	0.996	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.999	
1000	0.998	
1200	0.998	
1400	0.994	
1600	0.993	
1800	0.978	
2000	0.955	
2200	0.890	
2400	0.870	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	511
Annealing Point (°C)	<b>AP</b>	547
Transformation Temperature (°C)	<b>Tg</b>	562
Yield Point (°C)	<b>At</b>	599
Softening Point (°C)	<b>SP</b>	700
Expansion Coefficient $\alpha$ (-30~+70°C)		74
(10-7 /°C)	(+100~+300°C)	89
Thermal Conductivity (W/m·K)	<b>k</b>	1.070

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	749
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	308
Poisson's Ratio	$\sigma$	0.217
Knoop Hardness	<b>Hk</b>	540 [5]
Abrasion	<b>Aa</b>	120
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	2.58		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.4	2.9	3.0	3.1	3.3	3.9	4.5		
-20 ~ 0	2.4	2.9	3.0	3.2	3.4	4.0	4.6		
0 ~ 20	2.5	3.0	3.0	3.2	3.5	4.0	4.7		
20 ~ 40	2.5	3.0	3.1	3.3	3.5	4.1	4.8		
40 ~ 60	2.5	3.0	3.1	3.3	3.6	4.2	4.9		
60 ~ 80	2.5	3.1	3.1	3.3	3.6	4.3	5.0		

Refractive Index	$n_d$	<b>1.62588</b>	Abbe Number	$V_d$	<b>35.70</b>	Dispersion	$n_F - n_C$	<b>0.01754</b>
	$n_e$	1.625882		$V_e$	35.43		$n_{F'} - n_{C'}$	0.017532
		1.630031						0.017780

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.58769
$n_{1970}$	1.97009	1.59337
$n_{1530}$	1.52958	1.59970
$n_{1129}$	1.12864	1.60583
$n_t$	1.01398	1.60805
$n_s$	0.85211	1.61216
$n_{A'}$	0.76819	1.61511
$n_r$	0.70652	1.61790
$n_c$	0.65627	<b>1.62074</b>
$n_{c'}$	0.64385	1.62155
$n_{\text{He-Ne}}$	0.6328	1.62231
$n_D$	0.58929	1.62573
$n_d$	0.58756	<b>1.62588</b>
$n_e$	0.54607	1.63003
$n_F$	0.48613	<b>1.63828</b>
$n_{F'}$	0.47999	1.63933
$n_{\text{He-Cd}}$	0.44157	1.64720
$n_g$	0.435835	<b>1.64861</b>
$n_h$	0.404656	1.65769
$n_i$	0.365015	1.67454
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.012693
$n_C - n_{A'}$	0.005628
$n_d - n_C$	0.005139
$n_e - n_C$	0.009288
$n_g - n_d$	0.022725
$n_g - n_F$	0.010332
$n_h - n_g$	0.009086
$n_i - n_g$	0.025932
$n_{C'} - n_t$	0.013499
$n_e - n_{C'}$	0.008482
$n_{F'} - n_e$	0.009298
$n_i - n_{F'}$	0.035210

Relative Partial Dispersions	
$\theta_{C,t}$	0.7240
$\theta_{C,A'}$	0.3210
$\theta_{d,C}$	0.2931
$\theta_{e,C}$	0.5298
$\theta_{g,d}$	1.2962
$\theta_{g,F}$	0.5893
$\theta_{h,g}$	0.5183
$\theta_{i,g}$	1.4791
$\theta'_{C,t}$	0.7592
$\theta'_{e,C'}$	0.4771
$\theta'_{F',e}$	0.5229
$\theta'_{i,F'}$	1.9803

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0098
$\Delta\theta_{C,A'}$	0.0019
$\Delta\theta_{g,d}$	0.0056
$\Delta\theta_{g,F}$	0.0056
$\Delta\theta_{i,g}$	0.0530

Internal Transmittance			
$\lambda_{80}$	383	$\lambda_5$	359

CCI		
B	G	R
0.00	1.20	1.21

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.44963830	
A 2	1.22986408	E-1
A 3	1.38066723	
B 1	1.12094282	E-2
B 2	5.96265770	E-2
B 3	1.38178326	E2
1129 ~ 2325 nm		
A 1	1.44963830	
A 2	1.22986408	E-1
A 3	1.38066723	
B 1	1.12094282	E-2
B 2	5.96265770	E-2
B 3	1.38178326	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.090	
365		
370	0.470	
380	0.760	
390	0.890	
400	0.945	
420	0.977	
440	0.984	
460	0.987	
480	0.990	
500	0.992	
550	0.997	
600	0.997	
650	0.996	
700	0.997	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.993	
1600	0.993	
1800	0.980	
2000	0.965	
2200	0.917	
2400	0.890	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	544
Annealing Point (°C)	<b>AP</b>	571
Transformation Temperature (°C)	<b>Tg</b>	602
Yield Point (°C)	<b>At</b>	630
Softening Point (°C)	<b>SP</b>	699
Expansion Coefficient $\alpha$ (-30~+70°C)		81
(10-7 / °C) (+100~+300°C)		96
Thermal Conductivity (W/m·K)	<b>k</b>	1.043

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	786
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	319
Poisson's Ratio	$\sigma$	0.234
Knoop Hardness	<b>Hk</b>	530 [5]
Abrasion	<b>Aa</b>	136
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.82

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	<b>d</b>	2.71		$\lambda_5$	355				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.4	2.1	2.1	2.3	2.6	3.3	4.1		
-20 ~ 0	1.5	2.2	2.2	2.4	2.7	3.5	4.3		
0 ~ 20	1.6	2.3	2.3	2.6	2.9	3.6	4.5		
20 ~ 40	1.7	2.4	2.4	2.7	3.0	3.8	4.7		
40 ~ 60	1.8	2.5	2.5	2.8	3.1	3.9	4.9		
60 ~ 80	1.9	2.6	2.6	2.9	3.2	4.1	5.1		

Refractive Index	$n_d$	<b>1.62004</b> 1.620041	Abbe Number	$V_d$	<b>36.26</b> 35.99	Dispersion	$n_F - n_C$	<b>0.01710</b> 0.017099
		$n_e$		1.624088			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.58240
$n_{1970}$	1.97009	1.58806
$n_{1530}$	1.52958	1.59435
$n_{1129}$	1.12864	1.60041
$n_t$	1.01398	1.60260
$n_s$	0.85211	1.60663
$n_{A'}$	0.76819	1.60952
$n_r$	0.70652	1.61225
$n_c$	0.65627	<b>1.61502</b>
$n_{c'}$	0.64385	1.61581
$n_{\text{He-Ne}}$	0.6328	1.61655
$n_D$	0.58929	1.61989
$n_d$	0.58756	<b>1.62004</b>
$n_e$	0.54607	1.62409
$n_F$	0.48613	<b>1.63212</b>
$n_{F'}$	0.47999	1.63315
$n_{\text{He-Cd}}$	0.44157	1.64081
$n_g$	0.435835	<b>1.64218</b>
$n_h$	0.404656	1.65100
$n_i$	0.365015	1.66728
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.012426
$n_c - n_{A'}$	0.005500
$n_d - n_c$	0.005017
$n_e - n_c$	0.009064
$n_g - n_d$	0.022135
$n_g - n_F$	0.010053
$n_h - n_g$	0.008822
$n_i - n_g$	0.025105
$n_{c'} - n_t$	0.013213
$n_e - n_{c'}$	0.008277
$n_{F'} - n_e$	0.009062
$n_i - n_{F'}$	0.034131

Relative Partial Dispersions	
$\theta_{c,t}$	0.7267
$\theta_{c,A'}$	0.3217
$\theta_{d,c}$	0.2934
$\theta_{e,c}$	0.5301
$\theta_{g,d}$	1.2945
$\theta_{g,F}$	0.5879
$\theta_{h,g}$	0.5159
$\theta_{i,g}$	1.4682
$\theta'_{c,t}$	0.7620
$\theta'_{e,c'}$	0.4774
$\theta'_{F',e}$	0.5226
$\theta'_{i,F'}$	1.9685

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0099
$\Delta\theta_{c,A'}$	0.0019
$\Delta\theta_{g,d}$	0.0051
$\Delta\theta_{g,F}$	0.0051
$\Delta\theta_{i,g}$	0.0468

Internal Transmittance			
$\lambda_{80}$	385	$\lambda_5$	359

CCI		
B	G	R
0.00	1.20	1.19

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.42193846	
A 2	1.33827968	E-1
A 3	1.45060574	
B 1	1.07291511	E-2
B 2	5.72587546	E-2
B 3	1.45381805	E2
1129 ~ 2325 nm		
A 1	1.42193846	
A 2	1.33827968	E-1
A 3	1.45060574	
B 1	1.07291511	E-2
B 2	5.72587546	E-2
B 3	1.45381805	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.080	
365		
370	0.440	
380	0.730	
390	0.870	
400	0.942	
420	0.978	
440	0.987	
460	0.990	
480	0.992	
500	0.994	
550	0.997	
600	0.997	
650	0.996	
700	0.997	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.995	
1600	0.995	
1800	0.984	
2000	0.971	
2200	0.930	
2400	0.914	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	551
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	576
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	598
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	634
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	703
Expansion Coefficient ( $-30\sim+70^{\circ}\text{C}$ )	$\alpha$	81
Expansion Coefficient ( $+10\sim+300^{\circ}\text{C}$ )	$\alpha$	95
Thermal Conductivity (W/m·K)	<b>k</b>	1.394

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	776
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	315
Poisson's Ratio	$\sigma$	0.230
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	150
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.86

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	<b>d</b>	2.69		$\lambda_5$	355				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.7	2.3	2.3	2.5	2.8	3.4	4.2		
-20 ~ 0	1.8	2.3	2.4	2.6	2.9	3.6	4.4		
0 ~ 20	1.8	2.4	2.5	2.7	3.0	3.7	4.6		
20 ~ 40	1.9	2.5	2.6	2.8	3.1	3.9	4.8		
40 ~ 60	1.9	2.6	2.6	2.9	3.2	4.1	5.0		
60 ~ 80	2.0	2.7	2.7	3.0	3.4	4.2	5.2		

Refractive Index	$n_d$	<b>1.61293</b> 1.612929	Abbe Number	$V_d$	<b>37.00</b> 36.73	Dispersion	$n_F - n_C$	<b>0.01657</b> 0.016564
		$n_e$		1.616851			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.57589
$n_{1970}$	1.97009	1.58154
$n_{1530}$	1.52958	1.58781
$n_{1129}$	1.12864	1.59381
$n_t$	1.01398	1.59595
$n_s$	0.85211	1.59990
$n_{A'}$	0.76819	1.60272
$n_r$	0.70652	1.60537
$n_c$	0.65627	<b>1.60806</b>
$n_{c'}$	0.64385	1.60883
$n_{\text{He-Ne}}$	0.6328	1.60954
$n_D$	0.58929	1.61278
$n_d$	0.58756	<b>1.61293</b>
$n_e$	0.54607	1.61685
$n_F$	0.48613	<b>1.62463</b>
$n_{F'}$	0.47999	1.62562
$n_{\text{He-Cd}}$	0.44157	1.63302
$n_g$	0.435835	<b>1.63434</b>
$n_h$	0.404656	1.64284
$n_i$	0.365015	1.65850
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point. ( $^{\circ}\text{C}$ )	<b>StP</b>	548
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	577
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	597
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	633
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	708
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	77
	(+10~+300 $^{\circ}\text{C}$ )	91
Thermal Conductivity (W/m·K)	<b>k</b>	1.044

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	779
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	317
Poisson's Ratio	$\sigma$	0.229
Knoop Hardness	<b>Hk</b>	510 [5]
Abrasion	<b>Aa</b>	129
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.91

Partial Dispersions	
$n_c - n_t$	0.012109
$n_c - n_{A'}$	0.005347
$n_d - n_c$	0.004867
$n_e - n_c$	0.008789
$n_g - n_d$	0.021407
$n_g - n_F$	0.009710
$n_h - n_g$	0.008506
$n_i - n_g$	0.024167
$n_{c'} - n_t$	0.012873
$n_e - n_{c'}$	0.008025
$n_{F'} - n_e$	0.008767
$n_i - n_{F'}$	0.032885

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0107
$\Delta\theta_{c,A'}$	0.0021
$\Delta\theta_{g,d}$	0.0045
$\Delta\theta_{g,F}$	0.0046
$\Delta\theta_{i,g}$	0.0438

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.40691144	
A 2	1.28369745	E-1
A 3	1.51826191	
B 1	1.05633641	E-2
B 2	5.68483105	E-2
B 3	1.52107924	E2
1129 ~ 2325 nm		
A 1	1.40691144	
A 2	1.28369745	E-1
A 3	1.51826191	
B 1	1.05633641	E-2
B 2	5.68483105	E-2
B 3	1.52107924	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7310
$\theta_{c,A'}$	0.3228
$\theta_{d,c}$	0.2938
$\theta_{e,c}$	0.5306
$\theta_{g,d}$	1.2924
$\theta_{g,F}$	0.5862
$\theta_{h,g}$	0.5135
$\theta_{i,g}$	1.4590
$\theta'_{c,t}$	0.7666
$\theta'_{e,c'}$	0.4779
$\theta'_{F',e}$	0.5221
$\theta'_{i,F'}$	1.9584

Internal Transmittance			
$\lambda_{80}$	381	$\lambda_5$	358

CCI		
B	G	R
0.00	1.09	1.10

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.130	
365		
370	0.530	
380	0.790	
390	0.907	
400	0.950	
420	0.976	
440	0.984	
460	0.986	
480	0.989	
500	0.992	
550	0.996	
600	0.996	
650	0.995	
700	0.997	
800	0.999	
900	0.998	
1000	0.996	
1200	0.996	
1400	0.994	
1600	0.994	
1800	0.983	
2000	0.971	
2200	0.929	
2400	0.913	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	39				
Specific Gravity	<b>d</b>	2.67		$\lambda_5$		36			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.8	2.4	2.5	2.7	3.0	3.6	4.3		
-20 ~ 0	1.8	2.5	2.6	2.8	3.1	3.8	4.5		
0 ~ 20	2.0	2.6	2.7	3.0	3.2	3.9	4.7		
20 ~ 40	2.1	2.8	2.8	3.1	3.4	4.1	5.0		
40 ~ 60	2.2	2.9	2.9	3.2	3.5	4.3	5.2		
60 ~ 80	2.3	3.0	3.0	3.3	3.6	4.4	5.4		

Refractive Index	$n_d$	<b>1.60342</b> 1.603420	Abbe Number	$V_d$	<b>38.03</b> 37.76	Dispersion	$n_F - n_C$	<b>0.01587</b> 0.015868
		$n_e$		1.607179			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.56753
$n_{1970}$	1.97009	1.57306
$n_{1530}$	1.52958	1.57918
$n_{1129}$	1.12864	1.58500
$n_t$	1.01398	1.58708
$n_s$	0.85211	1.59089
$n_{A'}$	0.76819	1.59360
$n_r$	0.70652	1.59615
$n_c$	0.65627	<b>1.59875</b>
$n_{c'}$	0.64385	1.59948
$n_{\text{He-Ne}}$	0.6328	1.60017
$n_D$	0.58929	1.60328
$n_d$	0.58756	<b>1.60342</b>
$n_e$	0.54607	1.60718
$n_F$	0.48613	<b>1.61462</b>
$n_{F'}$	0.47999	1.61556
$n_{\text{He-Cd}}$	0.44157	1.62262
$n_g$	0.435835	<b>1.62388</b>
$n_h$	0.404656	1.63196
$n_i$	0.365015	1.64676
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.011667
$n_c - n_{A'}$	0.005143
$n_d - n_c$	0.004672
$n_e - n_c$	0.008431
$n_g - n_d$	0.020455
$n_g - n_F$	0.009259
$n_h - n_g$	0.008081
$n_i - n_g$	0.022880
$n_{c'} - n_t$	0.012401
$n_e - n_{c'}$	0.007697
$n_{F'} - n_e$	0.008385
$n_i - n_{F'}$	0.031191

Relative Partial Dispersions	
$\theta_{c,t}$	0.7353
$\theta_{c,A'}$	0.3241
$\theta_{d,c}$	0.2944
$\theta_{e,c}$	0.5313
$\theta_{g,d}$	1.2891
$\theta_{g,F}$	0.5835
$\theta_{h,g}$	0.5093
$\theta_{i,g}$	1.4419
$\theta'_{c,t}$	0.7711
$\theta'_{e,c'}$	0.4786
$\theta'_{F',e}$	0.5214
$\theta'_{i,F'}$	1.9395

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0102
$\Delta\theta_{c,A'}$	0.0022
$\Delta\theta_{g,d}$	0.0034
$\Delta\theta_{g,F}$	0.0036
$\Delta\theta_{i,g}$	0.0353

Internal Transmittance			
$\lambda_{80}$	378	$\lambda_5$	357

CCI		
B	G	R
0.00	0.79	0.81

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.38531342	
A 2	1.22372945	E-1
A 3	1.40508326	
B 1	1.04074567	E-2
B 2	5.57440088	E-2
B 3	1.44878733	E2
1129 ~ 2325 nm		
A 1	1.38531342	
A 2	1.22372945	E-1
A 3	1.40508326	
B 1	1.04074567	E-2
B 2	5.57440088	E-2
B 3	1.44878733	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.190	
365		
370	0.600	
380	0.840	
390	0.931	
400	0.963	
420	0.984	
440	0.989	
460	0.991	
480	0.993	
500	0.995	
550	0.997	
600	0.997	
650	0.997	
700	0.997	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.994	
1600	0.994	
1800	0.982	
2000	0.966	
2200	0.923	
2400	0.902	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	535
Annealing Point (°C)	<b>AP</b>	565
Transformation Temperature (°C)	<b>Tg</b>	588
Yield Point (°C)	<b>At</b>	624
Softening Point (°C)	<b>SP</b>	700
Expansion Coefficient $\alpha$ (-30~+70°C)		83
(10-7 / °C)	(+100~+300°C)	96
Thermal Conductivity (W/m·K)	<b>k</b>	1.040

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	763
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	309
Poisson's Ratio	$\sigma$	0.233
Knoop Hardness	<b>Hk</b>	540 [5]
Abrasion	<b>Aa</b>	128
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.84

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	385				
Specific Gravity	<b>d</b>	2.63		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> / °C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.4	1.9	1.9	2.1	2.4	3.0	3.7		
-20 ~ 0	1.4	2.0	2.1	2.3	2.5	3.2	3.9		
0 ~ 20	1.4	2.1	2.2	2.4	2.7	3.4	4.1		
20 ~ 40	1.6	2.3	2.3	2.5	2.8	3.6	4.4		
40 ~ 60	1.7	2.4	2.4	2.7	3.0	3.7	4.6		
60 ~ 80	1.7	2.5	2.6	2.8	3.1	3.9	4.8		

Refractive Index	$n_d$	<b>1.59551</b> 1.595509	Abbe Number	$V_d$	<b>39.24</b> 38.97	Dispersion	$n_F - n_C$	<b>0.01518</b> 0.015176
		$n_e$		1.599106			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.56075
$n_{1970}$	1.97009	1.56615
$n_{1530}$	1.52958	1.57212
$n_{1129}$	1.12864	1.57778
$n_t$	1.01398	1.57980
$n_s$	0.85211	1.58347
$n_{A'}$	0.76819	1.58609
$n_r$	0.70652	1.58854
$n_c$	0.65627	<b>1.59103</b>
$n_{c'}$	0.64385	1.59173
$n_{\text{He-Ne}}$	0.6328	1.59240
$n_D$	0.58929	1.59538
$n_d$	0.58756	<b>1.59551</b>
$n_e$	0.54607	1.59911
$n_F$	0.48613	<b>1.60621</b>
$n_{F'}$	0.47999	1.60711
$n_{\text{He-Cd}}$	0.44157	1.61382
$n_g$	0.435835	<b>1.61501</b>
$n_h$	0.404656	1.62267
$n_i$	0.365015	1.63661
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.011234
$n_c - n_{A'}$	0.004942
$n_d - n_c$	0.004479
$n_e - n_c$	0.008076
$n_g - n_d$	0.019504
$n_g - n_F$	0.008807
$n_h - n_g$	0.007657
$n_i - n_g$	0.021600
$n_{c'} - n_t$	0.011938
$n_e - n_{c'}$	0.007372
$n_{F'} - n_e$	0.008003
$n_i - n_{F'}$	0.029504

Relative Partial Dispersions	
$\theta_{c,t}$	0.7402
$\theta_{c,A'}$	0.3256
$\theta_{d,c}$	0.2951
$\theta_{e,c}$	0.5322
$\theta_{g,d}$	1.2852
$\theta_{g,F}$	0.5803
$\theta_{h,g}$	0.5045
$\theta_{i,g}$	1.4233
$\theta'_{c,t}$	0.7765
$\theta'_{e,c'}$	0.4795
$\theta'_{F',e}$	0.5205
$\theta'_{i,F'}$	1.9190

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0094
$\Delta\theta_{c,A'}$	0.0022
$\Delta\theta_{g,d}$	0.0020
$\Delta\theta_{g,F}$	0.0023
$\Delta\theta_{i,g}$	0.0269

Internal Transmittance			
$\lambda_{80}$	378	$\lambda_5$	351

CCI		
B	G	R
0.00	0.82	0.82

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.37262713	
A 2	1.12636276	E-1
A 3	1.39786421	
B 1	1.03220068	E-2
B 2	5.50195044	E-2
B 3	1.47735609	E2
1129 ~ 2325 nm		
A 1	1.37262713	
A 2	1.12636276	E-1
A 3	1.39786421	
B 1	1.03220068	E-2
B 2	5.50195044	E-2
B 3	1.47735609	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.020	
360	0.270	
365		
370	0.640	
380	0.840	
390	0.928	
400	0.962	
420	0.982	
440	0.988	
460	0.990	
480	0.992	
500	0.994	
550	0.997	
600	0.997	
650	0.996	
700	0.997	
800	0.998	
900	0.997	
1000	0.996	
1200	0.996	
1400	0.994	
1600	0.993	
1800	0.983	
2000	0.968	
2200	0.935	
2400	0.915	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	529
Annealing Point (°C)	<b>AP</b>	560
Transformation Temperature (°C)	<b>Tg</b>	585
Yield Point (°C)	<b>At</b>	610
Softening Point (°C)	<b>SP</b>	695
Expansion Coefficient $\alpha$ (-30~+70°C)		84
(10-7 /°C) (+100~+300°C)		104
Thermal Conductivity (W/m·K)	<b>k</b>	1.034

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	750
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	305
Poisson's Ratio	$\sigma$	0.231
Knoop Hardness	<b>Hk</b>	530 [5]
Abrasion	<b>Aa</b>	133
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.79

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	380				
Specific Gravity	<b>d</b>	2.63		$\lambda_5$	350				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.3	1.7	1.7	1.9	2.2	2.8	3.4		
-20 ~ 0	1.3	1.8	1.8	2.0	2.3	2.9	3.5		
0 ~ 20	1.3	1.8	1.9	2.1	2.3	3.0	3.7		
20 ~ 40	1.4	1.9	1.9	2.1	2.4	3.1	3.8		
40 ~ 60	1.4	1.9	2.0	2.2	2.5	3.2	4.0		
60 ~ 80	1.5	2.0	2.0	2.3	2.6	3.3	4.1		



Refractive Index	$n_d$	<b>1.64769</b>	Abbe Number	$V_d$	<b>33.79</b>	Dispersion	$n_F - n_C$	<b>0.01916</b>
	$n_e$	1.647689		$V_e$	33.53		$n_{F'} - n_{C'}$	0.019167
		1.652221						0.019451

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.60753
$n_{1970}$	1.97009	1.61325
$n_{1530}$	1.52958	1.61971
$n_{1129}$	1.12864	1.62609
$n_t$	1.01398	1.62844
$n_s$	0.85211	1.63283
$n_{A'}$	0.76819	1.63600
$n_r$	0.70652	1.63901
$n_c$	0.65627	<b>1.64210</b>
$n_{c'}$	0.64385	1.64297
$n_{\text{He-Ne}}$	0.6328	1.64379
$n_D$	0.58929	1.64752
$n_d$	0.58756	<b>1.64769</b>
$n_e$	0.54607	1.65222
$n_F$	0.48613	<b>1.66126</b>
$n_{F'}$	0.47999	1.66242
$n_{\text{He-Cd}}$	0.44157	1.67109
$n_g$	0.435835	<b>1.67265</b>
$n_h$	0.404656	1.68269
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.013658
$n_c - n_{A'}$	0.006092
$n_d - n_c$	0.005593
$n_e - n_c$	0.010125
$n_g - n_d$	0.024956
$n_g - n_F$	0.011382
$n_h - n_g$	0.010042
$n_i - n_g$	
$n_{c'} - n_t$	0.014533
$n_e - n_{c'}$	0.009250
$n_{F'} - n_e$	0.010201
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.7126
$\theta_{c,A'}$	0.3178
$\theta_{d,c}$	0.2918
$\theta_{e,c}$	0.5283
$\theta_{g,d}$	1.3020
$\theta_{g,F}$	0.5938
$\theta_{h,g}$	0.5239
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7472
$\theta'_{e,c'}$	0.4756
$\theta'_{F',e}$	0.5244
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0074
$\Delta\theta_{c,A'}$	0.0010
$\Delta\theta_{g,d}$	0.0075
$\Delta\theta_{g,F}$	0.0070
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	386	$\lambda_5$	360

CCI		
B	G	R
0.00	1.48	1.49

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.44222294	
A 2	1.94432265	E-1
A 3	1.74092482	
B 1	1.04249404	E-2
B 2	5.50235257	E-2
B 3	1.69710769	E2
1129 ~ 2325 nm		
A 1	1.44222294	
A 2	1.94432265	E-1
A 3	1.74092482	
B 1	1.04249404	E-2
B 2	5.50235257	E-2
B 3	1.69710769	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.040	
365		
370	0.370	
380	0.700	
390	0.860	
400	0.928	
420	0.970	
440	0.981	
460	0.986	
480	0.989	
500	0.991	
550	0.996	
600	0.996	
650	0.995	
700	0.996	
800	0.998	
900	0.997	
1000	0.997	
1200	0.996	
1400	0.993	
1600	0.991	
1800	0.981	
2000	0.970	
2200	0.934	
2400	0.916	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	545
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	572
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	593
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	624
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	692
Expansion Coefficient ( $-30\sim+70^{\circ}\text{C}$ )	$\alpha$	83
Expansion Coefficient ( $+10\sim+300^{\circ}\text{C}$ )	$\alpha$	98
Thermal Conductivity (W/m·K)	<b>k</b>	1.024

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	798
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	322
Poisson's Ratio	$\sigma$	0.238
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	149
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.82

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	395				
Specific Gravity	<b>d</b>	2.79		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.8	1.5	1.6	1.8	2.1	2.9	3.7		
-20 ~ 0	1.0	1.7	1.7	1.9	2.3	3.1	4.0		
0 ~ 20	1.1	1.8	1.8	2.1	2.4	3.3	4.3		
20 ~ 40	1.1	1.9	2.0	2.3	2.6	3.5	4.5		
40 ~ 60	1.3	2.1	2.1	2.4	2.8	3.7	4.8		
60 ~ 80	1.4	2.2	2.3	2.6	2.9	3.9	5.0		

Refractive Index	$n_d$	<b>1.67270</b>	Abbe Number	$V_d$	<b>32.10</b>	Dispersion	$n_F - n_C$	<b>0.02095</b>
		1.672700			$V_e$		31.84	
	$n_e$	1.677651					$n_{F'} - n_{C'}$	0.021280

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.62988
$n_{1970}$	1.97009	1.63583
$n_{1530}$	1.52958	1.64258
$n_{1129}$	1.12864	1.64933
$n_t$	1.01398	1.65184
$n_s$	0.85211	1.65656
$n_{A'}$	0.76819	1.66000
$n_r$	0.70652	1.66326
$n_c$	0.65627	<b>1.66661</b>
$n_{c'}$	0.64385	1.66756
$n_{\text{He-Ne}}$	0.6328	1.66846
$n_D$	0.58929	1.67252
$n_d$	0.58756	<b>1.67270</b>
$n_e$	0.54607	1.67765
$n_F$	0.48613	<b>1.68756</b>
$n_{F'}$	0.47999	1.68884
$n_{\text{He-Cd}}$	0.44157	1.69840
$n_g$	0.435835	<b>1.70011</b>
$n_h$	0.404656	1.71126
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	556
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	585
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	608
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	640
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	700
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	79
	(+10~+300 $^{\circ}\text{C}$ )	95
Thermal Conductivity (W/m·K)	<b>k</b>	1.046

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	841
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	340
Poisson's Ratio	$\sigma$	0.236
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	140
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.81

Partial Dispersions	
$n_c - n_t$	0.014766
$n_c - n_{A'}$	0.006611
$n_d - n_c$	0.006093
$n_e - n_c$	0.011044
$n_g - n_d$	0.027414
$n_g - n_F$	0.012550
$n_h - n_g$	0.011144
$n_i - n_g$	
$n_{c'} - n_t$	0.015718
$n_e - n_{c'}$	0.010092
$n_{F'} - n_e$	0.011188
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0073
$\Delta\theta_{c,A'}$	0.0007
$\Delta\theta_{g,d}$	0.0101
$\Delta\theta_{g,F}$	0.0093
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.50659233	
A 2	2.04786135	E-1
A 3	1.92036668	
B 1	1.09501562	E-2
B 2	5.74980285	E-2
B 3	1.78128535	E2
1129 ~ 2325 nm		
A 1	1.50659233	
A 2	2.04786135	E-1
A 3	1.92036668	
B 1	1.09501562	E-2
B 2	5.74980285	E-2
B 3	1.78128535	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.2

Relative Partial Dispersions	
$\theta_{c,t}$	0.7046
$\theta_{c,A'}$	0.3155
$\theta_{d,c}$	0.2907
$\theta_{e,c}$	0.5270
$\theta_{g,d}$	1.3081
$\theta_{g,F}$	0.5988
$\theta_{h,g}$	0.5318
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7386
$\theta'_{e,c'}$	0.4742
$\theta'_{F',e}$	0.5258
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	390	$\lambda_5$	362

CCI		
B	G	R
0.00	2.11	2.17

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.010	
365		
370	0.240	
380	0.600	
390	0.800	
400	0.890	
420	0.957	
440	0.974	
460	0.981	
480	0.986	
500	0.989	
550	0.995	
600	0.996	
650	0.995	
700	0.996	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.995	
1600	0.995	
1800	0.987	
2000	0.977	
2200	0.944	
2400	0.930	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	2.91		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.5	2.2	2.3	2.6	2.9	3.7	4.7		
-20 ~ 0	1.7	2.4	2.4	2.7	3.0	3.9	5.0		
0 ~ 20	1.7	2.5	2.5	2.8	3.2	4.1	5.2		
20 ~ 40	1.7	2.6	2.7	2.9	3.4	4.4	5.5		
40 ~ 60	1.8	2.7	2.8	3.1	3.6	4.6	5.8		
60 ~ 80	1.9	2.8	2.9	3.3	3.7	4.8	6.1		

Refractive Index	$n_d$	<b>1.63980</b> 1.639799	Abbe Number	$V_d$	<b>34.46</b> 34.20	Dispersion	$n_F - n_C$	<b>0.01856</b> 0.018564
		$n_e$		1.644189			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.60036
$n_{1970}$	1.97009	1.60608
$n_{1530}$	1.52958	1.61249
$n_{1129}$	1.12864	1.61878
$n_t$	1.01398	1.62108
$n_s$	0.85211	1.62537
$n_{A'}$	0.76819	1.62846
$n_r$	0.70652	1.63138
$n_c$	0.65627	<b>1.63438</b>
$n_{c'}$	0.64385	1.63522
$n_{\text{He-Ne}}$	0.6328	1.63602
$n_D$	0.58929	1.63964
$n_d$	0.58756	<b>1.63980</b>
$n_e$	0.54607	1.64419
$n_F$	0.48613	<b>1.65294</b>
$n_{F'}$	0.47999	1.65406
$n_{\text{He-Cd}}$	0.44157	1.66244
$n_g$	0.435835	<b>1.66393</b>
$n_h$	0.404656	1.67361
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	543
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	572
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	594
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	629
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	696
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	80
	(+100~+300 $^{\circ}\text{C}$ )	99
Thermal Conductivity (W/m·K)	<b>k</b>	1.035

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	793
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	321
Poisson's Ratio	$\sigma$	0.236
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	141
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.83

Partial Dispersions	
$n_c - n_t$	0.013292
$n_c - n_{A'}$	0.005916
$n_d - n_c$	0.005424
$n_e - n_c$	0.009814
$n_g - n_d$	0.024134
$n_g - n_F$	0.010994
$n_h - n_g$	0.009680
$n_i - n_g$	
$n_{c'} - n_t$	0.014141
$n_e - n_{c'}$	0.008965
$n_{F'} - n_e$	0.009870
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0076
$\Delta\theta_{c,A'}$	0.0011
$\Delta\theta_{g,d}$	0.0069
$\Delta\theta_{g,F}$	0.0065
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.41680470	
A 2	1.96785057	E-1
A 3	1.68001322	
B 1	1.00732158	E-2
B 2	5.37616908	E-2
B 3	1.64672436	E2
1129 ~ 2325 nm		
A 1	1.41680470	
A 2	1.96785057	E-1
A 3	1.68001322	
B 1	1.00732158	E-2
B 2	5.37616908	E-2
B 3	1.64672436	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7160
$\theta_{c,A'}$	0.3187
$\theta_{d,c}$	0.2922
$\theta_{e,c}$	0.5287
$\theta_{g,d}$	1.3000
$\theta_{g,F}$	0.5922
$\theta_{h,g}$	0.5214
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7508
$\theta'_{e,c'}$	0.4760
$\theta'_{F',e}$	0.5240
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	385	$\lambda_5$	360

CCI		
B	G	R
0.00	1.37	1.38

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.050	
365		
370	0.410	
380	0.730	
390	0.870	
400	0.935	
420	0.973	
440	0.983	
460	0.987	
480	0.990	
500	0.992	
550	0.997	
600	0.997	
650	0.996	
700	0.997	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.995	
1600	0.994	
1800	0.984	
2000	0.973	
2200	0.936	
2400	0.919	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	390				
Specific Gravity	<b>d</b>	2.76		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.2	1.9	1.9	2.2	2.5	3.2	4.0		
-20 ~ 0	1.3	2.0	2.0	2.3	2.6	3.3	4.2		
0 ~ 20	1.3	2.1	2.1	2.4	2.7	3.5	4.4		
20 ~ 40	1.4	2.1	2.2	2.5	2.8	3.7	4.6		
40 ~ 60	1.4	2.2	2.3	2.6	2.9	3.8	4.8		
60 ~ 80	1.5	2.3	2.4	2.7	3.0	4.0	5.1		

Refractive Index	$n_d$	<b>1.68893</b>	Abbe Number	$V_d$	<b>31.07</b>	Dispersion	$n_F - n_C$	<b>0.02217</b>
	$n_e$	1.688931		$V_e$	30.83		$n_{F'} - n_{C'}$	0.022170
		1.694167						0.022516

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.64463
$n_{1970}$	1.97009	1.65062
$n_{1530}$	1.52958	1.65745
$n_{1129}$	1.12864	1.66438
$n_t$	1.01398	1.66699
$n_s$	0.85211	1.67192
$n_{A'}$	0.76819	1.67553
$n_r$	0.70652	1.67896
$n_c$	0.65627	<b>1.68250</b>
$n_{c'}$	0.64385	1.68350
$n_{\text{He-Ne}}$	0.6328	1.68445
$n_D$	0.58929	1.68874
$n_d$	0.58756	<b>1.68893</b>
$n_e$	0.54607	1.69417
$n_F$	0.48613	<b>1.70467</b>
$n_{F'}$	0.47999	1.70602
$n_{\text{He-Cd}}$	0.44157	1.71615
$n_g$	0.435835	<b>1.71797</b>
$n_h$	0.404656	1.72981
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	560
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	588
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	611
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	637
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	701
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		82
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	98
Thermal Conductivity (W/m·K)	<b>k</b>	1.006

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	855
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	344
Poisson's Ratio	$\sigma$	0.242
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	155
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.77

Partial Dispersions	
$n_c - n_t$	0.015507
$n_c - n_{A'}$	0.006966
$n_d - n_c$	0.006436
$n_e - n_c$	0.011672
$n_g - n_d$	0.029044
$n_g - n_F$	0.013310
$n_h - n_g$	0.011834
$n_i - n_g$	
$n_{c'} - n_t$	0.016512
$n_e - n_{c'}$	0.010667
$n_{F'} - n_e$	0.011849
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0071
$\Delta\theta_{c,A'}$	0.0007
$\Delta\theta_{g,d}$	0.0099
$\Delta\theta_{g,F}$	0.0092
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.54270810	
A 2	2.17113891	E-1
A 3	1.81904459	
B 1	1.13925005	E-2
B 2	5.79224572	E-2
B 3	1.67697189	E2
1129 ~ 2325 nm		
A 1	1.54270810	
A 2	2.17113891	E-1
A 3	1.81904459	
B 1	1.13925005	E-2
B 2	5.79224572	E-2
B 3	1.67697189	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.6995
$\theta_{c,A'}$	0.3142
$\theta_{d,c}$	0.2903
$\theta_{e,c}$	0.5265
$\theta_{g,d}$	1.3101
$\theta_{g,F}$	0.6004
$\theta_{h,g}$	0.5338
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7333
$\theta'_{e,c'}$	0.4738
$\theta'_{F',e}$	0.5262
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	391	$\lambda_5$	362

CCI		
B	G	R
0.00	2.30	2.36

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.010	
365		
370	0.230	
380	0.580	
390	0.790	
400	0.880	
420	0.951	
440	0.970	
460	0.978	
480	0.983	
500	0.987	
550	0.994	
600	0.995	
650	0.994	
700	0.995	
800	0.998	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.996	
1600	0.996	
1800	0.989	
2000	0.983	
2200	0.961	
2400	0.948	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	405				
Specific Gravity	<b>d</b>	2.98		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.3	1.9	2.0	2.2	2.6	3.4	4.5		
-20 ~ 0	1.3	2.0	2.1	2.3	2.7	3.6	4.7		
0 ~ 20	1.3	2.1	2.2	2.5	2.9	3.8	5.0		
20 ~ 40	1.4	2.2	2.3	2.6	3.0	4.0	5.2		
40 ~ 60	1.4	2.3	2.4	2.7	3.1	4.2	5.5		
60 ~ 80	1.4	2.4	2.5	2.8	3.3	4.4	5.7		

Refractive Index	$n_d$	<b>1.69895</b> 1.698947	Abbe Number	$V_d$	<b>30.13</b> 29.89	Dispersion	$n_F - n_C$	<b>0.02320</b> 0.023199
		$n_e$		1.704424			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65283
$n_{1970}$	1.97009	1.65905
$n_{1530}$	1.52958	1.66615
$n_{1129}$	1.12864	1.67335
$n_t$	1.01398	1.67606
$n_s$	0.85211	1.68120
$n_{A'}$	0.76819	1.68496
$n_r$	0.70652	1.68854
$n_c$	0.65627	<b>1.69222</b>
$n_{c'}$	0.64385	1.69327
$n_{\text{He-Ne}}$	0.6328	1.69426
$n_D$	0.58929	1.69875
$n_d$	0.58756	<b>1.69895</b>
$n_e$	0.54607	1.70442
$n_F$	0.48613	<b>1.71542</b>
$n_{F'}$	0.47999	1.71684
$n_{\text{He-Cd}}$	0.44157	1.72750
$n_g$	0.435835	<b>1.72941</b>
$n_h$	0.404656	1.74189
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	579
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	603
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	622
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	648
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	716
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	75
	(+10-7~+300 $^{\circ}\text{C}$ )	89
Thermal Conductivity (W/m·K)	<b>k</b>	1.049

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	875
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	353
Poisson's Ratio	$\sigma$	0.238
Knoop Hardness	<b>Hk</b>	500 [5]
Abrasion	<b>Aa</b>	136
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.04

Partial Dispersions	
$n_c - n_t$	0.016161
$n_c - n_{A'}$	0.007266
$n_d - n_c$	0.006722
$n_e - n_c$	0.012199
$n_g - n_d$	0.030465
$n_g - n_F$	0.013988
$n_h - n_g$	0.012478
$n_i - n_g$	
$n_{c'} - n_t$	0.017210
$n_e - n_{c'}$	0.011150
$n_{F'} - n_e$	0.012417
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0086
$\Delta\theta_{c,A'}$	0.0008
$\Delta\theta_{g,d}$	0.0111
$\Delta\theta_{g,F}$	0.0103
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.55849775	
A 2	2.30767007	E-1
A 3	1.84436099	
B 1	1.15367235	E-2
B 2	5.86095947	E-2
B 3	1.62981888	E2
1129 ~ 2325 nm		
A 1	1.55849775	
A 2	2.30767007	E-1
A 3	1.84436099	
B 1	1.15367235	E-2
B 2	5.86095947	E-2
B 3	1.62981888	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.6966
$\theta_{c,A'}$	0.3132
$\theta_{d,c}$	0.2898
$\theta_{e,c}$	0.5258
$\theta_{g,d}$	1.3132
$\theta_{g,F}$	0.6030
$\theta_{h,g}$	0.5379
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7303
$\theta'_{e,c'}$	0.4731
$\theta'_{F',e}$	0.5269
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	397	$\lambda_5$	367

CCI		
B	G	R
0.00	2.94	2.98

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360		
365		
370	0.140	
380	0.480	
390	0.720	
400	0.840	
420	0.939	
440	0.964	
460	0.974	
480	0.981	
500	0.986	
550	0.994	
600	0.994	
650	0.993	
700	0.995	
800	0.998	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.995	
1600	0.995	
1800	0.988	
2000	0.980	
2200	0.942	
2400	0.931	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	2.96		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.0	2.8	2.8	3.1	3.5	4.4	5.5		
-20 ~ 0	2.1	2.9	3.0	3.3	3.7	4.6	5.8		
0 ~ 20	2.1	3.0	3.1	3.4	3.8	4.9	6.1		
20 ~ 40	2.3	3.2	3.2	3.6	4.0	5.1	6.4		
40 ~ 60	2.4	3.3	3.4	3.7	4.2	5.3	6.7		
60 ~ 80	2.4	3.4	3.5	3.9	4.4	5.6	7.0		

Refractive Index	$n_d$	<b>1.66680</b>	Abbe Number	$V_d$	<b>33.05</b>	Dispersion	$n_F - n_C$	<b>0.02018</b>
		1.666800			$V_e$		32.80	
	$n_e$	1.671568					$n_{F'} - n_{C'}$	0.020477

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.62567
$n_{1970}$	1.97009	1.63132
$n_{1530}$	1.52958	1.63776
$n_{1129}$	1.12864	1.64425
$n_t$	1.01398	1.64667
$n_s$	0.85211	1.65123
$n_{A'}$	0.76819	1.65454
$n_r$	0.70652	1.65769
$n_c$	0.65627	<b>1.66092</b>
$n_{c'}$	0.64385	1.66184
$n_{\text{He-Ne}}$	0.6328	1.66271
$n_D$	0.58929	1.66662
$n_d$	0.58756	<b>1.66680</b>
$n_e$	0.54607	1.67157
$n_F$	0.48613	<b>1.68110</b>
$n_{F'}$	0.47999	1.68232
$n_{\text{He-Cd}}$	0.44157	1.69148
$n_g$	0.435835	<b>1.69311</b>
$n_h$	0.404656	1.70373
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.014252
$n_c - n_{A'}$	0.006381
$n_d - n_c$	0.005875
$n_e - n_c$	0.010643
$n_g - n_d$	0.026315
$n_g - n_F$	0.012017
$n_h - n_g$	0.010616
$n_i - n_g$	
$n_{c'} - n_t$	0.015170
$n_e - n_{c'}$	0.009725
$n_{F'} - n_e$	0.010752
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.7065
$\theta_{c,A'}$	0.3163
$\theta_{d,c}$	0.2912
$\theta_{e,c}$	0.5276
$\theta_{g,d}$	1.3045
$\theta_{g,F}$	0.5957
$\theta_{h,g}$	0.5262
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7408
$\theta'_{e,c'}$	0.4749
$\theta'_{F',e}$	0.5251
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0048
$\Delta\theta_{c,A'}$	0.0004
$\Delta\theta_{g,d}$	0.0084
$\Delta\theta_{g,F}$	0.0077
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$	389	$\lambda_5$	361

CCI		
B	G	R
0.00	1.86	1.92

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.47008105	
A 2	2.24752746	E-1
A 3	2.44968592	
B 1	1.02900432	E-2
B 2	5.41276904	E-2
B 3	2.37434940	E2
1129 ~ 2325 nm		
A 1	1.47008105	
A 2	2.24752746	E-1
A 3	2.44968592	
B 1	1.02900432	E-2
B 2	5.41276904	E-2
B 3	2.37434940	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.030	
365		
370	0.330	
380	0.660	
390	0.820	
400	0.906	
420	0.962	
440	0.973	
460	0.980	
480	0.985	
500	0.989	
550	0.994	
600	0.995	
650	0.994	
700	0.995	
800	0.998	
900	0.999	
1000	0.998	
1200	0.998	
1400	0.995	
1600	0.994	
1800	0.983	
2000	0.971	
2200	0.937	
2400	0.913	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	544
Annealing Point (°C)	<b>AP</b>	569
Transformation Temperature (°C)	<b>Tg</b>	591
Yield Point (°C)	<b>At</b>	621
Softening Point (°C)	<b>SP</b>	682
Expansion Coefficient $\alpha$ (-30~+70°C)		87
(10-7 /°C)	(+100~+300°C)	104
Thermal Conductivity (W/m·K)	<b>k</b>	0.988

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	817
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	328
Poisson's Ratio	$\sigma$	0.246
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	160
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.64

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	2.92		$\lambda_5$	360				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.4	1.1	1.2	1.3	1.7	2.5	3.4		
-20 ~ 0	0.5	1.3	1.3	1.4	1.8	2.7	3.6		
0 ~ 20	0.7	1.4	1.4	1.5	2.0	2.8	3.9		
20 ~ 40	0.7	1.5	1.5	1.7	2.1	3.0	4.1		
40 ~ 60	0.8	1.5	1.5	1.8	2.2	3.2	4.3		
60 ~ 80	0.8	1.6	1.6	1.9	2.3	3.3	4.5		



Refractive Index	$n_d$	<b>1.75500</b>	Abbe Number	$V_d$	<b>52.32</b>	Dispersion	$n_F - n_C$	<b>0.01443</b>
		1.754999			$V_e$		52.08	
	$n_e$	1.758437					$n_{F'} - n_{C'}$	0.014562

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.71387
$n_{1970}$	1.97009	1.72153
$n_{1530}$	1.52958	1.72961
$n_{1129}$	1.12864	1.73662
$n_t$	1.01398	1.73893
$n_s$	0.85211	1.74292
$n_{A'}$	0.76819	1.74565
$n_r$	0.70652	1.74814
$n_c$	0.65627	<b>1.75062</b>
$n_{c'}$	0.64385	1.75132
$n_{\text{He-Ne}}$	0.6328	1.75197
$n_D$	0.58929	1.75487
$n_d$	0.58756	<b>1.75500</b>
$n_e$	0.54607	1.75844
$n_F$	0.48613	<b>1.76505</b>
$n_{F'}$	0.47999	1.76588
$n_{\text{He-Cd}}$	0.44157	1.77191
$n_g$	0.435835	<b>1.77296</b>
$n_h$	0.404656	1.77954
$n_i$	0.365015	1.79083
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.011699
$n_c - n_{A'}$	0.004976
$n_d - n_c$	0.004375
$n_e - n_c$	0.007813
$n_g - n_d$	0.017957
$n_g - n_F$	0.007901
$n_h - n_g$	0.006588
$n_i - n_g$	0.017871
$n_{c'} - n_t$	0.012394
$n_e - n_{c'}$	0.007118
$n_{F'} - n_e$	0.007444
$n_i - n_{F'}$	0.024946

Relative Partial Dispersions	
$\theta_{c,t}$	0.8107
$\theta_{c,A'}$	0.3448
$\theta_{d,c}$	0.3032
$\theta_{e,c}$	0.5414
$\theta_{g,d}$	1.2443
$\theta_{g,F}$	0.5475
$\theta_{h,g}$	0.4565
$\theta_{i,g}$	1.2384
$\theta'_{c,t}$	0.8511
$\theta'_{e,c'}$	0.4888
$\theta'_{F',e}$	0.5112
$\theta'_{i,F'}$	1.7131

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0185
$\Delta\theta_{c,A'}$	0.0055
$\Delta\theta_{g,d}$	-0.0118
$\Delta\theta_{g,F}$	-0.0093
$\Delta\theta_{i,g}$	-0.0485

Internal Transmittance			
$\lambda_{80}$	347	$\lambda_5$	282

CCI		
B	G	R
0.00	0.39	0.40

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.08280170	
A 2	9.33988681	E-1
A 3	1.32367286	
B 1	1.81156360	E-2
B 2	3.04157575	E-3
B 3	9.10353195	E1
1129 ~ 2325 nm		
A 1	1.08280170	
A 2	9.33988681	E-1
A 3	1.32367286	
B 1	1.81156360	E-2
B 2	3.04157575	E-3
B 3	9.10353195	E1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280	0.030	
290	0.120	
300	0.210	
310	0.240	
320	0.470	
330	0.610	
340	0.730	
350	0.820	
360	0.880	
365		
370	0.930	
380	0.956	
390	0.972	
400	0.980	
420	0.988	
440	0.991	
460	0.994	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.993	
1600	0.993	
1800	0.984	
2000	0.958	
2200	0.880	
2400	0.620	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	651
Annealing Point (°C)	<b>AP</b>	670
Transformation Temperature (°C)	<b>Tg</b>	700
Yield Point (°C)	<b>At</b>	712
Softening Point (°C)	<b>SP</b>	738
Expansion Coefficient $\alpha$ (-30~+70°C)		58
(10-7 /°C) (+100~+300°C)		70
Thermal Conductivity (W/m·K)	<b>k</b>	0.842

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	51.0
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1222
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	473
Poisson's Ratio	$\sigma$	0.291
Knoop Hardness	<b>Hk</b>	720 [7]
Abrasion	<b>Aa</b>	61
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.48

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	4.40		$\lambda_5$	280				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20		4.5		4.6	4.8	5.3	5.6		
-20 ~ 0		4.5		4.7	4.9	5.3	5.7		
0 ~ 20		4.6		4.8	5.0	5.4	5.9		
20 ~ 40		4.7		4.9	5.1	5.6	6.1		
40 ~ 60		4.9		5.1	5.4	5.8	6.3		
60 ~ 80		5.1		5.4	5.6	6.0	6.6		

Refractive Index	$n_d$	<b>1.55671</b>	Abbe Number	$V_d$	<b>58.68</b>	Dispersion	$n_F - n_C$	<b>0.00948</b>
	$n_e$	1.556711		$V_e$	58.41		$n_{F'} - n_{C'}$	0.009488
		1.558973						0.009569

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.52907
$n_{1970}$	1.97009	1.53423
$n_{1530}$	1.52958	1.53972
$n_{1129}$	1.12864	1.54449
$n_t$	1.01398	1.54604
$n_s$	0.85211	1.54872
$n_{A'}$	0.76819	1.55053
$n_r$	0.70652	1.55218
$n_c$	0.65627	<b>1.55383</b>
$n_{c'}$	0.64385	1.55429
$n_{\text{He-Ne}}$	0.6328	1.55471
$n_D$	0.58929	1.55663
$n_d$	0.58756	<b>1.55671</b>
$n_e$	0.54607	1.55897
$n_F$	0.48613	<b>1.56331</b>
$n_{F'}$	0.47999	1.56385
$n_{\text{He-Cd}}$	0.44157	1.56779
$n_g$	0.435835	<b>1.56848</b>
$n_h$	0.404656	1.57277
$n_i$	0.365015	1.58012
$n_{334}$	0.334148	1.58807
$n_{326}$	0.326106	1.59060

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	507
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	547
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	642
Expansion Coefficient ( $\alpha$ )		76
	(-30~+70 $^{\circ}\text{C}$ )	
	(+10~+300 $^{\circ}\text{C}$ )	90
Thermal Conductivity (W/m·K)	<b>k</b>	1.000

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	783
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	317
Poisson's Ratio	$\sigma$	0.236
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	113
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Partial Dispersions	
$n_C - n_t$	0.007785
$n_C - n_{A'}$	0.003296
$n_d - n_C$	0.002885
$n_e - n_C$	0.005147
$n_g - n_d$	0.011768
$n_g - n_F$	0.005165
$n_h - n_g$	0.004295
$n_i - n_g$	0.011636
$n_{C'} - n_t$	0.008244
$n_e - n_{C'}$	0.004688
$n_{F'} - n_e$	0.004881
$n_i - n_{F'}$	0.016261

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.0015
$\Delta\theta_{C,A'}$	0.0004
$\Delta\theta_{g,d}$	-0.0026
$\Delta\theta_{g,F}$	-0.0021
$\Delta\theta_{i,g}$	-0.0073

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.28348331	
A 2	1.02800765	E-1
A 3	4.04609885	E-1
B 1	7.90900515	E-3
B 2	3.05971274	E-2
B 3	4.65268356	E1
1129 ~ 2325 nm		
A 1	1.18261390	
A 2	2.03921973	E-1
A 3	1.11763340	E-1
B 1	6.85280751	E-3
B 2	2.50893634	E-2
B 3	1.24101415	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.8205
$\theta_{C,A'}$	0.3474
$\theta_{d,C}$	0.3041
$\theta_{e,C}$	0.5425
$\theta_{g,d}$	1.2403
$\theta_{g,F}$	0.5444
$\theta_{h,g}$	0.4527
$\theta_{i,g}$	1.2264
$\theta'_{C,t}$	0.8615
$\theta'_{e,C'}$	0.4899
$\theta'_{F',e}$	0.5101
$\theta'_{i,F'}$	1.6993

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.170	0.010
310	0.590	0.270
320	0.840	0.650
330	0.937	0.850
340	0.971	0.929
350	0.985	0.963
360	0.992	0.979
365	0.994	0.984
370	0.995	0.988
380	0.996	0.990
390	0.997	0.993
400	0.998	0.994
420	0.998	0.995
440	0.998	0.995
460	0.998	0.996
480	0.998	0.996
500	0.999	0.997
550	0.999	0.997
600	0.999	0.997
650	0.998	0.996
700	0.999	0.997
800	0.999	0.997
900	0.998	0.995
1000	0.996	0.990
1200	0.995	0.988
1400	0.989	0.972
1600	0.992	0.980
1800	0.984	0.961
2000	0.972	0.932
2200	0.927	0.820
2400	0.890	0.750

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	32				
Specific Gravity	<b>d</b>	2.90		$\lambda_5$	30				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.2	2.5	2.5	2.6	2.8	3.0	3.3	4.2	
-20 ~ 0	2.2	2.5	2.6	2.7	2.8	3.1	3.5	4.3	
0 ~ 20	2.3	2.6	2.6	2.8	2.9	3.2	3.6	4.5	
20 ~ 40	2.4	2.7	2.7	2.8	3.0	3.3	3.7	4.6	
40 ~ 60	2.4	2.8	2.8	2.9	3.1	3.4	3.8	4.8	
60 ~ 80	2.4	2.8	2.9	3.0	3.1	3.5	3.9	4.9	

Refractive Index	$n_d$	<b>1.58913</b> 1.589130	Abbe Number	$V_d$	<b>61.23</b> 60.99	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	<b>0.00962</b> 0.009621 0.009697
		$n_e$		1.591426			$V_e$	60.99

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55937
$n_{1970}$	1.97009	1.56517
$n_{1530}$	1.52958	1.57128
$n_{1129}$	1.12864	1.57646
$n_t$	1.01398	1.57811
$n_s$	0.85211	1.58093
$n_{A'}$	0.76819	1.58280
$n_r$	0.70652	1.58451
$n_c$	0.65627	<b>1.58619</b>
$n_{c'}$	0.64385	1.58666
$n_{\text{He-Ne}}$	0.6328	1.58710
$n_D$	0.58929	1.58904
$n_d$	0.58756	<b>1.58913</b>
$n_e$	0.54607	1.59143
$n_F$	0.48613	<b>1.59581</b>
$n_{F'}$	0.47999	1.59636
$n_{\text{He-Cd}}$	0.44157	1.60032
$n_g$	0.435835	<b>1.60100</b>
$n_h$	0.404656	1.60530
$n_i$	0.365015	1.61261
$n_{334}$	0.334148	1.62045
$n_{326}$	0.326106	1.62293

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	590
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	628
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	697
Expansion Coefficient ( $\alpha$ )		57
	(-30~+70 $^{\circ}\text{C}$ )	
	(+100~+300 $^{\circ}\text{C}$ )	72
Thermal Conductivity (W/m·K)	<b>k</b>	0.991

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	881
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	354
Poisson's Ratio	$\sigma$	0.244
Knoop Hardness	<b>Hk</b>	550 [6]
Abrasion	<b>Aa</b>	118
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Partial Dispersions	
$n_c - n_t$	0.008076
$n_c - n_{A'}$	0.003385
$n_d - n_c$	0.002940
$n_e - n_c$	0.005236
$n_g - n_d$	0.011874
$n_g - n_F$	0.005193
$n_h - n_g$	0.004298
$n_i - n_g$	0.011602
$n_{c'} - n_t$	0.008545
$n_e - n_{c'}$	0.004767
$n_{F'} - n_e$	0.004930
$n_i - n_{F'}$	0.016250

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0054
$\Delta\theta_{c,A'}$	0.0017
$\Delta\theta_{g,d}$	-0.0034
$\Delta\theta_{g,F}$	-0.0026
$\Delta\theta_{i,g}$	-0.0064

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.26231429	
A 2	2.25154210	E-1
A 3	6.39119345	E-1
B 1	6.95586355	E-3
B 2	2.21310699	E-2
B 3	6.31662736	E1
1129 ~ 2325 nm		
A 1	1.09972335	
A 2	3.87872537	E-1
A 3	1.11247378	E-1
B 1	5.82303457	E-3
B 2	1.88745144	E-2
B 3	1.08214962	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	4.2
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8394
$\theta_{c,A'}$	0.3518
$\theta_{d,c}$	0.3056
$\theta_{e,c}$	0.5442
$\theta_{g,d}$	1.2342
$\theta_{g,F}$	0.5398
$\theta_{h,g}$	0.4467
$\theta_{i,g}$	1.2059
$\theta'_{c,t}$	0.8812
$\theta'_{e,c'}$	0.4916
$\theta'_{F',e}$	0.5084
$\theta'_{i,F'}$	1.6758

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290	0.110	
300	0.500	0.170
310	0.790	0.560
320	0.920	0.810
330	0.966	0.918
340	0.984	0.960
350	0.991	0.978
360	0.994	0.986
365	0.996	0.990
370	0.996	0.991
380	0.997	0.993
390	0.998	0.995
400	0.998	0.996
420	0.999	0.997
440	0.999	0.997
460	0.999	0.997
480	0.999	0.998
500	0.999	0.998
550	0.999	0.998
600	0.999	0.998
650	0.999	0.998
700	0.999	0.998
800	0.999	0.998
900	0.999	0.997
1000	0.997	0.993
1200	0.997	0.993
1400	0.985	0.963
1600	0.993	0.982
1800	0.986	0.966
2000	0.973	0.934
2200	0.904	0.770
2400	0.820	0.610

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	32				
Specific Gravity	<b>d</b>	3.23		$\lambda_5$	29				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.2	3.4	3.4	3.5	3.7	3.9	4.2	4.9	
-20 ~ 0	3.2	3.5	3.5	3.6	3.8	4.0	4.3	5.0	
0 ~ 20	3.3	3.6	3.6	3.7	3.9	4.2	4.4	5.2	
20 ~ 40	3.3	3.7	3.7	3.9	4.0	4.3	4.6	5.4	
40 ~ 60	3.4	3.8	3.8	4.0	4.1	4.4	4.7	5.6	
60 ~ 80	3.5	3.9	3.9	4.1	4.2	4.5	4.9	5.7	

Refractive Index	$n_d$	<b>1.51633</b>	Abbe Number	$V_d$	<b>64.24</b>	Dispersion	$n_F - n_C$	<b>0.00803</b>
		1.516330			$V_e$		64.04	
	$n_e$	1.518248					$n_{F'} - n_{C'}$	0.008092

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.48829
$n_{1970}$	1.97009	1.49417
$n_{1530}$	1.52958	1.50028
$n_{1129}$	1.12864	1.50528
$n_t$	1.01398	1.50681
$n_s$	0.85211	1.50933
$n_{A'}$	0.76819	1.51096
$n_r$	0.70652	1.51242
$n_c$	0.65627	<b>1.51386</b>
$n_{c'}$	0.64385	1.51425
$n_{\text{He-Ne}}$	0.6328	1.51462
$n_D$	0.58929	1.51626
$n_d$	0.58756	<b>1.51633</b>
$n_e$	0.54607	1.51825
$n_F$	0.48613	<b>1.52189</b>
$n_{F'}$	0.47999	1.52234
$n_{\text{He-Cd}}$	0.44157	1.52562
$n_g$	0.435835	<b>1.52619</b>
$n_h$	0.404656	1.52973
$n_i$	0.365015	1.53574
$n_{334}$	0.334148	1.54218
$n_{326}$	0.326106	1.54422

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	527
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	559
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	577
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	616
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	714
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		68
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	81
Thermal Conductivity (W/m·K)	<b>k</b>	1.182

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	811
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	336
Poisson's Ratio	$\sigma$	0.207
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	87
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Partial Dispersions	
$n_C - n_t$	0.007046
$n_C - n_{A'}$	0.002891
$n_d - n_C$	0.002475
$n_e - n_C$	0.004393
$n_g - n_d$	0.009857
$n_g - n_F$	0.004295
$n_h - n_g$	0.003543
$n_i - n_g$	0.009552
$n_{C'} - n_t$	0.007443
$n_e - n_{C'}$	0.003996
$n_{F'} - n_e$	0.004096
$n_i - n_{F'}$	0.013395

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0286
$\Delta\theta_{C,A'}$	0.0059
$\Delta\theta_{g,d}$	-0.0048
$\Delta\theta_{g,F}$	-0.0031
$\Delta\theta_{i,g}$	0.0014

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.13329383	
A 2	1.36897201	E-1
A 3	7.03456004	E-1
B 1	6.69407868	E-3
B 2	2.37391760	E-2
B 3	7.07030316	E1
1129 ~ 2325 nm		
A 1	1.01218580	
A 2	2.58122629	E-1
A 3	1.13916089	
B 1	5.66358122	E-3
B 2	1.96285352	E-2
B 3	1.12904303	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	2
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.8767
$\theta_{C,A'}$	0.3597
$\theta_{d,C}$	0.3080
$\theta_{e,C}$	0.5466
$\theta_{g,d}$	1.2265
$\theta_{g,F}$	0.5344
$\theta_{h,g}$	0.4408
$\theta_{i,g}$	1.1885
$\theta'_{C,t}$	0.9198
$\theta'_{e,C'}$	0.4938
$\theta'_{F',e}$	0.5062
$\theta'_{i,F'}$	1.6553

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290	0.060	
300	0.430	0.120
310	0.780	0.540
320	0.932	0.830
330	0.978	0.945
340	0.991	0.978
350	0.996	0.990
360	0.997	0.992
365	0.998	0.995
370	0.998	0.996
380	0.998	0.996
390	0.999	0.997
400	0.999	0.998
420	0.999	0.998
440	0.999	0.998
460	0.999	0.998
480	0.999	0.998
500	0.999	0.999
550	0.999	0.999
600	0.999	0.998
650	0.999	0.998
700	0.999	0.999
800	0.999	0.999
900	0.999	0.997
1000	0.997	0.993
1200	0.997	0.993
1400	0.969	0.924
1600	0.990	0.975
1800	0.981	0.952
2000	0.962	0.908
2200	0.860	0.680
2400	0.800	0.580

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	32				
Specific Gravity	<b>d</b>	2.50		$\lambda_5$	29				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.3	2.6	2.6	2.7	2.8	3.0	3.2	3.8	
-20 ~ 0	2.4	2.7	2.7	2.8	2.9	3.2	3.4	4.0	
0 ~ 20	2.5	2.8	2.9	3.0	3.1	3.3	3.6	4.2	
20 ~ 40	2.6	3.0	3.0	3.1	3.2	3.5	3.7	4.4	
40 ~ 60	2.8	3.1	3.1	3.2	3.3	3.6	3.9	4.6	
60 ~ 80	2.9	3.2	3.2	3.3	3.4	3.7	4.0	4.8	

Refractive Index	$n_d$	<b>1.60311</b> 1.603109	Abbe Number	$V_d$	<b>60.65</b> 60.40	Dispersion	$n_F - n_C$	<b>0.00995</b> 0.009944
		$n_e$		1.605481			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.57281
$n_{1970}$	1.97009	1.57865
$n_{1530}$	1.52958	1.58482
$n_{1129}$	1.12864	1.59008
$n_t$	1.01398	1.59177
$n_s$	0.85211	1.59465
$n_{A'}$	0.76819	1.59658
$n_r$	0.70652	1.59834
$n_c$	0.65627	<b>1.60007</b>
$n_{c'}$	0.64385	1.60056
$n_{\text{He-Ne}}$	0.6328	1.60101
$n_D$	0.58929	1.60302
$n_d$	0.58756	<b>1.60311</b>
$n_e$	0.54607	1.60548
$n_F$	0.48613	<b>1.61002</b>
$n_{F'}$	0.47999	1.61058
$n_{\text{He-Cd}}$	0.44157	1.61468
$n_g$	0.435835	<b>1.61539</b>
$n_h$	0.404656	1.61985
$n_i$	0.365015	1.62743
$n_{334}$	0.334148	1.63557
$n_{326}$	0.326106	1.63815

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	538
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	568
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	585
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	617
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	684
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	63
	(+100~+300 $^{\circ}\text{C}$ )	77
Thermal Conductivity (W/m·K)	<b>k</b>	0.961

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	901
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	359
Poisson's Ratio	$\sigma$	0.256
Knoop Hardness	<b>Hk</b>	570 [6]
Abrasion	<b>Aa</b>	117
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Partial Dispersions	
$n_c - n_t$	0.008303
$n_c - n_{A'}$	0.003489
$n_d - n_c$	0.003035
$n_e - n_c$	0.005407
$n_g - n_d$	0.012286
$n_g - n_F$	0.005377
$n_h - n_g$	0.004454
$n_i - n_g$	0.012031
$n_{c'} - n_t$	0.008787
$n_e - n_{c'}$	0.004923
$n_{F'} - n_e$	0.005101
$n_i - n_{F'}$	0.168440

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0037
$\Delta\theta_{c,A'}$	0.0015
$\Delta\theta_{g,d}$	-0.0033
$\Delta\theta_{g,F}$	-0.0026
$\Delta\theta_{i,g}$	-0.0073

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.22393171	
A 2	3.06482383	E-1
A 3	8.23950901	E-1
B 1	6.49521083	E-3
B 2	2.08194161	E-2
B 3	7.95168951	E1
1129 ~ 2325 nm		
A 1	1.12268320	
A 2	4.07804849	E-1
A 3	1.16161178	E-1
B 1	5.79521544	E-3
B 2	1.91303182	E-2
B 3	1.11113962	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.2

Relative Partial Dispersions	
$\theta_{c,t}$	0.8350
$\theta_{c,A'}$	0.3509
$\theta_{d,c}$	0.3052
$\theta_{e,c}$	0.5437
$\theta_{g,d}$	1.2355
$\theta_{g,F}$	0.5407
$\theta_{h,g}$	0.4479
$\theta_{i,g}$	1.2099
$\theta'_{c,t}$	0.8766
$\theta'_{e,c'}$	0.4911
$\theta'_{F',e}$	0.5089
$\theta'_{i,F'}$	1.6804

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290	0.030	
300	0.330	0.060
310	0.690	0.400
320	0.880	0.720
330	0.950	0.870
340	0.977	0.944
350	0.988	0.970
360	0.993	0.983
365	0.995	0.987
370	0.996	0.990
380	0.997	0.993
390	0.998	0.995
400	0.998	0.996
420	0.998	0.996
440	0.998	0.996
460	0.999	0.997
480	0.999	0.998
500	0.999	0.998
550	0.999	0.998
600	0.999	0.998
650	0.999	0.998
700	0.999	0.998
800	0.999	0.998
900	0.999	0.997
1000	0.997	0.993
1200	0.997	0.993
1400	0.985	0.963
1600	0.992	0.980
1800	0.983	0.959
2000	0.967	0.920
2200	0.890	0.740
2400	0.780	0.540

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	32				
Specific Gravity	<b>d</b>	3.36		$\lambda_5$	29				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.5	2.8	2.8	2.9	3.1	3.3	3.6	4.3	
-20 ~ 0	2.6	2.9	2.9	3.0	3.1	3.4	3.7	4.4	
0 ~ 20	2.6	2.9	2.9	3.1	3.2	3.5	3.8	4.6	
20 ~ 40	2.6	3.0	3.0	3.1	3.3	3.6	3.9	4.7	
40 ~ 60	2.7	3.0	3.0	3.2	3.3	3.6	4.0	4.8	
60 ~ 80	2.7	3.1	3.1	3.3	3.4	3.7	4.1	4.9	

Refractive Index	$n_d$	<b>1.58913</b> 1.589130	Abbe Number	$V_d$	<b>61.15</b> 60.93	Dispersion	$n_F - n_C$	<b>0.00963</b> 0.009634
		$n_e$		1.591430			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55775
$n_{1970}$	1.97009	1.56407
$n_{1530}$	1.52958	1.57069
$n_{1129}$	1.12864	1.57622
$n_t$	1.01398	1.57795
$n_s$	0.85211	1.58085
$n_{A'}$	0.76819	1.58276
$n_r$	0.70652	1.58448
$n_c$	0.65627	<b>1.58618</b>
$n_{c'}$	0.64385	1.58665
$n_{\text{He-Ne}}$	0.6328	1.58709
$n_D$	0.58929	1.58904
$n_d$	0.58756	<b>1.58913</b>
$n_e$	0.54607	1.59143
$n_F$	0.48613	<b>1.59581</b>
$n_{F'}$	0.47999	1.59636
$n_{\text{He-Cd}}$	0.44157	1.60031
$n_g$	0.435835	<b>1.60100</b>
$n_h$	0.404656	1.60528
$n_i$	0.365015	1.61256
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008230
$n_c - n_{A'}$	0.003418
$n_d - n_c$	0.002952
$n_e - n_c$	0.005250
$n_g - n_d$	0.011867
$n_g - n_F$	0.005185
$n_h - n_g$	0.004288
$n_i - n_g$	0.011567
$n_{c'} - n_t$	0.008702
$n_e - n_{c'}$	0.004778
$n_{F'} - n_e$	0.004928
$n_i - n_{F'}$	0.016208

Relative Partial Dispersions	
$\theta_{c,t}$	0.8543
$\theta_{c,A'}$	0.3548
$\theta_{d,c}$	0.3064
$\theta_{e,c}$	0.5449
$\theta_{g,d}$	1.2318
$\theta_{g,F}$	0.5382
$\theta_{h,g}$	0.4451
$\theta_{i,g}$	1.2006
$\theta'_{c,t}$	0.8966
$\theta'_{e,c'}$	0.4923
$\theta'_{F',e}$	0.5077
$\theta'_{i,F'}$	1.6699

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0207
$\Delta\theta_{c,A'}$	0.0048
$\Delta\theta_{g,d}$	-0.0059
$\Delta\theta_{g,F}$	-0.0043
$\Delta\theta_{i,g}$	-0.0124

Internal Transmittance			
$\lambda_{80}$	336	$\lambda_5$	300

CCI		
B	G	R
0.00	0.23	0.20

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.16262630	
A 2	3.25661051	E-1
A 3	1.35132486	
B 1	1.25957437	E-2
B 2	-3.26911050	E-3
B 3	1.19214596	E2
1129 ~ 2325 nm		
A 1	1.16262630	
A 2	3.25661051	E-1
A 3	1.35132486	
B 1	1.25957437	E-2
B 2	-3.26911050	E-3
B 3	1.19214596	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.060	
310	0.270	
320	0.530	
330	0.730	
340	0.850	
350	0.922	
360	0.956	
365		
370	0.975	
380	0.984	
390	0.989	
400	0.992	
420	0.993	
440	0.993	
460	0.995	
480	0.996	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.991	
1600	0.994	
1800	0.989	
2000	0.978	
2200	0.934	
2400	0.810	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	489
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	520
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	527
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	567
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	619
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	66
	(+10~+300 $^{\circ}\text{C}$ )	81
Thermal Conductivity (W/m·K)	<b>k</b>	1.126

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	3.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1008
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	403
Poisson's Ratio	$\sigma$	0.252
Knoop Hardness	<b>Hk</b>	630 [6]
Abrasion	<b>Aa</b>	100
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.29

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	2.82		$\lambda_5$		295			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.9	4.3	4.3	4.4	4.5	4.8	5.1		
-20 ~ 0	3.9	4.3	4.3	4.5	4.6	4.9	5.2		
0 ~ 20	4.0	4.4	4.4	4.5	4.7	5.0	5.3		
20 ~ 40	4.0	4.4	4.5	4.6	4.7	5.1	5.4		
40 ~ 60	4.1	4.5	4.5	4.7	4.8	5.2	5.5		
60 ~ 80	4.1	4.5	4.6	4.8	4.9	5.2	5.6		



Refractive Index	$n_d$	<b>1.59208</b>	Abbe Number	$V_d$	<b>61.00</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.009707
	$n_e$	1.594396		$V_e$	60.77			0.009781

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.56051
$n_{1970}$	1.97009	1.56687
$n_{1530}$	1.52958	1.57353
$n_{1129}$	1.12864	1.57908
$n_t$	1.01398	1.58082
$n_s$	0.85211	1.58373
$n_{A'}$	0.76819	1.58566
$n_r$	0.70652	1.58740
$n_c$	0.65627	<b>1.58911</b>
$n_{c'}$	0.64385	1.58958
$n_{\text{He-Ne}}$	0.6328	1.59003
$n_D$	0.58929	1.59199
$n_d$	0.58756	<b>1.59208</b>
$n_e$	0.54607	1.59440
$n_F$	0.48613	<b>1.59881</b>
$n_{F'}$	0.47999	1.59936
$n_{\text{He-Cd}}$	0.44157	1.60335
$n_g$	0.435835	<b>1.60404</b>
$n_h$	0.404656	1.60836
$n_i$	0.365015	1.61570
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008288
$n_c - n_{A'}$	0.003444
$n_d - n_c$	0.002974
$n_e - n_c$	0.005290
$n_g - n_d$	0.011957
$n_g - n_F$	0.005224
$n_h - n_g$	0.004322
$n_i - n_g$	0.011660
$n_{c'} - n_t$	0.008763
$n_e - n_{c'}$	0.004815
$n_{F'} - n_e$	0.004966
$n_i - n_{F'}$	0.016335

Relative Partial Dispersions	
$\theta_{c,t}$	0.8538
$\theta_{c,A'}$	0.3548
$\theta_{d,c}$	0.3064
$\theta_{e,c}$	0.5450
$\theta_{g,d}$	1.2318
$\theta_{g,F}$	0.5382
$\theta_{h,g}$	0.4452
$\theta_{i,g}$	1.2012
$\theta'_{c,t}$	0.8959
$\theta'_{e,c'}$	0.4923
$\theta'_{F',e}$	0.5077
$\theta'_{i,F'}$	1.6701

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0209
$\Delta\theta_{c,A'}$	0.0050
$\Delta\theta_{g,d}$	-0.0062
$\Delta\theta_{g,F}$	-0.0046
$\Delta\theta_{i,g}$	-0.0130

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	8.06742194	E-1
A 2	6.90488648	E-1
A 3	1.26477947	
B 1	1.48836231	E-2
B 2	2.51943058	E-3
B 3	1.11314570	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.060	
310	0.270	
320	0.530	
330	0.730	
340	0.850	
350	0.922	
360	0.956	
365		
370	0.975	
380	0.984	
390	0.989	
400	0.992	
420	0.993	
440	0.993	
460	0.995	
480	0.996	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.991	
1600	0.994	
1800	0.989	
2000	0.978	
2200	0.934	
2400	0.810	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	489
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	520
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	427
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	567
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	619
Expansion Coefficient ( $10^{-7}/^{\circ}\text{C}$ )	$\alpha$	66 (-30~+70 $^{\circ}\text{C}$ ) 81 (+100~+300 $^{\circ}\text{C}$ )
Thermal Conductivity (W/m·K)	<b>k</b>	1.130

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1008
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	403
Poisson's Ratio	$\sigma$	0.252
Knoop Hardness	<b>Hk</b>	630 [6]
Abrasion	<b>Aa</b>	100
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.29

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	3.2

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	2.82		$\lambda_5$	295				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.9	4.3	4.3	4.4	4.5	4.8	4.8	5.1	
-20 ~ 0	3.9	4.3	4.3	4.5	4.6	4.9	4.9	5.2	
0 ~ 20	4.0	4.4	4.4	4.5	4.7	4.7	5.0	5.3	
20 ~ 40	4.0	4.4	4.5	4.6	4.7	4.7	5.1	5.4	
40 ~ 60	4.1	4.5	4.5	4.7	4.8	4.8	5.2	5.5	
60 ~ 80	4.1	4.5	4.6	4.8	4.9	4.9	5.2	5.6	

Refractive Index	$n_d$	<b>1.58313</b>	Abbe Number	$V_d$	<b>59.38</b>	Dispersion	$n_F - n_C$	<b>0.00982</b>
		1.583130			$V_e$		59.13	
	$n_e$	1.585470					$n_{F'} - n_{C'}$	0.009901

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55402
$n_{1970}$	1.97009	1.55949
$n_{1530}$	1.52958	1.56533
$n_{1129}$	1.12864	1.57038
$n_t$	1.01398	1.57201
$n_s$	0.85211	1.57482
$n_{A'}$	0.76819	1.57671
$n_r$	0.70652	1.57843
$n_c$	0.65627	<b>1.58013</b>
$n_{c'}$	0.64385	1.58061
$n_{\text{He-Ne}}$	0.6328	1.58106
$n_D$	0.58929	1.58304
$n_d$	0.58756	<b>1.58313</b>
$n_e$	0.54607	1.58547
$n_F$	0.48613	<b>1.58995</b>
$n_{F'}$	0.47999	1.59051
$n_{\text{He-Cd}}$	0.44157	1.59457
$n_g$	0.435835	<b>1.59528</b>
$n_h$	0.404656	1.59969
$n_i$	0.365015	1.60719
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.008122
$n_C - n_{A'}$	0.003426
$n_d - n_C$	0.002992
$n_e - n_C$	0.005334
$n_g - n_d$	0.012153
$n_g - n_F$	0.005325
$n_h - n_g$	0.004412
$n_i - n_g$	0.011910
$n_{C'} - n_t$	0.008599
$n_e - n_{C'}$	0.004857
$n_{F'} - n_e$	0.005044
$n_i - n_{F'}$	0.016677

Relative Partial Dispersions	
$\theta_{C,t}$	0.8271
$\theta_{C,A'}$	0.3489
$\theta_{d,C}$	0.3047
$\theta_{e,C}$	0.5432
$\theta_{g,d}$	1.2376
$\theta_{g,F}$	0.5423
$\theta_{h,g}$	0.4493
$\theta_{i,g}$	1.2128
$\theta'_{C,t}$	0.8685
$\theta'_{e,C'}$	0.4906
$\theta'_{F',e}$	0.5094
$\theta'_{i,F'}$	1.6844

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0018
$\Delta\theta_{C,A'}$	0.0010
$\Delta\theta_{g,d}$	-0.0038
$\Delta\theta_{g,F}$	-0.0031
$\Delta\theta_{i,g}$	-0.0150

Internal Transmittance			
$\lambda_{80}$	326	$\lambda_5$	282

CCI		
B	G	R
0.00	0.17	0.14

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.39528097	
A 2	7.25519520	E-2
A 3	1.66335848	
B 1	1.11862030	E-2
B 2	-2.46748575	E-2
B 3	1.67717958	E2
1129 ~ 2325 nm		
A 1	1.39528097	
A 2	7.25519520	E-2
A 3	1.66335848	
B 1	1.11862030	E-2
B 2	-2.46748575	E-2
B 3	1.67717958	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290	0.050	
300	0.190	
310	0.410	
320	0.630	
330	0.790	
340	0.890	
350	0.940	
360	0.968	
365		
370	0.981	
380	0.987	
390	0.992	
400	0.994	
420	0.994	
440	0.995	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.998	
650	0.998	
700	0.998	
800	0.999	
900	0.998	
1000	0.998	
1200	0.998	
1400	0.993	
1600	0.997	
1800	0.988	
2000	0.975	
2200	0.914	
2400	0.840	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	467
Annealing Point (°C)	<b>AP</b>	494
Transformation Temperature (°C)	<b>Tg</b>	506
Yield Point (°C)	<b>At</b>	538
Softening Point (°C)	<b>SP</b>	607
Expansion Coefficient $\alpha$		
	(-30~+70°C)	72
	(+10~+300°C)	88
Thermal Conductivity (W/m·K)	<b>k</b>	1.028

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	5.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	891
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	357
Poisson's Ratio	$\sigma$	0.247
Knoop Hardness	<b>Hk</b>	590 [6]
Abrasion	<b>Aa</b>	113
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Other Properties								
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	340			
Specific Gravity	<b>d</b>	3.05		$\lambda_5$	285			
Temperature Coefficients of Refractive Index								
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20		3.2	3.2	3.3	3.4	3.8	4.1	
-20 ~ 0		3.2	3.2	3.3	3.5	3.8	4.1	
0 ~ 20		3.2	3.2	3.3	3.5	3.8	4.2	
20 ~ 40		3.2	3.2	3.3	3.5	3.8	4.2	
40 ~ 60		3.2	3.2	3.3	3.5	3.9	4.2	
60 ~ 80		3.2	3.2	3.3	3.5	3.9	4.3	

Refractive Index	$n_d$	<b>1.58593</b>	Abbe Number	$V_d$	<b>59.24</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.009890
		1.585930			$V_e$		58.99	
	$n_e$	1.588288						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55671
$n_{1970}$	1.97009	1.56222
$n_{1530}$	1.52958	1.56806
$n_{1129}$	1.12864	1.57311
$n_t$	1.01398	1.57475
$n_s$	0.85211	1.57757
$n_{A'}$	0.76819	1.57947
$n_r$	0.70652	1.58120
$n_c$	0.65627	<b>1.58292</b>
$n_{c'}$	0.64385	1.58340
$n_{\text{He-Ne}}$	0.6328	1.58385
$n_D$	0.58929	1.58584
$n_d$	0.58756	<b>1.58593</b>
$n_e$	0.54607	1.58829
$n_F$	0.48613	<b>1.59281</b>
$n_{F'}$	0.47999	1.59337
$n_{\text{He-Cd}}$	0.44157	1.59746
$n_g$	0.435835	<b>1.59817</b>
$n_h$	0.404656	1.60262
$n_i$	0.365015	1.61020
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.008169
$n_c - n_{A'}$	0.003449
$n_d - n_c$	0.003013
$n_e - n_c$	0.005371
$n_g - n_d$	0.012242
$n_g - n_F$	0.005365
$n_h - n_g$	0.004451
$n_i - n_g$	0.012026
$n_{c'} - n_t$	0.008649
$n_e - n_{c'}$	0.004891
$n_{F'} - n_e$	0.005081
$n_i - n_{F'}$	0.016829

Relative Partial Dispersions	
$\theta_{c,t}$	0.8260
$\theta_{c,A'}$	0.3487
$\theta_{d,c}$	0.3047
$\theta_{e,c}$	0.5431
$\theta_{g,d}$	1.2378
$\theta_{g,F}$	0.5425
$\theta_{h,g}$	0.4501
$\theta_{i,g}$	1.2160
$\theta'_{c,t}$	0.8673
$\theta'_{e,c'}$	0.4905
$\theta'_{F',e}$	0.5095
$\theta'_{i,F'}$	1.6876

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0014
$\Delta\theta_{c,A'}$	0.0010
$\Delta\theta_{g,d}$	-0.0039
$\Delta\theta_{g,F}$	-0.0031
$\Delta\theta_{i,g}$	-0.0130

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	8.81090017	E-1
A 2	5.95038859	E-1
A 3	1.22582098	
B 1	1.48496655	E-2
B 2	1.63577371	E-3
B 3	1.25113720	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.030	
290	0.140	
300	0.320	
310	0.550	
320	0.730	
330	0.850	
340	0.924	
350	0.960	
360	0.978	
365		
370	0.987	
380	0.992	
390	0.994	
400	0.995	
420	0.996	
440	0.996	
460	0.996	
480	0.998	
500	0.998	
550	0.999	
600	0.999	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.988	
1600	0.993	
1800	0.983	
2000	0.968	
2200	0.901	
2400	0.830	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	467
Annealing Point (°C)	<b>AP</b>	494
Transformation Temperature (°C)	<b>Tg</b>	506
Yield Point (°C)	<b>At</b>	538
Softening Point (°C)	<b>SP</b>	607
Expansion Coefficient $\alpha$ (-30~+70°C)		72
(10 <sup>-7</sup> /°C)	(+100~+300°C)	88
Thermal Conductivity (W/m·K)	<b>k</b>	1.030

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	5.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	891
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	357
Poisson's Ratio	$\sigma$	0.247
Knoop Hardness	<b>Hk</b>	590 [6]
Abrasion	<b>Aa</b>	113
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.19

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	340				
Specific Gravity	<b>d</b>	3.05		$\lambda_5$	285				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.3	3.7	3.7	3.8	4.0	4.3	4.6		
-20 ~ 0	3.2	3.6	3.6	3.8	3.9	4.3	4.6		
0 ~ 20	3.1	3.6	3.6	3.7	3.9	4.2	4.6		
20 ~ 40	3.1	3.5	3.6	3.7	3.9	4.2	4.6		
40 ~ 60	3.1	3.6	3.6	3.7	3.9	4.3	4.6		
60 ~ 80	3.2	3.7	3.7	3.8	4.0	4.4	4.8		

Refractive Index	$n_d$	<b>1.58573</b>	Abbe Number	$V_d$	<b>59.70</b>	Dispersion	$n_F - n_C$	<b>0.00981</b>
		1.585730			$V_e$		59.45	
	$n_e$	1.588070					$n_{F'} - n_{C'}$	0.009892

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.55621
$n_{1970}$	1.97009	1.56185
$n_{1530}$	1.52958	1.56781
$n_{1129}$	1.12864	1.57293
$n_t$	1.01398	1.57458
$n_s$	0.85211	1.57740
$n_{A'}$	0.76819	1.57930
$n_r$	0.70652	1.58103
$n_c$	0.65627	<b>1.58274</b>
$n_{c'}$	0.64385	1.58321
$n_{\text{He-Ne}}$	0.6328	1.58366
$n_D$	0.58929	1.58564
$n_d$	0.58756	<b>1.58573</b>
$n_e$	0.54607	1.58807
$n_F$	0.48613	<b>1.59255</b>
$n_{F'}$	0.47999	1.59311
$n_{\text{He-Cd}}$	0.44157	1.59716
$n_g$	0.435835	<b>1.59786</b>
$n_h$	0.404656	1.60227
$n_i$	0.365015	1.60976
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_C - n_t$	0.008157
$n_C - n_{A'}$	0.003435
$n_d - n_C$	0.002993
$n_e - n_C$	0.005333
$n_g - n_d$	0.012132
$n_g - n_F$	0.005313
$n_h - n_g$	0.004404
$n_i - n_g$	0.011900
$n_{C'} - n_t$	0.008634
$n_e - n_{C'}$	0.004856
$n_{F'} - n_e$	0.005036
$n_i - n_{F'}$	0.016656

Relative Partial Dispersions	
$\theta_{C,t}$	0.8313
$\theta_{C,A'}$	0.3501
$\theta_{d,C}$	0.3050
$\theta_{e,C}$	0.5435
$\theta_{g,d}$	1.2364
$\theta_{g,F}$	0.5415
$\theta_{h,g}$	0.4488
$\theta_{i,g}$	1.2128
$\theta'_{C,t}$	0.8728
$\theta'_{e,C'}$	0.4909
$\theta'_{F',e}$	0.5091
$\theta'_{i,F'}$	1.6838

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0045
$\Delta\theta_{C,A'}$	0.0019
$\Delta\theta_{g,d}$	-0.0043
$\Delta\theta_{g,F}$	-0.0034
$\Delta\theta_{i,g}$	-0.0123

Internal Transmittance			
$\lambda_{80}$	328	$\lambda_5$	289

CCI		
B	G	R
0.00	0.10	0.10

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.04745291	E0
A 2	4.28452873	E-1
A 3	1.14111303	E0
B 1	5.63209756	E-3
B 2	1.88321416	E-2
B 3	1.14197069	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.290	
310	0.510	
320	0.700	
330	0.830	
340	0.906	
350	0.949	
360	0.971	
365		
370	0.983	
380	0.988	
390	0.990	
400	0.996	
420	0.997	
440	0.996	
460	0.998	
480	0.999	
500	0.999	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.993	
1600	0.997	
1800	0.988	
2000	0.975	
2200	0.914	
2400	0.840	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	451
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	482
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	493
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	535
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	596
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		72
(+100~+300 $^{\circ}\text{C}$ )		90
Thermal Conductivity (W/m·K)	<b>k</b>	1.028

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	51.4
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	904
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	362
Poisson's Ratio	$\sigma$	0.250
Knoop Hardness	<b>Hk</b>	610 [6]
Abrasion	<b>Aa</b>	115
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.18

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	340				
Specific Gravity	<b>d</b>	3.05		$\lambda_5$		285			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.2	3.5	3.6	3.7	3.8	4.1	4.5		
-20 ~ 0	3.1	3.5	3.6	3.7	3.8	4.2	4.5		
0 ~ 20	3.1	3.5	3.6	3.7	3.8	4.2	4.5		
20 ~ 40	3.0	3.5	3.5	3.6	3.8	4.1	4.5		
40 ~ 60	3.0	3.5	3.5	3.6	3.8	4.2	4.6		
60 ~ 80	3.2	3.6	3.7	3.8	4.0	4.4	4.7		

Refractive Index	$n_d$	<b>1.51633</b>	Abbe Number	$V_d$	<b>64.06</b>	Dispersion	$n_F - n_C$	<b>0.00806</b>
		1.516330			$V_e$		63.87	
	$n_e$	1.518250					$n_{F'} - n_{C'}$	0.008114

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.48810
$n_{1970}$	1.97009	1.49404
$n_{1530}$	1.52958	1.50020
$n_{1129}$	1.12864	1.50523
$n_t$	1.01398	1.50677
$n_s$	0.85211	1.50930
$n_{A'}$	0.76819	1.51094
$n_r$	0.70652	1.51241
$n_c$	0.65627	<b>1.51385</b>
$n_{c'}$	0.64385	1.51424
$n_{\text{He-Ne}}$	0.6328	1.51462
$n_D$	0.58929	1.51626
$n_d$	0.58756	<b>1.51633</b>
$n_e$	0.54607	1.51825
$n_F$	0.48613	<b>1.52191</b>
$n_{F'}$	0.47999	1.52236
$n_{\text{He-Cd}}$	0.44157	1.52564
$n_g$	0.435835	<b>1.52620</b>
$n_h$	0.404656	1.52975
$n_i$	0.365015	1.53574
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	464
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	488
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	498
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	549
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	630
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		58
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	71
Thermal Conductivity (W/m·K)	<b>k</b>	1.169

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	793
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	327
Poisson's Ratio	$\sigma$	0.214
Knoop Hardness	<b>Hk</b>	560 [6]
Abrasion	<b>Aa</b>	69
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.93

Partial Dispersions	
$n_c - n_t$	0.007081
$n_c - n_{A'}$	0.002904
$n_d - n_c$	0.002484
$n_e - n_c$	0.004407
$n_g - n_d$	0.009874
$n_g - n_F$	0.004298
$n_h - n_g$	0.003544
$n_i - n_g$	0.009541
$n_{c'} - n_t$	0.007479
$n_e - n_{c'}$	0.004009
$n_{F'} - n_e$	0.004105
$n_i - n_{F'}$	0.013387

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0312
$\Delta\theta_{c,A'}$	0.0068
$\Delta\theta_{g,d}$	-0.0066
$\Delta\theta_{g,F}$	-0.0045
$\Delta\theta_{i,g}$	-0.0049

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.17473918	E-1
A 2	3.52687665	E-1
A 3	1.05579788	
B 1	5.27701411	E-3
B 2	1.70809497	E-2
B 3	1.04302583	E2
1129 ~ 2325 nm		
A 1	9.17473918	E-1
A 2	3.52687665	E-1
A 3	1.05579788	
B 1	5.27701411	E-3
B 2	1.70809497	E-2
B 3	1.04302583	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.2

Relative Partial Dispersions	
$\theta_{c,t}$	0.8785
$\theta_{c,A'}$	0.3603
$\theta_{d,c}$	0.3082
$\theta_{e,c}$	0.5468
$\theta_{g,d}$	1.2251
$\theta_{g,F}$	0.5333
$\theta_{h,g}$	0.4397
$\theta_{i,g}$	1.1837
$\theta'_{c,t}$	0.9217
$\theta'_{e,c'}$	0.4941
$\theta'_{F',e}$	0.5059
$\theta'_{i,F'}$	1.6499

Internal Transmittance			
$\lambda_{80}$	326	$\lambda_5$	299

CCI		
B	G	R
0.00	0.08	0.09

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300	0.080	
310	0.400	
320	0.710	
330	0.870	
340	0.942	
350	0.973	
360	0.986	
365		
370	0.992	
380	0.994	
390	0.996	
400	0.997	
420	0.997	
440	0.997	
460	0.997	
480	0.998	
500	0.999	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.974	
1600	0.994	
1800	0.988	
2000	0.974	
2200	0.870	
2400	0.800	

Other Properties								
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	330			
Specific Gravity	<b>d</b>	2.38		$\lambda_5$	295			
Temperature Coefficients of Refractive Index								
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )							
	t	C'	He-Ne	D	e	F'	g	i
-40 ~ -20	4.0	4.3	4.3	4.4	4.5	4.7	4.9	
-20 ~ 0	4.1	4.4	4.4	4.5	4.6	4.8	5.1	
0 ~ 20	4.1	4.5	4.5	4.6	4.7	4.9	5.2	
20 ~ 40	4.2	4.6	4.6	4.7	4.8	5.1	5.3	
40 ~ 60	4.3	4.7	4.7	4.8	4.9	5.2	5.5	
60 ~ 80	4.4	4.7	4.8	4.9	5.0	5.3	5.6	

Refractive Index	$n_d$	<b>1.80625</b> 1.806250	Abbe Number	$V_d$	<b>40.91</b> 40.66	Dispersion	$n_F - n_C$	<b>0.01971</b> 0.019709
		$n_e$		1.810931			$V_e$	40.66

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.76094
$n_{1970}$	1.97009	1.76797
$n_{1530}$	1.52958	1.77569
$n_{1129}$	1.12864	1.78303
$n_t$	1.01398	1.78566
$n_s$	0.85211	1.79048
$n_{A'}$	0.76819	1.79391
$n_r$	0.70652	1.79713
$n_c$	0.65627	<b>1.80039</b>
$n_{c'}$	0.64385	1.80132
$n_{\text{He-Ne}}$	0.6328	1.80218
$n_D$	0.58929	1.80608
$n_d$	0.58756	<b>1.80625</b>
$n_e$	0.54607	1.81093
$n_F$	0.48613	<b>1.82010</b>
$n_{F'}$	0.47999	1.82126
$n_{\text{He-Cd}}$	0.44157	1.82981
$n_g$	0.435835	<b>1.83132</b>
$n_h$	0.404656	1.84090
$n_i$	0.365015	1.85783
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.014736
$n_c - n_{A'}$	0.006484
$n_d - n_c$	0.005856
$n_e - n_c$	0.010537
$n_g - n_d$	0.025070
$n_g - n_F$	0.011217
$n_h - n_g$	0.009578
$n_i - n_g$	0.026514
$n_{c'} - n_t$	0.015658
$n_e - n_{c'}$	0.009615
$n_{F'} - n_e$	0.010331
$n_i - n_{F'}$	0.036572

Relative Partial Dispersions	
$\theta_{c,t}$	0.7477
$\theta_{c,A'}$	0.3290
$\theta_{d,c}$	0.2971
$\theta_{e,c}$	0.5346
$\theta_{g,d}$	1.2720
$\theta_{g,F}$	0.5691
$\theta_{h,g}$	0.4860
$\theta_{i,g}$	1.3453
$\theta'_{c,t}$	0.7850
$\theta'_{e,c'}$	0.4821
$\theta'_{F',e}$	0.5179
$\theta'_{i,F'}$	1.8336

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0091
$\Delta\theta_{c,A'}$	0.0036
$\Delta\theta_{g,d}$	-0.0077
$\Delta\theta_{g,F}$	-0.0062
$\Delta\theta_{i,g}$	-0.0372

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R
0.00	0.88	0.94

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.87409991	
A 2	2.97921402	E-1
A 3	1.35064285	
B 1	9.93318344	E-3
B 2	4.05501825	E-2
B 3	1.00502200	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.160	
350	0.470	
360	0.700	
365		
370	0.830	
380	0.890	
390	0.929	
400	0.950	
420	0.970	
440	0.979	
460	0.985	
480	0.989	
500	0.993	
550	0.997	
600	0.997	
650	0.998	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.988	
2000	0.969	
2200	0.919	
2400	0.730	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	534
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	558
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	574
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	607
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	646
Expansion Coefficient ( $10^{-7}/^{\circ}\text{C}$ )	$\alpha$	59 (-30~+70 $^{\circ}\text{C}$ ) 72 (+100~+300 $^{\circ}\text{C}$ )
Thermal Conductivity (W/m·K)	<b>k</b>	0.862

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1151
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	443
Poisson's Ratio	$\sigma$	0.298
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	76
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.88

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	4.49		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	6.5	7.4	7.4	7.7	8.0	8.8	9.6		
-20 ~ 0	6.6	7.4	7.5	7.7	8.1	8.9	9.7		
0 ~ 20	6.6	7.5	7.5	7.8	8.2	9.0	9.9		
20 ~ 40	6.5	7.5	7.5	7.8	8.2	9.1	10.0		
40 ~ 60	6.6	7.6	7.7	8.0	8.3	9.2	10.2		
60 ~ 80	6.8	7.8	7.9	8.2	8.6	9.5	10.5		



Refractive Index	$n_d$	<b>1.80835</b>	Abbe Number	$V_d$	<b>40.55</b>	Dispersion	$n_F - n_C$	<b>0.01994</b>
	$n_e$	1.808350		$V_e$	40.30		$n_{F'} - n_{C'}$	0.019936
		1.813086						0.020178

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.76397
$n_{1970}$	1.97009	1.77059
$n_{1530}$	1.52958	1.77793
$n_{1129}$	1.12864	1.78505
$n_t$	1.01398	1.78765
$n_s$	0.85211	1.79245
$n_{A'}$	0.76819	1.79590
$n_r$	0.70652	1.79914
$n_c$	0.65627	<b>1.80243</b>
$n_{c'}$	0.64385	1.80336
$n_{\text{He-Ne}}$	0.6328	1.80424
$n_D$	0.58929	1.80818
$n_d$	0.58756	<b>1.80835</b>
$n_e$	0.54607	1.81309
$n_F$	0.48613	<b>1.82237</b>
$n_{F'}$	0.47999	1.82354
$n_{\text{He-Cd}}$	0.44157	1.83219
$n_g$	0.435835	<b>1.83372</b>
$n_h$	0.404656	1.84340
$n_i$	0.365015	1.86048
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	491
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	515
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	527
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	568
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	603
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	64
	(+10~+300 $^{\circ}\text{C}$ )	79
Thermal Conductivity (W/m·K)	<b>k</b>	0.875

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1116
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	428
Poisson's Ratio	$\sigma$	0.303
Knoop Hardness	<b>Hk</b>	610 [6]
Abrasion	<b>Aa</b>	78
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.35

Partial Dispersions	
$n_c - n_t$	0.014785
$n_c - n_{A'}$	0.006535
$n_d - n_c$	0.005918
$n_e - n_c$	0.010654
$n_g - n_d$	0.025366
$n_g - n_F$	0.011348
$n_h - n_g$	0.009680
$n_i - n_g$	0.026762
$n_{c'} - n_t$	0.015716
$n_e - n_{c'}$	0.009723
$n_{F'} - n_e$	0.010455
$n_i - n_{F'}$	0.036937

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0047
$\Delta\theta_{c,A'}$	0.0028
$\Delta\theta_{g,d}$	-0.0081
$\Delta\theta_{g,F}$	-0.0067
$\Delta\theta_{i,g}$	-0.0431

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.83606127	
A 2	3.41720032	E-1
A 3	1.35280173	
B 1	9.81969903	E-3
B 2	3.85696264	E-2
B 3	1.07045530	E2
1129 ~ 2325 nm		
A 1	1.86267109	
A 2	3.15564131	E-1
A 3	1.30716934	
B 1	1.01627115	E-2
B 2	3.94096655	E-2
B 3	1.03774464	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.3
Phosphate Resistance	<b>PR</b>	2.2

Relative Partial Dispersions	
$\theta_{c,t}$	0.7416
$\theta_{c,A'}$	0.3278
$\theta_{d,c}$	0.2968
$\theta_{e,c}$	0.5344
$\theta_{g,d}$	1.2724
$\theta_{g,F}$	0.5692
$\theta_{h,g}$	0.4856
$\theta_{i,g}$	1.3424
$\theta'_{c,t}$	0.7789
$\theta'_{e,c'}$	0.4819
$\theta'_{F',e}$	0.5181
$\theta'_{i,F'}$	1.8306

Internal Transmittance			
$\lambda_{80}$	364	$\lambda_5$	336

CCI		
B	G	R
0.00	0.75	0.77

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.200	
350	0.540	
360	0.760	
365		
370	0.870	
380	0.922	
390	0.950	
400	0.965	
420	0.979	
440	0.985	
460	0.990	
480	0.993	
500	0.996	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.992	
2000	0.975	
2200	0.942	
2400	0.790	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	4.62		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	7.2	8.1	8.1	8.4	8.7	9.6	10.4		
-20 ~ 0	7.1	8.1	8.1	8.4	8.8	9.7	10.6		
0 ~ 20	7.1	8.1	8.2	8.5	8.7	9.8	10.7		
20 ~ 40	7.1	8.1	8.2	8.5	8.9	9.8	10.8		
40 ~ 60	7.2	8.2	8.3	8.6	9.0	10.0	11.0		
60 ~ 80	7.3	8.4	8.5	8.8	9.3	10.3	11.3		

Refractive Index	$n_d$	<b>1.81225</b>	Abbe Number	$V_d$	<b>40.29</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.020159
		1.812250			$V_e$		40.04	
	$n_e$	1.817039						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.76778
$n_{1970}$	1.97009	1.77433
$n_{1530}$	1.52958	1.78163
$n_{1129}$	1.12864	1.78876
$n_t$	1.01398	1.79136
$n_s$	0.85211	1.79620
$n_{A'}$	0.76819	1.79967
$n_r$	0.70652	1.80294
$n_c$	0.65627	<b>1.80627</b>
$n_{c'}$	0.64385	1.80721
$n_{\text{He-Ne}}$	0.6328	1.80809
$n_D$	0.58929	1.81207
$n_d$	0.58756	<b>1.81225</b>
$n_e$	0.54607	1.81704
$n_F$	0.48613	<b>1.82643</b>
$n_{F'}$	0.47999	1.82761
$n_{\text{He-Cd}}$	0.44157	1.83637
$n_g$	0.435835	<b>1.83791</b>
$n_h$	0.404656	1.84771
$n_i$	0.365015	1.86501
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.014909
$n_c - n_{A'}$	0.006599
$n_d - n_c$	0.005981
$n_e - n_c$	0.010770
$n_g - n_d$	0.025662
$n_g - n_F$	0.011484
$n_h - n_g$	0.009800
$n_i - n_g$	0.027101
$n_{c'} - n_t$	0.015850
$n_e - n_{c'}$	0.009829
$n_{F'} - n_e$	0.010576
$n_i - n_{F'}$	0.037398

Relative Partial Dispersions	
$\theta_{c,t}$	0.7396
$\theta_{c,A'}$	0.3273
$\theta_{d,c}$	0.2967
$\theta_{e,c}$	0.5343
$\theta_{g,d}$	1.2730
$\theta_{g,F}$	0.5697
$\theta_{h,g}$	0.4861
$\theta_{i,g}$	1.3444
$\theta'_{c,t}$	0.7768
$\theta'_{e,c'}$	0.4817
$\theta'_{F',e}$	0.5183
$\theta'_{i,F'}$	1.8328

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0039
$\Delta\theta_{c,A'}$	0.0026
$\Delta\theta_{g,d}$	-0.0080
$\Delta\theta_{g,F}$	-0.0066
$\Delta\theta_{i,g}$	-0.0433

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.83485816	
A 2	3.55717498	E-1
A 3	1.37757002	
B 1	9.78848200	E-3
B 2	3.83708700	E-2
B 3	1.09716920	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.200	
350	0.540	
360	0.760	
365		
370	0.870	
380	0.922	
390	0.950	
400	0.965	
420	0.979	
440	0.985	
460	0.990	
480	0.993	
500	0.996	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.992	
2000	0.975	
2200	0.942	
2400	0.790	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	491
Annealing Point (°C)	<b>AP</b>	515
Transformation Temperature (°C)	<b>Tg</b>	527
Yield Point (°C)	<b>At</b>	568
Softening Point (°C)	<b>SP</b>	603
Expansion Coefficient $\alpha$ (-30~+70°C)		64
(10 <sup>-7</sup> /°C)	(+100~+300°C)	79
Thermal Conductivity (W/m·K)	<b>k</b>	0.875

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	51.3
Phosphate Resistance	<b>PR</b>	2.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1116
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	428
Poisson's Ratio	$\sigma$	0.303
Knoop Hardness	<b>Hk</b>	610 [6]
Abrasion	<b>Aa</b>	78
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.35

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	4.62		$\lambda_5$	335				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	7.2	8.1	8.1	8.4	8.7	9.6	10.4		
-20 ~ 0	7.1	8.1	8.1	8.4	8.8	9.7	10.6		
0 ~ 20	7.1	8.1	8.2	8.5	8.7	9.8	10.7		
20 ~ 40	7.1	8.1	8.2	8.5	8.9	9.8	10.8		
40 ~ 60	7.2	8.2	8.3	8.6	9.0	10.0	11.0		
60 ~ 80	7.3	8.4	8.5	8.8	9.3	10.3	11.3		

Refractive Index	$n_d$	<b>1.85400</b>	Abbe Number	$V_d$	<b>40.38</b>	Dispersion	$n_F - n_C$	<b>0.02115</b>
		1.854000			$V_e$		40.13	
	$n_e$	1.859025					$n_{F'} - n_{C'}$	0.021407

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.80740
$n_{1970}$	1.97009	1.81425
$n_{1530}$	1.52958	1.82188
$n_{1129}$	1.12864	1.82934
$n_t$	1.01398	1.83207
$n_s$	0.85211	1.83714
$n_{A'}$	0.76819	1.84079
$n_r$	0.70652	1.84423
$n_c$	0.65627	<b>1.84772</b>
$n_{c'}$	0.64385	1.84871
$n_{\text{He-Ne}}$	0.6328	1.84964
$n_D$	0.58929	1.85381
$n_d$	0.58756	<b>1.85400</b>
$n_e$	0.54607	1.85903
$n_F$	0.48613	<b>1.86887</b>
$n_{F'}$	0.47999	1.87012
$n_{\text{He-Cd}}$	0.44157	1.87929
$n_g$	0.435835	<b>1.88090</b>
$n_h$	0.404656	1.89116
$n_i$	0.365015	1.90923
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.015652
$n_c - n_{A'}$	0.006929
$n_d - n_c$	0.006279
$n_e - n_c$	0.011304
$n_g - n_d$	0.026903
$n_g - n_F$	0.012031
$n_h - n_g$	0.010254
$n_i - n_g$	0.028327
$n_{c'} - n_t$	0.016640
$n_e - n_{c'}$	0.010316
$n_{F'} - n_e$	0.011091
$n_i - n_{F'}$	0.039114

Relative Partial Dispersions	
$\theta_{c,t}$	0.7400
$\theta_{c,A'}$	0.3276
$\theta_{d,c}$	0.2969
$\theta_{e,c}$	0.5344
$\theta_{g,d}$	1.2719
$\theta_{g,F}$	0.5688
$\theta_{h,g}$	0.4848
$\theta_{i,g}$	1.3393
$\theta'_{c,t}$	0.7773
$\theta'_{e,c'}$	0.4819
$\theta'_{F',e}$	0.5181
$\theta'_{i,F'}$	1.8272

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0039
$\Delta\theta_{c,A'}$	0.0028
$\Delta\theta_{g,d}$	-0.0089
$\Delta\theta_{g,F}$	-0.0073
$\Delta\theta_{i,g}$	-0.0476

Internal Transmittance			
$\lambda_{80}$	373	$\lambda_5$	340

CCI		
B	G	R
0.00	1.17	1.20

Constants of Dispersion Formula	
326 ~ 1129 nm	
A 1	1.97460503
A 2	3.61903592 E-1
A 3	1.38433241
B 1	1.01854258 E-2
B 2	3.84829118 E-2
B 3	1.03713627 E2
1129 ~ 2325 nm	
A 1	
A 2	
A 3	
B 1	
B 2	
B 3	

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.050	
350	0.300	
360	0.580	
365		
370	0.770	
380	0.860	
390	0.915	
400	0.944	
420	0.971	
440	0.981	
460	0.987	
480	0.992	
500	0.995	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.998	
1800	0.992	
2000	0.973	
2200	0.933	
2400	0.770	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	613
Yield Point (°C)	<b>At</b>	653
Softening Point (°C)	<b>SP</b>	
Expansion Coefficient $\alpha$ (-30~+70°C)		63
(10 <sup>-7</sup> /°C)	(+100~+300°C)	77
Thermal Conductivity (W/m·K)	<b>k</b>	0.819

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	4
Acid Resistance (Surface Group)	<b>SR</b>	3.2
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	
Poisson's Ratio	$\sigma$	
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	61
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.83

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					380
Specific Gravity	<b>d</b>	5.25		$\lambda_5$					340
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.9	6.7	6.8	7.1	7.4	8.2	9.0		
-20 ~ 0	5.8	6.7	6.8	7.1	7.4	8.3	9.2		
0 ~ 20	5.8	6.8	6.9	7.1	7.5	8.4	9.3		
20 ~ 40	5.9	6.9	6.9	7.2	7.6	8.5	9.5		
40 ~ 60	6.0	7.0	7.0	7.4	7.8	8.7	9.7		
60 ~ 80	6.1	7.1	7.2	7.5	7.9	8.9	9.9		

Refractive Index	$n_d$	<b>1.90270</b>	Abbe Number	$V_d$	<b>31.00</b>	Dispersion	$n_F - n_C$	<b>0.02912</b>
	$n_e$	1.902700		$V_e$	30.78		$n_{F'} - n_{C'}$	0.029115
		1.909580						0.029553

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.84527
$n_{1970}$	1.97009	1.85288
$n_{1530}$	1.52958	1.86154
$n_{1129}$	1.12864	1.87044
$n_t$	1.01398	1.87383
$n_s$	0.85211	1.88029
$n_{A'}$	0.76819	1.88504
$n_r$	0.70652	1.88957
$n_C$	0.65627	<b>1.89422</b>
$n_{C'}$	0.64385	1.89555
$n_{\text{He-Ne}}$	0.6328	1.89679
$n_D$	0.58929	1.90245
$n_d$	0.58756	<b>1.90270</b>
$n_e$	0.54607	1.90958
$n_F$	0.48613	<b>1.92334</b>
$n_{F'}$	0.47999	1.92510
$n_{\text{He-Cd}}$	0.44157	1.93828
$n_g$	0.435835	<b>1.94064</b>
$n_h$	0.404656	1.95587
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	578
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	610
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	61
	(+100~+300 $^{\circ}\text{C}$ )	76
Thermal Conductivity (W/m·K)	<b>k</b>	0.838

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1088
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	418
Poisson's Ratio	$\sigma$	0.302
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	97
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.83

Partial Dispersions	
$n_C - n_t$	0.020392
$n_C - n_{A'}$	0.009182
$n_d - n_C$	0.008479
$n_e - n_C$	0.015364
$n_g - n_d$	0.037938
$n_g - n_F$	0.017302
$n_h - n_g$	0.015233
$n_i - n_g$	
$n_{C'} - n_t$	0.021717
$n_e - n_{C'}$	0.014039
$n_{F'} - n_e$	0.015514
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0083
$\Delta\theta_{C,A'}$	0.0020
$\Delta\theta_{g,d}$	0.0027
$\Delta\theta_{g,F}$	0.0030
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.11102709	
A 2	3.70368094	E-1
A 3	1.62687484	
B 1	1.20714135	E-2
B 2	5.32464416	E-2
B 3	1.09166396	E2
1129 ~ 2325 nm		
A 1	2.11102709	
A 2	3.70368094	E-1
A 3	1.62687484	
B 1	1.20714135	E-2
B 2	5.32464416	E-2
B 3	1.09166396	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	4.2
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.7004
$\theta_{C,A'}$	0.3154
$\theta_{d,C}$	0.2912
$\theta_{e,C}$	0.5277
$\theta_{g,d}$	1.3030
$\theta_{g,F}$	0.5943
$\theta_{h,g}$	0.5232
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7348
$\theta'_{e,C'}$	0.4750
$\theta'_{F',e}$	0.5250
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$	398	$\lambda_5$	360

CCI		
B	G	R
0.00	3.61	3.84

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350		
360	0.050	
365		
370	0.280	
380	0.550	
390	0.720	
400	0.820	
420	0.909	
440	0.945	
460	0.963	
480	0.975	
500	0.982	
550	0.993	
600	0.996	
650	0.997	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.999	
1600	0.998	
1800	0.992	
2000	0.974	
2200	0.920	
2400	0.741	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					410
Specific Gravity	<b>d</b>	4.90		$\lambda_5$					360
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	4.0	5.1	5.1	5.5	6.0	7.1	8.4		
-20 ~ 0	4.0	5.1	5.2	5.6	6.1	7.3	8.7		
0 ~ 20	4.0	5.2	5.3	5.7	6.3	7.5	9.0		
20 ~ 40	4.1	5.4	5.4	5.8	6.4	7.8	9.3		
40 ~ 60	4.2	5.5	5.6	6.0	6.6	8.0	9.6		
60 ~ 80	4.4	5.7	5.8	6.3	6.9	8.4	10.0		

Refractive Index	$n_d$	<b>1.83220</b>	Abbe Number	$V_d$	<b>40.10</b>	Dispersion	$n_F - n_C$	<b>0.02075</b>
		1.832200			$V_e$		39.84	
	$n_e$	1.837128					$n_{F'} - n_{C'}$	0.021011

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.78602
$n_{1970}$	1.97009	1.79293
$n_{1530}$	1.52958	1.80058
$n_{1129}$	1.12864	1.80800
$n_t$	1.01398	1.81069
$n_s$	0.85211	1.81568
$n_{A'}$	0.76819	1.81926
$n_r$	0.70652	1.82262
$n_C$	0.65627	<b>1.82605</b>
$n_{C'}$	0.64385	1.82701
$n_{\text{He-Ne}}$	0.6328	1.82792
$n_D$	0.58929	1.83202
$n_d$	0.58756	<b>1.83220</b>
$n_e$	0.54607	1.83713
$n_F$	0.48613	<b>1.84680</b>
$n_{F'}$	0.47999	1.84803
$n_{\text{He-Cd}}$	0.44157	1.85707
$n_g$	0.435835	<b>1.85866</b>
$n_h$	0.404656	1.86881
$n_i$	0.365015	1.88683
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	578
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	597
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	607
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	644
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	677
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	63
	(+100~+300 $^{\circ}\text{C}$ )	74
Thermal Conductivity (W/m·K)	<b>k</b>	0.839

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1148
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	440
Poisson's Ratio	$\sigma$	0.304
Knoop Hardness	<b>Hk</b>	640 [6]
Abrasion	<b>Aa</b>	73
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.93

Partial Dispersions	
$n_C - n_t$	0.015354
$n_C - n_{A'}$	0.006789
$n_d - n_C$	0.006153
$n_e - n_C$	0.011081
$n_g - n_d$	0.026462
$n_g - n_F$	0.011860
$n_h - n_g$	0.010152
$n_i - n_g$	0.028165
$n_{C'} - n_t$	0.016322
$n_{F'} - n_e$	0.010898
$n_i - n_{F'}$	0.038801

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0050
$\Delta\theta_{C,A'}$	0.0026
$\Delta\theta_{g,d}$	-0.0064
$\Delta\theta_{g,F}$	-0.0052
$\Delta\theta_{i,g}$	-0.0322

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.97595301	
A 2	2.83924985	E-1
A 3	1.35176368	
B 1	1.04276395	E-2
B 2	4.27708222	E-2
B 3	1.01453710	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	5.2
Phosphate Resistance	<b>PR</b>	1.2

Relative Partial Dispersions	
$\theta_{C,t}$	0.7398
$\theta_{C,A'}$	0.3271
$\theta_{d,C}$	0.2965
$\theta_{e,C}$	0.5339
$\theta_{g,d}$	1.2750
$\theta_{g,F}$	0.5714
$\theta_{h,g}$	0.4891
$\theta_{i,g}$	1.3570
$\theta'_{C,t}$	0.7768
$\theta'_{e,C'}$	0.4813
$\theta'_{F',e}$	0.5187
$\theta'_{i,F'}$	1.8467

Internal Transmittance			
$\lambda_{80}$	376	$\lambda_5$	340

CCI		
B	G	R
0.00	1.32	1.36

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.050	
350	0.260	
360	0.550	
365		
370	0.730	
380	0.840	
390	0.903	
400	0.936	
420	0.966	
440	0.978	
460	0.985	
480	0.990	
500	0.994	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.998	
1000	0.997	
1200	0.997	
1400	0.996	
1600	0.994	
1800	0.988	
2000	0.969	
2200	0.925	
2400	0.750	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	410				
Specific Gravity	<b>d</b>	4.65		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.4	6.4	6.4	6.7	7.1	7.9	8.7		
-20 ~ 0	5.4	6.4	6.5	6.7	7.1	7.9	8.8		
0 ~ 20	5.5	6.5	6.5	6.8	7.2	8.0	8.9		
20 ~ 40	5.5	6.5	6.5	6.8	7.2	8.1	9.0		
40 ~ 60	5.6	6.6	6.7	7.0	7.4	8.3	9.3		
60 ~ 80	5.8	6.8	6.9	7.2	7.6	8.6	9.6		

Refractive Index	$n_d$	<b>1.76450</b>	Abbe Number	$V_d$	<b>49.09</b>	Dispersion	$n_F - n_C$	<b>0.01557</b>
		1.764500			$V_e$		48.85	
	$n_e$	1.768208					$n_{F'} - n_{C'}$	0.015726

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.72404
$n_{1970}$	1.97009	1.73103
$n_{1530}$	1.52958	1.73852
$n_{1129}$	1.12864	1.74527
$n_t$	1.01398	1.74758
$n_s$	0.85211	1.75168
$n_{A'}$	0.76819	1.75453
$n_r$	0.70652	1.75716
$n_c$	0.65627	<b>1.75981</b>
$n_{c'}$	0.64385	1.76055
$n_{\text{He-Ne}}$	0.6328	1.76125
$n_D$	0.58929	1.76436
$n_d$	0.58756	<b>1.76450</b>
$n_e$	0.54607	1.76821
$n_F$	0.48613	<b>1.77538</b>
$n_{F'}$	0.47999	1.77628
$n_{\text{He-Cd}}$	0.44157	1.78284
$n_g$	0.435835	<b>1.78399</b>
$n_h$	0.404656	1.79120
$n_i$	0.365015	1.80360
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	578
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	599
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	611
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	644
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	676
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	57
	(+100~+300 $^{\circ}\text{C}$ )	71
Thermal Conductivity (W/m·K)	<b>k</b>	0.841

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1144
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	439
Poisson's Ratio	$\sigma$	0.301
Knoop Hardness	<b>Hk</b>	680 [7]
Abrasion	<b>Aa</b>	50
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.71

Partial Dispersions	
$n_c - n_t$	0.012232
$n_c - n_{A'}$	0.005282
$n_d - n_c$	0.004692
$n_e - n_c$	0.008400
$n_g - n_d$	0.019488
$n_g - n_F$	0.008608
$n_h - n_g$	0.007208
$n_i - n_g$	0.019614
$n_{c'} - n_t$	0.012975
$n_e - n_{c'}$	0.007657
$n_{F'} - n_e$	0.008069
$n_i - n_{F'}$	0.027325

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0085
$\Delta\theta_{c,A'}$	0.0038
$\Delta\theta_{g,d}$	-0.0113
$\Delta\theta_{g,F}$	-0.0092
$\Delta\theta_{i,g}$	-0.0544

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.26144128	
A 2	7.82115273	E-1
A 3	1.15823645	
B 1	5.72512582	E-3
B 2	2.19829752	E-2
B 3	8.80482200	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7855
$\theta_{c,A'}$	0.3392
$\theta_{d,c}$	0.3013
$\theta_{e,c}$	0.5394
$\theta_{g,d}$	1.2515
$\theta_{g,F}$	0.5528
$\theta_{h,g}$	0.4629
$\theta_{i,g}$	1.2596
$\theta'_{c,t}$	0.8251
$\theta'_{e,c'}$	0.4869
$\theta'_{F',e}$	0.5131
$\theta'_{i,F'}$	1.7376

Internal Transmittance			
$\lambda_{80}$	333	$\lambda_5$	274

CCI		
B	G	R
0.00	0.30	0.31

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.150	
290	0.320	
300	0.460	
310	0.590	
320	0.690	
330	0.780	
340	0.850	
350	0.900	
360	0.937	
365		
370	0.954	
380	0.973	
390	0.981	
400	0.986	
420	0.991	
440	0.993	
460	0.996	
480	0.997	
500	0.998	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.988	
2000	0.963	
2200	0.905	
2400	0.670	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	365				
Specific Gravity	<b>d</b>	4.29		$\lambda_5$	275				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	6.5	7.2	7.2	7.4	7.7	8.3	8.8		
-20 ~ 0	6.5	7.1	7.2	7.4	7.7	8.3	8.9		
0 ~ 20	6.4	7.1	7.2	7.4	7.7	8.3	8.9		
20 ~ 40	6.3	7.1	7.1	7.4	7.7	8.3	8.9		
40 ~ 60	6.5	7.2	7.3	7.5	7.8	8.5	9.1		
60 ~ 80	6.7	7.5	7.5	7.8	8.1	8.8	9.4		



Refractive Index	$n_d$	<b>1.86100</b>	Abbe Number	$V_d$	<b>37.10</b>	Dispersion	$n_F - n_C$	<b>0.02321</b>
	$n_e$	1.861000		$V_e$	36.85		$n_{F'} - n_{C'}$	0.023517

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.81215
$n_{1970}$	1.97009	1.81904
$n_{1530}$	1.52958	1.82677
$n_{1129}$	1.12864	1.83449
$n_t$	1.01398	1.83736
$n_s$	0.85211	1.84276
$n_{A'}$	0.76819	1.84667
$n_r$	0.70652	1.85038
$n_c$	0.65627	<b>1.85416</b>
$n_{c'}$	0.64385	1.85523
$n_{\text{He-Ne}}$	0.6328	1.85624
$n_D$	0.58929	1.86080
$n_d$	0.58756	<b>1.86100</b>
$n_e$	0.54607	1.86650
$n_F$	0.48613	<b>1.87737</b>
$n_{F'}$	0.47999	1.87875
$n_{\text{He-Cd}}$	0.44157	1.88899
$n_g$	0.435835	<b>1.89080</b>
$n_h$	0.404656	1.90238
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	560
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	583
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	593
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	628
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	664
Expansion Coefficient ( $\alpha$ )		
(-30~+70 $^{\circ}\text{C}$ )		62
(+100~+300 $^{\circ}\text{C}$ )		77
Thermal Conductivity (W/m·K)	<b>k</b>	0.817

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1121
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	430
Poisson's Ratio	$\sigma$	0.305
Knoop Hardness	<b>Hk</b>	660 [7]
Abrasion	<b>Aa</b>	77
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.71

Partial Dispersions	
$n_c - n_t$	0.016800
$n_c - n_{A'}$	0.007490
$n_d - n_c$	0.006839
$n_e - n_c$	0.012343
$n_g - n_d$	0.029797
$n_g - n_F$	0.013427
$n_h - n_g$	0.011584
$n_i - n_g$	
$n_{c'} - n_t$	0.017873
$n_e - n_{c'}$	0.011270
$n_{F'} - n_e$	0.012247
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0032
$\Delta\theta_{c,A'}$	0.0019
$\Delta\theta_{g,d}$	-0.0038
$\Delta\theta_{g,F}$	-0.0029
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	2.00621420	
A 2	3.47029888	E-1
A 3	1.41688382	
B 1	1.05499238	E-2
B 2	4.45845013	E-2
B 3	1.05995250	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7239
$\theta_{c,A'}$	0.3227
$\theta_{d,c}$	0.2947
$\theta_{e,c}$	0.5318
$\theta_{g,d}$	1.2839
$\theta_{g,F}$	0.5785
$\theta_{h,g}$	0.4991
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7600
$\theta'_{e,c'}$	0.4792
$\theta'_{F',e}$	0.5208
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R
0.00	1.80	1.88

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.060	
360	0.310	
365		
370	0.580	
380	0.750	
390	0.850	
400	0.908	
420	0.957	
440	0.975	
460	0.983	
480	0.989	
500	0.993	
550	0.998	
600	0.998	
650	0.999	
700	0.999	
800	0.999	
900	0.998	
1000	0.999	
1200	0.999	
1400	0.997	
1600	0.996	
1800	0.989	
2000	0.970	
2200	0.923	
2400	0.740	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$					390
Specific Gravity	<b>d</b>	4.89		$\lambda_5$					350
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	5.4	6.4	6.4	6.7	7.1	8.0	9.0		
-20 ~ 0	5.4	6.4	6.5	6.8	7.2	8.2	9.2		
0 ~ 20	5.4	6.5	6.5	6.9	7.3	8.3	9.4		
20 ~ 40	5.4	6.5	6.6	6.9	7.4	8.4	9.6		
40 ~ 60	5.5	6.7	6.7	7.1	7.6	8.7	9.9		
60 ~ 80	5.7	6.9	6.9	7.3	7.8	8.9	10.2		

Refractive Index	$n_d$	<b>1.69350</b>	Abbe Number	$V_d$	<b>53.18</b>	Dispersion	$n_F - n_C$	<b>0.01304</b>
		1.693500			$V_e$		52.93	
	$n_e$	1.696610					$n_{F'} - n_{C'}$	0.013160

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65737
$n_{1970}$	1.97009	1.66392
$n_{1530}$	1.52958	1.67089
$n_{1129}$	1.12864	1.67702
$n_t$	1.01398	1.67906
$n_s$	0.85211	1.68263
$n_{A'}$	0.76819	1.68507
$n_r$	0.70652	1.68731
$n_c$	0.65627	<b>1.68955</b>
$n_{c'}$	0.64385	1.69018
$n_{\text{He-Ne}}$	0.6328	1.69076
$n_D$	0.58929	1.69338
$n_d$	0.58756	<b>1.69350</b>
$n_e$	0.54607	1.69661
$n_F$	0.48613	<b>1.70259</b>
$n_{F'}$	0.47999	1.70334
$n_{\text{He-Cd}}$	0.44157	1.70879
$n_g$	0.435835	<b>1.70974</b>
$n_h$	0.404656	1.71570
$n_i$	0.365015	1.72592
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	503
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	522
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	534
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	575
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	615
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		76
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	92
Thermal Conductivity (W/m·K)	<b>k</b>	0.887

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1078
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	419
Poisson's Ratio	$\sigma$	0.285
Knoop Hardness	<b>Hk</b>	620 [6]
Abrasion	<b>Aa</b>	115
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Partial Dispersions	
$n_c - n_t$	0.010490
$n_c - n_{A'}$	0.004481
$n_d - n_c$	0.003949
$n_e - n_c$	0.007056
$n_g - n_d$	0.016239
$n_g - n_F$	0.007148
$n_h - n_g$	0.005962
$n_i - n_g$	0.016179
$n_{c'} - n_t$	0.011117
$n_e - n_{c'}$	0.006429
$n_{F'} - n_e$	0.006731
$n_i - n_{F'}$	0.022580

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0082
$\Delta\theta_{c,A'}$	0.0033
$\Delta\theta_{g,d}$	-0.0090
$\Delta\theta_{g,F}$	-0.0072
$\Delta\theta_{i,g}$	-0.0390

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.17776146	
A 2	6.34591345	E-1
A 3	1.20435649	
B 1	5.57618243	E-3
B 2	2.06821469	E-2
B 3	9.96322776	E1
1129 ~ 2325 nm		
A 1	1.17776146	
A 2	6.34591345	E-1
A 3	1.20435649	
B 1	5.57618243	E-3
B 2	2.06821469	E-2
B 3	9.96322776	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	53.2
Phosphate Resistance	<b>PR</b>	4.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8044
$\theta_{c,A'}$	0.3436
$\theta_{d,c}$	0.3028
$\theta_{e,c}$	0.5411
$\theta_{g,d}$	1.2453
$\theta_{g,F}$	0.5482
$\theta_{h,g}$	0.4572
$\theta_{i,g}$	1.2407
$\theta'_{c,t}$	0.8448
$\theta'_{e,c'}$	0.4885
$\theta'_{F',e}$	0.5115
$\theta'_{i,F'}$	1.7158

Internal Transmittance			
$\lambda_{80}$	346	$\lambda_5$	288

CCI		
B	G	R
0.00	0.35	0.32

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.010	
290	0.060	
300	0.150	
310	0.280	
320	0.450	
330	0.610	
340	0.740	
350	0.840	
360	0.913	
365		
370	0.949	
380	0.969	
390	0.979	
400	0.984	
420	0.989	
440	0.991	
460	0.993	
480	0.995	
500	0.997	
550	0.998	
600	0.997	
650	0.997	
700	0.998	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.996	
1600	0.995	
1800	0.988	
2000	0.969	
2200	0.918	
2400	0.720	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	360				
Specific Gravity	<b>d</b>	3.69		$\lambda_5$	285				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.5	3.0	3.0	3.1	3.3	3.8	4.2		
-20 ~ 0	2.5	3.0	3.0	3.2	3.4	3.8	4.3		
0 ~ 20	2.5	3.0	3.1	3.2	3.4	3.9	4.3		
20 ~ 40	2.5	3.1	3.1	3.3	3.5	4.0	4.4		
40 ~ 60	2.5	3.1	3.1	3.3	3.5	4.0	4.5		
60 ~ 80	2.5	3.1	3.2	3.3	3.6	4.1	4.6		

Refractive Index	$n_d$	<b>1.69304</b>	Abbe Number	$V_d$	<b>52.93</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.013093
		1.693040			$V_e$		52.70	
	$n_e$	1.696160						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65455
$n_{1970}$	1.97009	1.66189
$n_{1530}$	1.52958	1.66960
$n_{1129}$	1.12864	1.67621
$n_t$	1.01398	1.67835
$n_s$	0.85211	1.68203
$n_{A'}$	0.76819	1.68453
$n_r$	0.70652	1.68680
$n_c$	0.65627	<b>1.68906</b>
$n_{c'}$	0.64385	1.68970
$n_{\text{He-Ne}}$	0.6328	1.69029
$n_D$	0.58929	1.69292
$n_d$	0.58756	<b>1.69304</b>
$n_e$	0.54607	1.69616
$n_F$	0.48613	<b>1.70216</b>
$n_{F'}$	0.47999	1.70291
$n_{\text{He-Cd}}$	0.44157	1.70837
$n_g$	0.435835	<b>1.70932</b>
$n_h$	0.404656	1.71528
$n_i$	0.365015	1.72550
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.010719
$n_c - n_{A'}$	0.004537
$n_d - n_c$	0.003975
$n_e - n_c$	0.007095
$n_g - n_d$	0.016276
$n_g - n_F$	0.007158
$n_h - n_g$	0.005966
$n_i - n_g$	0.016189
$n_{c'} - n_t$	0.011351
$n_e - n_{c'}$	0.006463
$n_{F'} - n_e$	0.006747
$n_i - n_{F'}$	0.022598

Relative Partial Dispersions	
$\theta_{c,t}$	0.8187
$\theta_{c,A'}$	0.3465
$\theta_{d,c}$	0.3036
$\theta_{e,c}$	0.5419
$\theta_{g,d}$	1.2431
$\theta_{g,F}$	0.5467
$\theta_{h,g}$	0.4557
$\theta_{i,g}$	1.2365
$\theta'_{c,t}$	0.8593
$\theta'_{e,c'}$	0.4893
$\theta'_{F',e}$	0.5107
$\theta'_{i,F'}$	1.7107

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0237
$\Delta\theta_{c,A'}$	0.0065
$\Delta\theta_{g,d}$	-0.0117
$\Delta\theta_{g,F}$	-0.0091
$\Delta\theta_{i,g}$	-0.0453

Internal Transmittance			
$\lambda_{80}$	320	$\lambda_5$	

CCI		
B	G	R
0.00	0.14	0.14

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.07959634	
A 2	7.31872134	E-1
A 3	1.17111107	
B 1	4.70047543	E-3
B 2	1.98615758	E-2
B 3	8.70359900	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i 10 \text{ mm}}$	$\tau_{i 25 \text{ mm}}$
280	0.390	
290	0.530	
300	0.640	
310	0.730	
320	0.800	
330	0.870	
340	0.916	
350	0.948	
360	0.968	
365		
370	0.980	
380	0.987	
390	0.991	
400	0.993	
420	0.995	
440	0.997	
460	0.997	
480	0.998	
500	0.999	
550	0.999	
600	0.999	
650	0.999	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.990	
1600	0.991	
1800	0.979	
2000	0.949	
2200	0.850	
2400	0.590	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	494
Annealing Point (°C)	<b>AP</b>	515
Transformation Temperature (°C)	<b>Tg</b>	525
Yield Point (°C)	<b>At</b>	562
Softening Point (°C)	<b>SP</b>	596
Expansion Coefficient $\alpha$ (-30~+70°C)		54
(10 <sup>-7</sup> /°C)	(+100~+300°C)	72
Thermal Conductivity (W/m·K)	<b>k</b>	0.923

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	3
Acid Resistance (Surface Group)	<b>SR</b>	53.0
Phosphate Resistance	<b>PR</b>	4.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1103
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	427
Poisson's Ratio	$\sigma$	0.291
Knoop Hardness	<b>Hk</b>	650 [7]
Abrasion	<b>Aa</b>	79
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.44

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	3.66		$\lambda_5$					
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	6.6	7.1	7.2	7.3	7.5	8.0	8.5		
-20 ~ 0	6.7	7.3	7.3	7.5	7.7	8.2	8.7		
0 ~ 20	6.8	7.4	7.4	7.6	7.8	8.3	8.8		
20 ~ 40	6.8	7.4	7.5	7.7	7.8	8.4	9.0		
40 ~ 60	6.9	7.6	7.6	7.8	8.0	8.6	9.1		
60 ~ 80	7.0	7.7	7.7	7.9	8.2	8.7	9.3		

Refractive Index	$n_d$	<b>1.74320</b>	Abbe Number	$V_d$	<b>49.29</b>	Dispersion	$n_F - n_C$	<b>0.01507</b>
	$n_e$	1.743200		$V_e$	49.05		$n_{F'} - n_{C'}$	0.015077
		1.746790						0.015226

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.70409
$n_{1970}$	1.97009	1.71082
$n_{1530}$	1.52958	1.71804
$n_{1129}$	1.12864	1.72458
$n_t$	1.01398	1.72681
$n_s$	0.85211	1.73078
$n_{A'}$	0.76819	1.73354
$n_r$	0.70652	1.73609
$n_c$	0.65627	<b>1.73866</b>
$n_{c'}$	0.64385	1.73937
$n_{\text{He-Ne}}$	0.6328	1.74005
$n_D$	0.58929	1.74306
$n_d$	0.58756	<b>1.74320</b>
$n_e$	0.54607	1.74679
$n_F$	0.48613	<b>1.75373</b>
$n_{F'}$	0.47999	1.75460
$n_{\text{He-Cd}}$	0.44157	1.76096
$n_g$	0.435835	<b>1.76207</b>
$n_h$	0.404656	1.76905
$n_i$	0.365015	1.78108
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	511
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	533
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	541
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	581
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	623
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		74
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	92
Thermal Conductivity (W/m·K)	<b>k</b>	0.876

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1147
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	445
Poisson's Ratio	$\sigma$	0.289
Knoop Hardness	<b>Hk</b>	620 [6]
Abrasion	<b>Aa</b>	90
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	1.83

Partial Dispersions	
$n_C - n_t$	0.011847
$n_C - n_{A'}$	0.005115
$n_d - n_C$	0.004543
$n_e - n_C$	0.008133
$n_g - n_d$	0.018870
$n_g - n_F$	0.008336
$n_h - n_g$	0.006984
$n_i - n_g$	0.019016
$n_{C'} - n_t$	0.012567
$n_e - n_{C'}$	0.007413
$n_{F'} - n_e$	0.007813
$n_i - n_{F'}$	0.026483

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0079
$\Delta\theta_{C,A'}$	0.0037
$\Delta\theta_{g,d}$	-0.0108
$\Delta\theta_{g,F}$	-0.0088
$\Delta\theta_{i,g}$	-0.0510

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.47574184	
A 2	4.96132743	E-1
A 3	1.23796236	
B 1	7.36950000	E-3
B 2	2.51891746	E-2
B 3	9.80306651	E1
1129 ~ 2325 nm		
A 1	1.47574184	
A 2	4.96132743	E-1
A 3	1.23796236	
B 1	7.36950000	E-3
B 2	2.51891746	E-2
B 3	9.80306651	E1

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	
Acid Resistance (Surface Group)	<b>SR</b>	51.2
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.7858
$\theta_{C,A'}$	0.3393
$\theta_{d,C}$	0.3013
$\theta_{e,C}$	0.5394
$\theta_{g,d}$	1.2516
$\theta_{g,F}$	0.5529
$\theta_{h,g}$	0.4632
$\theta_{i,g}$	1.2613
$\theta'_{C,t}$	0.8254
$\theta'_{e,C'}$	0.4869
$\theta'_{F',e}$	0.5131
$\theta'_{i,F'}$	1.7393

Internal Transmittance			
$\lambda_{80}$	347	$\lambda_5$	308

CCI		
B	G	R
0.00	0.37	0.38

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.090	
320	0.330	
330	0.560	
340	0.720	
350	0.830	
360	0.904	
365		
370	0.944	
380	0.965	
390	0.977	
400	0.983	
420	0.988	
440	0.991	
460	0.993	
480	0.996	
500	0.997	
550	0.998	
600	0.998	
650	0.998	
700	0.999	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.997	
1800	0.991	
2000	0.974	
2200	0.936	
2400	0.750	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	370				
Specific Gravity	<b>d</b>	4.20		$\lambda_5$	310				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	3.3	3.9	3.9	4.1	4.3	4.8	5.3		
-20 ~ 0	3.3	3.9	3.9	4.1	4.3	4.9	5.4		
0 ~ 20	3.3	3.9	3.9	4.1	4.4	4.9	5.5		
20 ~ 40	3.2	3.9	4.0	4.2	4.4	5.0	5.6		
40 ~ 60	3.2	4.0	4.0	4.2	4.5	5.1	5.7		
60 ~ 80	3.2	4.0	4.0	4.2	4.5	5.1	5.7		

Refractive Index	$n_d$	<b>1.73077</b>	Abbe Number	$V_d$	<b>40.51</b>	Dispersion	$n_F - n_C$	<b>0.01804</b>
	$n_e$	1.730770		$V_e$	40.25		$n_{F'} - n_{C'}$	0.018040
		1.735050						0.018262

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.68805
$n_{1970}$	1.97009	1.69488
$n_{1530}$	1.52958	1.70237
$n_{1129}$	1.12864	1.70939
$n_t$	1.01398	1.71185
$n_s$	0.85211	1.71632
$n_{A'}$	0.76819	1.71948
$n_r$	0.70652	1.72243
$n_c$	0.65627	<b>1.72542</b>
$n_{c'}$	0.64385	1.72626
$n_{\text{He-Ne}}$	0.6328	1.72705
$n_D$	0.58929	1.73061
$n_d$	0.58756	<b>1.73077</b>
$n_e$	0.54607	1.73505
$n_F$	0.48613	<b>1.74346</b>
$n_{F'}$	0.47999	1.74452
$n_{\text{He-Cd}}$	0.44157	1.75240
$n_g$	0.435835	<b>1.75379</b>
$n_h$	0.404656	1.76267
$n_i$	0.365015	1.77858
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	461
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	489
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	497
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	529
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	574
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	86
	(+10~+300 $^{\circ}\text{C}$ )	105
Thermal Conductivity (W/m·K)	<b>k</b>	1.114

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	1133
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	445
Poisson's Ratio	$\sigma$	0.273
Knoop Hardness	<b>Hk</b>	630 [6]
Abrasion	<b>Aa</b>	118
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.03

Partial Dispersions	
$n_c - n_t$	0.013567
$n_c - n_{A'}$	0.005939
$n_d - n_c$	0.005354
$n_e - n_c$	0.009635
$n_g - n_d$	0.023019
$n_g - n_F$	0.010333
$n_h - n_g$	0.008885
$n_i - n_g$	0.024789
$n_{c'} - n_t$	0.014410
$n_e - n_{c'}$	0.008792
$n_{F'} - n_e$	0.009470
$n_i - n_{F'}$	0.034057

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0154
$\Delta\theta_{c,A'}$	0.0042
$\Delta\theta_{g,d}$	-0.0046
$\Delta\theta_{g,F}$	-0.0031
$\Delta\theta_{i,g}$	-0.0117

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.74038960	
A 2	1.76996917	E-1
A 3	1.76775413	
B 1	1.03398870	E-2
B 2	4.84822765	E-2
B 3	1.36671996	E2
1129 ~ 2325 nm		
A 1	1.74038960	
A 2	1.76996917	E-1
A 3	1.76775413	
B 1	1.03398870	E-2
B 2	4.84822765	E-2
B 3	1.36671996	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	3
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	52.2
Phosphate Resistance	<b>PR</b>	3.1

Relative Partial Dispersions	
$\theta_{c,t}$	0.7521
$\theta_{c,A'}$	0.3292
$\theta_{d,c}$	0.2968
$\theta_{e,c}$	0.5341
$\theta_{g,d}$	1.2760
$\theta_{g,F}$	0.5728
$\theta_{h,g}$	0.4925
$\theta_{i,g}$	1.3741
$\theta'_{c,t}$	0.7891
$\theta'_{e,c'}$	0.4814
$\theta'_{F',e}$	0.5186
$\theta'_{i,F'}$	1.8649

Internal Transmittance			
$\lambda_{80}$	379	$\lambda_5$	340

CCI		
B	G	R
0.00	1.88	1.91

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340	0.020	
350	0.220	
360	0.500	
365		
370	0.700	
380	0.810	
390	0.870	
400	0.912	
420	0.950	
440	0.964	
460	0.974	
480	0.982	
500	0.989	
550	0.996	
600	0.994	
650	0.995	
700	0.998	
800	0.998	
900	0.998	
1000		
1200		
1400		
1600		
1800		
2000		
2200		
2400		

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	410				
Specific Gravity	<b>d</b>	3.24		$\lambda_5$	340				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative (10 <sup>-6</sup> / $^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.1	2.8	2.8	3.0	3.3	4.0	4.7		
-20 ~ 0	2.1	2.8	2.8	3.1	3.4	4.0	4.8		
0 ~ 20	2.1	2.8	2.8	3.1	3.4	4.1	4.9		
20 ~ 40	2.0	2.8	2.9	3.1	3.4	4.2	5.0		
40 ~ 60	2.0	2.8	2.9	3.1	3.5	4.3	5.1		
60 ~ 80	2.0	2.8	2.9	3.1	3.5	4.3	5.3		

Refractive Index	$n_d$	<b>1.68948</b>	Abbe Number	$V_d$	<b>31.02</b>	Dispersion	$n_F - n_C$	<b>0.02223</b>
		1.689480			$V_e$		30.78	
	$n_e$	1.694731					$n_{F'} - n_{C'}$	0.022569

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.64632
$n_{1970}$	1.97009	1.65189
$n_{1530}$	1.52958	1.65832
$n_{1129}$	1.12864	1.66500
$n_t$	1.01398	1.66756
$n_s$	0.85211	1.67245
$n_{A'}$	0.76819	1.67605
$n_r$	0.70652	1.67949
$n_C$	0.65627	<b>1.68303</b>
$n_{C'}$	0.64385	1.68403
$n_{\text{He-Ne}}$	0.6328	1.68498
$n_D$	0.58929	1.68929
$n_d$	0.58756	<b>1.68948</b>
$n_e$	0.54607	1.69473
$n_F$	0.48613	<b>1.70525</b>
$n_{F'}$	0.47999	1.70660
$n_{\text{He-Cd}}$	0.44157	1.71674
$n_g$	0.435835	<b>1.71856</b>
$n_h$	0.404656	1.73034
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	453
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	484
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	504
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	539
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	582
Expansion Coefficient ( $\alpha$ )		
	(-30~+70 $^{\circ}\text{C}$ )	101
	(+100~+300 $^{\circ}\text{C}$ )	130
Thermal Conductivity (W/m·K)	<b>k</b>	1.020

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	845
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	337
Poisson's Ratio	$\sigma$	0.254
Knoop Hardness	<b>Hk</b>	530 [5]
Abrasion	<b>Aa</b>	197
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.62

Partial Dispersions	
$n_C - n_t$	0.015462
$n_C - n_{A'}$	0.006973
$n_d - n_C$	0.006454
$n_e - n_C$	0.011705
$n_g - n_d$	0.029076
$n_g - n_F$	0.013305
$n_h - n_g$	0.011789
$n_i - n_g$	
$n_{C'} - n_t$	0.016470
$n_e - n_{C'}$	0.010697
$n_{F'} - n_e$	0.011837
$n_i - n_{F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0035
$\Delta\theta_{C,A'}$	0.0003
$\Delta\theta_{g,d}$	0.0080
$\Delta\theta_{g,F}$	0.0074
$\Delta\theta_{i,g}$	

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.52780829	
A 2	2.32776367	E-1
A 3	1.71638781	
B 1	1.14135883	E-2
B 2	5.59068566	E-2
B 3	1.71511800	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.6957
$\theta_{C,A'}$	0.3137
$\theta_{d,C}$	0.2904
$\theta_{e,C}$	0.5267
$\theta_{g,d}$	1.3083
$\theta_{g,F}$	0.5987
$\theta_{h,g}$	0.5304
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7298
$\theta'_{e,C'}$	0.4740
$\theta'_{F',e}$	0.5260
$\theta'_{i,F'}$	

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R
0.00	1.29	1.27

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.010	
360	0.210	
365		
370	0.600	
380	0.820	
390	0.903	
400	0.940	
420	0.969	
440	0.979	
460	0.984	
480	0.988	
500	0.991	
550	0.997	
600	0.996	
650	0.995	
700	0.997	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.995	
1800	0.980	
2000	0.962	
2200	0.927	
2400	0.890	

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	40				
Specific Gravity	<b>d</b>	2.88		$\lambda_5$	36				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.1	-0.2	-0.2	0.1	0.5	1.4	2.4		
-20 ~ 0	-1.1	-0.3	-0.2	0.1	0.5	1.4	2.5		
0 ~ 20	-1.2	-0.3	-0.2	0.1	0.5	1.5	2.7		
20 ~ 40	-1.3	-0.4	-0.3	0.0	0.5	1.5	2.7		
40 ~ 60	-1.4	-0.4	-0.3	0.0	0.5	1.6	2.9		
60 ~ 80	-1.4	-0.4	-0.3	0.1	0.5	1.7	3.0		



Refractive Index	$n_d$	<b>1.69453</b>	Abbe Number	$V_d$	<b>30.66</b>	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	0.022656
		1.694530			$V_e$		30.42	
	$n_e$	1.699883						

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.65099
$n_{1970}$	1.97009	1.65653
$n_{1530}$	1.52958	1.66294
$n_{1129}$	1.12864	1.66966
$n_t$	1.01398	1.67224
$n_s$	0.85211	1.67720
$n_{A'}$	0.76819	1.68086
$n_r$	0.70652	1.68435
$n_c$	0.65627	<b>1.68796</b>
$n_{c'}$	0.64385	1.68898
$n_{\text{He-Ne}}$	0.6328	1.68995
$n_D$	0.58929	1.69433
$n_d$	0.58756	<b>1.69453</b>
$n_e$	0.54607	1.69988
$n_F$	0.48613	<b>1.71061</b>
$n_{F'}$	0.47999	1.71199
$n_{\text{He-Cd}}$	0.44157	1.72233
$n_g$	0.435835	<b>1.72419</b>
$n_h$	0.404656	1.73622
$n_i$	0.365015	
$n_{334}$	0.334148	
$n_{326}$	0.326106	

Partial Dispersions	
$n_c - n_t$	0.015711
$n_c - n_{A'}$	0.007096
$n_d - n_c$	0.006575
$n_e - n_c$	0.011928
$n_g - n_d$	0.029657
$n_g - n_F$	0.013576
$n_h - n_g$	0.012032
$n_i - n_g$	
$n_{c'} - n_t$	0.016737
$n_e - n_{c'}$	0.010902
$n_{F'} - n_e$	0.012107
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{c,t}$	0.6935
$\theta_{c,A'}$	0.3132
$\theta_{d,c}$	0.2902
$\theta_{e,c}$	0.5265
$\theta_{g,d}$	1.3090
$\theta_{g,F}$	0.5992
$\theta_{h,g}$	0.5311
$\theta_{i,g}$	
$\theta'_{c,t}$	0.7274
$\theta'_{e,c'}$	0.4738
$\theta'_{F',e}$	0.5262
$\theta'_{i,F'}$	

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0030
$\Delta\theta_{c,A'}$	0.0002
$\Delta\theta_{g,d}$	0.0080
$\Delta\theta_{g,F}$	0.0073
$\Delta\theta_{i,g}$	

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.53013396	
A 2	2.45362280	E-1
A 3	1.78233031	
B 1	1.14236857	E-2
B 2	5.55101852	E-2
B 3	1.79074300	E2
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320		
330		
340		
350	0.010	
360	0.210	
365		
370	0.600	
380	0.820	
390	0.903	
400	0.940	
420	0.969	
440	0.979	
460	0.984	
480	0.988	
500	0.991	
550	0.997	
600	0.996	
650	0.995	
700	0.997	
800	0.999	
900	0.999	
1000	0.999	
1200	0.999	
1400	0.998	
1600	0.995	
1800	0.980	
2000	0.962	
2200	0.927	
2400	0.890	

Thermal Properties		
Strain Point (°C)	<b>StP</b>	453
Annealing Point (°C)	<b>AP</b>	484
Transformation Temperature (°C)	<b>Tg</b>	504
Yield Point (°C)	<b>At</b>	539
Softening Point (°C)	<b>SP</b>	582
Expansion Coefficient $\alpha$ (-30~+70°C)		101
(10 <sup>-7</sup> /°C)	(+100~+300°C)	130
Thermal Conductivity (W/m·K)	<b>k</b>	1.020

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	845
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	337
Poisson's Ratio	$\sigma$	0.254
Knoop Hardness	<b>Hk</b>	530 [5]
Abrasion	<b>Aa</b>	197
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.62

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	400				
Specific Gravity	<b>d</b>	2.88		$\lambda_5$	355				
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.1	-0.2	-0.2	0.1	0.5	1.4	2.4		
-20 ~ 0	-1.1	-0.3	-0.2	0.1	0.5	1.4	2.5		
0 ~ 20	-1.2	-0.3	-0.2	0.1	0.5	1.5	2.7		
20 ~ 40	-1.3	-0.4	-0.3	0.0	0.5	1.5	2.7		
40 ~ 60	-1.4	-0.4	-0.3	0.0	0.5	1.6	2.9		
60 ~ 80	-1.4	-0.4	-0.3	0.1	0.5	1.7	3.0		

Refractive Index	$n_d$	<b>1.54814</b>	Abbe Number	$V_d$	<b>45.73</b>	Dispersion	$n_F - n_C$	<b>0.01199</b>
	$n_e$	1.548141		$V_e$	45.45		$n_{F'} - n_{C'}$	0.011986
		1.550989						0.012123

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.51892
$n_{1970}$	1.97009	1.52371
$n_{1530}$	1.52958	1.52892
$n_{1129}$	1.12864	1.53374
$n_t$	1.01398	1.53542
$n_s$	0.85211	1.53845
$n_{A'}$	0.76819	1.54058
$n_r$	0.70652	1.54256
$n_c$	0.65627	<b>1.54456</b>
$n_{c'}$	0.64385	1.54513
$n_{\text{He-Ne}}$	0.6328	1.54566
$n_D$	0.58929	1.54804
$n_d$	0.58756	<b>1.54814</b>
$n_e$	0.54607	1.55099
$n_F$	0.48613	<b>1.55655</b>
$n_{F'}$	0.47999	1.55725
$n_{\text{He-Cd}}$	0.44157	1.56242
$n_g$	0.435835	<b>1.56333</b>
$n_h$	0.404656	1.56911
$n_i$	0.365015	1.57931
$n_{334}$	0.334148	1.59092
$n_{326}$	0.326106	1.59476

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	361
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	396
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	406
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	453
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	567
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		93
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	106
Thermal Conductivity (W/m·K)	<b>k</b>	0.951

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	613
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	252
Poisson's Ratio	$\sigma$	0.217
Knoop Hardness	<b>Hk</b>	420 [4]
Abrasion	<b>Aa</b>	124
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.94

Partial Dispersions	
$n_C - n_t$	0.009141
$n_C - n_{A'}$	0.003985
$n_d - n_C$	0.003576
$n_e - n_C$	0.006424
$n_g - n_d$	0.015189
$n_g - n_F$	0.006779
$n_h - n_g$	0.005775
$n_i - n_g$	0.015976
$n_{C'} - n_t$	0.009705
$n_e - n_{C'}$	0.005860
$n_{F'} - n_e$	0.006263
$n_i - n_{F'}$	0.022054

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	0.0014
$\Delta\theta_{C,A'}$	0.0012
$\Delta\theta_{g,d}$	-0.0025
$\Delta\theta_{g,F}$	-0.0019
$\Delta\theta_{i,g}$	-0.0092

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.24772961	
A 2	1.01954909	E-1
A 3	3.50479619	E-1
B 1	9.26606623	E-3
B 2	4.51754311	E-2
B 3	4.50186705	E1
1129 ~ 2325 nm		
A 1	1.23587282	
A 2	1.14028206	E-1
A 3	9.21822183	E-1
B 1	8.98302029	E-3
B 2	4.39009973	E-2
B 3	1.14338154	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.1

Relative Partial Dispersions	
$\theta_{C,t}$	0.7626
$\theta_{C,A'}$	0.3325
$\theta_{d,C}$	0.2983
$\theta_{e,C}$	0.5360
$\theta_{g,d}$	1.2672
$\theta_{g,F}$	0.5656
$\theta_{h,g}$	0.4818
$\theta_{i,g}$	1.3329
$\theta'_{C,t}$	0.8005
$\theta'_{e,C'}$	0.4834
$\theta'_{F',e}$	0.5166
$\theta'_{i,F'}$	1.8192

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.290	0.040
320	0.800	0.570
330	0.954	0.880
340	0.988	0.970
350	0.995	0.988
360	0.997	0.993
365	0.997	0.994
370	0.998	0.995
380	0.998	0.996
390	0.999	0.997
400	0.999	0.998
420	0.999	0.998
440	0.999	0.998
460	0.999	0.998
480	0.999	0.998
500	0.999	0.999
550	0.999	0.999
600	0.999	0.999
650	0.999	0.999
700	0.999	0.999
800	0.999	0.999
900	0.999	0.999
1000	0.999	0.999
1200	0.999	0.999
1400	0.998	0.996
1600	0.996	0.991
1800	0.983	0.958
2000	0.960	0.903
2200	0.919	0.810
2400	0.880	0.730

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	32				
Specific Gravity	<b>d</b>	2.95		$\lambda_5$		30			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.2	1.6	1.7	1.8	2.0	2.5	3.0	4.5	
-20 ~ 0	1.2	1.7	1.7	1.9	2.1	2.6	3.1	4.7	
0 ~ 20	1.2	1.7	1.8	1.9	2.2	2.7	3.2	4.9	
20 ~ 40	1.3	1.8	1.8	2.0	2.2	2.8	3.3	5.0	
40 ~ 60	1.3	1.8	1.9	2.1	2.3	2.9	3.4	5.2	
60 ~ 80	1.3	1.9	1.9	2.1	2.4	2.9	3.5	5.4	

Refractive Index	$n_d$	<b>1.53172</b>	Abbe Number	$V_d$	<b>48.95</b>	Dispersion	$n_F - n_C$	<b>0.01086</b>
	$n_e$	1.531717		$V_e$	48.67		$n_{F'} - n_{C'}$	0.010862
		1.534301						0.010977

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.50343
$n_{1970}$	1.97009	1.50833
$n_{1530}$	1.52958	1.51361
$n_{1129}$	1.12864	1.51837
$n_t$	1.01398	1.51998
$n_s$	0.85211	1.52282
$n_{A'}$	0.76819	1.52480
$n_r$	0.70652	1.52663
$n_c$	0.65627	<b>1.52846</b>
$n_{c'}$	0.64385	1.52897
$n_{\text{He-Ne}}$	0.6328	1.52946
$n_D$	0.58929	1.53162
$n_d$	0.58756	<b>1.53172</b>
$n_e$	0.54607	1.53430
$n_F$	0.48613	<b>1.53932</b>
$n_{F'}$	0.47999	1.53995
$n_{\text{He-Cd}}$	0.44157	1.54459
$n_g$	0.435835	<b>1.54540</b>
$n_h$	0.404656	1.55056
$n_i$	0.365015	1.55959
$n_{334}$	0.334148	1.56978
$n_{326}$	0.326106	1.57312

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	398
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	436
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	453
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	501
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	637
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		83
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	90
Thermal Conductivity (W/m·K)	<b>k</b>	1.016

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	605
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	251
Poisson's Ratio	$\sigma$	0.205
Knoop Hardness	<b>Hk</b>	450 [5]
Abrasion	<b>Aa</b>	113
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	3.07

Partial Dispersions	
$n_c - n_t$	0.008482
$n_c - n_{A'}$	0.003660
$n_d - n_c$	0.003258
$n_e - n_c$	0.005842
$n_g - n_d$	0.136860
$n_g - n_F$	0.006082
$n_h - n_g$	0.005153
$n_i - n_g$	0.014190
$n_{c'} - n_t$	0.008998
$n_e - n_{c'}$	0.005326
$n_{F'} - n_e$	0.005651
$n_i - n_{F'}$	0.019641

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0046
$\Delta\theta_{c,A'}$	0.0018
$\Delta\theta_{g,d}$	-0.0031
$\Delta\theta_{g,F}$	-0.0024
$\Delta\theta_{i,g}$	-0.0087

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.22310794	
A 2	8.11217929	E-2
A 3	3.21400939	E-1
B 1	8.97805333	E-3
B 2	4.45756957	E-2
B 3	4.05962247	E1
1129 ~ 2325 nm		
A 1	1.20208094	
A 2	1.02467101	E-1
A 3	1.01797415	E-1
B 1	8.49251346	E-3
B 2	4.19306973	E-2
B 3	1.22687120	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	1.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7809
$\theta_{c,A'}$	0.3370
$\theta_{d,c}$	0.2999
$\theta_{e,c}$	0.5378
$\theta_{g,d}$	1.2600
$\theta_{g,F}$	0.5599
$\theta_{h,g}$	0.4744
$\theta_{i,g}$	1.3064
$\theta'_{c,t}$	0.8197
$\theta'_{e,c'}$	0.4852
$\theta'_{F',e}$	0.5148
$\theta'_{i,F'}$	1.7893

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.330	0.060
320	0.790	0.550
330	0.947	0.870
340	0.985	0.963
350	0.994	0.986
360	0.997	0.993
365	0.998	0.994
370	0.998	0.995
380	0.998	0.996
390	0.998	0.997
400	0.999	0.998
420	0.999	0.998
440	0.999	0.998
460	0.999	0.998
480	0.999	0.998
500	0.999	0.998
550	0.999	0.998
600	0.999	0.999
650	0.999	0.998
700	0.999	0.999
800	0.999	0.999
900	0.999	0.998
1000	0.998	0.996
1200	0.997	0.993
1400	0.996	0.990
1600	0.993	0.983
1800	0.973	0.934
2000	0.933	0.840
2200	0.860	0.690
2400	0.810	0.590

Other Properties									
Bubble Quality Group	<b>B</b>	B	Coloring	$\lambda_{80}/\lambda_{70}$	32				
Specific Gravity	<b>d</b>	2.79		$\lambda_5$	30				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.9	2.3	2.3	2.4	2.6	3.0	3.4	4.7	
-20 ~ 0	1.9	2.4	2.4	2.5	2.7	3.1	3.6	4.9	
0 ~ 20	2.0	2.5	2.5	2.6	2.8	3.3	3.7	5.1	
20 ~ 40	2.1	2.6	2.6	2.7	2.9	3.4	3.9	5.3	
40 ~ 60	2.1	2.7	2.7	2.9	3.1	3.5	4.0	5.6	
60 ~ 80	2.2	2.8	2.8	3.0	3.2	3.7	4.2	5.8	

Refractive Index	$n_d$	<b>1.58144</b> 1.581439	Abbe Number	$V_d$	<b>40.77</b> 40.49	Dispersion	$n_F - n_C$	<b>0.01426</b> 0.014263
		$n_e$		1.584824			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.54936
$n_{1970}$	1.97009	1.55423
$n_{1530}$	1.52958	1.55961
$n_{1129}$	1.12864	1.56480
$n_t$	1.01398	1.56667
$n_s$	0.85211	1.57011
$n_{A'}$	0.76819	1.57256
$n_r$	0.70652	1.57487
$n_c$	0.65627	<b>1.57722</b>
$n_{c'}$	0.64385	1.57788
$n_{\text{He-Ne}}$	0.6328	1.57850
$n_D$	0.58929	1.58131
$n_d$	0.58756	<b>1.58144</b>
$n_e$	0.54607	1.58482
$n_F$	0.48613	<b>1.59148</b>
$n_{F'}$	0.47999	1.59232
$n_{\text{He-Cd}}$	0.44157	1.59856
$n_g$	0.435835	<b>1.59967</b>
$n_h$	0.404656	1.60670
$n_i$	0.365015	1.61928
$n_{334}$	0.334148	1.63387
$n_{326}$	0.326106	1.63876

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	381
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	420
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	440
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	468
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	590
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		87
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	98
Thermal Conductivity (W/m·K)	<b>k</b>	0.899

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	585
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	240
Poisson's Ratio	$\sigma$	0.219
Knoop Hardness	<b>Hk</b>	460 [5]
Abrasion	<b>Aa</b>	130
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.99

Partial Dispersions	
$n_c - n_t$	0.010546
$n_c - n_{A'}$	0.004656
$n_d - n_c$	0.004222
$n_e - n_c$	0.007607
$n_g - n_d$	0.018226
$n_g - n_F$	0.008185
$n_h - n_g$	0.007038
$n_i - n_g$	0.019619
$n_{c'} - n_t$	0.011210
$n_e - n_{c'}$	0.006943
$n_{F'} - n_e$	0.007499
$n_i - n_{F'}$	0.026961

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0014
$\Delta\theta_{c,A'}$	0.0011
$\Delta\theta_{g,d}$	-0.0021
$\Delta\theta_{g,F}$	-0.0016
$\Delta\theta_{i,g}$	-0.0081

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.31960626	
A 2	1.23752633	E-1
A 3	2.10055351	E-1
B 1	1.01863415	E-2
B 2	4.83593508	E-2
B 3	2.73272029	E1
1129 ~ 2325 nm		
A 1	1.29915001	
A 2	1.44676555	E-1
A 3	1.00019303	E-1
B 1	9.67218844	E-3
B 2	4.65408008	E-2
B 3	1.20780522	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7394
$\theta_{c,A'}$	0.3264
$\theta_{d,c}$	0.2960
$\theta_{e,c}$	0.5333
$\theta_{g,d}$	1.2779
$\theta_{g,F}$	0.5739
$\theta_{h,g}$	0.4934
$\theta_{i,g}$	1.3755
$\theta'_{c,t}$	0.7762
$\theta'_{e,c'}$	0.4808
$\theta'_{F',e}$	0.5192
$\theta'_{i,F'}$	1.8668

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.010	
320	0.350	0.070
330	0.780	0.540
340	0.940	0.850
350	0.981	0.954
360	0.993	0.982
365	0.995	0.986
370	0.996	0.990
380	0.997	0.993
390	0.998	0.995
400	0.998	0.996
420	0.998	0.996
440	0.998	0.996
460	0.999	0.997
480	0.999	0.998
500	0.999	0.998
550	0.999	0.998
600	0.999	0.998
650	0.999	0.998
700	0.999	0.999
800	0.999	0.999
900	0.999	0.998
1000	0.998	0.996
1200	0.998	0.995
1400	0.996	0.990
1600	0.994	0.984
1800	0.979	0.948
2000	0.953	0.880
2200	0.905	0.780
2400	0.870	0.700

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	34				
Specific Gravity	<b>d</b>	3.23		$\lambda_5$		31			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.8	2.4	2.5	2.7	2.9	3.5	4.2	6.3	
-20 ~ 0	1.9	2.5	2.6	2.8	3.1	3.7	4.4	6.5	
0 ~ 20	1.9	2.6	2.7	2.9	3.2	3.8	4.5	6.8	
20 ~ 40	2.0	2.7	2.8	3.0	3.3	4.0	4.7	7.0	
40 ~ 60	2.1	2.8	2.9	3.1	3.4	4.1	4.9	7.3	
60 ~ 80	2.1	2.9	3.0	3.2	3.5	4.3	5.1	7.5	

Refractive Index	$n_d$	<b>1.56732</b>	Abbe Number	$V_d$	<b>42.86</b>	Dispersion	$n_F - n_C$	<b>0.01324</b>
	$n_e$	1.570466		$V_e$	42.58		$n_{F'} - n_{C'}$	0.013238
								0.013399

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.53658
$n_{1970}$	1.97009	1.54138
$n_{1530}$	1.52958	1.54668
$n_{1129}$	1.12864	1.55170
$n_t$	1.01398	1.55348
$n_s$	0.85211	1.55673
$n_{A'}$	0.76819	1.55904
$n_r$	0.70652	1.56120
$n_c$	0.65627	<b>1.56339</b>
$n_{c'}$	0.64385	1.56401
$n_{\text{He-Ne}}$	0.6328	1.56459
$n_D$	0.58929	1.56721
$n_d$	0.58756	<b>1.56732</b>
$n_e$	0.54607	1.57047
$n_F$	0.48613	<b>1.57663</b>
$n_{F'}$	0.47999	1.57741
$n_{\text{He-Cd}}$	0.44157	1.58317
$n_g$	0.435835	<b>1.58418</b>
$n_h$	0.404656	1.59065
$n_i$	0.365015	1.60217
$n_{334}$	0.334148	1.61543
$n_{326}$	0.326106	1.61986

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	380
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	418
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	432
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	471
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	591
Expansion Coefficient ( $\alpha$ )		89
	(-30~+70 $^{\circ}\text{C}$ )	
	(+10~+300 $^{\circ}\text{C}$ )	100
Thermal Conductivity (W/m·K)	<b>k</b>	0.912

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	589
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	242
Poisson's Ratio	$\sigma$	0.220
Knoop Hardness	<b>Hk</b>	420 [4]
Abrasion	<b>Aa</b>	136
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Partial Dispersions	
$n_c - n_t$	0.009910
$n_c - n_{A'}$	0.004353
$n_d - n_c$	0.003931
$n_e - n_c$	0.007075
$n_g - n_d$	0.168610
$n_g - n_F$	0.007554
$n_h - n_g$	0.006471
$n_i - n_g$	0.017986
$n_{c'} - n_t$	0.010529
$n_e - n_{c'}$	0.006456
$n_{F'} - n_e$	0.006943
$n_i - n_{F'}$	0.024760

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0008
$\Delta\theta_{c,A'}$	0.0010
$\Delta\theta_{g,d}$	-0.0020
$\Delta\theta_{g,F}$	-0.0015
$\Delta\theta_{i,g}$	-0.0074

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.29471773	
A 2	1.08880981	E-1
A 3	2.20322964	E-1
B 1	9.86579479	E-3
B 2	4.77568828	E-2
B 3	2.88509863	E1
1129 ~ 2325 nm		
A 1	1.27520167	
A 2	1.28823528	E-1
A 3	1.01138010	E-1
B 1	9.37656096	E-3
B 2	4.58001584	E-2
B 3	1.23589724	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7486
$\theta_{c,A'}$	0.3288
$\theta_{d,c}$	0.2969
$\theta_{e,c}$	0.5344
$\theta_{g,d}$	1.2737
$\theta_{g,F}$	0.5706
$\theta_{h,g}$	0.4888
$\theta_{i,g}$	1.3587
$\theta'_{c,t}$	0.7858
$\theta'_{e,c'}$	0.4818
$\theta'_{F',e}$	0.5182
$\theta'_{i,F'}$	1.8479

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310	0.040	
320	0.470	0.150
330	0.840	0.650
340	0.957	0.890
350	0.985	0.963
360	0.994	0.986
365	0.996	0.989
370	0.997	0.992
380	0.998	0.995
390	0.998	0.996
400	0.998	0.996
420	0.999	0.997
440	0.999	0.997
460	0.999	0.998
480	0.999	0.998
500	0.999	0.998
550	0.999	0.998
600	0.999	0.998
650	0.999	0.998
700	0.999	0.999
800	0.999	0.999
900	0.999	0.997
1000	0.998	0.994
1200	0.997	0.993
1400	0.996	0.990
1600	0.994	0.984
1800	0.979	0.948
2000	0.950	0.870
2200	0.890	0.760
2400	0.850	0.670

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	33				
Specific Gravity	<b>d</b>	3.10		$\lambda_5$		31			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	0.9	1.5	1.5	1.7	2.0	2.5	3.0	4.9	
-20 ~ 0	1.0	1.6	1.7	1.8	2.1	2.6	3.2	5.1	
0 ~ 20	1.1	1.7	1.8	2.0	2.2	2.8	3.4	5.4	
20 ~ 40	1.2	1.9	1.9	2.1	2.4	3.0	3.6	5.7	
40 ~ 60	1.3	2.0	2.0	2.2	2.5	3.1	3.8	5.9	
60 ~ 80	1.4	2.1	2.1	2.4	2.6	3.3	4.0	6.2	

Refractive Index	$n_d$	<b>1.58159</b>	Abbe Number	$V_d$	<b>40.86</b>	Dispersion	$n_F - n_C$	<b>0.01423</b>
	$n_e$	1.581591		$V_e$	40.58		$n_{F'} - n_{C'}$	0.014235
		1.584970						0.014415

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.54982
$n_{1970}$	1.97009	1.55460
$n_{1530}$	1.52958	1.55990
$n_{1129}$	1.12864	1.56502
$n_t$	1.01398	1.56687
$n_s$	0.85211	1.57029
$n_{A'}$	0.76819	1.57273
$n_r$	0.70652	1.57504
$n_c$	0.65627	<b>1.57738</b>
$n_{c'}$	0.64385	1.57804
$n_{\text{He-Ne}}$	0.6328	1.57866
$n_D$	0.58929	1.58147
$n_d$	0.58756	<b>1.58159</b>
$n_e$	0.54607	1.58497
$n_F$	0.48613	<b>1.59161</b>
$n_{F'}$	0.47999	1.59246
$n_{\text{He-Cd}}$	0.44157	1.59868
$n_g$	0.435835	<b>1.59979</b>
$n_h$	0.404656	1.60681
$n_i$	0.365015	1.61937
$n_{334}$	0.334148	1.63392
$n_{326}$	0.326106	1.63880

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	345
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	379
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	404
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	454
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	550
Expansion Coefficient ( $\alpha$ )		91
	(-30~+70 $^{\circ}\text{C}$ )	
	(+100~+300 $^{\circ}\text{C}$ )	107
Thermal Conductivity (W/m·K)	<b>k</b>	0.885

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	596
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	245
Poisson's Ratio	$\sigma$	0.217
Knoop Hardness	<b>Hk</b>	450 [5]
Abrasion	<b>Aa</b>	145
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.88

Partial Dispersions	
$n_c - n_t$	0.010505
$n_c - n_{A'}$	0.004644
$n_d - n_c$	0.004213
$n_e - n_c$	0.007591
$n_g - n_d$	0.018194
$n_g - n_F$	0.008172
$n_h - n_g$	0.007026
$n_i - n_g$	0.019583
$n_{c'} - n_t$	0.011167
$n_e - n_{c'}$	0.006929
$n_{F'} - n_e$	0.007486
$n_i - n_{F'}$	0.026913

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	-0.0004
$\Delta\theta_{c,A'}$	0.0008
$\Delta\theta_{g,d}$	-0.0018
$\Delta\theta_{g,F}$	-0.0013
$\Delta\theta_{i,g}$	-0.0072

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.31884698	
A 2	1.25014653	E-1
A 3	2.15794324	E-1
B 1	1.01474939	E-2
B 2	4.81636043	E-2
B 3	2.85517448	E1
1129 ~ 2325 nm		
A 1		
A 2		
A 3		
B 1		
B 2		
B 3		

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7380
$\theta_{c,A'}$	0.3262
$\theta_{d,c}$	0.2960
$\theta_{e,c}$	0.5333
$\theta_{g,d}$	1.2781
$\theta_{g,F}$	0.5741
$\theta_{h,g}$	0.4936
$\theta_{i,g}$	1.3757
$\theta'_{c,t}$	0.7747
$\theta'_{e,c'}$	0.4807
$\theta'_{F',e}$	0.5193
$\theta'_{i,F'}$	1.8670

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.470	0.420
330	0.850	0.730
340	0.963	0.916
350	0.989	0.975
360	0.996	0.990
365	0.997	0.993
370	0.998	0.995
380	0.999	0.997
390	0.999	0.998
400	0.999	0.998
420	0.999	0.999
440	0.999	0.999
460	0.999	0.999
480	0.999	0.999
500	0.999	0.999
550	0.999	0.999
600	0.999	0.999
650	0.999	0.999
700	0.999	0.999
800	0.999	0.999
900	0.999	0.999
1000	0.999	0.999
1200	0.999	0.999
1400	0.998	0.996
1600	0.996	0.990
1800	0.980	0.952
2000	0.955	0.890
2200	0.911	0.790
2400	0.880	0.720

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	335				
Specific Gravity	<b>d</b>	3.27		$\lambda_5$	310				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.0	1.7	1.7	1.9	2.2	2.8	3.4	5.5	
-20 ~ 0	1.0	1.7	1.7	1.9	2.2	2.8	3.5	5.7	
0 ~ 20	1.1	1.8	1.8	2.0	2.3	3.0	3.7	5.9	
20 ~ 40	1.1	1.9	1.9	2.1	2.4	3.1	3.8	6.1	
40 ~ 60	1.2	2.0	2.0	2.2	2.5	3.2	4.0	6.3	
60 ~ 80	1.4	2.1	2.2	2.4	2.7	3.4	4.2	6.6	



Refractive Index	$n_d$	<b>1.62004</b> 1.620041	Abbe Number	$V_d$	<b>36.27</b> 36.01	Dispersion	$n_F - n_C$	<b>0.01709</b> 0.017095
		$n_e$		1.624093			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.58471
$n_{1970}$	1.97009	1.58959
$n_{1530}$	1.52958	1.59510
$n_{1129}$	1.12864	1.60067
$n_t$	1.01398	1.60275
$n_s$	0.85211	1.60668
$n_{A'}$	0.76819	1.60953
$n_r$	0.70652	1.61225
$n_c$	0.65627	<b>1.61502</b>
$n_{c'}$	0.64385	1.61581
$n_{\text{He-Ne}}$	0.6328	1.61655
$n_D$	0.58929	1.61989
$n_d$	0.58756	<b>1.62004</b>
$n_e$	0.54607	1.62409
$n_F$	0.48613	<b>1.63211</b>
$n_{F'}$	0.47999	1.63314
$n_{\text{He-Cd}}$	0.44157	1.64072
$n_g$	0.435835	<b>1.64207</b>
$n_h$	0.404656	1.65071
$n_i$	0.365015	1.66635
$n_{334}$	0.334148	1.68482
$n_{326}$	0.326106	1.69111

Thermal Properties		
Strain Point. ( $^{\circ}\text{C}$ )	<b>StP</b>	385
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	418
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	436
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	470
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	580
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	86
	(+10~+300 $^{\circ}\text{C}$ )	97
Thermal Conductivity (W/m·K)	<b>k</b>	0.814

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	571
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	234
Poisson's Ratio	$\sigma$	0.223
Knoop Hardness	<b>Hk</b>	420 [4]
Abrasion	<b>Aa</b>	140
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Partial Dispersions	
$n_c - n_t$	0.012265
$n_c - n_{A'}$	0.005485
$n_d - n_c$	0.005022
$n_e - n_c$	0.009074
$n_g - n_d$	0.022030
$n_g - n_F$	0.009957
$n_h - n_g$	0.008640
$n_i - n_g$	0.024279
$n_{c'} - n_t$	0.013052
$n_e - n_{c'}$	0.008287
$n_{F'} - n_e$	0.009043
$n_i - n_{F'}$	0.033214

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0007
$\Delta\theta_{c,A'}$	0.0011
$\Delta\theta_{g,d}$	-0.0007
$\Delta\theta_{g,F}$	-0.0003
$\Delta\theta_{i,g}$	-0.0011

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.39446503	
A 2	1.59230985	E-1
A 3	2.45470216	E-1
B 1	1.10571872	E-2
B 2	5.07194882	E-2
B 3	3.14440142	E1
1129 ~ 2325 nm		
A 1	1.37920265	
A 2	1.74908080	E-1
A 3	9.72480533	E-1
B 1	1.06616552	E-2
B 2	4.96089256	E-2
B 3	1.16926659	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7175
$\theta_{c,A'}$	0.3209
$\theta_{d,c}$	0.2938
$\theta_{e,c}$	0.5308
$\theta_{g,d}$	1.2887
$\theta_{g,F}$	0.5825
$\theta_{h,g}$	0.5054
$\theta_{i,g}$	1.4202
$\theta'_{c,t}$	0.7531
$\theta'_{e,c'}$	0.4782
$\theta'_{F',e}$	0.5218
$\theta'_{i,F'}$	1.9166

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.040	
330	0.440	0.120
340	0.810	0.590
350	0.944	0.860
360	0.980	0.951
365	0.986	0.965
370	0.991	0.978
380	0.995	0.987
390	0.996	0.991
400	0.997	0.993
420	0.998	0.995
440	0.998	0.995
460	0.998	0.996
480	0.998	0.996
500	0.999	0.997
550	0.999	0.998
600	0.999	0.998
650	0.999	0.997
700	0.999	0.998
800	0.999	0.998
900	0.999	0.998
1000	0.998	0.995
1200	0.998	0.995
1400	0.996	0.990
1600	0.994	0.985
1800	0.980	0.951
2000	0.962	0.908
2200	0.921	0.810
2400	0.890	0.750

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	345				
Specific Gravity	<b>d</b>	3.61		$\lambda_5$	320				
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.1	2.9	3.0	3.3	3.6	4.4	5.3	8.2	
-20 ~ 0	2.3	3.1	3.1	3.5	3.8	4.6	5.5	8.6	
0 ~ 20	2.5	3.3	3.3	3.6	4.0	4.8	5.8	8.9	
20 ~ 40	2.5	3.4	3.5	3.8	4.2	5.1	6.0	9.3	
40 ~ 60	2.7	3.6	3.7	4.0	4.4	5.3	6.3	9.6	
60 ~ 80	2.9	3.8	3.8	4.2	4.6	5.5	6.6	10.0	

Refractive Index	$n_d$	<b>1.59551</b>	Abbe Number	$V_d$	<b>39.26</b>	Dispersion	$n_F - n_C$	<b>0.01517</b>
	$n_e$	1.595509		$V_e$	38.99		$n_{F'} - n_{C'}$	0.015169
		1.599108					$n_{F'} - n_{C'}$	0.015365

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.56224
$n_{1970}$	1.97009	1.56716
$n_{1530}$	1.52958	1.57263
$n_{1129}$	1.12864	1.57797
$n_t$	1.01398	1.57992
$n_s$	0.85211	1.58352
$n_{A'}$	0.76819	1.58611
$n_r$	0.70652	1.58855
$n_c$	0.65627	<b>1.59103</b>
$n_{c'}$	0.64385	1.59173
$n_{\text{He-Ne}}$	0.6328	1.59239
$n_D$	0.58929	1.59538
$n_d$	0.58756	<b>1.59551</b>
$n_e$	0.54607	1.59911
$n_F$	0.48613	<b>1.60620</b>
$n_{F'}$	0.47999	1.60710
$n_{\text{He-Cd}}$	0.44157	1.61377
$n_g$	0.435835	<b>1.61495</b>
$n_h$	0.404656	1.62249
$n_i$	0.365015	1.63604
$n_{334}$	0.334148	1.65185
$n_{326}$	0.326106	1.65718

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	390
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	426
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	445
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	485
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	590
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	85
	(+10~+300 $^{\circ}\text{C}$ )	96
Thermal Conductivity (W/m·K)	<b>k</b>	0.878

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	588
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	241
Poisson's Ratio	$\sigma$	0.222
Knoop Hardness	<b>Hk</b>	400 [4]
Abrasion	<b>Aa</b>	151
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.87

Partial Dispersions	
$n_c - n_t$	0.111090
$n_c - n_{A'}$	0.004923
$n_d - n_c$	0.004479
$n_e - n_c$	0.008078
$n_g - n_d$	0.019438
$n_g - n_F$	0.008748
$n_h - n_g$	0.007545
$n_i - n_g$	0.021090
$n_{c'} - n_t$	0.011813
$n_e - n_{c'}$	0.007374
$n_{F'} - n_e$	0.007991
$n_i - n_{F'}$	0.289380

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0014
$\Delta\theta_{c,A'}$	0.0011
$\Delta\theta_{g,d}$	-0.0018
$\Delta\theta_{g,F}$	-0.0012
$\Delta\theta_{i,g}$	-0.0060

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.35351322	
A 2	1.30212912	E-1
A 3	1.58337266	E-1
B 1	1.05624626	E-2
B 2	4.96606652	E-2
B 3	2.07965806	E1
1129 ~ 2325 nm		
A 1	1.33265695	
A 2	1.51642865	E-1
A 3	1.00238959	E-1
B 1	1.00208464	E-2
B 2	4.78779669	E-2
B 3	1.19439670	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	2
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	1
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7323
$\theta_{c,A'}$	0.3245
$\theta_{d,c}$	0.2953
$\theta_{e,c}$	0.5325
$\theta_{g,d}$	1.2814
$\theta_{g,F}$	0.5767
$\theta_{h,g}$	0.4974
$\theta_{i,g}$	1.3903
$\theta'_{c,t}$	0.7688
$\theta'_{e,c'}$	0.4799
$\theta'_{F',e}$	0.5201
$\theta'_{i,F'}$	1.8834

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.170	0.010
330	0.650	0.340
340	0.890	0.750
350	0.996	0.918
360	0.987	0.968
365	0.991	0.977
370	0.993	0.983
380	0.996	0.990
390	0.997	0.993
400	0.998	0.995
420	0.998	0.996
440	0.998	0.996
460	0.998	0.996
480	0.999	0.997
500	0.999	0.998
550	0.999	0.998
600	0.999	0.998
650	0.999	0.998
700	0.999	0.998
800	0.999	0.998
900	0.999	0.998
1000	0.998	0.995
1200	0.998	0.995
1400	0.995	0.988
1600	0.994	0.986
1800	0.981	0.953
2000	0.960	0.903
2200	0.916	0.800
2400	0.880	0.740

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	34				
Specific Gravity	<b>d</b>	3.36		$\lambda_5$		32			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	1.9	2.6	2.7	2.9	3.2	3.8	4.6	6.8	
-20 ~ 0	2.0	2.7	2.8	3.0	3.3	4.0	4.8	7.1	
0 ~ 20	2.1	2.9	2.9	3.2	3.5	4.2	5.0	7.4	
20 ~ 40	2.2	3.0	3.0	3.3	3.6	4.4	5.2	7.7	
40 ~ 60	2.3	3.1	3.2	3.4	3.8	4.5	5.4	8.0	
60 ~ 80	2.5	3.3	3.3	3.5	3.9	4.7	5.6	8.3	

Refractive Index	$n_d$	<b>1.59551</b> 1.595509	Abbe Number	$V_d$	<b>38.77</b> 38.50	Dispersion	$n_F - n_C$	<b>0.01537</b> 0.015361
		$n_e$		1.599153			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.56207
$n_{1970}$	1.97009	1.56696
$n_{1530}$	1.52958	1.57243
$n_{1129}$	1.12864	1.57779
$n_t$	1.01398	1.57975
$n_s$	0.85211	1.58338
$n_{A'}$	0.76819	1.58599
$n_r$	0.70652	1.58846
$n_c$	0.65627	<b>1.59097</b>
$n_{c'}$	0.64385	1.59169
$n_{\text{He-Ne}}$	0.6328	1.59236
$n_D$	0.58929	1.59537
$n_d$	0.58756	<b>1.59551</b>
$n_e$	0.54607	1.59915
$n_F$	0.48613	<b>1.60634</b>
$n_{F'}$	0.47999	1.60725
$n_{\text{He-Cd}}$	0.44157	1.61400
$n_g$	0.435835	<b>1.61520</b>
$n_h$	0.404656	1.62284
$n_i$	0.365015	1.63656
$n_{334}$	0.334148	1.65255
$n_{326}$	0.326106	1.65795

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	377
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	419
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	441
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	478
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	565
Expansion Coefficient $\alpha$ (-30~+70 $^{\circ}\text{C}$ )		88
(10-7 / $^{\circ}\text{C}$ )	(+100~+300 $^{\circ}\text{C}$ )	100
Thermal Conductivity (W/m·K)	<b>k</b>	0.865

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	598
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	244
Poisson's Ratio	$\sigma$	0.223
Knoop Hardness	<b>Hk</b>	410 [4]
Abrasion	<b>Aa</b>	132
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.79

Partial Dispersions	
$n_c - n_t$	0.011228
$n_c - n_{A'}$	0.004982
$n_d - n_c$	0.004534
$n_e - n_c$	0.008178
$n_g - n_d$	0.019689
$n_g - n_F$	0.008862
$n_h - n_g$	0.007643
$n_i - n_g$	0.021360
$n_{c'} - n_t$	0.011940
$n_e - n_{c'}$	0.007466
$n_{F'} - n_e$	0.008095
$n_i - n_{F'}$	0.029310

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0023
$\Delta\theta_{c,A'}$	0.0015
$\Delta\theta_{g,d}$	-0.0024
$\Delta\theta_{g,F}$	-0.0018
$\Delta\theta_{i,g}$	-0.0099

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.34660215	
A 2	1.36322343	E-1
A 3	1.83371587	E-1
B 1	1.06313733	E-2
B 2	4.91403013	E-2
B 3	2.39154655	E1
1129 ~ 2325 nm		
A 1	1.32558993	
A 2	1.57859674	E-1
A 3	1.03396744	E-1
B 1	1.01008566	E-2
B 2	4.74276657	E-2
B 3	1.23686168	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	1
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	1.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.7309
$\theta_{c,A'}$	0.3243
$\theta_{d,c}$	0.2952
$\theta_{e,c}$	0.5324
$\theta_{g,d}$	1.2818
$\theta_{g,F}$	0.5769
$\theta_{h,g}$	0.4976
$\theta_{i,g}$	1.3905
$\theta'_{c,t}$	0.7673
$\theta'_{e,c'}$	0.4798
$\theta'_{F',e}$	0.5202
$\theta'_{i,F'}$	1.8836

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280		
290		
300		
310		
320	0.220	0.020
330	0.680	0.390
340	0.912	0.790
350	0.975	0.939
360	0.990	0.976
365	0.993	0.983
370	0.995	0.988
380	0.997	0.992
390	0.998	0.994
400	0.998	0.995
420	0.998	0.996
440	0.999	0.997
460	0.999	0.997
480	0.999	0.998
500	0.999	0.998
550	0.999	0.998
600	0.999	0.998
650	0.999	0.998
700	0.999	0.998
800	0.999	0.998
900	0.999	0.998
1000	0.998	0.996
1200	0.998	0.996
1400	0.996	0.990
1600	0.994	0.986
1800	0.979	0.948
2000	0.956	0.890
2200	0.907	0.780
2400	0.870	0.710

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	34				
Specific Gravity	<b>d</b>	3.37		$\lambda_5$		31			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	2.5	3.1	3.2	3.4	3.7	4.4	5.2	7.6	
-20 ~ 0	2.5	3.3	3.3	3.5	3.9	4.6	5.4	7.9	
0 ~ 20	2.6	3.4	3.4	3.7	4.0	4.7	5.5	8.1	
20 ~ 40	2.7	3.5	3.5	3.8	4.1	4.9	5.7	8.4	
40 ~ 60	2.8	3.6	3.6	3.9	4.2	5.0	5.9	8.7	
60 ~ 80	2.8	3.7	3.7	4.0	4.3	5.2	6.1	8.9	

Refractive Index	$n_d$	<b>1.49700</b> 1.497003	Abbe Number	$V_d$	<b>81.14</b> 80.74	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	<b>0.00613</b> 0.006125 0.006174
		$n_e$		1.498466			$V_e$	

Refractive Indices		
	$\lambda$ (μm)	
$n_{2325}$	2.32542	1.47980
$n_{1970}$	1.97009	1.48286
$n_{1530}$	1.52958	1.48617
$n_{1129}$	1.12864	1.48913
$n_t$	1.01398	1.49011
$n_s$	0.85211	1.49182
$n_{A'}$	0.76819	1.49299
$n_r$	0.70652	1.49407
$n_c$	0.65627	<b>1.49513</b>
$n_{c'}$	0.64385	1.49543
$n_{He-Ne}$	0.6328	1.49571
$n_D$	0.58929	1.49695
$n_d$	0.58756	<b>1.49700</b>
$n_e$	0.54607	1.49847
$n_F$	0.48613	<b>1.50126</b>
$n_{F'}$	0.47999	1.50160
$n_{He-Cd}$	0.44157	1.50412
$n_g$	0.435835	<b>1.50455</b>
$n_h$	0.404656	1.50727
$n_i$	0.365015	1.51185
$n_{334}$	0.334148	1.51673
$n_{326}$	0.326106	1.51826

Partial Dispersions	
$n_C - n_t$	0.005027
$n_C - n_{A'}$	0.002139
$n_d - n_C$	0.001870
$n_e - n_C$	0.003333
$n_g - n_d$	0.007551
$n_g - n_F$	0.003296
$n_h - n_g$	0.002716
$n_i - n_g$	0.007300
$n_{C'} - n_t$	0.005325
$n_e - n_{C'}$	0.003035
$n_{F'} - n_e$	0.003139
$n_i - n_{F'}$	0.010249

Relative Partial Dispersions	
$\theta_{C,t}$	0.8207
$\theta_{C,A'}$	0.3492
$\theta_{d,C}$	0.3053
$\theta_{e,C}$	0.5442
$\theta_{g,d}$	1.2328
$\theta_{g,F}$	0.5381
$\theta_{h,g}$	0.4434
$\theta_{i,g}$	1.1918
$\theta'_{C,t}$	0.8625
$\theta'_{e,C'}$	0.4916
$\theta'_{F',e}$	0.5084
$\theta'_{i,F'}$	1.6600

Deviation of Relative Partial Dispersions	
$\Delta\theta_{C,t}$	-0.1067
$\Delta\theta_{C,A'}$	-0.0251
$\Delta\theta_{g,d}$	0.0366
$\Delta\theta_{g,F}$	0.0279
$\Delta\theta_{i,g}$	0.1462

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	1.14031443	
A 2	7.71496272	E-2
A 3	1.43721957	
B 1	5.95466872	E-3
B 2	2.23953953	E-2
B 3	2.74290057	E2
1129 ~ 2325 nm		
A 1	7.65663766	E-1
A 2	4.51879777	E-1
A 3	1.13199134	
B 1	3.48152533	E-3
B 2	1.28720516	E-2
B 3	2.14351131	E2

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280	0.510	0.190
290	0.670	0.370
300	0.800	0.580
310	0.890	0.750
320	0.943	0.860
330	0.971	0.930
340	0.986	0.966
350	0.994	0.985
360	0.996	0.991
365	0.997	0.993
370	0.998	0.995
380	0.999	0.997
390	0.999	0.998
400	0.999	0.998
420	0.999	0.998
440	0.999	0.998
460	0.999	0.998
480	0.999	0.998
500	0.999	0.999
550	0.999	0.999
600	0.999	0.999
650	0.999	0.998
700	0.999	0.999
800	0.999	0.999
900	0.999	0.998
1000	0.998	0.996
1200	0.998	0.996
1400	0.999	0.998
1600	0.999	0.997
1800	0.998	0.995
2000	0.998	0.995
2200	0.996	0.991
2400	0.995	0.987

Thermal Properties		
Strain Point (°C)	<b>StP</b>	
Annealing Point (°C)	<b>AP</b>	
Transformation Temperature (°C)	<b>Tg</b>	448
Yield Point (°C)	<b>At</b>	471
Softening Point (°C)	<b>SP</b>	
Expansion Coefficient $\alpha$ (-30~+70°C)		136
(10-7 / °C)	(+100~+300°C)	161
Thermal Conductivity (W/m·K)	<b>k</b>	0.780

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	1
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2~3
Acid Resistance (Surface Group)	<b>SR</b>	51.0
Phosphate Resistance	<b>PR</b>	4.2

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	716
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	275
Poisson's Ratio	$\sigma$	0.302
Knoop Hardness	<b>Hk</b>	380 [4]
Abrasion	<b>Aa</b>	476
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	310				
Specific Gravity	<b>d</b>	3.66		$\lambda_5$					
Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	$dn / dT$ relative (10 <sup>-6</sup> /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-6.4	-6.3	-6.3	-6.3	-6.2	-6.0	-5.9	-5.5	
-20 ~ 0	-6.7	-6.6	-6.6	-6.5	-6.4	-6.3	-6.1	-5.7	
0 ~ 20	-6.9	-6.8	-6.8	-6.7	-6.7	-6.5	-6.4	-5.9	
20 ~ 40	-7.2	-7.0	-7.0	-7.0	-6.9	-6.7	-6.6	-6.1	
40 ~ 60	-7.4	-7.3	-7.3	-7.2	-7.1	-7.0	-6.8	-6.3	
60 ~ 80	-7.7	-7.5	-7.5	-7.4	-7.4	-7.2	-7.0	-6.6	

Refractive Index	$n_d$	<b>1.48749</b> 1.487490	Abbe Number	$V_d$	<b>70.36</b> 70.17	Dispersion	$\frac{n_F - n_C}{n_F' - n_C'}$	<b>0.00693</b> 0.006929 0.006971
		$n_e$		1.489145			$V_e$	

Refractive Indices		
	$\lambda$ ( $\mu\text{m}$ )	
$n_{2325}$	2.32542	1.46218
$n_{1970}$	1.97009	1.46761
$n_{1530}$	1.52958	1.47323
$n_{1129}$	1.12864	1.47778
$n_t$	1.01398	1.47915
$n_s$	0.85211	1.48138
$n_{A'}$	0.76819	1.48282
$n_r$	0.70652	1.48410
$n_c$	0.65627	<b>1.48535</b>
$n_{c'}$	0.64385	1.48569
$n_{\text{He-Ne}}$	0.6328	1.48601
$n_D$	0.58929	1.48743
$n_d$	0.58756	<b>1.48749</b>
$n_e$	0.54607	1.48915
$n_F$	0.48613	<b>1.49228</b>
$n_{F'}$	0.47999	1.49266
$n_{\text{He-Cd}}$	0.44157	1.49546
$n_g$	0.435835	<b>1.49594</b>
$n_h$	0.404656	1.49896
$n_i$	0.365015	1.50404
$n_{334}$	0.334148	1.50946
$n_{326}$	0.326106	1.51116

Thermal Properties		
Strain Point ( $^{\circ}\text{C}$ )	<b>StP</b>	465
Annealing Point ( $^{\circ}\text{C}$ )	<b>AP</b>	502
Transformation Temperature ( $^{\circ}\text{C}$ )	<b>Tg</b>	500
Yield Point ( $^{\circ}\text{C}$ )	<b>At</b>	567
Softening Point ( $^{\circ}\text{C}$ )	<b>SP</b>	676
Expansion Coefficient $\alpha$	(-30~+70 $^{\circ}\text{C}$ )	89
	(+10~+300 $^{\circ}\text{C}$ )	97
Thermal Conductivity (W/m·K)	<b>k</b>	1.002

Mechanical Properties		
Young's Modulus (108N/m <sup>2</sup> )	<b>E</b>	622
Rigidity Modulus (108N/m <sup>2</sup> )	<b>G</b>	253
Poisson's Ratio	$\sigma$	0.229
Knoop Hardness	<b>Hk</b>	530 [5]
Abrasion	<b>Aa</b>	113
Photoelastic Constant (nm/cm/10 <sup>5</sup> Pa)	$\beta$	2.87

Partial Dispersions	
$n_c - n_t$	0.006201
$n_c - n_{A'}$	0.002523
$n_d - n_c$	0.002144
$n_e - n_c$	0.003799
$n_g - n_d$	0.008455
$n_g - n_F$	0.003670
$n_h - n_g$	0.003015
$n_i - n_g$	0.008099
$n_{c'} - n_t$	0.006546
$n_{e'} - n_{c'}$	0.003454
$n_{F'} - n_e$	0.003517
$n_i - n_{F'}$	0.011382

Deviation of Relative Partial Dispersions	
$\Delta\theta_{c,t}$	0.0181
$\Delta\theta_{c,A'}$	0.0029
$\Delta\theta_{g,d}$	0.0016
$\Delta\theta_{g,F}$	0.0021
$\Delta\theta_{i,g}$	0.0331

Constants of Dispersion Formula		
326 ~ 1129 nm		
A 1	9.77409944	E-1
A 2	2.10950834	E-1
A 3	1.37142848	
B 1	5.57649364	E-3
B 2	1.77000313	E-2
B 3	1.49211443	E2
1129 ~ 2325 nm		
A 1	8.79731455	E-1
A 2	3.08634219	E-1
A 3	1.02136885	
B 1	4.90947559	E-3
B 2	1.57419667	E-2
B 3	1.11412218	E2

Chemical Properties		
Water Resistance (Powder Group)	<b>RW(P)</b>	3
Acid Resistance (Powder Group)	<b>RA(P)</b>	4
Weathering Resistance (Surface Group)	<b>W(S)</b>	2
Acid Resistance (Surface Group)	<b>SR</b>	3.0
Phosphate Resistance	<b>PR</b>	2.0

Relative Partial Dispersions	
$\theta_{c,t}$	0.8949
$\theta_{c,A'}$	0.3641
$\theta_{d,c}$	0.3094
$\theta_{e,c}$	0.5483
$\theta_{g,d}$	1.2202
$\theta_{g,F}$	0.5297
$\theta_{h,g}$	0.4351
$\theta_{i,g}$	1.1689
$\theta'_{c,t}$	0.9390
$\theta'_{e,c'}$	0.4955
$\theta'_{F',e}$	0.5045
$\theta'_{i,F'}$	1.6328

Internal Transmittance			
$\lambda_{80}$		$\lambda_5$	

CCI		
B	G	R

Internal Transmittance		
$\lambda$ (nm)	$\tau_{i10\text{ mm}}$	$\tau_{i25\text{ mm}}$
280	0.190	0.010
290	0.610	0.290
300	0.860	0.680
310	0.954	0.890
320	0.984	0.961
330	0.993	0.983
340	0.997	0.993
350	0.998	0.995
360	0.998	0.996
365	0.999	0.997
370	0.999	0.998
380	0.999	0.998
390	0.999	0.998
400	0.999	0.999
420	0.999	0.999
440	0.999	0.999
460	0.999	0.999
480	0.999	0.999
500	0.999	0.999
550	0.999	0.999
600	0.999	0.999
650	0.999	0.998
700	0.999	0.999
800	0.999	0.999
900	0.999	0.997
1000	0.998	0.994
1200	0.997	0.992
1400	0.981	0.952
1600	0.991	0.977
1800	0.983	0.958
2000	0.968	0.921
2200	0.860	0.700
2400	0.850	0.670

Other Properties									
Bubble Quality Group	<b>B</b>		Coloring	$\lambda_{80}/\lambda_{70}$	30				
Specific Gravity	<b>d</b>	2.46		$\lambda_5$		27			
Temperature Coefficients of Refractive Index									
Range of Temperature ( $^{\circ}\text{C}$ )	$dn / dT$ relative ( $10^{-6}/^{\circ}\text{C}$ )								
	t	C'	He-Ne	D	e	F'	g	i	
-40 ~ -20	-1.2	-1.2	-1.2	-1.1	-1.1	-0.9	-0.7	-0.3	
-20 ~ 0	-1.2	-1.1	-1.1	-1.0	-1.0	-0.8	-0.6	-0.2	
0 ~ 20	-1.2	-1.0	-1.0	-0.9	-0.8	-0.7	-0.5		
20 ~ 40	-1.1	-0.9	-0.9	-0.8	-0.7	-0.6	-0.4	0.1	
40 ~ 60	-1.0	-0.8	-0.8	-0.7	-0.6	-0.5	-0.3	0.3	
60 ~ 80	-1.0	-0.7	-0.7	-0.6	-0.5	-0.3	-0.1	0.4	