OHARA GmbH
Im Langgewann 4
D-65719 Hofheim

Tel. +49 6192 9650 50
Fax +49 6192 9650 51
eMail info@ohara-gmbh.com
Web www.ohara-gmbh.com

$\theta_{g,F}$ - ν_d Diagram Optical Glass



	θ C,t	θ C,A'	θ g,d	θ g,F	θ h,g	Π d
NSL7	0.8305	0.3492	1.2391	0.5436	1.2185	60.49
PBM2	0.7168	0.3198	1.2894	0.5828	1.4214	36.26

*NSL7 and PBM2 are not among the recommended glass types. Considering that standard practice for showing anomalous dispersion has used these two glass types, we have decided to keep using these two glass types as our normal glass points.

Date: 09/2008