

Refractive Index	n_d	1,59551 1,595509	Abbe Number	ν_d	38,77	Dispersion	$n_F - n_C$	0,015361
Refractive Index	n_e	1,599153	Abbe Number	ν_e	38,50	Dispersion	$n_F - n_{C'}$	0,015561

Refractive Indices		
$\lambda(\mu m)$		
n_{2325}	2.32542	1,56207
n_{1970}	1.97009	1,56696
n_{1530}	1.52958	1,57243
n_{1129}	1.12864	1,57779
n_t	1.01398	1,57975
n_s	0.85211	1,58338
$n_{A'}$	0.76819	1,58599
n_r	0.70652	1,58846
n_C	0.65627	1,59097
$n_{C'}$	0.64385	1,59169
n_{He-Ne}	0.6328	1,59236
n_D	0.58929	1,59537
n_d	0.58756	1,59551
n_e	0.54607	1,59915
n_F	0.48613	1,60634
$n_{F'}$	0.47999	1,60725
n_{He-Cd}	0.44157	1,61400
n_g	0.435835	1,61520
n_h	0.404656	1,62284
n_i	0.365015	1,63656
n_{334}	0.334148	1,65255
N_{326}	0.326106	1,65795

Constants of Dispersion Formula	
A_1	1,34660215E+00
A_2	1,36322343E-01
A_3	1,83371587E-01
B_1	1,06313733E-02
B_2	4,91403013E-02
B_3	2,39154655E+01

Chemical Properties	
Water Resistance (Powder) Group RW(P)	1
Acid Resistance (Powder) Group RA(P)	1
Weathering Resistance (Surface) Group	2~3
Acid Resistance (Surface) Group SR	1.0
Phosphate Resistance PR	2.0

Mechanical Properties	
Young's Modulus E ($10^9 N/m^2$)	59,8
Rigidity Modulus G ($10^9 N/m^2$)	24,4
Poisson's Ratio σ	0,223
Knoop Hardness Hk [Class]	420 4
Abrasion Aa	138
Photoelastic Constant β (nm/cm/ $10^5 Pa$)	2,78

Temperature Coefficients of Refractive Index								
Range of (°C)	dn/dT relative ($10^{-6}/^{\circ}C$)							
	t	C'	He-Ne	D	e	F'	g	i
-40~-20	2,5	3,1	3,2	3,4	3,7	4,4	5,2	7,6
-20~0	2,5	3,3	3,3	3,5	3,9	4,6	5,4	7,9
0~20	2,6	3,4	3,4	3,7	4,0	4,7	5,5	8,1
20~40	2,7	3,5	3,5	3,8	4,1	4,9	5,7	8,4
40~60	2,8	3,6	3,6	3,9	4,2	5,0	5,9	8,7
60~80	2,8	3,7	3,7	4,0	4,3	5,2	6,1	8,9

Partial Dispersions	
$n_C - n_t$	0,011228
$n_C - n_{A'}$	0,004982
$n_d - n_C$	0,004534
$n_e - n_C$	0,008178
$n_g - n_d$	0,019689
$n_g - n_F$	0,008862
$n_h - n_g$	0,007643
$n_i - n_g$	0,021360
$n_{C'} - n_t$	0,011940
$n_e - n_{C'}$	0,007466
$n_F - n_e$	0,008095
$n_i - n_F$	0,029310

Relative Partial Dispersion	
$\theta_{C,t}$	0,7309
$\theta_{C,A'}$	0,3243
$\theta_{d,C}$	0,2952
$\theta_{e,C}$	0,5324
$\theta_{g,d}$	1,2818
$\theta_{g,F}$	0,5769
$\theta_{h,g}$	0,4976
$\theta_{i,g}$	1,3905
$\theta'_{C,t}$	0,7673
$\theta'_{e,C'}$	0,4798
$\theta'_{F,e}$	0,5202
$\theta'_{i,F'}$	1,8836

Deviation of Relative Dispersions	
$\Delta \theta_{C,t}$	0,0023
$\Delta \theta_{C,A'}$	0,0015
$\Delta \theta_{g,d}$	-0,0024
$\Delta \theta_{g,F}$	-0,0018
$\Delta \theta_{i,g}$	-0,0099

Thermal Properties	
Strain Point STP (°C)	377
Annealing Point AP (°C)	419
Transformation Temperature Tg (°C)	442
Yield Point At (°C)	485
Softening Point SP (°C)	565
Expansion Coefficients (-30~+70°C)	89
α ($10^{-7}/^{\circ}C$) (+100~+300°C)	101
Thermal Conductivity k (W/m·K)	0,865

Coloring			
λ_{80}	340	λ_5	315
λ_{70}			

Internal Transmittance			
$\lambda_{0.80}$	335	$\lambda_{0.05}$	316

CCI		
B	G	R
0,00	0,02	0,02

Internal Transmittance		
$\lambda(nm)$	τ 10mm	T 25mm
240		
250		
260		
270		
280		
290		
300		
310		
320	0,22	0,02
330	0,68	0,39
340	0,912	0,79
350	0,975	0,939
360	0,990	0,976
365	0,993	0,983
370	0,995	0,988
380	0,997	0,992
390	0,998	0,994
400	0,998	0,995
420	0,998	0,996
440	0,999	0,997
460	0,999	0,997
480	0,999	0,998
500	0,999	0,998
550	0,999	0,998
600	0,999	0,998
650	0,999	0,998
700	0,999	0,998
800	0,999	0,998
900	0,999	0,998
1000	0,998	0,996
1200	0,998	0,996
1400	0,996	0,990
1600	0,994	0,986
1800	0,979	0,948
2000	0,956	0,89
2200	0,907	0,78
2400	0,87	0,71

Other Properties	
Density d	3,37