

Refractive Index	n_d	1,60562 1,605620	Abbe Number	ν_d	43,70	Dispersion	$n_F - n_C$	0,013857
Refractive Index	n_e	1,608909	Abbe Number	ν_e	43,41	Dispersion	$n_F - n_{C'}$	0,014026

Refractive Indices		
$\lambda(\mu m)$		
n_{2325}	2.32542	1,57351
n_{1970}	1.97009	1,57850
n_{1530}	1.52958	1,58402
n_{1129}	1.12864	1,58926
n_t	1.01398	1,59113
n_s	0.85211	1,59453
$n_{A'}$	0.76819	1,59695
n_r	0.70652	1,59921
n_C	0.65627	1,60151
$n_{C'}$	0.64385	1,60215
n_{He-Ne}	0.6328	1,60276
n_D	0.58929	1,60550
n_d	0.58756	1,60562
n_e	0.54607	1,60891
n_F	0.48613	1,61536
$n_{F'}$	0.47999	1,61618
n_{He-Cd}	0.44157	1,62222
n_g	0.435835	1,62329
n_h	0.404656	1,63010
n_i	0.365015	1,64228

Constants of Dispersion Formula	
A ₁	1,41059317E+00
A ₂	1,11201306E-01
A ₃	1,34148939E+00
B ₁	9,63312192E-03
B ₂	4,98778210E-02
B ₃	1,52237696E+02

Chemical Properties	
Water Resistance (Powder) Group RW(P)	1
Acid Resistance (Powder) Group RA(P)	1
Weathering Resistance (Surface) Group	1~2
Acid Resistance (Surface) Group SR	1.0
Phosphate Resistance PR	1.0

Mechanical Properties	
Young's Modulus E (10 ⁹ N/m ²)	76,2
Rigidity Modulus G (10 ⁹ N/m ²)	30,6
Poisson's Ratio σ	0,244
Knoop Hardness Hk [Class]	530 5
Abrasion Aa	159
Photoelastic Constant β (nm/cm/10 ⁵ Pa)	2,41

Partial Dispersions	
$n_C - n_t$	0,010380
$n_C - n_{A'}$	0,004557
$n_d - n_C$	0,004113
$n_e - n_C$	0,007402
$n_g - n_d$	0,017671
$n_g - n_F$	0,007927
$n_h - n_g$	0,006811
$n_i - n_g$	0,018992
$n_{C'} - n_t$	0,011028
$n_e - n_{C'}$	0,006754
$n_F - n_e$	0,007272
$n_i - n_F$	0,026102

Relative Partial Dispersion	
$\theta_{C,t}$	0,7491
$\theta_{C,A'}$	0,3289
$\theta_{d,C}$	0,2968
$\theta_{e,C}$	0,5342
$\theta_{g,d}$	1,2752
$\theta_{g,F}$	0,5721
$\theta_{h,g}$	0,4915
$\theta_{i,g}$	1,3706
$\theta'_{C,t}$	0,7863
$\theta'_{e,C'}$	0,4815
$\theta'_{F,e}$	0,5185
$\theta'_{i,F'}$	1,8610

Deviation of Relative Dispersions	
$\Delta \theta_{C,t}$	-0,0026
$\Delta \theta_{C,A'}$	0,0001
$\Delta \theta_{g,d}$	0,0012
$\Delta \theta_{g,F}$	0,0013
$\Delta \theta_{i,g}$	0,0115

Thermal Properties	
Strain Point STP (°C)	548
Annealing Point AP (°C)	577
Transformation Temperature Tg (°C)	599
Yield Point At (°C)	641
Softening Point SP (°C)	722
Expansion Coefficients (-30~+70°C)	84
α (10 ⁻⁷ /°C) (+100~+300°C)	97
Thermal Conductivity k (W/m·K)	0,931

Coloring			
λ_{80}	380	λ_5	345
λ_{70}			

Internal Transmittance			
$\lambda_{0.80}$	375	$\lambda_{0.05}$	350

CCI		
B	G	R
0,00	0,69	0,65

Internal Transmittance	
$\lambda(nm)$	τ 10mm
280	
290	
300	
310	
320	
330	
340	
350	0,06
360	0,41
370	0,72
380	0,87
390	0,938
400	0,965
420	0,986
440	0,991
460	0,991
480	0,993
500	0,995
550	0,998
600	0,997
650	0,996
700	0,997
800	0,999
900	0,998
1000	0,998
1200	0,998
1400	0,995
1600	0,994
1800	0,980
2000	0,962
2200	0,919
2400	0,89

Other Properties	
Density d	2,91

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dT relative (10 ⁻⁶ /°C)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	0,6	1,0	1,0	1,2	1,4	1,9	2,4
-20~0	0,7	1,1	1,1	1,3	1,5	2,0	2,6
0~20	0,7	1,1	1,2	1,3	1,6	2,1	2,7
20~40	0,8	1,2	1,2	1,4	1,7	2,2	2,9
40~60	0,8	1,3	1,3	1,5	1,8	2,4	3,0
60~80	0,9	1,4	1,4	1,6	1,9	2,5	3,2