

Refractive Index	n_d	1,62299 1,622992	Abbe Number	ν_d	58,16	Dispersion	n_F-n_C	0,010711
Refractive Index	n_e	1,625545	Abbe Number	ν_e	57,89	Dispersion	$n_F-n_{C'}$	0,010805

Refractive Indices		
$\lambda(\mu m)$		
n_{2325}	2.32542	1,59236
n_{1970}	1.97009	1,59797
n_{1530}	1.52958	1,60399
n_{1129}	1.12864	1,60927
n_t	1.01398	1,61100
n_s	0.85211	1,61399
$n_{A'}$	0.76819	1,61603
n_r	0.70652	1,61789
n_C	0.65627	1,61974
$n_{C'}$	0.64385	1,62026
n_{He-Ne}	0.6328	1,62074
n_D	0.58929	1,62290
n_d	0.58756	1,62299
n_e	0.54607	1,62555
n_F	0.48613	1,63045
$n_{F'}$	0.47999	1,63106
n_{He-Cd}	0.44157	1,63552
n_g	0.435835	1,63630
n_h	0.404656	1,64116
n_i	0.365015	1,64948

Constants of Dispersion Formula	
A ₁	9,53128328E-01
A ₂	6,37613977E-01
A ₃	1,65245647E+00
B ₁	3,87638985E-03
B ₂	1,85094632E-02
B ₃	1,59442367E+02

Chemical Properties	
Water Resistance (Powder) Group RW(P)	2
Acid Resistance (Powder) Group RA(P)	4
Weathering Resistance (Surface) Group	2~3
Acid Resistance (Surface) Group SR	52.2
Phosphate Resistance PR	3.2

Mechanical Properties	
Young's Modulus E (10 ⁹ N/m ²)	85,4
Rigidity Modulus G (10 ⁹ N/m ²)	33,8
Poisson's Ratio σ	0,265
Knoop Hardness Hk [Class]	560 6
Abrasion Aa	150
Photoelastic Constant β (nm/cm/10 ⁵ Pa)	1,80

Partial Dispersions	
n_C-n_t	0,008741
$n_C-n_{A'}$	0,003709
n_d-n_C	0,003253
n_e-n_C	0,005806
n_g-n_d	0,013304
n_g-n_F	0,005846
n_h-n_g	0,004866
n_i-n_g	0,013186
$n_{C'}-n_t$	0,009259
$n_e-n_{C'}$	0,005288
$n_{F'}-n_e$	0,005517
$n_i-n_{F'}$	0,018420

Relative Partial Dispersion	
$\theta_{C,t}$	0,8161
$\theta_{C,A'}$	0,3463
$\theta_{d,C}$	0,3037
$\theta_{e,C}$	0,5421
$\theta_{g,d}$	1,2421
$\theta_{g,F}$	0,5458
$\theta_{h,g}$	0,4543
$\theta_{i,g}$	1,2311
$\theta'_{C,t}$	0,8569
$\theta'_{e,C'}$	0,4894
$\theta'_{F,e}$	0,5106
$\theta'_{i,F'}$	1,7048

Deviation of Relative Dispersions	
$\Delta \theta_{C,t}$	-0,0035
$\Delta \theta_{C,A'}$	-0,0001
$\Delta \theta_{g,d}$	-0,0018
$\Delta \theta_{g,F}$	-0,0016
$\Delta \theta_{i,g}$	-0,0069

Thermal Properties	
Strain Point STP (°C)	615
Annealing Point AP (°C)	639
Transformation Temperature Tg (°C)	658
Yield Point At (°C)	685
Softening Point SP (°C)	746
Expansion Coefficients (-30~+70°C)	65
α (10 ⁻⁷ /°C) (+100~+300°C)	78
Thermal Conductivity k (W/m·K)	0,845

Coloring			
λ_{80}	360	λ_5	320
λ_{70}			

Internal Transmittance			
$\lambda_{0.80}$	357	$\lambda_{0.05}$	327

CCI		
B	G	R
0,00	0,32	0,30

Internal Transmittance	
$\lambda(nm)$	τ 10mm
280	
290	
300	
310	
320	
330	0,13
340	0,44
350	0,70
360	0,85
370	0,926
380	0,959
390	0,976
400	0,985
420	0,991
440	0,992
460	0,994
480	0,995
500	0,997
550	0,998
600	0,997
650	0,997
700	0,998
800	0,998
900	0,998
1000	0,998
1200	0,998
1400	0,991
1600	0,994
1800	0,987
2000	0,973
2200	0,918
2400	0,81

Other Properties	
Density d	3,60

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dT relative (10 ⁻⁶ /°C)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	1,3	1,6	1,6	1,7	1,8	2,1	2,4
-20~0	1,4	1,7	1,7	1,8	1,9	2,2	2,5
0~20	1,4	1,8	1,8	1,9	2,0	2,4	2,7
20~40	1,5	1,9	1,9	2,0	2,2	2,5	2,8
40~60	1,6	2,0	2,0	2,1	2,3	2,6	3,0
60~80	1,6	2,1	2,1	2,2	2,4	2,8	3,1