

Refractive Index n_d	1,83400 1,834000	Abbe Number ν_d	37,17	Dispersion n_F-n_C	0,022437
Refractive Index n_e	1,839321	Abbe Number ν_e	36,92	Dispersion $n_F-n_{C'}$	0,022735

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1,78810
n_{1970}	1.97009	1,79430
n_{1530}	1.52958	1,80135
n_{1129}	1.12864	1,80854
n_t	1.01398	1,81125
n_s	0.85211	1,81641
$n_{A'}$	0.76819	1,82017
n_r	0.70652	1,82374
n_C	0.65627	1,82739
$n_{C'}$	0.64385	1,82843
$n_{\text{He-Ne}}$	0.6328	1,82940
n_D	0.58929	1,83380
n_d	0.58756	1,83400
n_e	0.54607	1,83932
n_F	0.48613	1,84983
$n_{F'}$	0.47999	1,85116
$n_{\text{He-Cd}}$	0.44157	1,86106
n_g	0.435835	1,86281
n_h	0.404656	1,87401
n_i	0.365015	1,89407

Constants of Dispersion Formula	
A ₁	1,95539063E+00
A ₂	3,02550219E-01
A ₃	1,34311390E+00
B ₁	1,09111365E-02
B ₂	4,54666700E-02
B ₃	1,13580850E+02

Chemical Properties	
Water Resistance (Powder) Group RW(P)	1
Acid Resistance (Powder) Group RA(P)	3
Weathering Resistance (Surface) Group	3
Acid Resistance (Surface) Group SR	51.2
Phosphate Resistance PR	1.2

Mechanical Properties	
Young's Modulus E (10 ⁹ N/m ²)	953
Rigidity Modulus G (10 ⁹ N/m ²)	366
Poisson's Ratio σ	0,302
Knoop Hardness Hk [Class]	520 5
Abrasion Aa	160
Photoelastic Constant β (nm/cm/10 ⁹ Pa)	1,36

Partial Dispersions	
n_C-n_t	0,016137
$n_C-n_{A'}$	0,007222
n_d-n_C	0,006608
n_e-n_C	0,011929
n_g-n_d	0,028810
n_g-n_F	0,012981
n_h-n_g	0,011196
n_i-n_g	0,031262
n_C-n_t	0,017174
$n_e-n_{C'}$	0,010892
n_F-n_e	0,011843
n_i-n_F	0,042908

Relative Partial Dispersion	
$\theta_{C,t}$	0,7192
$\theta_{C,A'}$	0,3219
$\theta_{d,C}$	0,2945
$\theta_{e,C}$	0,5317
$\theta_{g,d}$	1,2840
$\theta_{g,F}$	0,5786
$\theta_{h,g}$	0,4990
$\theta_{i,g}$	1,3933
$\theta'_{C,t}$	0,7554
$\theta'_{e,C'}$	0,4791
$\theta'_{F,e}$	0,5209
$\theta'_{i,F'}$	1,8873

Deviation of Relative Dispersions	
$\Delta \theta_{C,t}$	-0,0019
$\Delta \theta_{C,A'}$	0,0010
$\Delta \theta_{g,d}$	-0,0035
$\Delta \theta_{g,F}$	-0,0027
$\Delta \theta_{i,g}$	-0,0205

Thermal Properties	
Strain Point STP (°C)	609
Annealing Point AP (°C)	635
Transformation Temperature Tg (°C)	655
Yield Point At (°C)	688
Softening Point SP (°C)	721
Expansion Coefficients (-30~+70°C)	85
α (10 ⁻⁷ /°C) (+100~+300°C)	98
Thermal Conductivity k (W/m·K)	0,701

Coloring			
λ_{80}	425	λ_5	340
λ_{70}			

Internal Transmittance			
$\lambda_{0.80}$	377	$\lambda_{0.05}$	336

CCI		
B	G	R
0,00	1,58	1,64

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	
310	
320	
330	
340	0,08
350	0,31
360	0,56
370	0,73
380	0,83
390	0,89
400	0,927
420	0,957
440	0,968
460	0,976
480	0,983
500	0,989
550	0,995
600	0,995
650	0,995
700	0,997
800	0,998
900	0,998
1000	0,998
1200	0,999
1400	0,998
1600	0,995
1800	0,986
2000	0,968
2200	0,927
2400	0,80

Other Properties	
Bubble Quality Group B	
Density d	4,71
Remarks	

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dT relative (10 ⁻⁶ /°C)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	-1,4	-0,6	-0,6	-0,3	0,0	0,8	1,6
-20~0	-1,4	-0,6	-0,5	-0,2	0,1	0,9	1,8
0~20	-1,4	-0,5	-0,5	-0,2	0,2	1,1	2,0
20~40	-1,4	-0,5	-0,4	-0,1	0,2	1,1	2,1
40~60	-1,4	-0,4	-0,4	-0,1	0,3	1,2	2,2
60~80	-1,3	-0,4	-0,3	0,0	0,4	1,4	2,4