

Refractive Index	n_d	1,51742 1,517417	Abbe Number	ν_d	52,43	Dispersion	$n_F - n_C$	0,009869
Refractive Index	n_e	1,519765	Abbe Number	ν_e	52,14	Dispersion	$n_F - n_{C'}$	0,009968

Refractive Indices		
$\lambda(\mu m)$		
n_{2325}	2.32542	1,49004
n_{1970}	1.97009	1,49501
n_{1530}	1.52958	1,50033
n_{1129}	1.12864	1,50501
n_t	1.01398	1,50656
n_s	0.85211	1,50924
$n_{A'}$	0.76819	1,51108
n_r	0.70652	1,51276
n_C	0.65627	1,51444
$n_{C'}$	0.64385	1,51492
n_{He-Ne}	0.6328	1,51536
n_D	0.58929	1,51733
n_d	0.58756	1,51742
n_e	0.54607	1,51976
n_F	0.48613	1,52431
$n_{F'}$	0.47999	1,52488
n_{He-Cd}	0.44157	1,52907
n_g	0.435835	1,52980
n_h	0.404656	1,53444
n_i	0.365015	1,54252

Constants of Dispersion Formula	
A ₁	1,09666153E+00
A ₂	1,68990073E-01
A ₃	1,20580827E+00
B ₁	6,67491123E-03
B ₂	3,36095450E-02
B ₃	1,41668738E+02

Chemical Properties	
Water Resistance (Powder) Group RW(P)	1
Acid Resistance (Powder) Group RA(P)	1
Weathering Resistance (Surface) Group	1
Acid Resistance (Surface) Group SR	1.0
Phosphate Resistance PR	1.0

Mechanical Properties	
Young's Modulus E (10 ⁹ N/m ²)	64,0
Rigidity Modulus G (10 ⁹ N/m ²)	28,1
Poisson's Ratio σ	0,139
Knoop Hardness Hk [Class]	480 5
Abrasion Aa	113
Photoelastic Constant β (nm/cm/10 ⁵ Pa)	2,82

Partial Dispersions	
$n_C - n_t$	0,007887
$n_C - n_{A'}$	0,003365
$n_d - n_C$	0,002973
$n_e - n_C$	0,005321
$n_g - n_d$	0,012387
$n_g - n_F$	0,005491
$n_h - n_g$	0,004635
$n_i - n_g$	0,012715
$n_{C'} - n_t$	0,008359
$n_e - n_{C'}$	0,004849
$n_F - n_e$	0,005119
$n_i - n_F$	0,017635

Relative Partial Dispersion	
$\theta_{C,t}$	0,7992
$\theta_{C,A'}$	0,3410
$\theta_{d,C}$	0,3012
$\theta_{e,C}$	0,5392
$\theta_{g,d}$	1,2551
$\theta_{g,F}$	0,5564
$\theta_{h,g}$	0,4697
$\theta_{i,g}$	1,2884
$\theta'_{C,t}$	0,8386
$\theta'_{e,C'}$	0,4865
$\theta'_{F,e}$	0,5135
$\theta'_{i,F'}$	1,7692

Deviation of Relative Dispersions	
$\Delta \theta_{C,t}$	0,0065
$\Delta \theta_{C,A'}$	0,0016
$\Delta \theta_{g,d}$	-0,0007
$\Delta \theta_{g,F}$	-0,0002
$\Delta \theta_{i,g}$	0,0024

Thermal Properties	
Strain Point STP (°C)	429
Annealing Point AP (°C)	465
Transformation Temperature Tg (°C)	464
Yield Point At (°C)	522
Softening Point SP (°C)	655
Expansion Coefficients (-30~+70°C)	80
α (10 ⁻⁷ /°C) (+100~+300°C)	93
Thermal Conductivity k (W/m·K)	1,09

Coloring			
λ_{80}	360	λ_5	335
λ_{70}			

Internal Transmittance			
$\lambda_{0.80}$	360	$\lambda_{0.05}$	337

CCI		
B	G	R
0,00	0,22	0,20

Internal Transmittance	
$\lambda(nm)$	τ 10mm
280	
290	
300	
310	
320	
330	
340	0,18
350	0,57
360	0,81
370	0,917
380	0,960
390	0,980
400	0,989
420	0,995
440	0,996
460	0,997
480	0,998
500	0,998
550	0,999
600	0,999
650	0,998
700	0,998
800	0,999
900	0,998
1000	0,998
1200	0,998
1400	0,996
1600	0,994
1800	0,978
2000	0,950
2200	0,89
2400	0,86

Other Properties	
Density d	2,46

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dT relative (10 ⁻⁶ /°C)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	1,8	2,2	2,2	2,3	2,5	2,8	3,2
-20~ 0	1,8	2,2	2,2	2,3	2,5	2,9	3,3
0~20	1,8	2,2	2,3	2,4	2,6	2,9	3,3
20~40	1,9	2,3	2,3	2,4	2,6	3,0	3,4
40~60	1,9	2,3	2,3	2,5	2,7	3,1	3,5
60~80	1,9	2,3	2,3	2,5	2,7	3,1	3,6